

UC-NRLF




⌘B 296 559

REESE LIBRARY  
OF THE  
UNIVERSITY OF CALIFORNIA.

Class No. 438  
M67  
24









TREATISE

ON

MINERALOGY.

110

THE FIRST

MINERALOGY.

EDINBURGH:  
PRINTED AT THE CALEDONIAN MERCURY PRESS.



TREATISE  
ON  
MINERALOGY,

OR THE  
NATURAL HISTORY OF THE MINERAL KINGDOM.

BY  
FREDERICK MOHS,

PROFESSOR IN THE MINING ACADEMY OF FREIBERG.

*Translated from the German, with considerable Additions,*

BY  
WILLIAM HAIDINGER, F.R.S.E.



VOL. III.

EDINBURGH :

PRINTED FOR ARCHIBALD CONSTABLE AND CO. EDINBURGH ;  
AND HURST, ROBINSON, AND CO. LONDON.

1825.





## CONTENTS OF VOL. III.

---

---

### PHYSIOGRAPHY.

ORDER XI.	Glance	.	.	.	.	.	1
ORDER XII.	Blende	.	.	.	.	.	31
ORDER XIII.	Sulphur	.	.	.	.	.	47

### CLASS III.

ORDER I.	Resin	.	.	.	.	.	56
ORDER II.	Coal	.	.	.	.	.	61

### APPENDIX I.

Minerals, the greater part of which will probably form in future distinct Species in the Mineral System	67
--	----

### APPENDIX II.

Minerals, which will probably never form distinct Species in the Mineral System	177
Plates and Explanations	189
Index	289

CONTENTS OF VOL. III

APPENDIX I

1	Class III
2	Class II
3	Class I
4	Class IV
5	Class V
6	Class VI
7	Class VII
8	Class VIII
9	Class IX
10	Class X
11	Class XI
12	Class XII
13	Class XIII
14	Class XIV
15	Class XV
16	Class XVI
17	Class XVII
18	Class XVIII
19	Class XIX
20	Class XX
21	Class XXI
22	Class XXII
23	Class XXIII
24	Class XXIV
25	Class XXV
26	Class XXVI
27	Class XXVII
28	Class XXVIII
29	Class XXIX
30	Class XXX

APPENDIX II

Shows the general part of which will probably form the  
 subject-matter of the Mineral System

APPENDIX III

Shows the general part of which will probably form the  
 subject-matter of the Mineral System

Notes and Explanations

177  
 180  
 183





# PHYSIOGRAPHY.

## ORDER XI. GLANCE.

### GENUS I. COPPER-GLANCE.

#### I. TETRAHEDRAL COPPER-GLANCE.

Tetrahedral Copper-Pyrites. JAM. Syst. Vol. III. p. 315.  
 Tetrahedral Copper-Glance. Man. p. 276. Grey Copper.  
 Fahlerz. PHILL. p. 300. Fahlerz. Schwarzerz. WERN.  
 Hoffm. H. B. III. 2. S. 119. 127. Kupferfahlerz.  
 Schwarzgiltigerz. Graugiltigerz? HAUSM. I. S. 164.  
 166. 168. Fahlerz. LEONH. S. 262. Cuivre gris.  
 HAÜY. Traité, T. III. p. 537. Tabl. comp. p. 86.  
 Traité, 2de Ed. T. III. p. 441.

Fundamental form. Hexahedron. Vol. I. Fig. 1.

Simple forms.  $H(f)$ ;  $\frac{O}{2}(P)$  Vol. I. Fig. 13.,

Kapnik, Transylvania;  $-\frac{O}{2}(e)$  Vol. I. Fig. 14.;

$D(o)$  Vol. I. Fig. 31.;  $A_2$ , Vol. I. Fig. 32;  $\frac{B}{2}$

Vol. I. Fig. 17.;  $\frac{C_1}{2}(l)$  Vol. I. Fig. 15., Kapnik;

$-\frac{C_1}{2}(r)$  Vol. I. Fig. 16.

Char. of Comb. Semi-tessular with inclined faces.

Combinations. 1.  $\frac{O}{2}$ .  $-\frac{O}{2}$ . Fig. 158., Kapnik.

2.  $H$ .  $\frac{O}{2}$ . Cornwall.

3.  $\frac{O}{2}$ .  $\frac{C_1}{2}$ . Vol. I. Fig. 77. Kapnik.

Some yield arsenic, others antimony, when roasted, and the residue melts in different ways. After roasting, they yield a globule of copper.

3. The tetrahedral Copper-glance partakes in the modes of occurrence of the pyramidal Copper-pyrites, and is found in beds and veins; but it occurs seldom or not at all in the repositories of Tin-ore. It is accompanied by the same minerals as pyramidal Copper-pyrites, frequently also by prismatic Hal-baryte.

4. Varieties considered as Fahlerz are found in veins near Freiberg in Saxony, and in beds in Anhalt, in the county of Gömör in Hungary, in Stiria, &c.; varieties called Schwarzerz are met with in veins at Schwatz and other places in Tyrol, at Kapnik in Transylvania, at Cremnitz in Hungary, also at Clausthal and Andreasberg in the Hartz. Tetrahedral Copper-glance occurs besides in the neighbourhood of Dillenburg; in Mansfeld; in small quantities at Airthrie and other places in Scotland; in Cornwall, and in America.

## 2. PRISMATOIDAL COPPER-GLANCE.

Prismatic Antimony-Glance. JAM. Syst. Vol. III. p. 407. Prismatic Copper-Glance. Man. p. 277.

Fundamental form. Scalene four-sided pyramid of unknown dimensions. Vol. I. Fig. 7.

Simple forms.  $P + \infty (M)$ ;  $\check{P}r (P)$ ;  $\check{P}r + \infty (h)$ .

Char. of Comb. Prismatic. Combination. 1.  $\check{P}r$ .

$P + \infty$ .  $\check{P}r + \infty$ . Sim. Fig. 9.

Cleavage,  $\check{P}r + \infty$  rather perfect, though interrupted. Fracture imperfect conchoidal. Surface rough.

Lustre metallic. Colour blackish lead-grey. Streak unchanged.

Brittle. Hardness = 3.0. Sp. Gr. = 5.735.



*Compound Varieties.* Massive: composition granular, individuals strongly connected,

## OBSERVATIONS.

1. The prismatic Copper-glance has been hitherto found only in the beds of brachytypous Parachrose-baryte at St Gertraud near Wolfsberg in the valley of Lavant in Carinthia. It is very nearly allied to the following species. It will depend upon future accurate examinations, particularly of its regular forms, whether or not the varieties of the two species are identical.\*

2. Before the blowpipe the present species gives very nearly the same results as the following one. It appears to contain sulphur, antimony, lead, and copper, and it yields also a little silver, for the extraction of which it is collected by the miners, without, however, properly speaking, being an object of mining.

## 3. DI-PRISMATIC COPPER-GLANCE.

Axifragible Antimony-Glance, or Bournonite. JAM. Syst. Vol. III. p. 399. Bournonite. Triple Sulphuret. PHILL. p. 336. Schwarzspiesglaserz. WERN. Hoffm. H. B. IV. 1. S. 111. Bleifahlerz. Spiessglanzbleierz. HAUSM. I. S. 170. 173. Bournonit. LEONH. S. 155. Plomb sulfuré antimonifère. HAÜY. Tabl. comp. p. 80. Antimoine sulfuré plombo-cuprifère. Traité de Crist. T. II. p. 483.

Fundamental form. Scalene four-sided pyramid.

$P = 136^{\circ} 7', 66^{\circ} 13', 133^{\circ} 3'$ . Vol. I. Fig. 9. AP.

$$a : b : c = 1 : \sqrt{1.137} : \sqrt{0.226}.$$

Simple forms.  $P = \infty (k)$ ;  $P = 1$ ;  $P (P)$ ;

$$(\text{Pr} = 1)^5 (y) = 114^{\circ} 14', 115^{\circ} 2', 109^{\circ} 16';$$

\* The present species was determined by Professor MOHS, before he was acquainted with any of the varieties of the following one. Though it is likely that they do not present any specific difference, it would be too precipitate to unite them, without being capable of affording a demonstration of their identity. H.

$(\check{P}r + \infty)^5 (n) = 96^\circ 31'$ ;  $(\bar{P}r - 2)^5$ ;  $(\bar{P}r - 1)^5$ ;  
 $\check{P}r - 1 (e) = 129^\circ 45'$ ;  $\check{P}r (d) = 93^\circ 40'$ ;  
 $\check{P}r + 1 (f) = 54^\circ 48'$ ;  $\check{P}r + \infty (s)$ ;  $\bar{P}r - 1 (o)$   
 $= 87^\circ 8'$ ;  $\frac{3}{4} \bar{P}r = 64^\circ 44'$ ;  $\bar{P}r (p) = 50^\circ 51'$ ;  
 $\bar{P}r + \infty (r)$ .

Char. of Comb. Prismatic.

- Combinations. 1.  $P - \infty$ .  $\bar{P}r - 1$ .  $\check{P}r$ .  $\bar{P}r + \infty$ .  
 $\check{P}r + \infty$ . Fig. 24. Bräunsdorf, Saxony.
2.  $P - \infty$ .  $\bar{P}r - 1$ .  $P$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  
 $\bar{P}r + \infty$ . Neusohl, Hungary.
3.  $P - \infty$ .  $\check{P}r - 1$ .  $\check{P}r$ .  $\check{P}r + 1$ .  $\bar{P}r - 1$ .  
 $(\check{P}r - 1)^5$ .  $P$ .  $\bar{P}r$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  
 $\bar{P}r + \infty$ . Fig. 181. Cornwall.
4.  $P - \infty$ .  $\check{P}r - 1$ .  $\bar{P}r - 1$ .  $P - 1$ .  $\check{P}r$ .  $\frac{3}{4} \bar{P}r$ .  
 $(\check{P}r - 1)^5$ .  $(\bar{P}r - 2)^5$ .  $\bar{P}r$ .  $(\bar{P}r - 1)^5$ .  $P$ .  
 $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  $\bar{P}r + \infty$ . Neudorf, Anhalt.

Cleavage, imperfect; the most distinct is parallel to  $\check{P}r + \infty$ , less distinct cleavages are observed parallel to  $P - \infty$  and  $\bar{P}r + \infty$ ; traces of  $\bar{P}r - 1$  and  $(\check{P}r + \infty)^5$ . Fracture conchoidal, uneven. Surface, nearly equal in all the forms, often highly smooth and splendent. The striæ parallel to the intersections with  $\check{P}r$  almost always depend upon regular composition.

Lustre metallic. Colour steel-grey, inclining to blackish lead-grey or iron-black, according to the physical quality of the surface. Streak unchanged.

Brittle. Hardness = 2.5 ... 3.0. Sp. Gr. = 5.763, crystals from Anhalt.



*Compound Varieties.* Twin-crystals: axis of revolution perpendicular, face of composition parallel to a face of the horizontal prism  $\check{P}r$ . The individuals are generally continued beyond the face of composition. The axes of two individuals cross each other at angles of  $93^{\circ} 40'$  and  $86^{\circ} 20'$ . The composition is frequently repeated in parallel layers, and forms striæ upon the faces, particularly upon the pyramid  $P$ , and upon the prism  $\check{P}r$  itself, but also upon those which produce with it parallel edges of combination. The situation of these striæ is useful for discovering the true position of the faces of pyramids and prisms. Massive: composition granular, strongly connected.

## OBSERVATIONS.

1. Two varieties, one from Cornwall, and another from Clausthal, have yielded to KLAPROTH,

Antimony	28.50	19.75.
Lead	39.00	42.50.
Copper	13.50	11.75.
Iron	1.00	5.00.
Sulphur	16.00	18.00.

Before the blowpipe upon charcoal it melts, smokes, and yields afterwards a black globule. In a strong heat the charcoal becomes covered with oxide of lead. It is easily soluble in heated nitric acid.

2. Di-prismatic Copper-glance has been hitherto found only in veins, and is accompanied by axotomous and prismatic Antimony-glance, hexahedral Lead-glance, dodecahedral Garnet-blende, &c.

3. The first varieties of this species noticed by mineralogists were those from Cornwall, where they occur with axotomous Antimony-glance in Wheal Boys in the parish of Endellion near Redruth. Another variety, from

Kapnik in Transylvania, where it is found with dodecahedral Garnet-blende, tetrahedral Copper-glance, &c. had likewise been known long ago. It has been found afterwards in large and magnificent crystals, at Neudorf in Anhalt, also at Andreasberg in the Hartz. It occurs at Bräunsdorf in Saxony in a vein of rhombohedral Quartz, containing argentiferous prismatic Arsenical-pyrites, at Neusohl in Hungary, at Offenbanya in Transylvania, with ores of gold, and in other localities.

#### 4. PRISMATIC COPPER-GLANCE.

Rhomboidal Copper-Glance, or Vitreous Copper-Ore. *JAM. Syst. Vol. III. p. 328.* Prismatic Copper-Glance, or Vitreous Copper. *Man. p. 278.* Vitreous Copper. Sulphuret of Copper. *PHILL. p. 297.* Kupferglas. *WERN. Hoffm. H. B. III. 2. S. 103.* Kupferglanz. *HAUSM. I. S. 142.* Kupferglanz. *LEONH. S. 254.* Cuivre sulfuré. *HAÛY. Traité, T. III. p. 551. Tabl. comp. p. 87. Traité, 2de Ed. T. III. p. 454.*

Fundamental form. Scalene four-sided pyramid.

$P = 126^{\circ} 52', 125^{\circ} 22', 80^{\circ} 6'.$  Vol. I. Fig. 9. *Ap.*

$$a : b : c = 1 : \sqrt{2.95} : \sqrt{2.80}.$$

Simple forms.  $P - \infty$ ;  $P (P)$ ;  $(\check{P}r + \infty)^5 (d)$

$= 63^{\circ} 48'$ ;  $(P)^5 (a) = 148^{\circ} 20', 65^{\circ} 28', 124^{\circ} 11'$ ;

$(\check{P}r + \infty)^5 (e) = 114^{\circ} 16'$ ;  $\check{P}r (o) = 119^{\circ} 35'$ ;

$\frac{3}{4}\check{P}r + 1 = 97^{\circ} 41'$ ;  $\check{P}r + \infty (p)$ ;  $\check{P}r + \infty (s).$

Char. of Comb. Prismatic.

Combinations. 1.  $\check{P}r.$   $\check{P}r + \infty.$   $\check{P}r + \infty.$

2.  $(P)^5.$   $(\check{P}r + \infty)^5.$   $\check{P}r + \infty.$  Sim. Fig. 7.

The individuals of Fig. 41.

3.  $\check{P}r.$   $P.$   $(P)^5.$   $(\check{P}r + \infty)^5.$   $\check{P}r + \infty.$   $\check{P}r + \infty.$

Sim. Fig. 30. All of them from Cornwall.

Cleavage, traces of  $\check{P}r$ , very imperfect. Fracture conchoidal. Surface, most of the forms smooth, only the faces parallel to the axis, and



particularly  $\text{Pr} + \infty$ , are streaked parallel to their common intersections, often deeply furrowed.

Lustre metallic. Colour blackish lead-grey. Streak unchanged, sometimes shining.

Very sectile. Hardness = 2.5 ... 3.0. Sp. Gr. = 5.695, the compact variety from the Bannat.

*Compound Varieties.* Twin-crystals: 1. Axis of revolution perpendicular to one or to both faces of  $\text{Pr}$ ; face of composition parallel to it; Sim. Fig. 38., only that the re-entering angles between  $l$  and  $l$  are filled up; 2. Axis of revolution perpendicular, face of composition parallel to a face of  $(\text{Pr})^3$ , the individuals are continued beyond the face of composition, Fig. 41. The inclination of  $s$  on  $s'$  is equal to that of the acute terminal edge of  $(\text{Pr})^3 = 88^\circ 9'$  on one side, and =  $91^\circ 51'$  on the other; the respective inclinations of  $a$  on  $a'$  are =  $153^\circ 37'$  and =  $157^\circ 19'$ . Massive: composition granular, of various sizes of individuals, generally small, and often impalpable; in the last case, the fracture becomes uneven, even or flat conchoidal. Plates.

#### OBSERVATIONS.

1. The division of Vitreous Copper in the Wernerian system, into *foliated* and *compact* Vitreous Copper, depends upon the state of mechanical composition and the perfection of cleavage. But few varieties only are comprehended in the first subspecies, namely, such as possess a granular composition and distinct traces of cleavage. Far the greater part is compact Vitreous Copper, which embraces not only the compact varieties, consisting of impalpable individuals,

but by a curious anomaly also the crystals, in which but indistinct traces of cleavage can be observed. There exist transitions among all these varieties.

2. According to KLAPROTH, it consists of

Copper	76.50	78.50.
Sulphur	22.00	18.50.
Iron	0.50	2.25.
Silica	0.00	0.75.

It is the sulphuret of copper,  $\text{Cu S}$ , in which the proportion of copper and sulphur is, according to BERZELIUS, = 79.73 : 20.27. In the oxidating flame of the blowpipe it melts and emits with a noise glowing drops. In the reducing flame it becomes covered with a coat, and does not melt. If the sulphur has been driven off, a globule of copper remains. In heated nitric acid the copper is dissolved, and the solution assumes a green colour, but the sulphur remains undissolved.

3. If we except the tetrahedral Copper-glance, the present species is among those belonging to the genus, the one which occurs most frequently in nature, both in beds and veins. It is associated chiefly with other ores of copper, with hexahedral Iron-pyrites, rhombohedral Quartz, &c. It is one of those minerals which, by decomposition, are converted into copper-black.

4. Large and well defined crystals of this species occur in several mines near Redruth and in other districts, in Cornwall. In that place, and in the vicinity of Freiberg, the present species occurs in veins. Compound varieties, and in a few rare instances also crystals, have been found in beds in the Bannat of Temeswar, near Catharinenburg in Siberia, in Mansfeld, in Hessa, &c.; in the two last countries in bituminous shale. The fossil corn-ears, which were referred by LINNÆUS to the genus *Phalaris*, from Frankenberg in Hessa, consist in part of prismatic Copper-glance, and contain often a little native Silver. Prismatic Copper-Glance is found in the district of Siegen, in the mines of Kupferberg and Rudelstadt in Silesia, in Sweden, Norway, and



other countries. The foliated variety is found in Cornwall, in the Bannat, in Siegen, and in Mansfeld.

5. It is a rich and highly valuable ore of copper.

## GENUS II. SILVER-GLANCE.

### 1. HEXAHEDRAL SILVER-GLANCE.

Hexahedral Silver-Glance. JAM. Syst. Vol. III. p. 338. Man. p. 279. Sulphuret of Silver. Vitreous Silver. PHILL. p. 288. Glaserz. WERN. Hoffm. H. B. III. 2. S. 57. Glanzerz. HAUSM. I. S. 136. Silberglanz. LEONH. S. 169. Argent sulfuré. HAÛY. T. III. p. 398. Tabl. comp. p. 74. Traité, 2de Ed. T. III. p. 265.

Fundamental form. Hexahedron. Vol. I. Fig. 1.

Simple forms.  $\overset{\cdot}{H}$  (*r*) Himmelsfürst, Freiberg;  $\overset{\circ}{O}$

(*n*) Vol. I. Fig. 2., Joachimsthal, Bohemia;  $\overset{\circ}{D}$

(*s*), Vol. I. Fig. 31., Himmelsfürst;  $\overset{\cdot}{C}_1$  (*o*)

Vol. I. Fig. 34., Morgenstern mine, Freiberg.

Char. of Comb. Tessular.

Combinations. 1. H. O. Vol. I. Fig. 3. and 4.

2. H. D. Fig. 151. 3. H.  $C_1$ . Fig. 153. 4. H.

O. D.  $C_1$ . All of them from the mines near Freiberg.

Cleavage, sometimes traces parallel to the dodecahedron. Fracture imperfect and small conchoidal, uneven. Surface, nearly of the same description in all the forms, often uneven, and possessing low degrees of lustre. Subject to tarnish.

Lustre metallic. Colour blackish lead-grey. Streak shining.

Malleable. Hardness = 2.0 ... 2.5. Sp. Gr. = 7.196, crystals from Freiberg.

*Compound Varieties.* Reticulated, arborescent, dentiform, filiform, and capillary shapes: individuals sometimes distinguishable, sometimes impalpable; the dentiform and some other imitative shapes are longitudinally streaked. Massive: composition impalpable; fracture uneven. Plates, and superficial coatings.

## OBSERVATIONS.

1. According to KLAPROTH, the hexahedral Silver-glance is composed of

Silver 85·00.

Sulphur 15·00.

It is  $\text{Ag S}^2$ , according to BERZELIUS, which would make the proportion = 87·05 : 12·96. It is easily fusible before the blowpipe, and intumescs, but it gives a globule of silver by a continuation of the blast. It is soluble in dilute nitric acid.

2. It has been hitherto found almost exclusively in veins, accompanied by a great variety of species, particularly ores of silver, lead, and antimony, dodecahedral Garnetblende, several species of the order Pyrites and of the genus Lime-haloide. Sometimes, though rarely, it is found along with hexahedral Gold. The rock adjoining the veins is often impregnated with it, and it is itself often covered with Silver-black, which sometimes owes its formation to the decomposition of hexahedral Silver-glance.

3. There are but few localities where the present species is found in any considerable quantity. It occurs at Freiberg, Marienberg, Annaberg, Schneeberg, Johanngeorgensstadt in Saxony; in Bohemia, principally at Joachimsthal; at Schemnitz and Cremnitz in Hungary, where it is called *Weichgewächs*; in the Koliwan mountains in Siberia, in Mexico and Peru. It has been found in smaller quantities, both massive and crystallised, in several mines of Cornwall, in the Hartz, in Norway, in Dauphiny, &c.



4. The hexahedral Silver-glance is an important species for the extraction of silver.

### GENUS III. LEAD-GLANCE.

#### 1. HEXAHEDRAL LEAD-GLANCE.

Hexahedral Galena or Lead-glance. JAM. Syst. Vol. III. p. 353. Man. p. 280. Galena. Sulphuret of Lead. Blue Lead. PHILL. p. 332. 335. Bleiglanz. Blau-Bleierz. WERN. Hoffm. H. B. IV. 1. S. 1. 13. Bleischweif. Bleiglanz. HAUSM. I. S. 178. 179. Bleiglanz. LEONH. S. 225. Plomb sulfuré. HAÜY. Traité, T. III. p. 456. Tabl. comp. p. 79. Traité, 2de Ed. T. III. p. 341.

Fundamental form. Hexahedron. Vol. I. Fig. 1.

Simple forms. H (*P*), Freiberg;  $\bar{O}$  (*e*) Vol. I. Fig. 2., Bleiberg; D (*o*) Vol. I. Fig. 31.; B (*l*) Vol. I. Fig. 33.; C<sub>2</sub> (*z*) Vol. I. Fig. 34.

Char. of Comb. Tessular.

Combinations. 1. H. O., Vol. I. Fig. 3. and 4. Alston, Cumberland.

2. H. O. D. Pfaffenberg mine, Anhalt.

3. H. O. C<sub>2</sub>. Przibram, Bohemia.

4. H. O. D. B. Fig. 155. Feistritz, Stiria.

Cleavage, hexahedron, highly perfect, and easily obtained. Fracture conchoidal, seldom observable. Surface, the hexahedron and the trigonal-icositetrahedron streaked parallel to the edges of combination with the octahedron. Sometimes subject to tarnish.\*

---

\* Mr ALLAN first observed, in several specimens in his own cabinet, that in some combinations of the hexahedron with the octahedron from Alston, the faces of the octahedron are tarnished, and present iridescent tints, while those of the hexahedron have retained their original lead-grey colour. H.

Lustre metallic. Colour pure lead-grey. Streak unchanged.

Rather sectile. Hardness = 2.5. Sp. Gr. = 7.568, of a cleavable variety.

*Compound Varieties.* Twin-crystals: face of composition parallel, axis of revolution perpendicular to a face of the octahedron. The individuals either terminate at the face of composition, or they reach beyond it, and are often compressed in the direction of the axis of revolution. It is found at Kapnik in Transylvania. Reticulated, tabular, and some other imitative shapes, the individuals of which are often still observable. Massive: composition granular, of various sizes of individuals, sometimes impalpable. In this case the colour becomes pale or whitish lead-grey, the fracture even, or flat conchoidal, and the streak shining. The granular particles of composition sometimes become elongated or compressed in one direction, and then approach to columnar or lamellar ones. Pseudomorphoses of rhombohedral Lead-baryte. Plates, &c.

#### OBSERVATIONS.

1. The substance called *Blue Lead* is generally separated from the species of hexahedral Lead-glance, and considered as a species of its own. The varieties of it, however, are nothing else but the form of rhombohedral Lead-baryte, filled up with the substance of hexahedral Lead-glance, sometimes in pretty coarse granular compositions, as in the varieties from Poullaouen in Brittany, sometimes quite compact, as in some of those from Zschopau in Saxony. The Blue Lead from Cornwall sometimes shews composition. The remainder of the species has been divided into

*Common and Compact Lead-glance*, according to the crystallised state of the individuals, or the size of the grain in the compositions. By decomposition sometimes a black sooty substance is produced, called *Friable Lead-glance*.

2. According to THOMSON, the hexahedral Lead-glance consists of

Lead 85·13.

Sulphur 13·02.

Iron 0·50.

It is  $Pb S^2$ , the proportions of lead and sulphur being = 86·55 : 13·45. Some varieties contain a small quantity of silver, others antimony. Before the blowpipe it melts, if it is heated with precaution, and yields globules of metallic lead, after the sulphur has been driven off. It is partly soluble in nitric acid, and leaves a white residue.

3. Hexahedral Lead-glance is frequently found in veins, but also in great quantity in beds, particularly in limestone rocks. In beds it is accompanied by various other ores of lead, also by dodecahedral Garnet-blende, several species of Pyrites, Iron-ore, &c.; in veins it occurs, besides these, along with ores of silver, copper, and antimony, sometimes with hexahedral Gold. In both kinds of repositories it is associated with octahedral Fluor-haloide, rhombohedral Lime-haloide, rhombohedral Quartz, and many other species.

4. The remarkable beds of hexahedral Lead-glance in Carinthia, which occur in limestone, and are worked at Deutsch-Bleiberg, Windisch-Bleiberg, Windisch-Kappel, Ebriach, and other places, possess in several respects a striking similarity to those of Derbyshire, Durham, and Northumberland, in England, in both of which countries they are accompanied and intersected by lead veins. But it is also found in beds in older rocks, as in Stiria, Carinthia, &c. In veins it occurs in rocks of various ages, from gneiss to the coal formations, in several parts of Saxony and Bohemia, in the Hartz, in Anhalt, in Hungary, in Transylvania, in France, in Scotland, and in many other countries.



Fine crystals have been obtained from the Pfaffenberg mine near Neudorf in Anhalt, from Saxony, from Transylvania, from Cumberland and Durham, &c. Compact Lead-glance chiefly occurs at Freiberg in Saxony, in the Hartz, in Carinthia, and at Leadhills in Scotland. The localities of Blue Lead have been mentioned above.

5. Hexahedral Lead-glance is that mineral which yields most of the lead annually produced. On account of its generally containing a small quantity of silver, it is also employed to a considerable extent for the extraction of that metal, or also of gold, if it contains an admixture of it, which is sometimes the case. Potters use either the hexahedral Lead-glance itself reduced to powder, or the litharge produced from it for glazing coarse pottery.

#### GENUS IV. TELLURIUM-GLANCE.

##### I. PRISMATIC TELLURIUM-GLANCE.

Prismatic Black Tellurium. JAM. Syst. Vol. III. p. 369.  
 Prismatic Tellurium-Glance. Man. p. 281. Black Tellurium. PHILL. p. 328. Nagyager-Erz. WERN. Hoffm. H. B. IV. 1. S. 134. Blättertellur. HAUSM. I. S. 132. Blätter-Tellur. LEONH. S. 182. Tellure natif aurifère et plombifère. HAÜY. Traité, T. IV. p. 327. Tellure natif auro-plombifère. Tabl. comp. p. 119. Traité, 2de Ed. T. IV. p. 381.

Fundamental form. Scalene four-sided pyramid\*.

Vol. I. Fig. 9.

Simple forms.  $P - \infty$ ;  $P + \infty = 90^\circ$  (nearly);

$\check{P}r + \infty$ ;  $\check{P}r + \infty$ .

Char. of Comb. Prismatic.

\* According to PHILLIPS and BROOKE, it is an acute isosceles pyramid, the edge at its base being  $= 140^\circ$ . A combination quoted by PHILLIPS is similar to Fig. 92. having the oblique edges between  $b$  and  $b$  replaced by the faces of a pyramid, the base of which is  $= 122^\circ 50'$ . H.

Combinations. 1. P — ∞. P + ∞.  $\check{P}r + \infty$ .

2. P — ∞. P + ∞.  $\check{P}r + \infty$ .  $\bar{P}r + \infty$ . Nagyag, Transylvania.

Cleavage, P — ∞, very perfect. Fracture not observable. Surface, P — ∞ smooth.

Lustre metallic. Colour blackish lead-grey. Streak unchanged.

Highly flexible in thin laminæ. Very sectile. Hardness = 1.0 ... 1.5. Sp. Gr. = 7.085.

*Compound Varieties.* Massive: composition granular, of various sizes of individuals, sometimes longish.

## OBSERVATIONS.

1. According to KLAPROTH, the prismatic Tellurium-glance consists of

Tellurium	32.20.
Lead	54.00.
Gold	9.00.
Silver	0.50.
Copper	1.30.
Sulphur	3.00.

Before the blowpipe it melts easily upon charcoal, emits white fumes, which are deposited upon the charcoal, and gives a malleable metallic globule. With borax it gives a bead of gold containing a little silver. It is easily soluble in nitric acid.

2. It has been hitherto found only in veins with hexahedral Gold, hexahedral Glance-blende, dodecahedral Garnet-blende, macrotypous Parachrose-baryte, &c.

3. Its chief locality is Nagyag in Transylvania, from whence it obtained its ancient name of *Nagiaker-Erz*. It is found also with prismatic Antimony-glance, at Offenbanya in the same country.

## GENUS V. MOLYBDENA-GLANCE.

## I. RHOMBOHEDRAL MOLYBDENA-GLANCE.

Rhomboidal Molybdena. JAM. Syst. Vol. III. p. 372. Man. p. 282. Sulphuret of Molybdena. PHILL. p. 248. Wasserblei. WERN. Hoffm. H. B. IV. 1. S. 231. Wasserblei. HAUSM. I. S. 197. Molybdänglanz. LEONH. S. 162. Molybdène sulfuré. HAÜY. Traité, T. IV. p. 289. Tabl. comp. p. 114. Traité, 2de Ed. T. IV. p. 326.

Fundamental form. Rhombohedron, of unknown dimensions. Vol. I. Fig. 7.

Simple forms.  $R - \infty$ ;  $P$ ;  $P + \infty$ . They occur in combination with each other, and seem to possess a di-rhombohedral character.

Cleavage,  $R - \infty$ , highly perfect. Fracture not observable. Surface,  $R - \infty$  smooth;  $P$  and  $P + \infty$  horizontally streaked.

Lustre metallic. Colour pure lead-grey. Streak unchanged.

Thin laminae are highly flexible. Very sectile. Hardness = 1.0 ... 1.5. Sp. Gr. = 4.591.

*Compound Varieties.* Massive: composition granular, of various sizes of individuals.

## OBSERVATIONS.

1. According to BUCHOLZ, rhombohedral Molybdena-glance consists of

Molybdena 60.00.

Sulphur 40.00.

It does not melt, nor is it reduced before the blowpipe, but it emits sulphureous fumes, which are deposited on the charcoal. It deflagrates with nitre, and is soluble with effervescence in nitric acid, leaving a grey residue.



2. It is generally found imbedded in several rocks, particularly in granite, and is not unfrequently met with in several repositories of pyramidal Tin-ore. Besides this species, it is most commonly accompanied by rhombohedral Quartz and prismatic Scheelium-ore.

3. Among the oldest known localities of the present species are Altenberg in Saxony, and Schlaggenwald and Zinnwald in Bohemia. As in these places, it occurs also in Cornwall, along with pyramidal Tin-ore. In Norway and Sweden it occurs imbedded in zircon-syenite and granite; in granite also at Carrock in Cumberland, and in Westmoreland in England, at Loch Creran in Scotland, &c. It is frequent in the granite and gneiss of the United States of North America, and has been found also in the valley of Chamouni in Savoy, and in Silesia.

#### GENUS VI. BISMUTH-GLANCE.

##### 1. PRISMATIC BISMUTH-GLANCE.

Prismatic Bismuth-Glance. JAM. Syst. Vol. III. p. 384. Man. p. 283. Sulphuret of Bismuth. PHILL. p. 273. Wismuthglanz. WERN. Hoffm. H. B. IV. 1. S. 68. Wismuthglanz. HAUSM. I. S. 190. Wismuthglanz. LEONH. S. 213. Bismuth sulfuré. HAÛY. Traité, T. IV. p. 190. Tabl. comp. p. 105. Traité, 2de Ed. T. IV. p. 210.

**Fundamental form.** Scalene four-sided pyramid of unknown dimensions. Vol. I. Fig. 9.

Simple forms and combinations not determined.

**Cleavage,** imperfect in the direction of  $P + \infty$ , which is nearly equal to  $90^\circ$ ; with great perfection parallel to one of the diagonals, less distinctly parallel to the other;  $P - \infty$  imperfect. **Fracture** scarcely observable. **Surface** of the prisms deeply streaked parallel to the axis.

Lustre metallic. Colour lead-grey, inclining a little to steel-grey. Streak unchanged.

Rather sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 6.549, the variety from Rezbanya.

*Compound Varieties.* Massive: composition granular, the individuals being of various sizes; or columnar, individuals straight and aggregated in various directions.

#### OBSERVATIONS.

1. According to SAGE it consists of

Bismuth 60.00.

Sulphur 40.00.

According to this analysis it is  $\text{Bi S}^6$ , which corresponds to 59.51 of bismuth, and 40.49 of sulphur. It is volatilised before the blowpipe, and covers the charcoal with a yellow areola. It is easily fusible, and emits continually small drops in a state of incandescence. It is easily soluble in nitric acid, and the solution yields a white precipitate on being further diluted.

2. Prismatic Bismuth-glance occurs principally in veins, but is found also in beds. It is generally associated with octahedral Bismuth, also with several species of Pyrites, with pyramidal Tin-ore, rhombohedral Quartz, &c.

3. It is rather a rare mineral. It is found at Altenberg, at Schneeberg, and some other places in Saxony, at Joachimsthal in Bohemia, at Rezbanya in Upper Hungary, in the latter place in beds; near Redruth and Botallack in Cornwall; at Riddarhyttan in Sweden, with uncleavable Cerium-ore; in the mountains of Beresof in Siberia, &c. Very fine varieties, in large cleavable individuals, are found at Carrock in Cumberland.

## GENUS VII. ANTIMONY-GLANCE.

## 1. PRISMATIC ANTIMONY-GLANCE.

Graphic Gold-Glance or Graphic Tellurium. JAM. Syst. Vol. III. p. 377. Prismatic Antimony-Glance. Man. p. 284. Graphic Tellurium. Graphic Gold. PHILL. p. 327. Schriftez. WERN. Hoffm. H. B. IV. 1. S. 129. Schrifttellur. HAUSM. I. S. 130. Schrift-Tellur. LEONH. S. 183. Tellure natif aurifère et argentifère. HAÛY. Traité, T. IV. p. 326. Tellure natif auro-argentifère. Tabl. comp. p. 119. Traité, 2de Ed. T. IV. p. 380.

Fundamental form. Scalene four-sided pyramid.  
Vol. I. Fig. 9.

Simple forms.  $P - \infty (k)$ ;  $P (P)$ ;  $\frac{3}{4} P + 2 (b)$ ;  
 $(\check{P}r)^5 (z)$ ;  $(\check{P}r)^5 (a)$ ;  $(\check{P}r + \infty)^5 (d)$ ;  $\check{P}r (o)$ ;  
 $\check{P}r + \infty (r)$ ;  $\check{P}r + \infty (s)$ .

Char. of Comb. Prismatic.

Combinations. 1.  $P - \infty$ .  $\check{P}r$ .  $P$ .  $\check{P}r + \infty$ .  $\check{P}r + \infty$ .  
2.  $P - \infty$ .  $\check{P}r$ .  $P$ .  $(\check{P}r)^5$ .  $(\check{P}r)^5$ .  $\frac{3}{4} P + 2$ .  
 $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  $\check{P}r + \infty$ . Fig. 35.

Cleavage,  $\check{P}r + \infty$ , highly perfect;  $\check{P}r + \infty$  perfect though not so easily obtained. Fracture uneven. Surface,  $\check{P}r + \infty$  vertically streaked;  $\check{P}r + \infty$  fused like; the remaining faces smooth. Lustre metallic. Colour pure steel-grey. Streak unchanged.

Very sectile. Hardness = 1.5 ... 2.0. Sp. Gr. = 5.723, MÜLLER VON REICHENSTEIN.

*Compound Varieties.* Regular composition of acicular crystals nearly at angles of  $60^\circ$  and  $120^\circ$ , in one plane, frequently repeated and imparting to the whole the appearance of certain characters for



writing. Massive: composition imperfectly columnar or granular, small but not impalpable.

## OBSERVATIONS.

1. It is possible that the crystal represented in Fig. 35. is not a simple one, but compound parallel to the plane  $r$ , in which case the combinations might be hemi-prismatic. The angle  $dd$  over  $s$  is  $= 85^\circ 40'$ , over  $r = 94^\circ 20'$  very nearly, the inclination of  $o$  on  $r$  about  $125^\circ$ . The present species presents a great many different varieties of crystalline forms, which being generally very much engaged among each other, and moreover modified by regular composition, have not yet been satisfactorily developed.\*

2. According to KLAPROTH, it consists of

Tellurium 60.00.

Gold 30.00.

Silver 10.00.

It is remarkable, that the specific gravity of such a composition should be so low as has been stated above, it being much less than that of tellurium itself. By calculation the specific gravity is found above 10.0, which agrees pretty well with that of the Yellow Tellurium, as given by MÜLLER VON REICHENSTEIN, but this cannot refer to the same species, the specific gravity of which is given above. The prismatic Antimony-glance melts easily into a grey globule, which fumes and covers the charcoal with a white oxide. After having continued the blast for some time, a ductile metallic globule is obtained. It is soluble in nitric acid.

3. The prismatic Antimony-glance occurs at Offenbanya in Transylvania, in very narrow, but quite regular veins

---

\* It is difficult to trace the identity of the series of crystallisation in Fig. 35. with the figure given by Mr PHILLIPS, unless one of them be discovered to have been in fact a compound crystal. The inclination of  $c^3$  on  $c^3$  over  $M$  follows  $= 94^\circ 30'$ , nearly the same as  $d$  on  $d$  over  $r$ , and  $M$  on  $h$  is given  $= 126^\circ 8'$ , perhaps a more accurate measurement than that indicated above by approximation  $= 125^\circ$ . H.

which traverse porphyry, several of them at a short distance from each other and parallel. It is accompanied by hexahedral Gold and rhombohedral Quartz, rarely by prismatic Tellurium-glance. It is occasionally met with along with the latter, at Nagyag in Transylvania.

4. It is a valuable ore, on account of its contents of gold and silver.

2. PRISMATOIDAL ANTIMONY-GLANCE.

Prismatic Antimony-Glance or Grey Antimony. JAM. Syst. Vol. III. p. 390. Man. p. 285. Grey Antimony. Sulphuret of Antimony. PHILL. p. 329. Grauspiesglaserz. WERN. Hoffm. H. B. IV. 1. S. 102. Grauspiesglanzerz. HAUSM. I. S. 194. Antimonglanz. S. 152. Antimoine sulfuré. HAÜY. Traité, T. IV. p. 264. Tabl. comp. p. 112. Traité, 2de Ed. T. IV. p. 291.

Fundamental form. Scalene four-sided pyramid.

$P = 109^\circ 16'$ ,  $108^\circ 10'$ ,  $110^\circ 59'$ . Vol. I. Fig.

9. R. G.

$$a : b : c = 1 : \sqrt{0.9577} : \sqrt{0.9327}.$$

Simple forms.  $\frac{4}{3}P - 2$  (*s*);  $P$  (*P*);  $P + \infty$  (*m*)

$= 90^\circ 45'$ ;  $(\frac{4}{3}\check{P}r - 2)^5$  (*e*);  $(\frac{4}{3}\check{P}r - 2)^7$  (*b*);

$\check{P}r - 1$  (*a*)  $= 127^\circ 51'$ ;  $\check{P}r + \infty$  (*o*).

Char. of Comb. Prismatic.

Combinations. 1.  $\frac{4}{3}P - 2$ .  $P + \infty$ .  $\check{P}r + \infty$ .

2.  $P$ .  $P + \infty$ .  $\check{P}r + \infty$ . Both similar to Fig. 6.

3.  $P$ .  $(\frac{4}{3}\check{P}r - 2)^7$ .  $P + \infty$ .  $\check{P}r + \infty$ .

4.  $\frac{4}{3}P - 2$ .  $\check{P}r - 1$ .  $(\frac{4}{3}\check{P}r - 2)^5$ .  $P$ .  $(\frac{4}{3}\check{P}r - 2)^7$ .  $P + \infty$ .  $\check{P}r + \infty$ . Fig. 32.

All of them from Felsöbanya, Hungary.

Cleavage, highly perfect in the direction of  $\check{P}r + \infty$ ; less distinct  $P - \infty$ ,  $P + \infty$  and  $\check{P}r + \infty$ , sometimes pretty easily obtained. Fracture small conchoidal, rather imperfect. Surface, the ver-

tical planes deeply striated parallel to their own intersections, and rough. The pyramids in a parallel position with P are sometimes irregularly streaked in a horizontal direction, but generally smooth, as also the other inclined faces. Subject to tarnish.

Lustre metallic. Colour lead-grey, inclining to steel-grey. Streak unchanged.

Sectile. Thin laminae are a little flexible parallel to the intersection of  $\text{Pr} + \infty$  with  $\text{P} - \infty$ . Crystals sometimes bent. Hardness = 2.0. Sp. Gr. = 4.620 the cleavable variety from Anhalt.

*Compound Varieties.* Massive: composition columnar, of various sizes of individuals, sometimes very thin, but not impalpable. They are long and straight, either parallel or divergent from several common centres, and aggregated in a second angular granular composition. The faces of composition are irregularly streaked in a longitudinal direction. Sometimes the composition is granular, and then the individuals often become impalpable, but are generally very strongly connected; the fracture becomes even or uneven. Capillary crystals often form a tissue resembling wool or felt.

#### OBSERVATIONS.

1. The present species has been divided into *Common* and *Plumose Grey Antimony*, differing chiefly in the size of their individuals. The latter consists of capillary crystals, which are sometimes even flexible, and either implanted in groupes, or interlaced with each other; sometimes also they form massive varieties in which the columnar composition



is very delicate. The common Grey Antimony has been farther subdivided into *radiated*, *foliated*, and *compact*. The first contains the crystals and massive varieties with a columnar composition, the second only granular compositions, in which the individuals can still be distinguished; and the third those in which the composition is impalpable.

2. According to PROUST and THOMSON, the prismatic Antimony-glance consists of

Antimony	75·00	73·77.
Sulphur	25·00	26·23.

Its chemical formula is  $Sb S^3$ , corresponding to 72·77 of antimony, and 27·23 sulphur. It is very fusible before the blowpipe, and is absorbed by the charcoal. By a continued blast it may be volatilised without leaving any considerable residue.

3. The greater part of the varieties of prismatic Antimony-glance are found in veins, which in some instances almost exclusively consist of this species. Yet it occurs also in beds, particularly with brachytypous Parachrosebaryte, and beds seem almost always to be the repositories of the compact varieties. Frequently it is associated with prismatic Hal-baryte, often with prismatic Purple-blende, and commonly also with rhombohedral Quartz. It occurs besides along with various other species of the orders Glance, Blende, and Haloide, with prismatic Antimonybaryte, and not unfrequently with hexahedral Gold. Its decomposition produces the *Antimony-ochre*, a friable or compact yellow substance, with which it is often associated or covered.

4. Veins consisting almost entirely of the present species have been discovered at Pösing near Pressburg in Hungary, and at Wolfsthal in the county of Stollberg in the Hartz; such as contain considerable quantities of it associated with other minerals, at Felsöbanya in Upper Hungary, at Cremnitz, Schemnitz, and other places in Lower Hungary, and in France, from whence beautiful varieties are obtained. It occurs also in Scotland, in Cornwall, at Bräunsdorf near Freiberg in Saxony, and at Neudorf in

Anhalt. The fibrous variety occurs at Loben in the valley of the Lavant in Carinthia, in beds of brachytypous Parachrose-baryte, and the compact one particularly at Magurka in Hungary.

5. It is used for extracting the crude antimony, or the metal itself, which is employed in the manufacture of several metallic alloys, and in medicine.

### 3. AXOTOMOUS ANTIMONY-GLANCE.

Prismatoidal Antimony-Glance, or Grey Antimony (in part). JAM. Syst. Vol. III. p. 390. Man. p. 285.

Fundamental form. Scalene four-sided pyramid.  
Vol. I. Fig. 9.

Simple forms.  $P + \infty = 101^{\circ}20'$  (nearly);  $\check{P}r + \infty$ .  
Combinations, of the preceding forms, their terminations not observed.

Cleavage,  $P - \infty$  highly perfect; less distinct, though easily observed, when the crystals are not too small,  $P + \infty$  and  $\check{P}r + \infty$ . Fracture not observable.

Lustre metallic. Colour steel-grey. Streak unchanged.

Sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 5.564.

*Compound Varieties.* Massive: composition columnar, individuals generally very delicate; straight and parallel, or divergent.

#### OBSERVATIONS.

1. Nothing as yet is known of the proportions among the ingredients of the present species. It contains sulphur, antimony, and lead.

2. The axotomous Antimony-glance seems to be a rare mineral, or at least not sufficiently attended to by mine-

ralogists. It occurs in masses of considerable dimensions in Cornwall, sometimes along with the di-prismatic Copper-glance. In Hungary it is engaged in rhombohedral Limehaloide, but its locality is not exactly known.

## GENUS VIII. MELANE\*-GLANCE.

## 1. PRISMATIC MELANE GLANCE.

Rhomboidal Silver-Glance or Brittle Silver-Glance. JAM. Syst. Vol. III. p. 345. Prismatic Melane-Glance. Man. p. 287. Brittle Sulphuret of Silver. PHILL. p. 390. Sprödglaserz. WERN. Hoffm. H. B. III. 2. S. 63. Sprödglanzerz. HAUSM. I. S. 138. Schwarzgiltigerz. LEONH. S. 202. Argent noir. HAÜY. Traité, T. III. p. 416. Argent antimonie sulfuré noir. Tabl. comp. p. 76. Traité, 2de Ed. T. III. p. 280.

Fundamental form. Scalene four-sided pyramid.

$P = 130^{\circ} 16', 104^{\circ} 19', 96^{\circ} 7'$ . Vol. I. Fig. 9.

R. G.

$$a : b : c = 1 : \sqrt{2.526} : \sqrt{1.187}.$$

Simple forms.  $P - \infty$ ;  $P (P)$ ;  $P + \infty = 111^{\circ} 8'$ ;  $(\check{P}r)^5 (a)$ ;  $(\check{P}r + \infty)^5 (d) = 72^{\circ} 13'$ ;  $(\bar{P}r + \infty)^5 = 142^{\circ} 10'$ ;  $(\bar{P}r)^5$ ;  $\check{P}r (o) = 115^{\circ} 39'$ ;  $\check{P}r + \infty (p)$ ;  $\bar{P}r + \infty (s)$ .

Char. of Comb. Prismatic.

1.  $\check{P}r$ .  $\check{P}r + \infty$ .  $\bar{P}r + \infty$ . Alte Hoffnung mine, Freiberg.
2.  $P$ .  $(\check{P}r + \infty)^5$ .  $\bar{P}r + \infty$ . Fig. 7. Alte Hoffnung mine.
3.  $\check{P}r$ .  $P$ .  $(\bar{P}r)^5$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  $\bar{P}r + \infty$ . Fig. 30. Prizibram, Bohemia.
4.  $P - \infty$ .  $\check{P}r$ .  $P$ .  $(\bar{P}r)^5$ .  $(\check{P}r)^5$ .  $P + \infty$ .

\* From  $\mu\acute{\iota}\lambda\alpha\varsigma$ , black,



$(\check{P}r + \infty)^3$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  $\check{P}r + \infty$ .  
Morgenstern mine, Freiberg.

Cleavage,  $(\check{P}r + \infty)^3$  and  $\check{P}r + \infty$ , imperfect and interrupted. Fracture conchoidal, uneven. Surface,  $\check{P}r$  and  $\check{P}r + \infty$  generally streaked parallel to their edges of combination with each other; the other forms smooth.

Lustre metallic. Colour iron-black. Streak unchanged.

Sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 6.269, a crystal from Przibram.

*Compound Varieties.* Twin-crystals: face of composition parallel, axis of revolution perpendicular to a face of  $\check{P}r$ ; the composition is frequently repeated, either in parallel layers, or contiguous to several parts of the same individual. Thence compound masses arise, consisting of alternating laminæ of two or more individuals, as in prismatic Lime-haloide, di-prismatic Lead-baryte, &c., with the forms of which those of the present species agree in a remarkable manner. Massive: composition granular, individuals strongly connected; fracture uneven.

#### OBSERVATIONS.

1. According to KLAPROTH, it consists of

Silver	66.50.
Antimony	10.00.
Iron	5.00.
Sulphur	12.00.
Copper and Arsenic	0.50.

BERZELIUS could not discover any antimony by the blow.

pipe, and is therefore of opinion that it is a compound of sulphur, arsenic, and silver. Before the blowpipe, upon charcoal, it yields a dark coloured metallic globule, which may be reduced either with soda and silica, or with saltpetre. It is soluble in dilute nitric acid.

2. The prismatic Melane-glance is found in silver veins along with other ores of silver, also with hexahedral Lead-glance, dodecahedral Garnet-blende, and several species of the orders Pyrites, Haloide, and Baryte. It is sometimes associated with native Arsenic and hexahedral Gold. Prismatic Melane-glance in compact varieties is often intimately mixed with hexahedral Lead-glance, and with prismatic Antimony-glance, a mixture designated by the name of *White Silver*, the *Weissgiltigerz* of the Wernerian system. The richer it is in silver, the more it approaches in its properties to the pure varieties of the present species, while in the contrary cases it yields more nearly the characters of compact hexahedral Lead-glance and compact prismatic Antimony-glance, or of a mixture of both, and differs from them perhaps only in the colour. It is evident that the White Silver does not deserve to be ranked as a particular species, on account of this mode of formation, and the variable proportions of the species entering into the mixture. It is found in silver veins in Saxony.

3. The prismatic Melane-glance occurs chiefly in Saxony, Bohemia, and Hungary; in the last of which countries it is called *Röschgewächs*. Its chief localities in Saxony are the mining districts of Freiberg, Schneeberg, and Johanngeorgenstadt, in Bohemia those of Przibram and Ratiborwitz, and in Hungary those of Schemnitz and Cremnitz. It is found also at Joachimsthal in Bohemia; at Andreasberg in the Hartz, here only in small quantities; at Zacatecas in Mexico, and in Peru.

4. On account of its considerable contents of silver, it is a valuable ore for the extraction of that metal.

5. The two following minerals must here be noticed, as they seem to be nearly allied to the prismatic Melane-glance.

i. *Flexible Sulphuret of Silver.*

Flexible Sulphuret of Silver. PHILL. p. 289. Argent sulfuré flexible. BOURNON. Cat. p. 209.

Hemi-prismatic. A crystal is given by Mr PHILLIPS, observed and measured by Mr BROOKE. It nearly resembles Fig. 172., but is flattened between  $P$  and  $P$ , having the edges between  $M$  and  $T$  replaced by one plane  $e$ , and those between  $l$  and  $P$  by two planes,  $d^2$  and  $d^1$ . Angles,  $M$  on  $T = 125^\circ$ ,  $e$  on  $T = 159^\circ$ ,  $l$  on  $l = 121^\circ$ ,  $d^2$  on  $d^2 = 83^\circ 30'$ ,  $d^1$  on  $d^1 = 48^\circ$ ,  $k$  on  $k = 126^\circ 40'$ ,  $s$  on  $s = 90^\circ$ . Cleavage perfect, parallel to  $P$ .

Lustre metallic. Colour dark externally, nearly black.

Streak shining, but less so than hexahedral Silver-glance.

Thin laminae flexible. Yields readily to the knife.

It consists, according to the experiments of Dr WOLLASTON, of silver, sulphur, and a little iron. This mineral was first discovered by Count BOURNON, who suspects Hungary to be the locality of the specimens he examined.

ii. *Sulphuret of Silver and Antimony.*

Sulphuret of Silver and Antimony. PHILL. p. 290. Mine d'argent grise antimoniale. ROMÉ DE L'ISLE. Vol. III. p. 54.

Prismatic. Combinations similar to Fig. 23., without  $h$ , and having several other prisms ( $g^1, g^2, g^3$ ) contiguous to its obtuse edge, which in the figure is that between two adjacent faces of  $M$ . Inclination, according to PHILLIPS, of  $x$  on  $x = 130^\circ 8'$ ,  $P$  on  $P = 60^\circ 56'$ ,  $s$  on  $s = 57^\circ 45'$ ,  $M$  on  $M$  (adjacent) =  $100^\circ$ ,  $g^1$  on  $g^1 = 119^\circ 40'$ ,  $g^2$  on  $g^2 = 139^\circ$ ,  $g^3$  on  $g^3 = 167^\circ$ .

Cleavage, easy parallel to  $M$  and in other directions. Surface striated in a longitudinal direction.

Lustre metallic. Colour approaching to silver white.

Yields easily to the knife. Sp. Gr. = 5.5.

Before the blowpipe it gives out copious white vapours and a slight sulphureous odour, leaving behind a white metallic globule. It is supposed to consist chiefly of antimony,



sulphur, and silver. The locality quoted of this mineral is the mine of Himmelsfürst near Freiberg. It had first been distinguished by ROMÉ DE L'ISLE; Mr FREIESLEBEN had given it the name of *Schilfglaserz*, but it was only of late more accurately described by Mr PHILLIPS.

## ORDER XII. BLENDE.

## GENUS I. GLANCE-BLENDE.

## 1. HEXAHEDRAL GLANCE-BLENDE.

Prismatic Manganese-Blende. JAM. Syst. Vol. III. p. 406. Man. p. 288. Sulphuret of Manganese. PHILL. p. 246. Manganblende. BREITH. Hoffm. H. B. IV. 2. S. 197. Schwarzerz. HAUSM. I. S. 199. Manganlanz. LEONH. S. 370. Manganèse sulfuré. HAÜY. Tabl. comp. p. 111. Traité, 2de Ed. T. IV. p. 268.

Fundamental form. Hexahedron. Vol. I. Fig. 1.

Simple forms. H; O, Vol. I. Fig. 2.

Combinations. 1. H. O. Vol. I. Fig. 3. and 4.

Cleavage, hexahedron, perfect; traces of the dodecahedron. Fracture uneven, imperfect conchoidal. Surface rough.

Lustre imperfect metallic. Colour iron-black. Streak dark-green. Opake.

Rather sectile. Hardness = 3.5 ... 4.0. Sp. Gr. = 4.014, a cleavable variety.

*Compound Varieties.* Massive: composition granular, of various sizes of individuals; faces of composition irregularly streaked or rough.

## OBSERVATIONS.

1. According to KLAPROTH and VAUQUELIN, the hexahedral Glance-blende consists of

Protoxide of Manganese	82·00	85·00.
Sulphur	11·00	15·00.
Carbonic Acid	5·00	0·00.

It is generally, however, considered as a sulphuret of manganese. Before the blowpipe it is melted with difficulty, and only on its thinnest edges. It emits sulphuretted hydrogen, if reduced to powder and thrown into nitric, muriatic, or dilute sulphuric acid, and is dissolved.

2. It is a rare mineral. It occurs chiefly in veins along with prismatic Tellurium-glance, at Nagyag in Transylvania. According to PHILLIPS, it is found also in Cornwall.

## GENUS II. GARNET-BLENDE.

### I. DODECAHEDRAL GARNET-BLENDE.

Dodecahedral Zinc-Blende. JAM. Syst. Vol. III. p. 410. Man. p. 238. Blende. Sulphuret of Zinc. PHILL. p. 351. Blende. WERN. Hoffm. H. B. IV. 1. S. 73. Blende. HAUSM. 1. S. 229. Blende. LEONH. S. 309. Zinc sulfuré. HAÜY. Traité, T. IV. p. 167. Tabl. comp. p. 103. Traité, 2de Ed. T. IV. p. 186.

Fundamental form. Hexahedron. Vol. I. Fig. 1.

Simple forms.  $\overset{\cdot}{H}(s)$  Cornwall;  $\frac{O}{2}(g)$  Vol. I. Fig. 13;

—  $\frac{O}{2}(g)$  Vol. I. Fig. 14.;  $D(P)$  Vol. I. Fig. 31.;

$\frac{B}{2}$  Vol. I. Fig. 17.; —  $\frac{C_2}{2}(y)$  Vol. I. Fig. 16.

Char. of Comb. Semi-tessular, with inclined faces.

Combinations. 1.  $\frac{O}{2}$  —  $\frac{O}{2}$ . Fig. 158. Cornwall.

2.  $\frac{O}{2}$  —  $\frac{C_2}{2}$ . Vol. I. Fig. 78, the faces  $r$  considerably enlarged, so as to intersect each other. Junge hohe Birke mine near Freiberg.

3. D. —  $\frac{C_2}{2}$ . Fig. 162. Alston Moor, Cumberland.

4.  $\frac{O}{2}$  —  $\frac{O}{2}$ . D.  $\frac{B}{2}$ . Kapnik, Transylvania.

5. H.  $\frac{O}{2}$ . D. —  $\frac{C_2}{2}$ . Alston Moor.

Cleavage, dodecahedron highly perfect. Fracture conchoidal. Surface, the tetrahedrons and the two tetragonal dodecahedrons generally, though faintly streaked parallel to their common intersections; the trigonal dodecahedron is often uneven or curved, but at the same time smooth and shining.

Lustre adamantine. Colour green, yellow, red, brown, black, none of them bright. Streak white ... reddish-brown, corresponding to the colour. Transparent ... translucent.

Brittle. Hardness = 3.5 ... 4.0. Sp. Gr. = 4.078, a cleavable variety; = 4.027, a columnar, compound variety.

*Compound Varieties.* Twin-crystals: face of composition parallel, axis of revolution perpendicular to a face of the octahedron. Fig. 156. and 163. This composition is often repeated, either in parallel layers, or in the direction of several faces of the octahedron. Reniform and other imitative shapes: surface rough; composition columnar, often almost impalpable; straight, divergent, and frequently producing a second curved lamellar, or granular composition. Massive: composition columnar or granular.



lar, sometimes impalpable, often very distinct. The fracture of impalpable compositions is uneven or even.

#### OBSERVATIONS.

1. Although the subspecies distinguished among the varieties of the species *Blende* have been denominated after their colours, yet they do not depend entirely or solely upon these colours. The colours of *yellow Blende* are green, yellow, or pale reddish-brown; its varieties possess the highest degrees of transparency which occur in the species. The red and brown colours of the *brown Blende* are darker, and its degrees of transparency lower than in the preceding subspecies. The varieties of *black Blende* are either black and opaque, or they are blood-red. *Brown Blende* has been farther subdivided into *foliated*, *radiated*, and *fibrous brown Blende*. Simple varieties and compound ones, consisting of granular individuals, are contained in the first of these divisions; columnar compositions, in which the individuals are still discernible, in the second; and very thin columnar or impalpable compositions originating from them, which assume various imitative shapes, are comprehended in the third division. In the columnar compositions the individuals often present in the cross fracture the even faces of regular composition parallel to a face of the octahedron. Three of the faces of cleavage may be easily obtained parallel to the axis, and produce with the above mentioned faces of composition a regular six-sided prism. On account of the great facility with which the faces of composition may be obtained, it is more difficult to observe the inclined faces of cleavage, which nevertheless are very distinct, and produce with the vertical ones the dodecahedron, as the real form of cleavage of the species. The exact distinction of the Wernerian subspecies of yellow, brown, and black *Blende*, requires a great deal of practice, and can be acquired only empirically, and even then many varieties will occur that render the distinction impossible. This is a sure though empirical demonstration that the distinction itself is useless.

2. According to THOMSON and GUENIVEAU, it consists of

Zinc	59.09	62.00.
Iron	12.05	1.50.
Sulphur	23.86	34.00.

Its chemical formula is  $Zn S^2$ , agreeing with 66.72 of zinc and 33.28 of sulphur. When strongly heated in the oxidating flame of the blowpipe, it gives off vapours of zinc, which form a coating on the charcoal, but it does not melt. It is soluble in nitric acid, during which process sulphuretted hydrogen is disengaged.

3. Dodecahedral Garnet-blende is frequently found in nature; but all its varieties are not equally common. It is met with in beds and veins, accompanied chiefly by hexahedral Lead-glance, several species of Iron-pyrites, Arsenical-pyrites, Copper-pyrites, several Haloides, Barytes, &c., in beds also by dodecahedral Garnet, octahedral Iron-ore, and several species of Augite-spar. It is not rare in rich silver veins, and is associated with native Silver, and the different ores of that metal.

4. Yellow Blende principally occurs in fine varieties at Schemnitz in Lower Hungary, and at Kapnik in Transylvania; also at Scharfenberg, Schwarzenberg, and Rittersgrün in Saxony, at Ratiborzitz in Bohemia, at Gummerrud in Norway, and other places. Brown Blende is found at Freiberg, and other localities in Saxony, in Bohemia, Hungary, and Transylvania, in the Hartz, at Sahla in Sweden, in great quantities in Derbyshire and Cumberland; also in Cornwall in England. The radiated variety in particular is found at Przibram; it is that variety which contains the greatest proportion of cadmium. The chief localities of fibrous Blende are Raibel in Carinthia, Geroldseck in Swabia, and Wheal Unity in Cornwall; of black Blende, Freiberg, Annaberg, Breitenbrunn, and Schwarzenberg in Saxony, and many places in Bohemia, Hungary, Transylvania, Silesia, in the Hartz and other countries.

5. The application of dodecahedral Garnet-blende for the extraction of zinc, is as yet very limited.

## GENUS III. PURPLE-BLENDE.

## I. PRISMATIC PURPLE-BLENDE.

Prismatic Antimony-Blende or Red Antimony. JAM. Syst. Vol. III. p. 421. Man. p. 290. Red Antimony. PHILL. p. 331. Rothspiesglaserz. WERN. Hoffm. H. B. IV. 1. S. 114. Rothspiesglanzerz. HAUSM. I. S. 225. Antimonblende. LEONH. S. 157. Antimoine hydro-sulfuré. HAÜY. Traité, T. IV. p. 276. Antimoine oxydé sulfuré. Tabl. comp. p. 113. Traité, 2de Ed. T. IV. p. 311.

Fundamental form. Scalene four-sided pyramid.

Inclination of the axis =  $11^{\circ} 19'$  in the plane of the long diagonal. Vol. I. Fig. 41. AP.

$$a : b : c : d = 5.0 : 3.1 : c : 1.$$

Simple forms.  $P - \infty$ ;  $\frac{\check{P}_r + 1}{2} = 15^{\circ} 47'$ ;  $-\frac{\check{P}_r}{2} = 34^{\circ} 6'$ ;  $\check{P}_r + \infty$ . The faces of all the forms hitherto observed, are parallel to one of the diagonals of P, and this is supposed to be the short diagonal.

Char. of Comb. Hemi-prismatic. Inclination of  $P - \infty$  on  $\check{P}_r + \infty = 101^{\circ} 19'$ .

Combinations. 1.  $-\frac{\check{P}_r}{2}$ .  $\check{P}_r + \infty$ . 2.  $P - \infty$ .  $-\frac{\check{P}_r}{2}$ .  $\check{P}_r + \infty$ . 3.  $P - \infty$ .  $\frac{\check{P}_r + 1}{2}$ .  $-\frac{\check{P}_r}{2}$ .  $\check{P}_r + \infty$ . All of them are elongated, and often appear only as thin filaments parallel to the short diagonal; the termination of the crystals in that direction has not been observed.

Cleavage.  $\check{P}_r + \infty$  highly perfect; less distinct  $P_r + \infty$ ; there are traces in other directions perhaps of  $P + \infty$ . Fracture not observable.



Surface more or less deeply streaked parallel to the edges of combination.

Lustre common or metallic adamantine. Colour cherry-red. Streak cherry-red or brownish-red. Feebly translucent.

Secile. Thin laminae are slightly flexible. Hardness = 1.0 ... 1.5. Sp. Gr. = 4.5 ... 4.6.

*Compound Varieties.* Tufts of capillary crystals. Massive: composition very thin columnar, straight and divergent from common centres.

## OBSERVATIONS.

1. The division of Red Antimony in the system of WERNER is similar to that of the Grey Antimony. *Common Red Antimony* forms the first, and *Tinder-Ore* the second subspecies. The *Tinder-Ore* comprises those varieties which, originally consisting of short capillary individuals, interlaced with each other, appear in flakes resembling tinder, while the *Common Red Antimony* refers to crystals, and to those compound varieties, in which the columnar individuals are still discernible.

2. According to KLAPROTH, the prismatic Purple-blende consists of

Antimony	67.50.
Oxygen	10.80.
Sulphur	19.70.

Alone before the blowpipe it melts easily upon charcoal, by which it is absorbed, and at last entirely volatilised. Immersed in nitric acid, it is covered with a white coating.

3. It is almost always accompanied by prismatic Antimony-glance, which has induced some mineralogists to believe it to have been produced from a decomposition of that species. It occurs in veins; besides the above mentioned species, it is accompanied by prismatic Antimony-baryte, rhombohedral Quartz, &c.

4. The varieties of this species occur at Bräunsdorf near Freiberg in Saxony, at Malazka near Pösing in Hungary, and at Allemont in Dauphiny in France. The principal localities of Tinder-ore are Clausthal and Andreasberg in the Hartz.

#### GENUS IV. RUBY-BLENDE.

##### 1. RHOMBOHEDRAL RUBY-BLENDE.

Rhomboidal Ruby-blende or Red Silver. JAM. Syst. Vol. III. p. 425. Man. p. 291. Red Silver. Ruby Silver. PHILL. p. 291. Rothgiltigerz. WERN. Hoffm. H. B. III. 2. S. 67. Rothgiltigerz. HAUSM. I. S. 221. Rothgiltigerz. LEONH. S. 199. Argent antimonie sulfuré. HAÜY. Traité, T. III. p. 402. Tabl. comp. p. 75. Traite, 2de Ed. T. III. p. 269.

Fundamental form. Rhombohedron.  $R = 108^{\circ} 18'$ . Vol. I. Fig. 7. R. G.

$$a = \sqrt{1.895}.$$

Simple forms.  $R - \infty (o)$ ;  $R - 2 (s) = 157^{\circ} 40'$ ;  $R - 1 (z) = 137^{\circ} 39'$ ;  $R (P)$ ;  $R + 1 (g, i) = 80^{\circ} 59'$ ;  $R + \infty (k)$ ;  $P + \infty (n)$ ;  $(P - 2)^5 (t)$ ;  $(P - 1)^5 (a)$ ;  $(\frac{5}{4}P - 1)^5 (b)$ ;  $(P)^5 (h)$ ;  $(P)^5$ ;  $(P + 1)^5$ .

Char. of Comb. Rhombohedral. Sometimes the configuration of the opposite apices is different. Of the faces of  $R + \infty$  often only the alternating ones appear, as in rhombohedral Tourmaline.

Combinations. 1.  $R - 1. P + \infty. R + 1.$

$R - 1.$  Fig. 182. Andreasberg, Hartz.\*

2,  $R - 1. \frac{R + \infty}{2}. P + \infty.$  Fig. 136. Andreasberg.

---

\* In the cabinet of Mr ALLAN. H.

3.  $(\frac{5}{4}P - 1)^5$ .  $(P)^5$ .  $P + \infty$ . Saxony.
4.  $R - 2$ .  $R - 1$ .  $(P)^5$ .  $P + \infty$ . Beschertglück, Saxony.
5.  $R - 1$ .  $(P - 2)^5$ .  $R$ .  $P + \infty$ . Joachimsthal, Bohemia.
6.  $R + 1$ .  $(P)^5$ .  $R + \infty$ .  $P + \infty$ . Marienberg, Saxony.
7.  $R - 1$ .  $R + 1$ .  $(P)^5$ .  $(P)^5$ .  $P + \infty$ . Beschertglück.
8.  $R - 1$ .  $(P - 2)^5$ .  $R$ .  $(P - 1)^5$ .  $(\frac{5}{4}P - 1)^5$ .  $(P)^5$ .  $P + \infty$ . Fig. 126.

Cleavage,  $R$ , in several varieties pretty distinct, in others scarcely observable. Fracture conchoidal. Surface,  $R - 2$  streaked parallel to the edges of combination with  $R - 1$ ;  $R - 1$ ,  $(P - 2)^5$  and the pyramids belonging to  $R$ , also  $P + \infty$  often striated parallel to their common edges of combination;  $P + \infty$  is sometimes rough, as is also  $(\frac{5}{4}P - 1)^5$ .

Lustre common adamantine in light coloured varieties, metallic adamantine in dark coloured ones. Colour iron-black ... cochineal-red. Streak several shades of cochineal-red, corresponding to the colour; in some varieties it is almost aurora-red. Semi-transparent ... opaque.

Sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 5.846, crystals from Beschertglück.

*Compound Varieties.* Twin-crystals. 1. Face of composition perpendicular, axis of revolution parallel to an edge of  $R - 1$ . Fig. 139. This



kind of regular composition is frequently repeated, contiguous to all the terminal edges of  $R - 1$ , as in Fig. 140., or still farther, since two new individuals may again be joined to every one of the former group. A great number of individuals are often joined in that manner. 2. Face of composition parallel, axis of revolution perpendicular to a face of  $R - 2$ . This mode of composition forms the supplement to the preceding one, but it is far less frequent. 3. Face of composition parallel to a face of  $R + \infty$ , axis of revolution perpendicular to it. If the individuals are continued beyond the face of composition, then the composition is parallel to all the faces of  $R + \infty$ . Massive : composition granular, of various sizes of individuals, strongly connected. If the composition becomes impalpable, fracture is uneven, even, or flat conchoidal. Plates, superficial coatings.

#### OBSERVATIONS.

1. The difference between the *Light* and *Dark Red Silver*, though originally founded on the different tints of colour and streak of the two minerals, and on their lustre, which is dependent upon them, is deeper rooted in the essence of these bodies than it would appear at first sight. The forms of the *Light Red Silver* have not yet been ascertained with sufficient exactness; they do not seem, however, to be very different from those of the *Dark Red Silver*, and also the peculiarities in their crystallisations are common to both. There is no difference in their hardness. The specific gravity of the two substances, however, is considerably different, being circumscribed, as far as our present information goes, within the limits of 5·8 ... 5·9



for the dark red, and of 5·4 ... 5·6 for the light red variety. A dark red cleavable variety from the Hartz gave 5·831, a light red one, also cleavable, from Annaberg, 5·524, and a crystallised one from the Churprinz mine near Freiberg, having the colour of the dark red variety, 5·422. This subject deserves the particular attention of mineralogists, though as yet it is impossible to settle any thing in regard to the determination of the species. The colours of the Dark Red Silver are dark cochineal-red passing into iron-black, its streak is more or less deep cochineal-red, and it is opaque or but faintly translucent on the edges. The colours of Light Red Silver are more distinctly cochineal-red, but approach in some varieties to those of Dark Red Silver; its streak is light cochineal-red, and often almost aurora-red; it is translucent on the edges, and frequently semi-transparent. In these properties, however, the two varieties are joined by transitions.

2. The rhombohedral Ruby-blende consists, according to BONSDORF, of

Silver	58·949.
Antimony	22·846.
Sulphur	16·609.
Earthy substances	0·299.

He gives for its chemical formula  $3 \text{ Ag S}^2 + 2 \text{ Sb S}^3$ , which corresponds to 58·98 of silver, 23·47 antimony, and 17·55 of sulphur. It decrepitates before the blowpipe upon charcoal, melts and emits fumes of sulphur and antimony, after which it yields a globule of silver. It is soluble in dilute nitric acid.

3. The rhombohedral Ruby-blende has been hitherto always found in veins, associated with various other ores of silver, with hexahedral Silver, hexahedral Lead-glance, dodecahedral Garnet-blende, and several species of Pyrites: the light red varieties often with native Arsenic, prismatic Iron-pyrites, octahedral Cobalt-pyrites, and other species.

4. Rhombohedral Ruby-blende is confined to a small number of localities, but in some of these it occurs in pret-

ty considerable quantities. It is found in many of the veins near Freiberg, also at Marienberg, Annaberg, Schneeberg, and Johanngeorgenstadt in Saxony; likewise at Joachimsthal, Przibram, and other places in Bohemia. The light red varieties are more generally met with in the districts of the Saxon and Bohemian mines, nearer the highest ridge of mountains, while the dark red occur in greater proportion in the neighbourhood of Freiberg, and in other places of the lower districts. The dark red silver is found in beautiful crystals at Andreasberg in the Hartz. It is met with also at Schemnitz, Cremnitz, Nagybanya, &c. in Hungary, in Alsace and Dauphiny in France, at Kongsberg in Norway. Some other countries produce but a small quantity of it, as, for instance, Cornwall; but it is very abundant in Mexico and Peru.

5. It is a valuable mineral for the extraction of silver. It has been observed that the dark red yields a greater quantity of silver than the light red variety.

## 2. HEMI-PRISMATIC RUBY-BLENDE.

One of the varieties commonly comprised among the Dark Red Silver.

Fundamental form. Scalene four-sided pyramid.

$P = \left\{ \begin{array}{l} 128^{\circ} 59' \\ 121^{\circ} 1' \end{array} \right\}$ ,  $130^{\circ} 7'$ ,  $77^{\circ} 16'$ . Inclination of the axis =  $11^{\circ} 6'$ , in the plane of the long diagonal. Vol. I. Fig. 41. AP.

$$a : b : c : d = 5.1 : 9.5 : 8.7 : 1.$$

Simple forms.  $P - \infty (b)$ ;  $\frac{P}{2} = 128^{\circ} 59'$ ;  $P + \infty$

$$(f) = 86^{\circ} 4'; - \frac{(\bar{P}r)^5}{2}; - \frac{\bar{P}r + 1}{2} (t) = 47^{\circ}$$

$$26'; \frac{\frac{5}{4} \bar{P}r + 2}{2} = 28^{\circ} 9'.$$



Char. of Comb. Hemi-prismatic. Inclination of  
 $P - \infty$  on  $\check{P}r + \infty = 101^\circ 6'$ .

Combination. 1.  $P - \infty$ . —  $\frac{\check{P}r + 1}{2}$ .  $P + \infty$ . Fig.

183. There occur many secondary faces; the whole has much the appearance of crystals of hemi-prismatic Vitriol-salt.

Cleavage,  $\frac{5}{4} \frac{\check{P}r + 2}{2}$  and  $\check{P}r + \infty$ , imperfect. Fracture imperfect conchoidal. Surface, deeply streaked parallel to the edges of combination with  $\frac{5}{4} \frac{\check{P}r + 2}{2}$ , particularly  $P - \infty$  and  $P + \infty$ , as indicated in the figure; the pyramids are smooth, —  $\frac{\check{P}r + 1}{2}$  rough, though even.

Lustre intermediate between metallic and metallic adamantine. Colour iron-black. Streak dark cherry-red. Opaque, except in thin splinters, where it transmits a deep blood-red colour.

Very sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 5.234.

#### OBSERVATIONS.

1. The chemical composition of this species has not been as yet exactly ascertained. Before the blowpipe it gives results nearly agreeing with those of rhombohedral Ruby-blende, but it contains only about 35 ... 40 per cent. of silver, besides sulphur and antimony. The only specimen of it, in the possession of Mr VON WEISSENBACH at Freiberg, is supposed to have been found in the mine called Neue Hoffnung Gottes, at Bräunsdorf near Freiberg in

Saxony. It consists only of crystals, and is not accompanied by any other mineral.\*

### 3. PERITOMOUS RUBY-BLENDE.

Prismato-rhomboidal Ruby-blende or Cinnabar. JAM. Syst. Vol. III. p. 435. Man. p. 292. Cinnabar. Sulphuret of Mercury. PHILL. p. 358. Zinnober. Quecksilber-Lebererz. WERN. Hoffm. H. B. III. 2. S. 26. 33. Zinnober. Stinkzinnober. Lebererz. HAUSM. I. S. 213. 215. 216. Zinnober. LEONH. S. 187. Mercure sulfuré. HAÜY. Traité, T. III. p. 437. Tabl. comp. p. 78. Traité, 2de Ed. T. III. p. 313.

Fundamental form. Rhombohedron.  $R = 71^{\circ} 47'$ .

Vol. I. Fig. 7. HAÜY.

$$a = \sqrt{15.75}.$$

Simple forms.  $R - \infty (o)$ ;  $R - 2 (u) = 122^{\circ} 35'$ ;  $\frac{4}{3} R - 2 (z) = 110^{\circ} 6'$ ;  $\frac{4}{5} R - 1 (k) = 101^{\circ} 59'$ ;  $R - 1 (a) = 92^{\circ} 36'$ ;  $R (P)$ ;  $R + \infty (l)$ .

Char. of Comb. Rhombohedral.

Combinations. 1.  $R - \infty$ .  $R + \infty$ . Almaden, Spain.

2.  $R - \infty$ .  $R - 2$ .  $\frac{4}{3} R - 2$ .  $R$ . Idria, Carniola.

3.  $R - \infty$ .  $\frac{4}{3} R - 2$ .  $R$ .  $R + \infty$ . Almaden.

4.  $R - \alpha$ .  $R - 2$ .  $\frac{4}{3} R - 2$ .  $\frac{4}{5} R - 1$ .  $R - 1$ .

$R$ .  $R + \infty$ . Fig. 125. Almaden.

Cleavage,  $R + \infty$ , highly perfect. Fracture conchoidal. Surface, the rhombohedrons horizontally streaked, some of them very deeply.

Lustre adamantine, inclining to metallic in dark coloured varieties. Colour several shades of co-

\* I must here mention a finely crystallised specimen in the possession of Mr BROOKE, which seems to have some properties analogous to the hemi-prismatic Ruby-blende. Yet its combinations appear to be tetarto-prismatic, and may therefore belong to another species. II.

chineal-red, the darker varieties inclining to lead-grey. Streak scarlet-red. Semi-transparent ... translucent on the edges.

Sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 8.098, the cleavage variety from Neumarktel.

*Compound Varieties.* Twin-crystals: face of composition parallel, axis of revolution perpendicular to a face of R —  $\infty$ ; the individuals frequently continued beyond the face of composition. Rarely in some indistinct imitative shapes. Massive: composition granular, of various sizes of individuals, generally small, and often impalpable. In the last case fracture becomes uneven, even, or flat conchoidal. Plates, superficial coatings. There is sometimes a tendency to thin columnar composition, the mass being friable, and the colour scarlet-red.

## OBSERVATIONS.

1. *Cinnabar* and *Quicksilver Liver-Ore* or *Hepatic Cinnabar*, which formerly used to be distinguished as two different species, in fact do not differ more from each other than calcareous spar and compact limestone, or crystallised and compact hexahedral Lead-glance. The *Quicksilver Liver-Ore* is a compound variety of *Cinnabar*, sometimes impure, and having on that account a streak which is not perfectly scarlet-red, but inclines to brown. There is a farther subdivision of each of these two kinds of rhombohedral Ruby-blende. The *dark red* *Cinnabar* comprehends the crystals, and those compound varieties in which the individuals are still discernible; it is generally cochineal-red. The *bright red* *Cinnabar* is friable, and of a scarlet-red colour. The *compact* *Quicksilver Liver-Ore* contains uniform massive varieties of a granular composition, consisting of impalpable individuals. The *slaty* *Quicksilver Liver-*



Ore is the same thing, only interrupted by irregularly streaked smooth faces, which possess a slaty appearance. These, however, are entirely accidental, and have no relation to the composition itself. These varieties, and the dark-red Cinnabar, are closely connected by transitions, as is always the case in well determined species. This is not so immediately the case in the bright red Cinnabar, perhaps because the latter seems to have undergone a kind of disintegration, as the traces of columnar composition which are often observable, indicate.

2. According to two analyses by KLAPROTH, it consists of

Mercury	84.50	85.00.
Sulphur	14.75	14.25.

Its chemical formula is  $\text{Hg S}^2$ , corresponding to 86.29 of mercury, and 13.71 of sulphur. The Quicksilver Liver-Ore contains small quantities of carbon, silica, oxide of iron, and other foreign admixtures. Before the blowpipe the pure varieties are entirely volatilised. It is soluble in nitric acid. It may be obtained in crystalline masses, shewing a columnar composition, on being sublimated.

3. Peritomous Ruby-blende chiefly occurs in beds, accompanied by fluid Mercury, and the rare species of dodecahedral Mercury and pyramidal Pearl-kerate, sometimes only by rhombohedral Lime-haloide and rhombohedral Quartz. Some of its varieties have also been found in veins, where they occur along with several ores of iron. It is found besides in small quantities in the beds of brachytypous Parachrose-baryte.

4. It occurs in beds in gneiss, at Reichenau in Upper Carinthia, and at Hartenstein in Saxony; also at Dumbrawa in Transylvania, in greywacke. Included in limestone in irregular beds, and in those veins of calcareous spar which traverse it in all directions, it is found at Hermagor, Windisch-Kappel, and other places in Carinthia, but particularly at Neumarkt in Carniola. Its most important repositories, however, are Idria in Carniola, the Palatinate,

and Almaden in Spain. At Idria it occurs in beds of bituminous shale, with black Mineral-resin, and dark grey sandstone, associated with limestone. It seems that the repositories of Moschellandsberg, Wolfstein, and Almaden, are much of the same nature. The peritomous Ruby-blende is found in veins at Schemnitz, Cremnitz, and Rosenau in Hungary, at Horzowitz in Bohemia, and in the Erzberg near Eisenerz in Stiria. The Quicksilver Liver-Ore has been found only at Idria, the bright red Cinnabar at Wolfstein in the Palatinate. Peritomous Ruby-blende is found besides in considerable quantities in Mexico and Peru, in China, Japan, &c.; small quantities are met with in several countries.

5. It is used for the extraction of mercury; but only if very pure, it may be employed as a pigment in its natural state.

## ORDER XIII. SULPHUR.

## GENUS I. SULPHUR.

## I. PRISMATOIDAL SULPHUR.

Yellow Orpiment or Prismatic Sulphur. *JAM. Syst.* Vol. III. p. 455. Prismatic Sulphur or Yellow Orpiment. *Man.* p. 293. Orpiment. *PHILL.* p. 277. Gelbes Rauschgelb. *WERN. Hoffm. H. B. IV. 1. S.* 220. Rauschgelb. *HAUSM. I. S.* 208. Auripigment. *LEONH. S.* 168. Arsenic sulfuré jaune. *HAÜY. Traité,* T. IV. p. 234. *Tabl. comp.* p. 109. *Traite,* 2de Ed. T. IV. p. 247.

Fundamental form. Scalene four-sided pyramid.

$P = 131^{\circ} 36', 94^{\circ} 20', 105^{\circ} 6'.$  Vol. I. Fig. 7. *AP.*

$$a : b : c : = 1 : \sqrt{0.8} : \sqrt{2.2}.$$

Simple forms.  $P (P)$ ;  $P + \infty = 117^{\circ} 49'$ ;  $(\check{P}r)^5$ ;

$(\check{P}r + \infty)^5 (u) = 79^{\circ} 20'$ ;  $\check{P}r (o) = 83^{\circ} 37'$ ;

$\check{P}r + \infty (s)$ ;  $\check{P}r + \infty.$

Char. of Comb. Prismatic.

Combinations. 1.  $P. P + \infty. (\check{P}r + \infty)^3$ . Sim. Fig. 36., without  $n$  and  $x$ .

2.  $\check{P}r. P. (\check{P}r + \infty)^5. \check{P}r + \infty$ . Fig. 17.

3.  $\check{P}r. P. (\check{P}r)^5. P + \infty. (\check{P}r + \infty)^3. \check{P}r + \infty$ .

All of them from Tajowa, Hungary.

Cleavage,  $\check{P}r + \infty$ , highly perfect; the faces of cleavage are streaked parallel to the edges of intersection with  $\check{P}r + \infty$ , parallel to which there are likewise some traces of cleavage. Fracture scarcely observable. Surface,  $\check{P}r + \infty$ , rough, but even; all the other faces are streaked parallel to their edges of combination with  $\check{P}r + \infty$ , and generally uneven.

Lustre metallic-pearly upon the perfect faces of cleavage, for the rest resinous. Colour several shades of lemon-yellow. Streak lemon-yellow, generally a little paler than the colour. Semi-transparent ... translucent on the edges.

Sectile. Thin laminae are highly flexible. Hardness = 1.5 ... 2.0. Sp. Gr. = 3.480, a cleavable variety.

*Compound Varieties.* Reniform, botryoidal, and other imitative shapes: composition curved lamellar, faces of composition commonly rough. Massive: composition granular, of various sizes of individuals; faces of composition uneven, often irregularly streaked.

#### OBSERVATIONS.

I. *Orpiment* and *Realgar*, the prismatic and the hemi-prismatic Sulphur, are improperly united within one



and the same species in most mineralogical works. Their specific difference is obvious in several of their properties, in the measures of their angles, the character of their combinations, and particularly in their cleavage. Eminent faces of cleavage, like those in the present species, never disappear altogether in simple varieties, and may be observed even in compound ones, though the particles of composition be nearly impalpable. But no trace of such a cleavage exists in the following species, and this circumstance will therefore always yield a sure and palpable, though not the only character for distinguishing Orpiment from Realgar.

2. According to KLAPROTH and LAUGIER, the prismatic Sulphur consists of

Sulphur	38·00	38·14.
Arsenic	62·00	61·86.

Its chemical formula  $As S^3$  agrees with 39·08 of sulphur, and 60·92 of arsenic. Before the blowpipe upon charcoal it burns with a blue flame, and emits fumes of sulphur and arsenic. It is soluble in the nitric, muriatic, and sulphuric acids.

3. The prismatic Sulphur is found in imbedded nodules, more rarely in imbedded crystals in blue clay, and is accompanied by hemi-prismatic Sulphur. In this way it is met with at Tajowa near Neusohl in Lower Hungary, in the neighbourhood of Vienna, and probably also in Wallachia, Servia, and other countries. At Kapnik in Transylvania, and Felsöbanya in Upper Hungary, it occurs in metalliferous veins with several species of Pyrites, Blende, and Glance, with native Arsenic, and particularly with hemi-prismatic Sulphur. It is found likewise in Natolia, China, and Mexico.

5. It is used as a pigment.

## 2. HEMI-PRISMATIC SULPHUR.

Red Orpiment or Ruby Sulphur or Hemi-prismatic Sulphur. JAM. Syst. Vol. III. p. 451. Hemi-prismatic

Sulphur, or Red Orpiment. Man. p. 294. Rothes Rauschgelb. WERN. Hoffm. H. B. IV. 1. S. 224. Realgar. HAUSM. I. S. 210. Realgar. LEONH. S. 166. Arsenic sulfuré rouge. HAÜY. Traité, T. IV. p. 228. Tabl. comp. p. 109. Traité, 2de Ed. T. IV. p. 247.

Fundamental form. Scalene four-sided pyramid.

$P = \left\{ \begin{matrix} 130^\circ 1' \\ 131^\circ 59' \end{matrix} \right\}$ ,  $142^\circ 59'$ ,  $62^\circ 44'$ . Inclination of the axis =  $4^\circ 1'$  in the plane of the long diagonal. Vol. I. Fig. 41. Ap.

$$a : b : c : d = 14.2 : 38.55 : 29.25 : 1.$$

Simple forms.  $\pm \frac{P}{2} \left\{ \begin{matrix} n \\ n' \end{matrix} \right\} = \left\{ \begin{matrix} 130^\circ 1' \\ 131^\circ 59' \end{matrix} \right\}$ ;  $P + \infty$

$$(f); \pm \frac{(\check{P}r)^5}{2} \left\{ \begin{matrix} q \\ q' \end{matrix} \right\} = \left\{ \begin{matrix} 94^\circ 2' \\ 96^\circ 36' \end{matrix} \right\}; - \frac{(\check{P})^5}{2} (l);$$

$$(\check{P}r + \infty)^5 (g) = 113^\circ 20'; (\check{P}r + \infty)^7 (w) = 90^\circ 48'; (\check{P} + \infty)^{\frac{5}{2}} = 124^\circ 30'; (\check{P}r + \infty)^5 (v)$$

$$= 53^\circ 56'; \pm \frac{\check{P}r}{2} \left\{ \begin{matrix} x \\ P \end{matrix} \right\} = \left\{ \begin{matrix} 73^\circ 18' \\ 66^\circ 44' \end{matrix} \right\}; \frac{\frac{5}{4} \check{P}r + 2}{2}$$

$$= 43^\circ 52'; \check{P}r + \infty (s); \check{P}r + \infty (u).$$

Char. of Comb. Hemi-prismatic. Inclination of  $P - \infty$  on  $\check{P}r + \infty = 85^\circ 59'$ .

Combinations. 1.  $-\frac{\check{P}r}{2}$ .  $P + \infty$ . Sim. Fig. 44., reversed.

$$2. -\frac{\check{P}r}{2}. -\frac{P}{2}. P + \infty. (\check{P}r + \infty)^5. \text{ Fig. 48.}$$

$$3. \frac{\check{P}r}{2}. \frac{P}{2}. \frac{(\check{P}r)^5}{2}. -\frac{\check{P}r}{2}. -\frac{P}{2}. -\frac{(\check{P}r)^5}{2}.$$

$$-\frac{(\check{P})^5}{2}. P + \infty. (\check{P}r + \infty)^5. (\check{P}r + \infty)^5.$$

$(\text{Pr} + \infty)^5$ .  $\check{\text{Pr}} + \infty$ .  $\text{Pr} + \infty$ . Fig. 184.

All of them from Nagyag, Transylvania.

Cleavage,  $-\frac{\check{\text{Pr}}}{2}$  and  $\text{Pr} + \infty$  rather perfect; less

distinct  $\frac{\text{P}}{2}$ ,  $\text{P} + \infty$  and  $\check{\text{Pr}} + \infty$ ; traces of

$(\check{\text{Pr}} + \infty)^3$ ; all of them much interrupted. Frac-

ture perfect conchoidal. Surface, the ptisms in

the direction of the principal axis streaked paral-

lel to that line, the inclined faces often rough,

particularly  $-\frac{\text{P}}{2}$ , and almost always  $\frac{\check{\text{Pr}}}{2}$  and

$\frac{3}{4} \frac{\check{\text{Pr}} + 2}{2}$ ;  $-\frac{\check{\text{Pr}}}{2}$  is sometimes streaked parallel

to the edges of combination with  $-\frac{\text{P}}{2}$ .

Lustre resinous. Colour, aurora-red, several shades, little differing from each other. Streak orange-yellow ... aurora-red.

Sectile. Hardness = 1.5 ... 2.0. Sp. Gr. = 3.556, a semi-transparent crystal.

*Compound Varieties.* Massive: composition granular, of various sizes of individuals, strongly connected. Fracture conchoidal, uneven.

#### OBSERVATIONS.

1. According to KLAPROTH and LAUGIER, hemi-prismatic Sulphur consists of

Sulphur 31.00                      30.43.

Arsenic 69.00                      69.57.

Its chemical formula is  $\text{As S}^2$ , which requires 29.96 of sul-



phur, and 70.04 of arsenic. It gives the same re-actions as the preceding species.

2. Some of the varieties of hemi-prismatic Sulphur occur along with the prismatic one, in beds of clay, as at Tajowa in Hungary. It is found in small nodules, along with tetrahedral Copper-glance and hexahedral Iron-pyrites, engaged in dolomite, a granular variety of macroty-pous Lime-haloide, at St Gothard in Switzerland. More generally it is met with in metalliferous veins, particularly with ores of silver and lead, with native Arsenic, several species of Pyrites, of Baryte, and Haloide, &c. The chief localities are Kapnik and Nagyag in Transylvania, Felsö-banya in Upper Hungary, Joachimsthal in Bohemia, Schneeberg in Saxony, Andreasberg in the Hartz, and many other places. Hemi-prismatic Sulphur is found in Peru, in the United States of North America, and along with the preceding species in the vicinity of several active volcanoes.

4. The hemi-prismatic Sulphur, like the preceding species, is used as a pigment.

### 3. PRISMATIC SULPHUR.

Prismatic Sulphur. JAM. Syst. Vol. III. p. 459. Man. p. 295. Sulphur. PHILL. p. 360. Natürlicher Schwefel. WERN. Hoffm. H. B. III. 1. S. 252. Schwefel. HAUSM. I. S. 61. Schwefel. LEONH. S. 109. Soufre. HAÛY. Traité, T. III. p. 277. Tabl. comp. p. 68. Traité, 2de Ed. T. IV. p. 407. MITSCHERLICH. Ann. de Chimie. Vol. XXIV. p. 264.

Fundamental form. Scalene four-sided pyramid.

$P = 106^{\circ} 38', 84^{\circ} 58', 143^{\circ} 17'$ . Vol. I. Fig. 7.

MITSCHERLICH.

$$a : b : c = 1 : \sqrt{0.2776} : \sqrt{0.1824}.$$

Simple forms.  $P - \infty (r)$ ;  $\frac{4}{5} P - 2 = 142^{\circ} 4'$ ,

$133^{\circ} 3', 62^{\circ} 9'$ ;  $\frac{4}{3} P - 2 (s) = 127^{\circ} 1', 113^{\circ} 11'$ ,

$90^{\circ} 15'$ ;  $\dot{P} (P)$ , Conil, Spain;  $P + \infty (m) =$

101° 59';  $\check{P}r (n) = 55^\circ 36'$ ;  $\check{P}r = 46^\circ 15'$ ;  
 $\check{P}r + \infty (o)$ .

Char. of Comb. Prismatic.

Combinations. 1.  $P - \infty$ .  $P$ .

2.  $P - \infty$ .  $\frac{4}{3}P - 2$ .  $\check{P}r$ .  $P$ .  $P + \infty$ . Fig. 18. Sicily.

3.  $P - \infty$ .  $\frac{4}{5}P - 2$ .  $\frac{4}{3}P - 2$ .  $\check{P}r$ .  $\check{P}r$ .  $P$ .  
 $P + \infty$ . Artern, Thuringia.

Cleavage,  $P$  and  $P + \infty$ , imperfect, difficultly obtained, and interrupted. Fracture conchoidal, sometimes highly perfect. Surface,  $\check{P}r$  commonly rough, the rest of the faces generally smooth and shining, possessing nearly the same physical quality.

Lustre resinous. Colour, several shades of sulphur-yellow, inclining sometimes to red or green. Streak sulphur-yellow, passing into white. Transparent ... translucent on the edges.

Sectile. Hardness = 1.5 ... 2.5. Sp. Gr. = 2.072, crystals from Spain.

*Compound Varieties.* Twin-crystals: axis of revolution perpendicular, face of composition parallel to a face of  $\check{P}r$ .\* Imbedded globules: surface uneven; composition impalpable, often impure. Massive: composition granular, often impalpable, strongly coherent; fracture uneven, even, flat conchoidal. Sometimes pulverulent.

---

\* This kind of regular composition has been observed by Dr G. ROSE. H.

## OBSERVATIONS.

1. The usual division of the present species into *common* and *volcanic* Sulphur depends upon the geological situation of their natural repositories. The second kind is a product of sublimation; it appears in the shape of crusts, superficial coatings, stalactites, or also in loose mealy masses; and consists generally of columnar particles of composition, not unfrequently terminating in crystalline points. It occurs sometimes also in very considerable crystals. Common Sulphur has been farther subdivided into *compact* and *earthy*, the last of which comprehends those varieties which, on account of the smallness of the individuals in the granular compositions, appear as a friable mealy powder.

2. The prismatic Sulphur is the pure sulphur as it occurs in nature, occasionally mixed with bitumen or clay. It acquires resinous electricity by friction, is easily inflammable, and burns with a blue or white flame, and a pungent smell of sulphurous acid. It is insoluble in water, but unites readily with potash or soda. It may be obtained crystallised by sublimation, or still more easily from solutions in liquids. Professor MITSCHERLICH has shewn, that the forms of sulphur, crystallised from fusion, are incompatible with those of the present species. They are hemi-prismatic, being generally oblique rhombic prisms of  $90^{\circ} 32'$ , the terminal face of which is inclined to the obtuse edge of the prism, which is itself commonly replaced, at an angle of  $95^{\circ} 46'$ ; a horizontal prism in the direction of the short diagonal measures  $90^{\circ} 18'$ . It occurs almost always in regular compositions. The crystals are at first transparent, but they soon become opaque. It has not yet been observed in nature.

3. The prismatic Sulphur is principally met with in beds of prismatic Gypsum-haloide, or in the accompanying strata of clay. It is generally associated with rhombohedral Lime-haloide, and often also with prismatic Hal-baryte. In veins it occurs with pyramidal Copper-pyrites, hexahedral Lead-glance, hemi-prismatic Sulphur,



&c. It is deposited from several springs, and in large quantities from volcanoes. Sometimes it occurs in beds of bituminous Mineral-coal.

4. Prismatic Sulphur is found in splendid crystals, and pure massive varieties, also in globular concretions, which, however, are seldom without earthy or bituminous admixtures, in Sicily, and several provinces of Italy. It occurs in imbedded spheroidal masses of a brown colour, which is owing to bitumen, at Radoboy near Crapina in Croatia. Near Cracovia in Poland it is likewise met with in more or less pure massive varieties and small crystals. The finest crystals, besides Sicily, are known from Conil near Cadiz in Spain. Small crystals have been observed investing the brown coal from Artern in Thuringia. In veins it occurs in Swabia, in Spain, and in Transylvania. The earthy Sulphur is found in Poland, in Moravia, and other countries, the volcanic Sulphur in Iceland, near Vesuvius, in the Solfatara, in fine crystals in Teneriffe, in great profusion near the volcanoes of Java, and in the vicinity of most other active volcanoes. Prismatic Sulphur occurs besides in Savoy, in Piedmont, in Switzerland, at Lauenstein in Hanover, in South America, and many other countries.

5. Prismatic Sulphur requires to be purified, either by melting or by sublimation, for rendering it fit to be an object of commerce. It is used in the manufacture of gunpowder, of cinnabar, of several pharmaceutical preparations, of sulphuric acid, and various other articles.

---

### CLASS III.

RESIN. COAL.

---

#### ORDER I. RESIN.

GENUS I. MELICHRONE\*-RESIN.

##### 1. PYRAMIDAL MELICHRONE-RESIN.

Pyramidal Honeystone. JAM. Syst. Vol. III. p. 467.  
Pyramidal Mellilite or Honeystone. Man. p. 296.  
Mellite. PHILL. p. 374. Honigstein. WERN. Hoffm.  
H. B. III. 1. S. 334. Honigstein. HAUSM. III. S.  
811. Honigstein. LEONH. S. 648. Mellite. HAÜY.  
Traité, T. III. p. 335. Tabl. comp. p. 72. Traité, 2de  
Ed. T. IV. p. 445.

Fundamental form. Isosceles four-sided pyramid.

$P = 118^{\circ} 4', 93^{\circ} 22'$ . Vol. I. Fig. 8. HAÜY.

$$a = \sqrt{1.125.}$$

Simple forms.  $P - \infty (o)$ ;  $P - 1 (t) = 130^{\circ} 55',$   
 $73^{\circ} 44'$ ;  $\overset{*}{P} (P)$ ;  $[P + \infty] (g)$ .

Char. of Comb. Pyramidal.

Combinations. 1.  $P - \infty$ . P. Sim. Fig. 92.

2. P.  $[P + \infty]$ . 3.  $P - \infty$ .  $P - 1$ . P.

$[P + \infty]$ . Fig. 105. All of them from Artern.

---

\* From *μελίχρος*, having the colour of honey.

Cleavage, P, very difficult. Fracture conchoidal.

Surface, P —  $\infty$  rough and curved, P — 1 rough, P and [P +  $\infty$ ] smooth and shining.

Lustre resinous, inclining to vitreous. Colour honey-yellow, inclining often to red or brown. Streak white. Transparent ...translucent.

Sectile. Hardness = 2.0...2.5. Sp. Gr. = 1.597.

*Compound Varieties.* Small massive nodules : composition granular,

## OBSERVATIONS.

1. According to KLAPROTH, the present species consists of

Alumina 16.00.

Mellitic Acid 46.00.

Water 33.00.

It loses colour and transparency, when exposed to the flame of a candle, and is soluble in nitric acid.

2. It does not frequently occur in nature, as there is only one well authenticated locality of it, Artern in Thuringia, where it is found in a bed of brown coal, which is nearly earthy, sometimes accompanied by small crystals of prismatic Sulphur. It has been quoted from Switzerland.

## GENUS II. MINERAL-RESIN.

## 1. YELLOW MINERAL-RESIN.

Yellow Mineral Resin or Amber. JAM. Syst. Vol. III. p. 470. Man. p. 297. Amber. PHILL. p. 373. Bernstein. WERN. Hoffm. H. B. III. 1. S. 324. Börnstein. HAUSM. I. S. 92. Bernstein. LEONH. S. 664. Succin. HAÜY. Traité, T. III. p. 327. Tabl. comp. p. 71. Traité, 2de Ed. T. IV. p. 473.

Irregular forms, grains and spheroidal masses,



Cleavage none. Fracture conchoidal. Surface uneven and rough.

Lustre resinous. Colour yellow prevalent, passing into red, brown, and white. Streak white. Transparent ... translucent.

Not very brittle. Hardness = 2.0 ... 2.5. Sp. Gr. = 1.081, a honey-yellow variety. Resinous electricity produced by friction.

## OBSERVATIONS.

1. Two subspecies have been distinguished in *Amber*, according to their lustre and transparency. *Yellow Amber* contains yellow and red varieties, possessing the highest degrees of transparency to be met with in the species, while *white Amber* refers to white and pale yellow faintly translucent varieties. Often, however, both kinds are joined in one and the same specimen, and pass insensibly into each other, which demonstrates their identity.

2. According to DRAPPIER, it consists of

Carbon	80.59.
Hydrogen	7.31.
Oxygen	6.73.
Lime	1.54.
Alumina	1.10.
Silica	0.63.

It burns with a yellow flame, giving out an agreeable odour, and leaves a carbonaceous residue. It is soluble in alcohol.

3. The yellow Mineral-resin no doubt derives its origin from the vegetable kingdom. This receives an additional evidence by the insects and other organic bodies which it includes. It is found in beds of bituminous wood, from which it is disengaged by the action of the waves on the sea coast, and then thrown out or taken with nets.

4. The greatest quantity of the present species is obtained on the Prussian coasts of the Baltic, also on the coasts of Courland, Livonia, Pomerania, and Denmark. But it

has been found also, generally engaged in bituminous wood, in Sicily, in Spain, near Paris in France, in Greenland, in China, and other countries.

5. It is cut into various ornaments and works of art, it enters the composition of certain kinds of varnish, and serves for fumigation. Considerable value is attached to large specimens which are transparent.

## 2. BLACK MINERAL-RESIN.

Black Mineral Resin. JAM. Syst. Vol. III. p. 481. Man. p. 298. Mineral Oil. Bitumen. Mineral Pitch. PHILL. p. 366. 368. Erdöl. Erdpech. WERN. Hoffm. H. B. III. 1. S. 266. 270. IV. 2. S. 137. Bergpech. Elaterit. Bergtheer. Naphtha. HAUSM. I. S. 85. 87. 88. 89. Erdöl. Elaterit. Asphalt. LEONH. S. 678. 680. 681. Bitume. HAÜY. Traité, T. III. p. 310. Tabl. comp. p. 70. Traité, 2de Ed. T. IV. p. 452.

Aggregation solid, or fluid, and all the intermediate stages. No regular form. Stalactitic shapes: surface smooth. Massive.

Fracture conchoidal, more or less perfect, uneven.

Lustre resinous. Colour black prevalent, but passing also into various brown and red tints. Fluid varieties are sometimes perfectly colourless. Streak commonly unchanged, sometimes lighter than the colour. Translucent on the edges, opaque; some fluid varieties are transparent.

Sectile, malleable, elastic. Bituminous odour. Hardness = 0.0 ... 2.0. Sp. Gr. = 0.828, brown, malleable; = 1.073, black, slaggy; 1.160, hyacinth-red, slaggy.

### OBSERVATIONS.

1. *Mineral Oil* and *Mineral Pitch*, generally considered as two distinct species, are included in the black Mineral-

resin, as they scarcely differ in any thing but in their state of aggregation, which, however, from the perfectly fluid to the solid varieties, forms an un'interrupted series. The mineral oil is first inspissated, and then it is changed into mineral pitch by exposure to the air. Mineral pitch has been divided into *elastic*, *earthy*, and *slaggy*. The first is distinguished by its elasticity, which, however, it loses on exposure to the air, the fracture of the second is earthy, that of the third more or less perfectly conchoidal, and corresponding to the degrees of lustre it possesses. All these varieties are joined by transitions.

2. The fluid variety of the present species, called *Naphtha*, consists, according to THOMSON and SAUSSURE, of

Carbon	82.20	87.60.
Hydrogen	14.80	12.78.

Mineral oil is easily inflammable, and burns with a white flame and much smoke. Also the mineral pitch is very inflammable, and burns with a bituminous smell; some varieties melt in a higher temperature.

3. The fluid varieties of the present species ooze out of several rocks, as sandstone, slaty clay, &c., or they are found on the surface of springs and other waters. The elastic varieties occur only in the repositories of hexahedral Lead-glance in limestone rocks; the earthy ones in beds associated with limestone, and probably included in some of the coal formations. The slaggy varieties are often included in nodules in limestone, in agate balls, in veins, with hexahedral Lead-glance, octahedral Fluor-haloide, &c.; also in beds. It is met with on the shores and in the waters of the Dead Sea.

4. Fluid varieties have been found in various districts of Italy, in Sicily, in Zante, in the Caspian Sea, in Persia, and other countries in Asia; also, though in smaller quantities, in Westphalia and Alsace. Elastic mineral pitch, sometimes called *Mineral Caoutchouk*, has been hitherto found only at Castleton in Derbyshire. Earthy mineral pitch is found near Neufchatel in Switzerland, at Grund in the Hartz, in Dalmatia, &c.; the slaggy varieties occur



forming nodules in limestone at Bleiberg in Carinthia, imbedded in sandstone in Albania, in great profusion in the island of Trinidad. It is found in veins in the Iberg near Grund in the Hartz, in Derbyshire, and other places.

5. The different varieties of the present species allow of considerable application for illuminating, for fuel, in fire-works, in the manufacture of varnish, of black sealing-wax, and for other purposes.

## ORDER II. COAL.

### GENUS I. MINERAL-COAL.

#### I. BITUMINOUS MINERAL-COAL.

Brown Coal (excepting Alum-Earth). Black Coal. JAM. Syst. Vol. III. p. 495. 507. Bituminous Mineral Coal (excepting Alum-Earth). Man. p. 301. Black Coal. Common Coal. Cannel Coal. Jet. Brown Coal. PHILL. p. 370. 371. 372. Braunkohle (excepting Alaunerde). Schwarzkohle (excepting Stangenkohle). WERN. Hoffm. H. B. III. 1. S. 277. 291. Schwarzkohle. Braunkohle. HAUSM. I. S. 73. 77. Pechkohle. Blätterkohle. Kannelkohle. Gröbkohle. Russkohle. Braunkohle. Bituminöses Holz. Moorkohle. Erdkohle. Papierkohle. LEONH. S. 669. 670. 671. 672. 673. 675. 676. 677. Houille. Jayet. HAÜY. Traité, T. III. p. 316. 324. Houille (excepting H. bacillaire). Jayet. Tabl. comp. p. 71. Traité, 2de Ed. T. IV. p. 459. 470.

No regular form or structure. Fracture conchoidal, uneven.

Lustre resinous, more or less distinct. Colour, black or brown, passing in earthy varieties into greyish tints. Streak unchanged, except that it sometimes becomes shining. Opaque.

Sectile, in different degrees. Hardness = 1.0...2.5.

Sp. Gr. = 1.223, moor-coal from Teplitz ; = 1.270, common brown coal from Eibiswald in

Stiria; = 1·271, black coal from Newcastle; = 1·288, bituminous wood; 1·329, common brown coal from Leoben in Stiria; 1·423, cannel coal from Wigan in Lancashire.

*Compound Varieties.* Massive: composition lamellar, faces of composition smooth and even, different gradations; granular texture, often impalpable, and then fracture is uneven, even, or flat conchoidal. Ligniform shapes, the structure of which resembles that of wood, sometimes very distinct, but often obliterated, with the exception of some slight traces. Fracture then becomes conchoidal, particularly across the fibres. There are some earthy varieties of a loose friable texture.

#### OBSERVATIONS.

1. In the present species of bituminous Mineral-coal are comprised the *Brown Coal* and the *Black Coal* of WERNER, excepting the columnar coal, which must be referred to the following species. These two kinds, however, and still more so the varieties which they contain, are very difficult to be ascertained. Colour, structure, and the kind of lustre which depends upon the latter, are almost all that remain for their distinction. The colour of *Brown Coal*, as the name imports, is brown; it possesses a ligneous structure, or consists of earthy particles; the colour of *Black Coal* is black, not inclining to brown, and it does not possess the structure of wood. The varieties of *Brown Coal* are the following: *Bituminous Wood*, which presents a ligneous texture, and very seldom any thing like conchoidal fracture, imperfect, and without lustre; *Earthy Coal*, consisting of loose friable particles; *Moor Coal*, or *Trapezoidal Brown Coal*, distinguished by the want of ligneous structure, by the property of bursting and splitting into angular

fragments, when removed from its original repository, and the low degree of lustre upon its imperfect conchoidal fracture; *Common Brown Coal*, which, though it still shews traces of ligneous texture, is of a more firm consistency than the rest of the varieties, and possesses higher degrees of lustre upon its more perfect conchoidal fracture. Some varieties of Black coal immediately join those of Brown coal. They are: *Pitch Coal*, of a velvet-black colour, generally inclining to brown, strong lustre, and presenting in every direction large and perfect conchoidal fracture. *Slate Coal* possesses a more or less coarse slaty structure, which, however, seems to be rather a kind of lamellar composition, than real fracture. *Foliated Coal* is similarly compound, only the laminæ are thinner, and *Coarse Coal* has a composition resembling it, only the component particles are smaller, and approach to a granular appearance. *Cannel Coal* is without visible composition, and has a flat conchoidal fracture in every direction, with but little lustre, by which it is distinguished from Pitch-coal. It is most like the Moor coal, but the difference in their specific gravity is greater than between almost any other two varieties of coal. All these kinds are joined by numerous transitions, so that it often becomes doubtful to which of them we should ascribe certain specimens, though they undoubtedly are bituminous Mineral-coal.

2. The preceding varieties of coal consist of bitumen and carbon in various proportions. They are more or less easily inflammable, and burn with flame and a bituminous smell. Several varieties become soft, and others coak, when kindled. They leave a more or less considerable earthy residue.

3. The varieties called slate coal, foliated coal, coarse coal, cannel coal, and pitch coal, occur chiefly in the coal formation; some varieties of pitch-coal, also the moor-coal, bituminous wood and common brown coal, are met with in the formations above the chalk; the earthy coal, and some varieties of bituminous wood and common brown coal, are often included in diluvial and alluvial detritus. The coal



seams alternate with beds of slaty clay and common clay, sandstone, limestone, sand, &c. They are often associated with vegetable organic remains, in slaty clay, sometimes also with shells. Generally there is some hexahedral or prismatic Iron-pyrites intermixed along with them, and they are traversed by veins, generally narrow, of hexahedral Lead-glance.

4. The bituminous Mineral-coal is so universally distributed, that only a few localities can here be mentioned as examples. Bituminous wood is found in considerable quantity in Iceland, and is called *Surturbrand*; in the Meissner mountain in Hessa, in the Westerwald, at Voitsberg in Stiria, at Bovey in Devonshire. Earthy coal is found at Merseburg, Halle, Bernburg, at Eisleben in Thuringia. Moor coal occurs in the northern districts of Bohemia, as at Elbogen, Carlsbad, Teplitz, &c. also at Kaltennordheim. Common brown coal occurs in immense quantities on the river Sau, and on the foot of the Schwamberg Alps in Lower Stiria, at Judenburg, Leoben, and other places in Upper Stiria, in the Meissner in Hessa. Pitch coal is likewise found in the Meissner, at Planitz and Zwickau in Saxony, in Silesia, on the Rhine, in France; slaty coal at Potschappel in Saxony, in Silesia, in Westphalia, but particularly at Newcastle, Whitehaven, and other places in England and Scotland. Foliated coal is raised at Potschappel, at Löbegün near Halle on the Saale, also at Häring in the Tyrol, at Liege; coarse coal at Neustadt in the Hartz, at Potschappel in Saxony, in Silesia, &c.; and the cannel-coal particularly in Lancashire and Shropshire in England, and in Scotland.

5. The important use of the bituminous Mineral-coal is well known. The cannel-coal is worked into buttons, snuff-boxes, &c.

## 2. NON-BITUMINOUS MINERAL-COAL.

Glance Coal (excepting the first subsp.). JAM. Syst. Vol. III. p. 515. Man. p. 305. Mineral Carbon. Mineral Charcoal. Anthracite. Blind Coal. PHILL. p. 364. 365.

Stangenkohle. Glanzkohle. WERN. Hoffm. H. B. III. I. S. 295. 314. Anthrazit. HAUSM. I. S. 70. Kohlenblende. Glanzkohle. Stangenkohle. LEONH. S. 667. 668. 672. Anthracite. HAUY. *Traité*, T. III. p. 307. *Tabl. comp.* p. 69. *Traité*, 2de Ed. T. IV. p. 440.

No regular form or structure. Fracture conchoidal, often perfect.

Lustre imperfect metallic. Colour iron-black, sometimes inclining to greyish-black. Streak unchanged. Opaque.

Not very brittle. Hardness = 2.0 ... 2.5. Sp. Gr. = 1.400, columnar coal from Meissner; = 1.482, glance coal from Schönfeld, in Saxony.

*Compound Varieties.* Massive: composition lamellar, faces of composition either smooth and shining, or rough; generally impalpable, fracture conchoidal, more or less perfect. Some varieties are vesicular, others divided into columnar masses, meeting in rough faces.

## OBSERVATIONS.

1. Besides Glance-Coal, the present species contains also the Columnar Coal, which in the Wernerian system is comprised in the species of Black Coal, to which, however, it does not belong. The *Columnar Coal* in particular is remarkable for its irregular columnar composition, which is probably produced by fissures, and the low degree of lustre in its fracture. Glance-coal has been divided into *Conchoidal* and *Slaty Glance-Coal*, the latter of which in particular is designated by the name of Anthracite. The first of them possesses a perfect conchoidal fracture, the second is compound like Slate Coal.

2. The varieties of the present species do not contain any bitumen, but consist wholly of carbon, occasionally mixed with variable proportions of oxide of iron, silica, and alu-

mina. They are difficultly inflammable, and burn without smoke, flame, or bituminous smell, leaving a more or less considerable earthy residue.

3. The non-bituminous Mineral-coal is less frequent than the bituminous one. It very often occurs included in more ancient rocks; but some varieties are found in secondary strata. It is sometimes met with in veins traversing trap rocks.

4. The columnar coal is principally found on the Meissner in Hessa, along with the conchoidal Glance-coal, forming the uppermost division of a bed of bituminous wood, covered by basalt. It is said also to have been found in Dumfriesshire, and other districts of Scotland. Besides the Meissner, the conchoidal Glance-coal occurs at Schönfeld near Frauenstein in Saxony; in the neighbourhood of Spa; also in Ayrshire in Scotland, and in Staffordshire in England. The slaty Glance-coal is found in considerable quantity at Schönfeld; also at Lischwitz near Gera in Saxony, in Savoy, at Kongsberg in Norway, in the isle of Arran and other places in Scotland, as, for instance, in the trap rocks of the Calton hill near Edinburgh.

5. On account of its difficult inflammability, the employment of the non-bituminous Mineral-coal is less general than that of the bituminous one; yet it has been used for burning lime, in the process of refining iron, &c.

6. The *Mineral Charcoal* seems to be most nearly allied to the present species. It occurs in thin layers and massive specimens, of a very delicate columnar composition, and presenting on that account a kind of silky lustre. It is greyish-black or velvet-black, and inclosed in the varieties of bituminous Mineral-coal, particularly slate-coal and brown-coal. It occurs in many districts of Bohemia, Saxony, Silesia, England, &c. At Voitsberg in Stiria it is very plentiful in bituminous wood.



## APPENDIX I.

---

MINERALS, THE GREATER PART OF WHICH WILL PROBABLY  
FORM IN FUTURE DISTINCT SPECIES IN THE MINERAL  
SYSTEM.

---

### ACMITE.

#### SPAR.

Achmite. STRÖM. Edinb. Phil. Journ. Vol. IX. p. 55.

Hemi-prismatic. Combination observed similar to  
Fig. 186.\* Inclination of  $M$  on  $M$  over  $r = 86^{\circ}$   
 $56'$ , angle  $abc = 28^{\circ} 19'$ , MITSCHERLICH;  $s$  on  $s$   
 $= 119^{\circ} 30'$ , edge between  $s$  and  $s$  on  $r = 106^{\circ}$ ,  
AP. Twin-crystals compound parallel to  $r$ .

Cleavage, distinct parallel to  $M$ , also to  $r$  and  $l$   
and  $s$ . Fracture imperfect conchoidal. Surface,  
 $r$  irregularly streaked in a longitudinal direction,  
the rest of the faces pretty even, but not very  
smooth.

Lustre vitreous. Colour brownish-black. Streak  
pale yellowish-grey. Opaque, very thin edges are  
translucent, and shew a fine yellowish-brown tint.

Brittle. Hardness = 6.0 ... 6.5. Sp. Gr. = 3.24,  
STRÖM.

---

\* In the cabinet of Mr ALLAN.

It resembles paratomous Augite-spar in a remarkable degree, particularly in regard to form and regular composition. It has been found by BERZELIUS to consist of

Silica	55·25.
Oxide of Iron	31·25.
Oxide of Manganese	1·08.
Lime	0·72.
Soda	10·40.

It melts readily before the blowpipe, into a black globule.

It is found at Eger in Norway, imbedded in granite. Its name is derived from *ἀκμή* a point, from the form of the crystals.

#### ALLANITE.

##### ORE.

Allanite. THOMSON. Trans. Roy. Soc. Edinb. Vol. VI. p. 371. Prismatic Cerium-Ore or Allanite. JAM. Syst. Vol. III. p. 181. Man. p. 319. Allanite (in part). PHILL. p. 264.

Tetarto-prismatic. Combination observed similar to Fig. 185. Inclination of  $r$  on  $M = 129^\circ$ ,  $r$  on  $P = 116^\circ$ ,  $M$  on  $P = 115^\circ$ ;  $s$  on  $r = 135\frac{1}{2}^\circ$ ,  $d$  on  $r = 124\frac{1}{2}^\circ$ ,  $y$  on  $r = 109^\circ$ ,  $s$  on  $x = 156\frac{3}{4}^\circ$ ,  $x$  on  $t = 164\frac{1}{2}^\circ$ ,  $x$  on  $y = 151^\circ$ ,  $t$  on  $y = 166\frac{1}{2}^\circ$ , AP.

Cleavage parallel to  $r$  and  $P$  indistinct. Fracture imperfect conchoidal.

Lustre imperfect metallic. Colour brownish- or greenish-black. Streak greenish-grey. Opaque, faintly translucent in thin splinters, and brown. Brittle. Hardness = 6·0. Sp. Gr. = 4·001, BOURNON.

Allanite froths before the blowpipe, and melts imperfectly into a black scoria. It gelatinises in nitric acid, and consists, according to Dr THOMSON, of



Oxide of Cerium	33·90.
Oxide of Iron	25·40.
Silica	35·40.
Lime	9·20.
Alumina	4·10.

It was discovered at Alluk in East Greenland, by Sir CHARLES GIESECKE, and first observed by Mr ALLAN. It is accompanied by pyramidal Zircon, rhombohedral Quartz, &c.

## ALLOPHANE.

Allophane. JAM. Syst. Vol. III. p. 531. Man. p. 181. Allophane. PHILL. p. 88.

Reniform, botryoidal, massive: composition impalpable. Fracture conchoidal.

Lustre vitreous, inclining to resinous. Colour blue, green, brown. Transparent ... translucent on the edges.

Hardness = 3·0 nearly. Sp. Gr. = 1·852 ... 1·889, STROMEYER.

Without addition it is infusible before the blowpipe. With borax it melts into a transparent, colourless glass. It consists, according to STROMEYER, of

Alumina	32·202.
Silica	21·922.
Lime	0·730.
Sulphate of Lime	0·517.
Carbonate of Copper	3·058.
Hydrate of Iron	2·270.
Water	41·301.

It is found at Saalfeld in Thuringia, in the mining district of Schneeberg in Saxony, and other places. It was first described by Professor STROMEYER.



## ALUMINITE.

Aluminite. JAM. Syst. Vol. II. p. 55. Man. p. 314. Aluminite. PHILL. p. 145.

Reniform, massive: composition impalpable. Surface dull. Fracture fine grained and earthy. Friable.

Colour white. Streak white, a little glimmering. It soils. Opaque.

Sp. Gr. = 1.669, SCHREBER.

It is difficultly fusible. In acids it is readily dissolved, and does not effervesce. It imbibes water, but does not fall into pieces. According to STROMEYER, it consists of

*from Halle. from Newhaven.*

Alumina	30.262	29.868.
Sulphuric Acid	23.365	23.270.
Water	46.327	46.762.

It occurs at Halle on the Saale in Prussia, in beds of plastic clay, and also near Newhaven in Sussex in limestone.

## AMBLYGONITE.

## SPAR.

Amblygonite. JAM. Syst. Vol. III. p. 532. Man. p. 316. Amblygonite. PHILL. p. 198.

Prismatic.  $P + \infty = 106^\circ 10'$ . Cleavage,  $P + \infty$ . Fracture uneven.

Lustre vitreous, inclining to pearly. Colour greenish-white, passing into light mountain- and celandine-green. Streak white. Semi-transparent ... translucent.

Hardness = 6.0, BREITHAAPT. Sp. Gr. = 3.00 ... 3.04, BREITHAAPT.

Before the blowpipe it is easily fusible, intumescens, and is converted into a white enamel. According to BERZELIUS, it consists of alumina, the phosphoric and fluoric acids, and lithia, in greater quantities than any other mineral.

It has hitherto been found only at Chursdorf near Penig in Saxony, where it occurs in granite, along with rhombohedral Tourmaline and prismatic Topaz. It was first discovered to be a particular species by MR BREITHAUP.

## ANORTHITE.

## FELD-SPAR.

Anorthit. G. ROSE. Gilberts Annalen der Physik. 1823. St. 2. p. 173.

Tetarto-prismatic. Simple forms and combinations, also the regular compositions exactly similar to those of Albite, p. 255., represented in Figs. 84-87. Dr ROSE gives the following measurements of the angles.

$l$ on $M$	$= 122^{\circ} 2'$	$y$ on $P$ (over $x$ )	$= 98^{\circ} 29'$
$T$ on $l$	$= 120^{\circ} 30'$	$P$ on $M$ (over $s$ )	$= 85^{\circ} 48'$
$T$ on $M$	$= 117^{\circ} 28'$	$P$ on $M$ (opposite)	$= 94^{\circ} 12'$
$P$ on $T$	$= 110^{\circ} 57'$	$s$ on $M$	$= 115^{\circ} 20'$
$x$ on $P$	$= 128^{\circ} 27'$	$P$ on $n$	$= 133^{\circ} 13'$

Cleavage perfect parallel to  $P$  and  $M$ ; none parallel to  $T$ . Fracture conchoidal. Surface of  $T$  more smooth than of  $l$ .

Lustre pearly upon cleavage planes, vitreous in other directions. Colour white. Streak white. Transparent ... translucent.

Brittle. Hardness = 6.0. Sp. Gr. = 2.763, massive; = 2.656 small crystals, apparently not entirely free from pyroxene. ROSE.

According to Dr G. ROSE, it consists of

Silica	44.49.
Alumina	34.46.
Oxide of Iron	0.74.
Lime	15.68.
Magnesia	5.26.

Before the blowpipe it comports itself nearly like prismatic Feld-spar, Albite, and Labradorite, only that with soda it does not give a clear glass. It is entirely decomposed by concentrated muriatic acid.

The only locality of Anorthite is Mount Vesuvius; it is found lining cavities in limestone, along with a green variety of paratomous Augite-spar.

#### APHRITE.

Aphrite. JAM. Syst. Vol. II. p. 543. Man. p. 48.

Aphrite. PHILL. p. 150.

Prismatic. Cleavage monotomous, very distinct.

Massive: composition granular, sometimes scaly, sometimes not coherent.

Lustre pearly upon the faces of cleavage. Colour white. Streak white. Opaque.

Sectile. Feels fine, not greasy. Soils a little.

Hardness = 0.5 ... 1.0. Sp. Gr. = 2.533.

It effervesces violently with nitric acid, and is completely dissolved. The friable varieties readily absorb water, during which they give a crackling noise. According to BUCHOLZ, it consists of

Lime	51.500.
Silica	5.715.
Oxide of Iron	3.285.
Carbonic Acid	39.000.
Water	1.000.

It occurs at Rubiz near Gera in Saxony, upon the Meiss-



ner in HESSIA, and in several places in the county of Mansfeld. It is found in those varieties of secondary limestone, which have been called *Rauchwacke* and *Asche*, and is sometimes accompanied by, and intermixed with, prismatic Gypsum-haloide.

## ARFVEDSONITE.

SPAR.

Arfvedsonite. BROOKE. Ann. of Phil. No. XXIX. p. 381.  
PHILL. p. 377.

Cleavage, a rhombic prism of  $123^{\circ} 55'$ , with brilliant faces.

Colour black. Sp. Gr. = 3.44, BROOKE.

It resembles hemi-prismatic Augite-spar, and is generally considered as a ferriferous variety of it. It accompanies the dodecahedral Kouphone-spar from Greenland, and black paratomous Augite-spar, with which it is grouped with parallel axes, in the same manner as amphibole and pyroxene in several varieties of diallage. It has not been analysed, but according to Mr CHILDREN (Ann. of Phil. XI.III. p. 37.), it melts easily into a black globule, if exposed in the platina forceps to the blast of the blowpipe. With borax it gives a glass coloured by iron; with salt of phosphorus likewise, but paler, and becoming colourless on cooling; a dark grey silica skeleton remains undissolved.

## ARGENTIFEROUS COPPER-GLANCE.

GLANCE.

Argentiferous Copper-Glance. JAM. Syst. Vol. III. p. 551.  
Man. p. 321. Sulphuret of Silver and Copper. PHILL.  
p. 293.

Massive: composition impalpable.

Fracture flat conchoidal, even.

Lustre metallic. Colour blackish lead-grey. Streak shining.

Perfectly sectile. Soft. Sp.Gr. = 6.255, STROMEYER.

Constituent parts, according to STROMEYER,

Silver 52.272.

Copper 30.478.

Iron 0.333.

Sulphur 15.782.

It occurs along with pyramidal Copper-pyrites, rhombohedral Lime-haloide and rhombohedral Quartz at Schlangenberg in Siberia, and is very rare. It was first described by Professors HAUSMANN and STROMEYER.

#### ARSENICAL BISMUTH.

Arsenik-Wismuth. WERN. Syst. S. 56.

Implanted globular shapes, massive: composition thin columnar, impalpable, also curved lamellar.

Fracture imperfect conchoidal or uneven.

Lustre resinous. Colour dark hair-brown.

Rather brittle. Soft. Heavy.

It decrepitates briskly before the blowpipe, emits an arsenical odour, and is finally converted into a glass, which effervesces with borax.

It occurs at Schneeberg in Saxony.

#### ATACAMITE.

##### MALACHITE.

Prismatic Atacamite, JAM. Syst. Vol. II. p. 343. Man. p. 104. Muriate of Copper. PHILL. p. 313.

Prismatic. Combinations somewhat resembling Fig. 21.; often only the faces *o* and *d*, producing a combination like Fig. 1. Inclination of *o* on *o*

(adjacent) =  $107^{\circ} 10'$ ; of  $d$  on  $d$  (adj.) =  $112^{\circ} 45'$ ; of  $M$  on  $M$  (over  $o$ ) =  $80^{\circ}$ ,  $z$  on  $z$  (over  $M$ ) =  $127^{\circ} 7'$ . PHILLIPS. Reniform, massive: composition columnar.

Cleavage, perfect parallel to  $P$ , less distinct parallel to  $M$ .

Colours olive-, leek-, grass-, emerald-, and blackish-green. Streak apple-green. Nearly transparent ... translucent on the edges.

Rather brittle. Hardness = 3.0 ... 3.5. Sp. Gr. = 4.43, LEONHARD.

It communicates bright blue and green colours to the flame of a candle, or if exposed to the blast of the blow-pipe, it develops vapours of muriatic acid, and melts at last into a globule of copper. It is soluble without effervescence in nitric acid. It consists, according to PROUST and KLAPROTH, of

Oxide of Copper	76.595	73.00.
Muriatic Acid	10.638	10.10.
Water	12.767	16.90.

It is chiefly brought from Chili and Peru, but is also found in Europe, as in the repositories of Iron-ore at Schwarzenberg in Saxony, and upon lava in the neighbourhood of Mount Vesuvius. It is often produced when metallic copper or copper-ores have been exposed to the action of the atmosphere, or of sea-water.

## BABINGTONITE.

SPAR.

Babingtonite. LÉVY. Ann. of Phil. XL. p. 275.

Tetarto-prismatic. Combination observed, represented Fig. 187. Angles, according to LÉVY:



$p$  on  $m = 92^\circ 34'$ ;  $p$  on  $t = 88^\circ$ ,  $t$  on  $h = 155^\circ 25'$ ,  $m$  on  $t = 112^\circ 30'$ ,  $m$  on  $h = 137^\circ 5'$ ,  $p$  on  $d = 150^\circ 25'$ ,  $g$  on  $m = 132^\circ 15'$ ,  $h$  on  $g = 89^\circ 20'$ .

Cleavage distinct, parallel to  $p$  and  $t$ . Fracture imperfect conchoidal.

Lustre vitreous. Colour black, often greenish, thin splinters are faintly translucent, and of a green colour perpendicular to  $p$ , of a brown colour parallel to it. In larger crystals it appears opaque. Hardness = 5.5 ... 6.0.

It resembles certain dark coloured varieties of paratomous Augite-spar. According to Mr CHILDREN, it is composed of silica, iron, manganese, and lime, with a trace of titanium. It occurs at Arendal in Norway in small crystals disposed on the surface of crystals of Albite.

#### BARYTO-CALCITE.

##### HAL-BARYTE.

Baryto-Calcite. BROOKE. Ann. of Phil. XLIV. p. 114.  
Edin. Journ. of Science. Vol. I. p. 378.

Hemi-prismatic. Combinations similar to Fig. 44. and Fig. 188. Inclination of  $M$  on  $M = 106^\circ 54'$ ,  $h$  on  $P$  (over  $a$ ) =  $106^\circ 8'$ ,  $P$  on  $M = 102^\circ 54'$ , according to BROOKE;  $b$  on  $b = 95^\circ 15'$ ,  $h$  on the edge between  $b$  and  $b = 119^\circ$ ,  $P$  on the same edge =  $135^\circ$ ,  $c$  on  $c = 145^\circ 54'$ ,  $d$  on  $d$  over  $h = 68^\circ$ . It is also found massive, in granular compositions.

Cleavage perfect, parallel to  $M$ , less easily obtained

though perfect parallel to *P*. Fracture uneven, imperfect conchoidal. Surface, *h* striated parallel to the edges of combination with *M*, the vertical prisms parallel to the axis.

Lustre vitreous, inclining to resinous. Colour white, greyish, yellowish, or greenish. Streak white. Transparent ... translucent.

Hardness = 4.0. Sp. Gr. = 3.66, CHILDREN.

It does not melt alone before the blowpipe, but gives a clear globule with borax. It consists, according to Mr CHILDREN, of

Carbonate of Barytes 65.9.

Carbonate of Lime 33.6.

It sometimes gives traces of iron and manganese.

It occurs in pretty considerable quantities at Alston Moor in Cumberland, both massive and crystallised.

The discovery of Baryto-Calcite is in particular favourable to shew the advantages of a systematic nomenclature. Upon examining its characters and resemblance to other species, it is immediately arranged with the genus Hal-baryte, and must therefore assume the denomination of the *hemi-prismatic Hal-baryte*.

## BERGMANNITE.

## SPAR.

Bergmannite. JAM. Man. p. 317. Var. of pyramidal Felspar or Scapolite. Syst. Vol. II. p. 43. Bergmannite. PHILL. p. 200.

Massive: composition thin columnar, or promiscuous. Lustre pearly. Colour several tints of grey, passing into white and brick-red. Opaque. Not very brittle. Soft, passing into semi-hard,

**BREITHAAPT.** Scratches glass, and even quartz,  
**HAÜY.** Sp. Gr. = 2.300, **SCHUMACHER.**

Before the blowpipe it becomes white, and then melts without effervescence into a colourless glass. It occurs in the neighbourhood of Stavern in Norway, along with prismatic Feld-spar.

#### BISMUTHIC SILVER.

##### GLANCE ?

Bismuthic Silver. **JAM. Syst.** Vol. III. p. 554. **Man.** p. 318. Bismuthic Silver. **PHILL.** p. 294.

Acicular and capillary crystals. Massive: composition impalpable. Fracture uneven.

Lustre metallic. Colour light lead-grey, subject to be tarnished. Opake.

Sectile. Soft.

It melts readily before the blowpipe, covers the charcoal with an areola of the oxides of lead and bismuth, and finally yields a silver button. It is dissolved in dilute nitric acid, and, according to **KLAPROTH**, consists of

Lead	33.00.
Bismuth	27.00.
Silver	15.00.
Iron	4.30.
Copper	0.90.
Sulphur	16.30.

It has been found at Schapbach in Baden, along with several minerals of the orders Pyrites and Glance, and also with rhombohedral Quartz. It is used as an ore of silver.

#### BLACK COBALT OCHRE.

Black Cobalt-Ochre. **JAM. Syst.** Vol. II. p. 198. **Man.** p. 111. Earthy Cobalt. **PHILL.** p. 281.



Botryoidal, stalactitic, massive : composition impalpable. Fracture conchoidal ... very fine earthy. Colour blueish and brownish-black, blackish-brown.

Streak shining, even in friable varieties, with a somewhat resinous lustre. Opaque.

Sectile. Soils but little. Soft, sometimes passing into very soft. Sp. Gr. = 2.200, of the botryoidal compound variety from Saalfeld, BREITHAUPT.

Before the blowpipe it gives out an arsenical smell, and colours borax smalt blue. It consists of the oxides of cobalt and manganese.

It occurs at Saalfeld, Kamsdorf, and Glücksbrunn in Thuringia ; at Riechelsdorf in Hesse, in the principality of Fürstenberg, in different mineral repositories, which also contain several species of Cobalt-pyrites. It is used in the fabrication of smalt.

It seems that the yellow and the brown cobalt ochre are in a close connexion with the black variety ; yet they all require some farther examination.

## BLOEDITE.

## SALT.

Bloedit. JOHN. Chem. Unters. V. S. 240. LEONH. p. 636.

Massive : composition thin columnar. Fracture uneven, splintery.

Lustre faint, vitreous. Colour between flesh-red and brick-red. Translucent, becoming opaque and white by decomposition.

Soft.

It occurs at Ischel in Upper Austria, along with prismatic Gypsum-haloide and the Polyhalite. It consists, according to JOHN, of

Sulphate of Magnesia	36.66.
Sulphate of Soda	33.34.
Protosulphate of Manganese	0.33.
Muriate of Soda	22.00.
Water	0.34.

with a mechanical admixture of persulphate of iron with excess of base.

#### BREISLAKITE.

This name has been given to a substance from Vesuvius in very delicate capillary crystals, of a reddish-brown or chestnut-brown colour, bent and grouped like wool, on the surface of cavities in a kind of lava, resembling the *Graustein* of WERNER. Its other properties have not been ascertained. It contains a considerable quantity of copper, giving with salt of phosphorus a green globule in the oxidating flame, which becomes red in the reducing flame of the blowpipe.

#### BREWSTERITE.

##### KOUPHON-SPAR.

Brewsterite. BROOKE. Edin. Phil. Journ. Vol. VI. p. 112.  
Brewsterite. PHILL. p. 200.

Hemi-prismatic. Combination represented Fig. 189.

Inclination of the edge between  $d$  and  $d$  on that between  $h$  and  $h$ , =  $93^{\circ} 40'$ ;  $d$  on  $d$  =  $172^{\circ}$ .  
Prisms:  $h$  =  $176^{\circ}$ ;  $g$  =  $136^{\circ}$ ;  $e$  =  $131^{\circ}$ ;  $c$  =  $121^{\circ}$ . BROOKE.

Cleavage, perfect parallel to  $P$ , traces parallel to a plane, which replaces the edge between  $h$  and  $h$ .  
Fracture uneven.

Surface of the prisms streaked parallel to their common intersections.

Lustre vitreous, pearly upon  $P$ . Colour white,



inclining to yellow and grey. Transparent ... translucent.

Hardness = 5.0 ... 5.5. Sp. Gr. = 2.12 ... 2.20,  
Dr BREWSTER.

It is found in crystals and crystalline coats, associated with rhombohedral Lime-haloide, at Strontian in Argyllshire. It resembles particularly the prismatic and hemiprismatic Kouphone-spars, with which it has been formerly confounded. Before the blowpipe it loses first its water and becomes opaque, then it froths and swells up, but is difficultly fusible. It gives a skeleton of silica with salt of phosphorus.

## BROCHANTITE.

## MALACHITE.

Brochantite. LÉVY. Ann. of Phil. Oct. 1824. p. 241.

Prismatic. Combination observed similar to Fig. 21. without  $z$ , and compressed between  $P$  and  $P$ . Inclination of  $o$  on  $o$ , adjacent =  $150^{\circ} 30'$ ; of  $M$  on  $M$ , over the edge between  $o$  and  $o$  =  $114^{\circ} 20'$ , of  $d$  on  $d$ , adjacent =  $63^{\circ} 0'$ . LÉVY.

Cleavage, traces parallel to  $M$ . Surface,  $M$  blackish and dull, the remaining faces smooth and shining.

Colour emerald-green. Transparent.

Hardness = 3.5 ... 4.0, nearly.

According to the experiments before the blowpipe, made by Mr CHILDREN, it consists of sulphuric acid and oxide of copper. On account of its insolubility in water, it is either a salt with excess of base, or, as Mr CHILDREN supposes, it contains some other substance, as silica or alumina, beside the two above mentioned. It is found in small



but well defined crystals on a reniform variety of the hemiprismatic Habroneme-malachite, which itself covers octahedral Copper-ore, in the Bank mine at Ekatherineburgh, Siberia.

## BROOKITE.

## ORE.

Brookite. LÉVY. Ann. of Phil. Febr. 1825.

Prismatic.  $P = 135^\circ 46'$ ,  $101^\circ 37'$ ,  $94^\circ 44'$ . Vol. I.

Fig. 9. LÉVY.

$$a : b : c = 1 : \sqrt{3.237} : \sqrt{1.149}.$$

Simple forms.  $P - \infty (p)$ ;  $P (e^3)$ ;  $(\check{P}r - 1)^5 (b^{\frac{1}{2}}) = 126^\circ 31'$ ,  $135^\circ 41'$ ,  $72^\circ 0'$ ;  $(\check{P}r + \infty)^5 (m) = 100^\circ 0'$ ;  $(\frac{4}{3} \check{P} - 2)^5 (i) = 124^\circ 11'$ ,  $149^\circ 37'$ ,  $65^\circ 0'$ ;  $\frac{4}{3} \check{P}r (e^{\frac{5}{3}}) = 77^\circ 36'$ ;  $\check{P}r + 1 (e^{\frac{1}{4}}) = 56^\circ 24'$ ;  $\check{P}r + \infty (g')$ ;  $\check{P}r - 1 (a^2) = 148^\circ 56'$ ;  $\check{P}r (a')$  =  $124^\circ 52'$ ;  $\check{P}r + \infty (h')$ .

Char. of Comb. Prismatic.

Combination. 1.  $\check{P}r - 1$ .  $\check{P}r$ .  $(\frac{4}{3} \check{P} - 2)^5$ .  $(\check{P}r - 1)^5$ .  $\frac{4}{3} \check{P}r$ .  $P$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .  $\check{P}r + \infty$ . Snowdon, Fig. 190.

Lustre metallic adamantine. Colour hair-brown, passing into a deep orange-yellow, and some reddish tints. Streak yellowish-white. Translucent ... opaque, the brighter colours are observed by transmitted light.

Brittle. Hardness = 5.5 ... 6.0.

It contains titanium, but has not yet been analysed. The first varieties were noticed by Mr SORET among the minerals accompanying pyramidal Titanium-ore from Dau-

phiny; but much finer crystals, some of them half an inch in diameter, have lately been found at Snowdon in Wales. In both places they are accompanied by rhombohedral Quartz; in Dauphiny, besides pyramidal Titanium-ore, also by Crichtonite and Albite.

## BUCKLANDITE.

Bucklandite. LÉVY. Ann. of Phil. Febr. 1824. p. 134.

Hemi-prismatic. Combination observed similar to Fig. 16. only that the faces  $P'$ , contiguous to  $o$ , are larger than those marked  $P$ .

Inclination of the faces, according to LÉVY,

$o$  on  $d = 103^\circ 56'$ .       $o$  on  $P = 121^\circ 30'$ .

$d$  on  $d = 70^\circ 40'$ .       $o$  on  $o' = 99^\circ 41'$ .

$d$  on  $p = 125^\circ 20'$ .       $o$  on  $P' = 95^\circ 40'$ .

$o$  on  $p = 114^\circ 55'$ .       $d$  on  $P' = 160^\circ 24'$ .

Cleavage not observable. Colour dark-brown, nearly black. Opaque. It appears to be harder than paratomous Augite-spar.

It was discovered in small crystals on a specimen from Neskiel mine, near Arendal in Norway, where it occurs with black hemi-prismatic Augite-spar, with pyramidal Feld-spar, and with rhombohedral Lime-haloide. It resembles paratomous Augite-spar.

## CALAITE.

## SPAR.

Calaité or Mineral Turquoise. JAM. Syst. Vol. I. p. 403.

Man. p. 318. Calaité. PHILL. p. 79. Calaité. FISCHER.

Essai sur la Turquoise. Moscow. 1816.

Massive: composition impalpable. Fracture conchoidal.

Colour blue ... green, rather bright. Streak uncoloured. Feebly translucent on the edges ... opake.

Hardness = 6.0. Sp. Gr. = 2.830 ... 3.000, FISCHER.

It is not dissolved by muriatic acid. Before the blow-pipe it becomes brown in the reducing flame, and gives a green colour to it. It is infusible by itself, but very easily with borax or salt of phosphorus. According to BERZELIUS, it consists of phosphate of alumina and lime, silica, oxide of iron and copper, and a little water.

It is found in Persia, either in pebbles, or in small veins traversing a kind of trap in its original repository. Cut and polished, it is used for different ornamental purposes.

#### CHIASTOLITE.

##### SPAR.

Chiaistolite. JAM. Syst. Vol. II. p. 49. Man. p. 318. Chia-  
tolite. PHILL. p. 201.

Prismatic.  $P + \infty = 91^{\circ} 50'$ .  $\text{Pr} = 120^{\circ}$ . HAÜY.  
Cleavage,  $P - \infty$ .  $P + \infty$ .  $\text{Pr}$ .  $\text{Pr} + \infty$ .  $\text{Pr} + \infty$ ,  
all of them imperfect. Fracture imperfect con-  
choidal, splintery. The crystals present a black  
cross in their transverse section.

Lustre vitreous, indistinct. Colour white, grey.  
Streak white. Translucent.

Hardness = 5.0 ... 5.5, if the mineral be not disin-  
tegrated. Sp. Gr. = 2.944, HAÜY:

Before the blowpipe the whitish part of the crystals is infusible, but assumes a purer white tint. It melts but difficultly with either borax or salt of phosphorus. According to BERZELIUS, it is a compound of silica and alumina.



It occurs imbedded in clay-slate in a great number of places, at St Jago di Compostella in Spain; near Barèges in the Pyrenees; near Gefrees in the Bayreuth; besides in the Hartz, in Cumberland, in North America. It has also been found upon the Simplon in dolomite.

## CHILDRENITE.

Childrenite. BROOKE. Brandes' Quarterly Journal, Vol. XVI. p. 274.

Prismatic.  $P = 130^{\circ} 20'$ ,  $102^{\circ} 30'$ ,  $97^{\circ} 50'$ . BROOKE.

$$a : b : c = 1 : \sqrt{2.448} : \sqrt{1.103}.$$

Simple forms.  $P - \infty (f)$ ;  $\frac{1}{2} P (b) = 135^{\circ} 56'$ ,  $111^{\circ} 42'$ ,  $85^{\circ} 3'$ .  $P (e)$ ;  $\frac{3}{4} \check{P}r + 2 (a) = 55^{\circ} 6'$ ;  $\check{P}r + \infty (P)$ .

Cleavage, imperfect parallel to  $\check{P}r + \infty$ . Fracture uneven.

Lustre vitreous, inclining to resinous. Colour yellowish-white, wine-yellow, ochre-yellow, and pale yellowish-brown. Streak white. Translucent. Hardness = 4.5 ... 5.0.

Dr WOLLASTON found it to be a compound of phosphoric acid, alumina, and iron. It has been hitherto found only in the neighbourhood of Tavistock, disposed in single crystals and crystalline coats on brachytypous Parachrosebaryte, hexahedral Iron-pyrites, and rhombohedral Quartz, occasionally accompanied by rhombohedral Fluor-haloide.

## CHLOROPAL.

Chloropal, BERNHARDI and BRANDES. Schweigger's Journal. Chloropal. PHILL. p. 378.

Massive: composition impalpable, earthy. Fracture conchoidal, passing into earthy.

Colour pistachio-green. Opaque, or scarcely translucent on the edges.

Fragile. Hardness between 3·0 and 4·0. Sp. Gr. = 2·000, of a conchoidal variety; from 1·727 ... 1·870, the earthy varieties.

It consists, according to BRANDES, of

	<i>Conchoidal var.</i>	<i>Earthy var.</i>
Silica	46·00	45·00.
Oxide of Iron	35·30	32·00.
Manganese	2·00	0·00.
Alumina	1·00	0·75.
Water	18·00	20·00.
Manganese	a trace	2·00.
Potash	a trace	a trace.

It is remarkable for a very singular magnetic property. When taken from its original repositories, it breaks pretty readily in a kind of parallelopipeds, the upper end and two adjoining lateral edges having the opposite magnetic poles from the other two edges and the lower end. It is not phosphorescent.

It has been found accompanying uncleavable Quartz near Unghwar, in the county of the same name in Hungary, and is often called *Green Iron-Earth*.

#### CHLOROPHAEITE.

Chlorophaeite. MACCULLOCH. *Western Isles*. Vol. I. p. 504. PHILL. p. 202.

Massive: in small grains, imbedded in basalt or amygdaloid, and sometimes hollow. Fracture conchoidal ... nearly earthy.

Colour pistachio-green and transparent, or opaque; but soon turning into brown and black on being exposed to the air, without losing its lustre, which takes place also to the depth of an inch or two into the rock.

Brittle. Hardness, scratched by a quill. Sp. Gr. = 2.020.

Before the blowpipe it remains nearly unchanged, altering neither colour nor transparency. Besides silica, it contains iron and a little alumina. It occurs in Scuirmore cliff in the island of Rum, also in Fifeshire and in Iceland.

## CHONDRODITE.

## GEM.

Condroidite. HAÜY. *Traité*, 2de Ed. T. II. p. 476. Condroidite. Brucite. Maclureite. PHILL. p. 97.

Hemi-prismatic.  $\frac{P}{2}$ .  $P + \infty = 147^{\circ} 48'$ .  $\check{P}r + \infty$ .

HAÜY. Grains.

Cleavage,  $\frac{\check{P}r}{2} = 67^{\circ} 48'$ , very indistinct; also

$\check{P}r + \infty$ .  $\bar{P}r + \infty$ .

Lustre vitreous. Colour yellow ... brown. Transparent ... translucent.

Hardness = 6.5. Sp. Gr. = 3.199, of the variety from Ersby.

It is very difficultly fusible before the blowpipe. It loses its colour almost entirely, becomes opaque, and shews traces of fusion in its thinnest edges. The brown varieties act upon the magnetic needle, particularly if the double magnetism is employed. According to D'OHSSON, it consists of

Silica	38.00.
Magnesia	54.00.
Oxide of Iron	5.10.
Alumina	1.50.
Potash	0.86.



It occurs at Ersby in the parish of Pargas in Finland, along with Pargasite (hemi-prismatic Augite-spar) imbedded in rhombohedral Lime-haloide; also near Newton in Sussex county, New Jersey, along with Graphite and curved lamellar calcareous spar. Count D'OHSSON first described the Chondrodite from Pargas. Dr BRUCE discovered the American variety, which was named *Brucite* after him, by GIBBS. SEYBERT gave it the name of *Maclureite*.

#### COBALT-KIES.

##### PYRITES ?

Cobalt-Kies. JAM. Syst. Vol. III. p. 289. Man. p. 270.  
Sulphuret of Cobalt. PHILL. p. 280.

Massive: composition granular ... impalpable. Individuals indistinctly cleavable. Fracture conchoidal, uneven.

Lustre metallic. Colour pale steel-grey, tarnished copper-red.

Semi-hard.

It emits a sulphureous odour before the blowpipe, and after having been roasted, it communicates a blue colour to glass of borax. It consists, according to HISINGER, of

Cobalt	43·20.
Copper	14·40.
Iron	3·53.
Sulphur	38·50.

It is found at Riddarhyttan in Sweden, in beds in gneiss, along with pyramidal Copper-pyrites, and hemi-prismatic Augite-spar.

#### COBALTIC GALENA OR COBALTIC LEAD-GLANCE.

##### GLANCE.

Cobaltic Galena or Cobaltic Lead-Glance. JAM. Syst. Vol. III. p. 368.

Very small, moss-like, grouped crystals; massive : composition granular. Individuals cleavable. Colour lead-grey, inclining to blue. Lustre metallic, splendid (in the interior), shining. Opaque. Soft, sectile. Soils a little. Sp. Gr. = 8.444, BAUERSACHS.

This mineral has been formerly confounded with hexahedral Lead-glance. It is very probable that when better known, it will be found to belong to the same genus.

Before the blowpipe it shews nearly the same phenomena as hexahedral Lead-glance; the only variety hitherto known communicates a small blue colour to glass of borax. It consists, according to DU MENIL, of

Lead	62.89.
Arsenic	22.47.
Sulphur	0.47.
Iron	2.11.
Cobalt	0.94.
Arsenical Pyrites	1.44.

The loss of 9.76 is attributed to intermixed rhombohedral Lime-haloide. The contents of lead and of arsenic are very nearly in the proportion of 73.34 : 26.66, corresponding to BERZELIUS' formula  $Pb As$ .

It has hitherto been found only in the level of St George near Clausthal in the Hartz, in a vein of clay-slate and brown-spar, traversing greywacke. It was first described by Messrs BAUERSACHS and DU MENIL.

## COMPTONITE.

## KOUPHONE-SPAR.

Comptonite. BREWSTER. Edin. Phil. Journ. Vol. IV. p. 131. BROOKE. Ibid. Vol. VI. p. 112. PHILL. p. 201.

Prismatic. Combination observed nearly similar to Fig. 25., without  $\rho$ . Inclination of  $i$  on  $i =$

177° 35', of *s* on *s* (over *M*) = 91°, BROOKE ;  
= 93° 45' nearly, BREWSTER.

Cleavage, parallel to *T* and *M*, the first a little more distinct ; also parallel to *s*. Fracture small conchoidal, uneven. Surface *s* striated parallel to the edges of combination with *M* and *T* ; the remaining faces smooth.

Lustre vitreous. Colour white. Streak white. Transparent ...semi-transparent.

Hardness = 5.0 ... 5.5.

Before the blowpipe it gives nearly the same results as other species of the genus Kouphone-spar. It first gives off water, intumescs a little, and becomes opaque, then it melts imperfectly into a vesicular glass. The globule obtained with borax is transparent, but vesicular ; that with salt of phosphorus contains a skeleton of silica, and becomes opaque on cooling. With a little soda it melts imperfectly, but with a larger quantity it becomes infusible. The glass with solution of cobalt is dirty blueish-grey. According to Dr BREWSTER, it forms a gelatine if exposed in the state of powder to the action of nitric acid.

It occurs in the cavities of an amygdaloidal rock, along with paratomous Kouphone-spar, and has been hitherto found only at Mount Vesuvius. The name of Comptonite, given to this species by Dr BREWSTER, was proposed by Mr ALLAN.

#### CRONSTEDTITE.

Cronstedtit. STEINMANN. Schweigger's Journal. Neue Reihe. T. II. S. 69. Cronstedtite. PHILL. p. 227.

Rhombohedral.  $R - \infty$ .  $R + \infty$ . Reniform, massive : composition columnar.

Cleavage,  $R - \infty$  perfect ;  $R + \infty$  imperfect.



Lustre vitreous. Colour brownish-black. Streak dark leek-green. Opaque.

Thin laminae are elastic. Hardness = 2.5 (nearly).

Sp. Gr. = 3.348, STEINMANN.

Before the blowpipe it froths a little without melting: with borax it yields a black opaque and hard bead. Reduced to powder, it gelatinises in concentrated muriatic acid. It consists, according to STEINMANN, of

Silica	22.452.
Oxide of Iron	58.853.
Oxide of Manganese	2.885.
Magnesia	5.078.
Water	10.700.

It occurs at Przibram in Bohemia, in veins containing silver-ores, along with prismatic Iron-ore, brachytypous Parachrose-baryte, prismatic Iron-pyrites, and rhombohedral Lime-haloide. It has also been found at Wheal Maudlin in Cornwall.

## CUPREOUS BISMUTH.

## GLANCE ?

Cupreous Bismuth or Cupriferous Sulphuretted Bismuth. JAM. Syst. Vol. III. p. 386. Cupriferous Sulphuret of Bismuth. PHILL. p. 274.

Massive: composition columnar, impalpable. Fracture uneven.

Lustre metallic. Colour pale lead-grey, passing into steel-grey and tin-white; subject to tarnish. Streak black. Opaque.

Sectile. Soft.

It is partly soluble in nitric acid, leaving the sulphur undissolved. According to KLAPROTH, it consists of

Bismuth	47.24.
Copper	34.66.
Sulphur	12.58.

It occurs in the principality of Fürstenberg, in cobalt-veins,

along with octahedral Bismuth, pyramidal Copper-pyrites, &c.

#### CUPREOUS MANGANESE.

Cupreous Manganese. JAM. Syst. Vol. III. p. 558.

Small reniform and botryoidal groupes, massive. Composition impalpable. Fracture imperfect conchoidal.

Lustre resinous. Colour blueish-black. Streak unchanged. Opaque.

Not particularly brittle. Intermediate between semi-hard and soft. Sp. Gr. = 3.197 ... 3.216, BREITHAUPT.

Before the blowpipe it becomes brown, but is infusible. To borax and salt of phosphorus it communicates the colours of copper and manganese. It consists, according to LAMPADIUS, of

Black Oxide of Manganese	82.00.
Brown Oxide of Copper	13.50.
Silica	2.00.

BERZELIUS found it to contain a considerable quantity of water.

It occurs in the tin mines at Schlaggenwald in Bohemia, and was first distinguished by Messrs BREITHAUPT and LAMPADIUS.

#### DIASPORE.

SPAR.

Diaspore. JAM. Man. p. 322. Diaspore. PHILL. p. 78.  
Diaspore. HAÜY. Traité, 1ère Ed. T. IV. p. 358.

Prismatic.\* Cleavage  $P + \infty = 130^\circ$  (nearly).  
More distinctly  $\check{P}r + \infty$ .

---

\* Mr PHILLIPS mentions a doubly oblique prism, a tétartoprismatic form, Sim. Fig. 82. Incidence of  $M$  on  $T = 64^\circ 54'$ , of  $P$  on  $T = 101^\circ 20'$ , of  $P$  on  $M = 108^\circ 30'$ . H.

Lustre vitreous; that of  $\check{P}r + \infty$  is pearly. Colour greenish-grey. Translucent on the edges. Scratches glass. HAÜY. Sp. Gr. = 3.4324. HAÜY.

Before the blowpipe it decrepitates most violently, and splits into many small scaly particles, possessing a feeble alkaline reaction. According to VAUQUELIN and CHILDREN, it consists of

Alumina	80.00	76.06.
Protoxide of Iron	3.00	7.78.
Water	17.30	14.70.

BERZELIUS is of opinion that, besides these, it also contains some alkaline substance.

Its locality is unknown.

## ELAOLITE.

## SPAR.

Elaolite. JAM. Syst. Vol. II. p. 41. Man. p. 322. Fettstein. PHILL. p. 136.

Prismatic. Cleavage,  $P - \infty$ .  $\check{P}r + \infty$ . Less distinct  $P + \infty = 112^\circ$ . PHILL. Massive. Fracture conchoidal.

Lustre resinous. Colour duck-blue, passing into blue and green, or brick-red passing into grey and brown. Translucent. If cut, several varieties become opalescent.

Hardness = 5.5 ... 6.0. Sp. Gr. = 2.546 ... 2.618, HOFFMANN.

Before the blowpipe it melts into a white enamel. Reduced to powder, it forms a copious gelatine with acids. According to KLAPROTH, it consists of

Silica	46.50.
Alumina	30.25.



Lime	0.75.
Potash	18.00.
Oxide of Iron	1.00.
Water	2.00.

It occurs near Laurvig, Stavern, and Frederiksvärn in Norway, imbedded in Syenite along with prismatic Titanium-ore and pyramidal Zircon.

## EUCAIRITE.

## GLANCE.

Cuivre sélénié argental. HAÜY. *Traité*, 2de Ed. T. III. p. 470. Seleniuret of Silver and Copper. PHILL. p. 294. Eucairite. BERZELIUS.

Massive: composition granular. Cleavable.  
Lustre metallic. Colour lead-grey. Streak shining. Opaque.  
Soft.

Before the blowpipe it melts easily, and emits the odour of selenium. It is soluble in boiling nitric acid. Component parts, according to BERZELIUS,

Silver	38.93.
Copper	23.05.
Selenium	26.00.
Foreign substances	8.90.

It has been found only at Skrikerum mine in the parish of Tryserum in Smaland in Sweden, in a talcose or serpentine-like rock, accompanied by rhombohedral Lime-haloide.

## EUCHROITE.

## EMERALD-MALACHITE.

Euchroite. HAIDINGER. *Edinb. Journ. of Science*. Vol. II. p. 133. Dr TURNER. *Ibid.* p. 301.

Prismatic.  $P = 119^\circ 7'$ ,  $81^\circ 47'$ ,  $120^\circ 54'$ . Vol. I. Fig. 7. AP.

$$a : b : c = 1 : \sqrt{0.923} : \sqrt{0.344}.$$

Simple forms.  $P - \infty (P)$ ;  $P + \infty (M) = 117^\circ 20'$ ;  $(\check{P}r + \infty)^5 (s) = 95^\circ 12'$ ;  $(\check{P}r + \infty)^5 (i) = 78^\circ 47'$ ;  $\check{P}r (n) = 87^\circ 52'$ ;  $\check{P}r + \infty (k)$ .

Combinations. 1.  $P - \infty$ .  $\check{P}r$ .  $P + \infty$ .  $(\check{P}r + \infty)^5$ .  
 2.  $P - \infty$ .  $\check{P}r$ .  $P + \infty$ .  $(\check{P}r + \infty)^5$ .  $(\check{P}r + \infty)^5$ .  
 $\check{P}r + \infty$ . Fig: 192.

Cleavage, indistinct, parallel to  $n$  and  $m$ , interrupted. Fracture small conchoidal, uneven. Surface the vertical prisms striated, parallel to their common edges of combination,  $P - \infty$  often rounded.

Lustre vitreous. Colour bright emerald-green. Streak pale apple-green. Double refraction considerable. Transparent, translucent.

Rather brittle. Hardness = 3.5 ... 4.0. Sp. Gr. = 3.389.

According to Dr TURNER, it consists of

Peroxide of Copper	47.85.
Arsenic Acid	33.02.
Water	18.80.

In the matrass it loses its water, and becomes yellowish-green and friable. When heated to a certain point upon charcoal, it is reduced in an instant with a kind of deflagration, leaving a globule of malleable copper, with white metallic particles dispersed throughout it, which are entirely volatile at a continued blast.

It was discovered at Libethen in Hungary, in quartzose mica slate, and brought to London, under the name of *Euchroite*. It will enter the genus Emerald-malachite of MOHS, under the name of the *prismatic Emerald-malachite*.

## EUDIALYTE.

SPAR.

Eudialyte. JAM. Man. p. 322. Eudyalite. PHILL. p. 122.

Fundamental form. Rhombohedron.  $R = 73^\circ$ 

24' \* Vol. I. Fig. 7. WEISS.

$$a \approx \sqrt{13.5}.$$

Simple forms.  $R - \infty (o)$ ;  $R - 2 (z) = 126^\circ$   
13';  $R - 1 = 84^\circ 16'$ ;  $R (P)$ ;  $R + \infty (c)$ ;  
 $P + \infty (u)$ .

Char. of Comb. Rhombohedral.

Comb. 1.  $R - \infty$ .  $R - 2$ .  $R$ .  $P + \infty$ . Fig. 125.2.  $R - \infty$ .  $R - 2$ .  $R$ .  $R + \infty$ .  $P + \infty$ .Cleavage,  $R - \infty$  distinct;  $R - 2$  less distinct;  
 $R$  and  $P + \infty$  traces, not always observable.

Fracture conchoidal or uneven.

Surface smooth, but often rather uneven; of nearly  
the same description in all the forms.Lustre vitreous. Colour brownish-red. Streak  
white. Translucent on the edges ... opaque.

Hardness = 5.0 ... 5.5. Sp. Gr. = 2.898.

Before the blowpipe it melts into a leek-green scoria. If  
reduced to powder, it gelatinises with acids. According to  
STROMAYER, it consists of

Silica	52.00.
Zirconia	10.89.
Lime	10.14.
Soda	13.92.
Oxide of Iron	6.85.
Oxide of Manganese	2.57.
Muriatic Acid	1.03.

\* This angle has been found by Mr LÉVY =  $73^\circ 40'$ . Edinb.  
Phil. Journ. Vol. XII. p. 81. H.



It is found in Greenland mixed with dodecahedral Kouphone-spar, hemi-prismatic Augite-spar, and a mountain-green variety of prismatic Feld-spar. It was first described as a particular species by Professor STROMEYER.

## FAHLUNITE.

Triclasite. HAÜY. *Traité*, 2de Ed. T. III. p. 140. Fah-lunite. Triclasite. PHILL. p. 56. Fahlunite. HISINGER.

Hemi-prismatic.  $P + \infty = 109^{\circ} 28'$ . HAÜY. Reniform, massive. Cleavage,  $Pr = 78^{\circ} 28'$ .  $P + \infty$ . Fracture conchoidal ... uneven, splintery.

Lustre vitreous. Colour olive-green and oil-green, passing into yellow, brown, and black. Streak greyish-white. Feebly translucent on the edges ... opake.

Scratches glass, HAÜY. Sp. Gr. = 2.61 ... 2.66, HISINGER.

Before the blowpipe it becomes pale grey, and melts in its thinnest edges. It is but slowly dissolved in glass of borax, and communicates to it the colour produced by oxide of iron. It consists, according to HISINGER, of

Silica	46.79.
Alumina	26.73.
Magnesia	2.97.
Protoxide of Iron	5.01.
Oxide of Manganese	0.43.
Water	13.50.

It occurs at Fahlun in Sweden, in a talcose or chloritic slate, along with hexahedral Lead-glance, pyramidal Copper-pyrites, &c. It was described by HISINGER under the name of Fahlunite. It is doubtful, whether the forms and hardness given on the authority of HAÜY, refer to the same substance.

## FERGUSONITE.

## ORE.

Fergusonite. HAIDINGER. Trans. Roy. Soc. Edinb. Vol. X. Part 2d, p. 271. Allanite (in part). PHILL. p. 264.

Pyramidal. Fundamental form. Isosceles four-sided pyramid.  $P = 100^\circ 28', 128^\circ 27'$ . Vol. I. Fig. 8. AP.

$$a = \sqrt{4.5}.$$

Simple forms.  $P - \infty$  (i);  $P$  (s);  $\frac{(P - 1)^5}{2}$  (z)

$$\text{angle at the base} = 159^\circ 2'; \frac{[(P + \infty)^5]}{2}.$$

Char. of Comb. Hemi-pyramidal, with parallel faces.

Combinations. 1.  $P - \infty. \frac{[(P + \infty)^5]}{2}$ .

2.  $P - \infty. P. \frac{[(P + \infty)^5]}{2}$ , Fig. 110.

3.  $P - \infty. P. \frac{(P - 1)^5}{2}. \frac{[(P + \infty)^5]}{2}$ , Fig. 193.

Cleavage, traces parallel to P. Fracture perfect conchoidal. Surface rather uneven.

Lustre imperfect metallic, inclining to resinous. Colour dark brownish-black, in thin splinters pale. Streak very pale brown, like peritomous Titanium-ore. Opake, in thin splinters translucent.

Brittle. Hardness = 5.5 ... 6.0. Sp. Gr. = 5.838, ALLAN; = 5.800, TURNER. Not magnetic.

It loses its colour before the blowpipe, and becomes pale greenish-yellow, but is alone infusible. It is entirely

dissolved in salt of phosphorus, but some particles remain a long time unaltered. The pale greenish globule becomes opaque by flaming, or on cooling, when very much saturated. Before the whole portion has been dissolved, it assumes a pale rose colour in the reducing flame. It has been considered as an Yttrio-tantalite, which is not contradicted by the experiments before the blowpipe. It is described under that denomination in the German original of the present work.

It is found imbedded in rhombohedral Quartz at Kiker-taursak near Cape Farewell in Greenland. The specimens to which the preceding description refers are in the cabinet of Mr ALLAN, who proposed the name of Fergusonite.

## FIBROLITE.

Fibrolite. JAM. Syst. Vol. III. p. 535. Man. p. 322. Fibrolite. PHILL. p. 80.

Prismatic.  $P + \infty = 100^\circ$  (nearly). Cleavage  $P + \infty$ , imperfect. Fracture conchoidal. Massive: composition columnar.

Colour white, grey, inclining to green.

Harder than quartz, BOURNON. Sp. Gr. = 3.214; BOURNON.

It is infusible before the blowpipe. If rubbed it emits a dark red phosphoric light. According to CHENEVIX, it consists of

Silica 33.00.

Alumina 58.25.

Oxide of Iron 0.75.

It occurs in the Carnatic, and likewise in China, along with rhombohedral Corundum. It was described by Count BOURNON.



## FIGURESTONE OR AGALMATOLITE.

Figurestone or Agalmatolite. JAM. Syst. Vol. II. p. 261.  
Man. p. 126. Agalmatolite. PHILL. p. 119.

Massive : composition impalpable. Fracture coarse splintery, imperfectly slaty.

Colour white, grey, green, yellow, red, and brown, none of them bright. Acquires some lustre in the streak. Translucent, in most cases only on the edges.

Nearly sectile. Soft. Sp. Gr. = 2.815, KLAPROTH.

Before the blowpipe it is infusible, but becomes white. It is partly soluble in sulphuric acid, leaving a siliceous residue. It consists, according to KLAPROTH, of

Silica	54.50.
Alumina	34.00.
Potash	6.25.
Oxide of Iron	0.75.
Water	4.00.

It is brought from China. Less characteristic varieties have been found also in Transylvania and in Saxony. It is cut into figures and different ornaments.

## FLUATE OF CERIUM.

Fluate of Cerium. BERZELIUS. On the Blowpipe, transl. by J. G. CHILDREN, p. 209. PHILL. p. 266.

i. *Neutral Fluato.*

Six-sided prisms, plates and amorphous masses. Colour reddish.

It has been found by BERZELIUS to consist of 30.43 fluato of protoxide of cerium, and 68.00 fluato of peroxide of cerium, with a trace of yttria. Heated in the matrass or the glass tube, it corrodes the glass; alone it does not

fuse, but its colour changes to brown; with borax and salt of phosphorus it gives a red or orange coloured globule, which becomes pale on cooling. It occurs at Finbo and Broddbo near Fahlun, imbedded in Albite, rhombohedral Quartz, &c.

ii. *Fluate with excess of base.*

Traces of crystalline structure. Colour yellow.

It resembles porcelain jasper. It contains twice as much of the oxides of cerium as the preceding substance. It also comports itself much like it before the blowpipe. If heated alone on charcoal, its colour turns black at an incipient redness, but it assumes, on cooling, successively dark brown, red; and orange tints. It is found at Finbo.

iii. *Fluate of Cerium.*

Not described.

It has not been analysed, but presents nearly the same characters before the blowpipe as the preceding substance, except that in the matrass it does not give off so much water, and that its colour turns brown.

iv. *Fluate of Yttria and Cerium.*

Earthy, found in masses seldom exceeding the size of a pea. Colour pale red, sometimes deep red, yellow, or white. Easily scratched by the nail.

According to BERZELIUS, it is a mechanical mixture of fluat of yttria with fluat of cerium and silica. It gives nearly the same reactions as the Neutral Fluat i.

FLUELLITE.

HALOIDE ?

Fluellite of Wollaston. LÉVY. Ann. of Phil. Oct. 1824. p. 241.

Prismatic.  $P = 109^\circ, 82^\circ, 144^\circ$ . Vol. I. Fig. 9.  
Transverse section =  $105^\circ$  (nearly). WOLLASTON.

Colour white. Transparent. Index of refraction = 1.47 (that of the Wavellite being = 1.52),  
WOLLASTON.

It occurs in minute crystals affecting the form of the fundamental pyramid, with its most acute solid-angle replaced, along with the Wavellite from Cornwall, and was discovered by LÉVY, but named and examined by WOLLASTON, who found it to contain alumina and fluoric acid.

#### FORSTERITE.

##### GEM.

Forsterite. LÉVY. Ann. of Phil. XXXVII. p. 61.

Prismatic. Combination observed similar to Fig. 28, without *z* and *P*. Inclination of *M* on *M* =  $128^{\circ} 54'$ ; of *y* on *y* (over *M*) =  $107^{\circ} 48'$ ; *y* on *y* (adjacent) =  $139^{\circ} 14'$ .

Cleavage easy parallel to *o*.

Colourless, brilliant, translucent.

Hard enough to scratch quartz.

It contains, according to Mr CHILDREN, silica and magnesia. It was discovered by Mr LÉVY in small crystals, accompanying pleonaste and olive-green pyroxene on Mount Vesuvius. The angles of this substance agree pretty nearly with those of prismatic Corundum, given Vol. II. p. 304., in the same succession =  $128^{\circ} 35'$ ,  $107^{\circ} 29'$ , and  $139^{\circ} 53'$ , only the face perpendicular to the axis, which in Forsterite has even an easy cleavage parallel to it, has not yet been observed in prismatic Corundum.

#### GEHLENITE.

##### SPAR.

Gehlenite. JAM. Syst. Vol. I. p. 133. and Vol. III. p. 536.  
Man. p. 323. Gehlenite. PHILL. p. 35.



Pyramidal or prismatic.  $P - \infty$ .  $P + \infty$  or  $P - \infty$ .  $\check{P}r + \infty$ .  $\check{P}r + \infty$ . Cleavage,  $P - \infty$  distinct, the other faces imperfect.

Lustre resinous, inclining to vitreous. Colour different shades of grey, none of them bright. Opake. Sometimes faintly translucent on the edges.

Brittle. Hardness = 5.5...6.0. Sp. Gr. = 3.029.

It is difficultly fusible before the blowpipe, and only in thin splinters. Also in borax it is very slowly dissolved. It gelatinises in heated muriatic acid. It consists, according to FUCHS, of

Alumina	24.80.
Silica	29.64.
Lime	35.30.
Oxide of Iron	6.56.
Water	3.30.

It has been found on Mount Monzoni, in the valley of Fassa in the Tyrol, along with rhombohedral Lime-haloide. It was described by Professor FUCHS.

## GIBBSITE.

Gibbsite. TORREY. New York Medical and Physical Journal. No. I. p. 63.

Irregular stalactites, tuberoso masses.

Structure fibrous, the fibres radiating from the centre.

Lustre faint. Colour dirty greenish- or greyish-white. Slightly translucent.

Hardness a little above 3.0, but easily reduced to powder. Sp. Gr. = 2.400.

It yielded to TORREY, alumina 64.8, and water 34.7. It whitens before the blowpipe, but is infusible. Its locality

is Richmond in Massachusetts, North America, where it is found along with prismatic Iron-ore.

## GIESECKITE.

Gieseckite. JAM. Man. p. 323. Gieseckite. PHILL. p. 113.

Rhombohedral.  $R - \infty$ .  $R + \infty$ . Cleavage not perceptible. Fracture uneven, splintery.

Lustre resinous, faint. Colour olive-green, grey, brown. Streak uncoloured. Feebly translucent on the edges ... opaque.

Hardness = 2.5 ... 3.0. Sp. Gr. = 2.832.

According to STROMEYER, it consists of

Silica	46.07.
Alumina	33.82.
Magnesia	1.20.
Black Oxide of Iron	3.35.
Oxide of Manganese	1.15.
Potash	6.20.
Water	4.83.

It occurs in Greenland, with prismatic Feld-spar. It was first described by Mr SOWERBY.

## GMELINITE.

## KOUPHONE-SPAR.

Sarcolite. VAUQUELIN. Ann. du Mus. IX. 249. XI. 42.

Var. of Analcime. HAÛY. Traité, 2de Ed. T. III. p. 177. Hydrolite. DE DRÉE. Musée. p. 18. Gmelinite. BREWSTER. Edin. Journ. of Science. Vol. II. p. 262.

Rhombohedral. Combination  $P - \infty$ ,  $P + \infty$ , similar to Fig. 196. Angles approaching to those of rhombohedral Kouphone-spar, which are for the isosceles pyramid =  $145^{\circ} 54'$ ,  $71^{\circ} 48'$ . The inclination of  $y$  on  $y'$ , Dr BREWSTER found to be =  $83^{\circ} 36'$ .

Cleavage distinct, parallel to R. Fracture uneven. Surface streaked, the prism in a horizontal direction, the isosceles pyramid parallel to the edges of combination with R; R —  $\infty$  rough, but even. Lustre vitreous. Colour white passing into flesh-red. Streak white. Translucent. Hardness = 4.5. Sp. Gr. = 2.05, BREWSTER.

The Sarcolite of VAUQUELIN, which is quite different from the Sarcolite of THOMSON, is the same mineral to which DE DRÉE has given the name of Hydrolite, and has no connexion with the Analcime, as was supposed by HAÛY. The low degrees of hardness already remarked by VAUQUELIN, and the form discovered by LÉMAN in the varieties from the Vicentine, prove incontestibly that this mineral agrees more nearly with the rhombohedral Kouphone-spar. The variety represented in Fig. 196 is of a white colour, and marked with striæ, shewing indications of a regular composition according to the same law which so frequently occurs in other varieties of that mineral, and in Lévyne. It was found by Mr ALLAN in the little deer park of Glenarm, county of Antrim, Ireland, and mentioned in his *Synonymes*; it was recognised by LÉMAN as a variety of the Hydrolite from the Vicentine. Two analyses of the varieties from Vicenza and Castel yielded to VAUQUELIN,

Silica	50.00	50.00.
Alumina	20.00	20.00.
Lime	4.50	4.25.
Soda	4.50	4.25.
Water	21.00	20.00.

Dr BREWSTER found that Gmelinite possesses the property of flying off in numerous scales when held in the flame of a candle, and that its refractive power is lower than that of rhombohedral Kouphone-spar, the index being only 1.474. Both in the Vicentine and in Ireland it occurs in the cavities of amygdaloidal rocks.



## GREEN IRON-EARTH.

Grüne Eisenerde. WERN. Hoffm. H. B. III. 2. S. 304.

Reniform, botryoidal, globular. Surface smooth and shining. Composition very thin columnar, impalpable, also curved lamellar. Massive: composition impalpable. Fracture even ... uneven. Sometimes in the state of powder.

Lustre resinous. The impalpable particles dull. Colours siskin-green, passing into black and yellow. Streak yellowish-grey.

Brittle. Semi-hard. Not particularly heavy.

It becomes brown and black before the blowpipe, but does not melt. It is said to colour glass of borax red. It is not dissolved in nitric acid. Both the friable and the massive varieties have been found at Schneeberg in Saxony, and in the Hollerter Zug in the county of Sayn.

## HATCHETINE.

Hatchetine. J. J. CONYBEARE. Ann. of Phil. Vol. I. p. 136. PHILL. p. 374.

In the shape of flakes like spermaceti, or of granular masses, like bees' wax.

Lustre slightly glistening and pearly, and of considerable degrees of transparency, when in flakes, else dull and opaque. Colour yellowish-white, wax-yellow, and greenish-yellow.

Hardness, like soft tallow. Very light. Without odour or elasticity.

It melts below the boiling point of water. Ether dissolves it readily; being evaporated, the solution leaves a viscid oily inodorous matter. Distilled over the spirit-lamp, it gives a bituminous smell, a greenish-yellow butyraceous substance is disengaged, and a coaly residue remains in the

retort. At a lower temperature a light oil is distilled. It occurs in small contemporaneous veins with rhombohedral Quartz, rhombohedral Lime-haloide, and Iron-ores, at Merthyr Tydvil in South Wales. It has been described by Mr BRANDE under the denomination of *Mineral Adipocire*.

The description of Hatchetine agrees very nearly with the following one given of *Mountain Tallow*, in Vol. XI. of the Edinburgh Philosophical Journal.

Mountain Tallow has the colour and feel of tallow, and is tasteless; its specific gravity is = 0.6078 in its natural state, but it is increased by melting it to 0.933, the air bubbles being driven off. It melts at 118°, and boils at 290°; when melted it is transparent and colourless, but becomes opake and white on cooling. It is insoluble in water, but is dissolved by alcohol, oil of turpentine, olive-oil, and naphtha, when hot, but is precipitated when they cool. It does not form soap with alkaline substances, but is combustible. It has been found in a bog on the borders of Loch Fyne, and has been formerly noticed on the coast of Finland; in one of the Swedish lakes; near Strasburg; and by Professor JAMESON in Scotland.

## HAÜYNE.

## SPAR.

Haüyne. JAM. Syst. Vol. I. p. 394. Man. p. 323.  
Haüyne. PHILL. p. 111.

Tessular. Crystallised in dodecahedrons. Grains. Cleavage dodecahedron, not very distinct. Fracture uneven.

Lustre vitreous. Colour blue, commonly bright, verging to green, white. Streak white. Transparent ... translucent.

Scratches glass easily. HAÜY. Sp. Gr. = 2.687,  
L. GMELIN; = 3.333, GISMONDI.

Before the blowpipe it melts into a vesicular glass, and loses its colour. It effervesces if melted with glass of borax, and forms a transparent globule, which becomes yellow on cooling. According to L. GMELIN, it consists of

Silica	35·48.
Alumina	18·87.
Lime	12·00.
Sulphuric Acid	12·39.
Potash	15·45.
Oxide of Iron	1·16.
Water	1·20.

It occurs at Albano and Frascati near Rome, among the products of Vesuvius. Also in the neighbourhood of the Puy de Dome, on the lake of Laach, in the quarries of Niedermennich, and in several other places near Andernach, partly imbedded in pumice.

#### HISINGERITE.

Hisingrit. BERZELIUS. Afhandl. i Fysik, &c. III. S. 304. Hisingerite. PHILL. p. 204.

Massive. Cleavage distinct in only one direction.

Fracture earthy.

Colour black. Streak greenish-grey.

Sectile. Soft. Sp. Gr. = 3·045.

If gently heated before the blowpipe, it becomes magnetic; in a stronger heat it melts into a dull opaque black globule, and yields a yellowish-green glass with borax. It consists, according to BERZELIUS, of

Oxide of Iron	51·50.
Silica	27·50.
Alumina	5·50.
Oxide of Manganese	0·77.
Volatile substance	11·75.
Magnesia	a trace.

It has been found in the parish of Svärta in Südermanland, intermixed with rhombohedral Lime-haloide.



## HOPEITE.

## HALOIDE.

Hopeite. BREWSTER. Trans. Roy. Soc. Edinb. Vol. X.  
p. 107.

Prismatic.  $P = 139^{\circ} 41'$ ,  $107^{\circ} 2'$ ,  $86^{\circ} 49'$ . Vol.

I. Fig. 9. AP.

$$a : b : c = 1 : \sqrt{4.443} : \sqrt{1.493}.$$

Simple forms.  $P - \infty (g)$ ;  $P (P)$ ;  $(\check{P}r + \infty)^s$   
 $(s) = 81^{\circ} 34'$ ;  $\check{P}r (M) = 101^{\circ} 24'$ ;  $\check{P}r + \infty (l)$ ;  
 $\check{P}r + \infty (p)$ .

Char. of Comb. Prismatic.

Combination.  $P - \infty$ .  $\check{P}r$ .  $P$ .  $(\check{P}r + \infty)^s$ .  
 $\check{P}r + \infty$ .  $\check{P}r + \infty$ . Fig. 29.

Cleavage,  $\check{P}r + \infty$  perfect, less distinct  $\check{P}r + \infty$ .  
Surface,  $\check{P}r + \infty$  deeply streaked in a longitudinal  
direction, the rest of the faces smooth.

Lustre vitreous, pearly upon  $\check{P}r + \infty$ . Colour  
greyish-white. Streak white. Transparent ...  
translucent. Refraction double; two axes, the  
principal one perpendicular to the axis of  $P$  and  
to the face  $l$ ; angle of the resultant axes about  
 $48^{\circ}$ , in the plane of  $P - \infty (g)$ , contiguous to  
the obtuse lateral solid angle of  $P$ . Index of  
ordinary refraction nearly 1.601.

Sectile. Hardness = 2.5 ... 3.0. Sp. Gr. = 2.76,  
BREWSTER, of a perfect crystal.

Hopeite had been formerly considered as a variety of  
Stilbite. According to NORDENSKIÖLD, it gives off its  
water before the blowpipe, and then melts easily into a clear  
colourless globule, which tinges the flame green. It gives  
no skeleton of silica with salt of phosphorus, with which it

melts in all proportions. If much of the mineral is added, the globule turns opaque on cooling, but does not deposit any fumes of zinc on the charcoal. The globule obtained from fusing it with borax does not become opaque on cooling. With soda it gives a scoria, which is yellow when hot; copious fumes of zinc, and nearest the scoria also some of cadmium are deposited. The melted mineral forms a fine blue glass with solution of cobalt. Hopeite seems therefore to be a compound of some of the stronger acids, as phosphoric or boracic acid, of zinc, an earthy base, a little cadmium, and a great deal of water.

It has been hitherto found only in the calamine mines of Altenberg near Aix-la-Chapelle, and is very rare.

#### HUMBOLDTINE.

Humboldtine. MARIANO DE RIVERO. Ann. de Chimie.

Crystals belonging to the pyramidal system, according to HAÜY; massive plates.

Colour bright yellow.

Soft, yielding to the nail. Sp. Gr. = 1.3.

Acquires resinous electricity by friction.

According to RIVERO, it consists of

Protoxide of Iron 53.56.

Oxalic Acid 46.14.

On ignited charcoal it is decomposed, giving out a vegetable odour, while the colour of the remaining oxide of iron is changed into different shades of yellow, then black, and at last red. It is insoluble in water and alcohol. It occurs imbedded in moor-coal, near Bilin in Bohemia, and is supposed by RIVERO to have been produced from the decomposition of succulent plants.

#### HUMITE.

Humite. BOURNON. Cat. p. 52. PHILL. p. 205.

Form prismatic, according to PHILLIPS; combina-

tions somewhat resembling Fig. 28. and 38., with numerous pyramids and prisms between the six-sided terminal face and the six-sided prism, which has two angles of  $129^{\circ} 40'$  and four of  $115^{\circ} 10'$ . There occurs frequently regular composition, as in prismatic Lime-haloide, parallel to the faces of a rhombic prism.

Cleavage, traces parallel to the six-sided face.

Fracture imperfect conchoidal.

Lustre vitreous. Colour various shades of yellow, sometimes almost white, passing into reddish-brown. Transparent ...translucent.

Brittle. Hardness = 6.5 ... 7.0.

It occurs on Monte Somma, with mica and various other minerals. Alone before the blowpipe it becomes opaque on the outside, but is infusible. It gives a clear glass with borax.

## HYALOSIDERITE.

Hyalosiderit. WALCHNER. Schweiggers Neues Journal. Vol. IX. p. 65. Edin. Journ. of Science. Vol. I. p. 184.

Prismatic. Combination similar to Fig. 9. Inclination of  $M$  on  $M'$  adjacent,  $77^{\circ} 50'$ , of  $P$  on  $P'$ , adjacent,  $99^{\circ} 22'$ .

Cleavage indistinct parallel to  $h$ . Fracture small conchoidal. Surface tarnished brass-yellow, or gold-yellow.

Lustre vitreous, on the surface metallic. Colour reddish- or yellowish-brown. Streak of a cinna-



mon colour. Translucent on the edges, hyacinth-red or wine-yellow.

Hardness = 5.5. Sp. Gr. = 2.875.

It consists, according to Dr WALCHNER, of

Silica	31.634.
Protoxide of Iron	29.711.
Magnesia	32.403.
Alumina	2.211.
Oxide of Manganese	0.480.
Potash	2.788.
Chrome	a trace.

Before the blowpipe it becomes first black and magnetic, and then melts into a black magnetic globule. It was found imbedded in a brown basaltic amygdaloid in the Kaiserstuhl near Sasbach in Brisgaw, accompanied by paratomous Augite-spar, &c. The mixture of iron-slugs and of prismatic Chrysolite are very analogous to that of Hyalosiderite, and the latter is therefore considered by MITSCHERLICH as a peridot, in the chemical sense of the word, meaning a silicate of protoxide of iron, or of the isomorphous bases of protoxide of manganese, magnesia, &c. having the same prismatic form. Hardness and specific gravity are given lower than would be necessary for uniting Hyalosiderite with the natural-historical species of prismatic Chrysolite.

#### HYDRATE OF MAGNESIA.

##### MICA.

Native Hydrate of Magnesia. BREWSTER. Trans. Roy. Soc. Edin. Vol. IX. p. 239. Native Magnesia. JAM. Syst. Vol. II. p. 279. Man. p. 468. Hydrate of Magnesia. PHILL. p. 95.

Rhombohedral. Low six-sided prisms, rare.\* Mas-

---

\* A fine specimen of this variety is in the possession of Dr ANDERSON of Leith. H.

sive : composition lamellar, broad columnar, the latter sometimes stellular.

Cleavage, R —  $\infty$  perfect.

Lustre pearly upon the perfect faces of cleavage.

Colour white, inclining to green. Streak white.

Translucent, sometimes only on the edges. Some varieties lose their transparency on being exposed to the open air.

Sectile. Thin laminæ flexible. Hardness = 1·0 ...

1·5. Sp. Gr. = 2·350, the variety from Unst.

Before the blowpipe it loses in transparency and weight, and becomes friable. In acids it is dissolved without effervescence, and consists, according to Drs BRUCE and FYFE, of

Magnesia	70·00	69·75.
Water	30·00	30·25.

It occurs at Hoboken in New Jersey, in small veins in serpentine ; also at Swinanness in Unst, one of the Shetland isles, under similar circumstances. In the latter place it is frequently associated with a white variety of rhombohedral Lime-haloide.

## INDIANITE.

## SPAR.

Indianite. BOURNON. Phil. Trans. Y. 1802. II. p. 233.

Indianite. PHILL. p. 44.

Grains. Cleavage in two directions, forming an angle of  $95^{\circ} 15'$ , BROOKE.

Colour greenish-white. Translucent.

Scratches glass. Sp. Gr. = 2·74, BOURNON.

It is infusible before the blowpipe. If digested in acids, it becomes friable and gelatinous. It consists, according to CHENEVIX, of

Silica	42·50.
Alumina	37·50.
Lime	15·00.
Oxide of Iron	3·00.

and a trace of Oxide of Manganese.

It occurs in the Carnatic, imbedded in prismatic Feld-spar, and accompanied by rhombohedral Corundum, dodecahedral Garnet, hemi-prismatic and prismatic Augite-spar. Indianite is not a well defined species. Mr BROOKE observes, that the angle of its cleavage planes is that of silicate of lime (prismatic Augite-spar). It is supposed by BEUDANT to be a variety of Labradorite.

#### IRIDIUM.

##### METAL.

Iridium. JAM. Syst. Vol. III. p. 54. Alloy of Iridium and Osmium. PHILL. p. 326.

Rhombohedral. Six-sided prisms, combined in parallel position with two isosceles six-sided pyramids, having bases of  $110^{\circ} 36'$  and  $130^{\circ} 6'$ . BOURNON. Cleavage perpendicular to the axis. Grains. Lustre metallic. Colour pale steel-grey. Opaque. Brittle. Harder than native Platina. Sp. Gr. = 19·5, WOLLASTON.

If melted with nitre it becomes black; but again acquires both its colour and lustre, if heated with charcoal. It is not dissolved by nitro-muriatic acid. It is an alloy of iridium and osmium, and is found in South America with native Platina. It was first described by Dr WOLLASTON.



## IRON-SINTER.

Iron-Sinter. JAM. Syst. Vol. III. p. 250.

Reniform, stalactitic ... massive. Composition impalpable. Fracture conchoidal.

Lustre vitreous. Colour yellowish-, reddish-, blackish-brown. Transparent ... translucent on the edges.

Not very brittle. Soft. Sp. Gr. = 2.40, KARBSTEN.

Before the blowpipe it intumesces, and some varieties emit a strong arsenical odour, during which they are partly volatilised. It consists, according to KLAPROTH and STROMEYER, of

Oxide of Iron	67.00	33.46.
Arsenic Acid	0.00	26.06.
Sulphuric Acid	8.00	10.75.
Protoxide of Manganese	0.00	0.59.
Water	25.00	28.48.

It is found in several old mines, as at Freiberg and Schneeberg in Saxony, and in Upper Silesia.

## JEFFERSONITE.

## AUGITE-SPAR.

Jeffersonite (Polystomous Augite-Spar). KEATING. Journ. Acad. Nat. Sciences, Philadelphia. Vol. II. p. 194. Edinb. Phil. Journ. Vol. VII. p. 317. Jeffersonite. PHILL. p. 24.

Hemi-prismatic. Massive. Cleavage,  $P + \infty = 106^\circ$ ; also  $P - \infty$ , inclined at angles of  $94^\circ 45'$  and  $85^\circ 15'$  to the axis, less perfect than the former; besides these, also other faces occur, which are parallel to the axis, and intersect each other at angles of  $116^\circ$  and  $64^\circ$ , and of  $99^\circ 45'$  and  $80^\circ 15'$ , according to KEATING. Fracture uneven.

Lustre resinous: upon the faces of cleavage semi-metallic. Colour dark olive-green, passing into brown. Streak light green. Slightly translucent on the edges.

Hardness = 4.5. Sp. Gr. = 3.51 ... 3.60, KEATING.

Before the blowpipe it melts easily into a black globule. In heated nitro-muriatic acid one-tenth of it is dissolved, and the residue assumes a lighter colour. It consists, according to KEATING, of

Silica	56.00.
Lime	15.10.
Protoxide of Manganese	13.50.
Peroxide of Iron	10.00.
Oxide of Zinc	1.00.
Alumina	2.00.

It occurs near Sparta, Sussex county, New Jersey, along with octahedral and dodecahedral Iron-ore, dodecahedral Garnet, Chondrodite, &c. It is very nearly allied to the paratomous Augite-spar.

#### KARPHOLITE.

Karpholite. JAM. Man. p. 324. Karpholite or Carpholite. PHILL. p. 22.

Massive: composition thin columnar, scopiform and stellular, rather incoherent, meeting again in angularly granular compositions.

Lustre silky, colour high straw-yellow, sometimes approaching to wax-yellow. Opake.

The hardness appears to be low. Sp. Gr. = 2.935, BREITHAUPT.

It intumesces before the blow-pipe, becomes white, and melts imperfectly into a coherent mass. It consists, according to STEINMANN and STROMEYER, of

Silica	37·53	36·154.
Alumina	26·48	28·669.
Protoxide of Manganese	17·09	19·160.
Protoxide of Iron	5·64	2·290.
Lime	0·00	0·271.
Fluoric Acid	0·00	0·470.
Water	11·36	10·780.

It occurs in granite at Schlaggenwald in Bohemia, accompanied by octahedral Fluor-haloide and rhombohedral Quartz.

## KILLINITE.

Killinite of Taylor. PHILL. p. 322.

Irregular imbedded crystals, massive.

Cleavage parallel to a rhombic prism of  $135^\circ$  (nearly), and its short diagonal, PHILL. Fracture uneven.

Lustre vitreous, faint. Colour greenish-grey, often tinged brown by oxide of iron. Streak yellowish-white. Faintly translucent.

Sectile. Hardness = 4·0. Sp. Gr. = 2·698.

Its analysis by Dr BARKER yielded

Silica	52·49.
Alumina	24·50.
Potash	5·00.
Oxide of Iron	2·49.
Oxide of Manganese	0·75.
Water	5·00.

with 0·50 of lime, magnesia, and iron. It becomes white before the blowpipe, intumesces, and melts into a white enamel. It occurs in granite veins traversing mica-slate, at Killiney near Dublin in Ireland, along with prismatic Triphane-spar and rhombohedral Quartz.



## KNEBELITE.

Knebelite of Lenz and Doebereiner. PHILL. p. 206.

Massive. Fracture imperfect conchoidal.

Lustre glistening. Colour grey, spotted dirty white, red, brown, and green. Opaque.

Hard. Brittle. Difficultly frangible. Sp. Gr. = 3.714, DOEBEREINER.

It was found by DOEBEREINER to contain silica 32.5, protoxide of iron 32.0, and protoxide of manganese 35.0.

## KUPFERINDIG.

Kupferindig. BREITHAUP. Hoffm. H. B. IV. 2. S. 178.

Implanted spheroidal shapes, with a crystalline surface. Massive, plates: composition impalpable.

Fracture flat conchoidal, uneven.

Lustre resinous, faint. Colour indigo-blue, inclining sometimes to blackish-blue. Higher resinous lustre in the streak. Opaque.

Not particularly sectile. Intermediate between soft and very soft. Sp. Gr. = 3.80 ... 3.82, BREITH.

Before the blowpipe it burns before it becomes red-hot, with a blue flame, and melts into a globule, which is strongly agitated, and emits sparks. Finally it yields a button of copper. It occurs at Sangerhausen in Thuringia, the imitative crystalline varieties at Leogang in Salzburg.

## LATROBITE.

SPAR.

Latrobite. BROOKE. Ann. of Phil. XXIX. p. 383. PHILL. p. 380. CHILDREN. Ann. of Phil. XLIII. p. 38. Diploite of Breithaupt. GMELIN. Edinb. Journ. of Science. Vol. II. p. 287.

Tetarto-prismatic. Crystallised and massive.  
 Cleavage in three directions, intersecting each other  
 at angles of  $98^{\circ} 30'$ ,  $91^{\circ}$ , and  $93^{\circ} 30'$ .  
 Colour pale red. Hardness, between 5.0 and 6.0.  
 Sp. Gr. = 2.8, BROOKE ; = 2.720, GMELIN.

According to CHILDREN, it fuses before the blowpipe in the platina forceps into a white enamel. With borax it yields a globule, pale amethyst red in the oxidating flame, and colourless in the reducing one. With salt of phosphorus, a globule with a silica skeleton is obtained, yellow in the oxidating flame, and becoming opaque on cooling, transparent in the reducing flame. Professor GMELIN of Tübingen obtained from two analyses, one of them with carbonate of baryta, the other with carbonate of soda, the following results :

Silica	44.653	41.780.
Alumina	36.814	32.827.
Lime	8.291	9.787.
Oxide of Manganese	3.160	5.767,
Magnesia, with some manganese }	0.628	with a little magnesia.
Potash	6.575	6.575.
Water	2.041	2.041.

It occurs in Amitok island, near the coast of Labrador, with mica and rhombohedral Lime-haloide.

## LEELITE.

Leelite. CLARKE. Ann. of Phil. 1818. PHILL. p. 21.

Massive. Fracture splintery. Lustre and translucency like horn. Sp. Gr. = 2.71, CLARKE.

It consists, according to CLARKE, of silex 75, alumina 22, manganese 2.5, water 0.50. It occurs at Gryphytta in Westmania in Sweden.

## LEVYNE.

## KOUPHONE-SPAR.

Levyne. Dr BREWSTER. Edinb. Journ. of Science. Vol. II. p. 332.

Rhombohedral.  $R = 79^\circ 29'$ . Vol. I. Fig. 7. AP.  
 $a = \sqrt{8.3}$ .

Simple forms.  $R - \infty$  ( $o$ );  $R - 1$  ( $g$ ) =  $106^\circ 4'$ ;  
 $R$  ( $P$ );  $\frac{3}{4}R + 1$  ( $n$ ) =  $70^\circ 7'$ .

Char. of Comb. Rhombohedral.

Combination.  $R - \infty$ .  $R - 1$ .  $R$ . Fig. 194. represents two individuals compound parallel to  $R - \infty$ , the individuals continued beyond the face of composition, as in rhombohedral Kouphone-spar. Inclination of  $o$  on  $g$  =  $136^\circ 1'$ , of  $o$  on  $P$  =  $117^\circ 24'$ , of  $o$  on  $n$  =  $109^\circ 13'$ .

Cleavage, indistinct, parallel to  $R$ . Fracture imperfect conchoidal. Surface,  $R - 1$  and  $R$  streaked parallel to their common edges of intersection.  $R - \infty$  uneven, and generally curved, so that the opposite faces are often inclined on each other at an angle of  $2^\circ - 3^\circ$ .

Lustre vitreous. Colour white. Streak white. Semi-transparent.

Brittle. Hardness = 4.0.

Levyne was first observed by Mr HEULAND, and suspected to be a new mineral. Dr BREWSTER afterwards subjected it to an optical examination, and gave to it the name of Levyne, in honour of Mr LEVY, who had first examined its crystallographic properties.

In the glass tube it gives off a considerable quantity of water, and becomes opaque. Upon charcoal it intumesces a little. With salt of phosphorus it yields a transparent



globule, which contains a skeleton of silica, and becomes opake on cooling. It occurs at Dalsnypen in Faroe, with hemi-prismatic Kouphone-spar, in the vesicular cavities of an amygdaloid.

## LIGURITE.

VIVIANI. Mem. dell' Accad. delle Scienze, lettere ed arti di Genova. III. Ligurit. LEONHARD. S. 651.  
Ligurite. PHILL. p. 207.

Hemi-prismatic.  $\frac{Pr}{2}$ .  $P + \infty = 140^\circ$ .  $\bar{Pr} + \infty$ .

Inclination of  $\frac{Pr}{2}$  on  $\bar{Pr} + \infty = 152^\circ$  (nearly).

Fracture uneven.

Lustre of the fracture intermediate between vitreous and resinous. Colour apple-green. Streak greyish-white. Transparent ... translucent.

Hardness above 5.0. It is said to be harder than oriental chrysolite. Sp. Gr. = 3.49.

According to VIVIANI, who gave the preceding description of this mineral, it consists of

Silica	57.45.
Alumina	7.36.
Lime	25.30.
Magnesia	2.56.
Oxide of Iron	3.00.
Oxide of Manganese	0.50.

It has only been found on the banks of the Stura in the Appennines, in a talcous rock.

## MAGNESITE.

## HALOIDE.

Magnesite. JAM. Syst. Vol. II. p. 281. Man. p. 315.  
Carbonate of Magnesia. PHILL. p. 179.

Reniform, tuberoso, massive. Composition impalp-

able. Fracture flat conchoidal, sometimes fine earthy.

Dull. Colour yellowish-grey, cream-yellow, yellowish- and greyish-white. Streak white. Feebly translucent on the edges ...opaque.

Not very brittle. Semi-hard in a moderate degree (between 3·0 and 4·0). Compound varieties are often very tough; it has been observed that some of them give sparks with steel, and yet do not scratch the octahedral Fluor-haloide. Sp. Gr. = 2·808, BREITHAUPT.

Adheres pretty strongly to the tongue.

It is infusible before the blowpipe. It is dissolved with a slow effervescence in the nitric and dilute sulphuric acids. According to LAMPADIUS and KLAPROTH, it consists of

*From Moravia. From Stiria.*

Magnesia	47·00	48·00.
Carbonic Acid	51·00	49·00.
Water	1·60	3·00.

It occurs at Hrubtschitz in Moravia, in the Gulsen mountain in Stiria, at Baumgarten in Silesia, at Baudissero in Piedmont, in Spain, and in other countries. The *Magnesian Marble* of Mr NUTTAL, from Hoboken in New Jersey, which has been found both massive and crystallised in six-sided prisms, seems to possess some analogy with Magnesite.

#### MANGANESE-SPAR.

##### SPAR.

Manganese-Spar. JAM. Syst. Vol. II. p. 445. Man. p. 325.  
Siliciferous Oxide of Manganese. PHILL. p. 245.

Prismatic. Cleavage apparent in two directions perpendicular to each other, less distinct in two

others forming an angle of  $87^{\circ} 5'$ , according to ROSE, being the angle of Pyroxene.

Massive. Composition fine granular, strongly coherent.

Lustre intermediate between pearly and resinous.

Colour rose-red. Translucent on the edges.

Brittle. Hardness = 5.0 ... 5.5. Sp. Gr. = 3.538, BERZELIUS; = 3.685, BREITHAUPT.

Heated before the blowpipe, it becomes dark-brown, and melts into a reddish-brown globule. The colour it imparts to glass of borax in the oxidating flame is hyacinth-red; but in the reducing flame the glass remains white. According to LAMPADIUS and BERZELIUS, it consists of

*From Siberia. From Sweden.*

Oxide of Manganese	61.00	54.42.
Silica	30.00	48.00.
Oxide of Iron	5.00	a trace.
Alumina	2.00	0.00.
Lime and Magnesia	0.00	3.34.

It is found at Longbanshyttan in Sweden in beds of iron-ore, near Elbingerode in the Hartz, and in the district of Catharinenburg in Siberia; also near Callington in Cornwall, and other places.

The substances called *Allagite*, *Corneous Manganese*, *Photizite* and *Rhodonite*, appear to be compact varieties of the present species, occasionally mixed with a variable quantity of the macrotypous Parachrose-baryte. They have been analysed, the first by DU MENIL, the others by BRANDES, and found to consist of

*Allagite. Corn. Mang. Photizite. Rhodonite.*

Oxide of Manganese	75.00	57.16	37.39	49.87.
Silica	16.00	35.00	36.00	39.00.
Carbonic Acid	7.50	5.00	14.00	4.00.
Water	0.00	2.50	6.00	6.00.
Oxide of Iron	0.00	0.25	0.50	0.25.
Alumina	0.00	0.00	6.00	0.12.



The manganese in Allagite is in the state of peroxide, in all the rest it is protoxide.

They agree very nearly with the Manganese-spar in respect to hardness and specific gravity. Their colours are several green, brown, and reddish tints, which become darker on the surface on being exposed to the air, and generally assume at the same time a slight degree of lustre. They differ in a more or less perfect conchoidal fracture and slight shades of colour, which hardly allow of being expressed in words. They have all been found near Rübeland in the Hartz.

#### MARMOLITE.

Marmolite. NUTTALL. Silliman's Journal.

Massive. Cleavage in two directions, intersecting each other obliquely, one of them more distinct. Composition columnar.

Lustre pearly (inclining to metallic). Colour pale, green and grey. Opaque.

Brittle. Easily cut with a knife. Sp. Gr. = 2.47, NUTTALL.

It is said to resemble very much prismatic Talc-mica, with which it had hitherto been confounded. Before the blowpipe it decrepitates, hardens, and splits into laminae, but does not melt. With nitric acid it yields a thick partly gelatinous mass. It consists, according to NUTTALL, of

Magnesia	46.00.
Silica	36.00.
Lime	2.00.
Water	15.00.
Oxide of Iron and Chrome	0.50.

It occurs in serpentine at Hoboken, and in the Barehills near Baltimore.

## MASCAGNINE OR SULPHAT OF AMMONIAC.

## SALT.

Mascagnine or Sulphat of Ammoniac. JAM. Syst. Vol. III. p. 16. Man. p. 13.

Prismatic, according to MITSCHERLICH. Stalactitic: composition impalpable. Mealy efflorescence. Colour yellowish-grey, lemon-yellow. Semi-transparent ... opaque.

Taste pungent, bitter.

It is soluble in double its weight of water. It attracts moisture from the atmosphere, and is entirely volatile in a higher temperature. It consists of

Sulphuric Acid	53.29.
Ammonia	22.80.
Water	23.91.,

and its formula is  $\dot{N}H^{\circ} \ddot{S} + 2 Aq$ , according to BERZELIUS. It occurs in the neighbourhood of Vesuvius and Etna, in the Solfatara near Puzzuolo, and in the Lagunes near Siena in Tuscany.

## MELLILITE.

Mellilite. JAM. Man. p. 325. Mellilite. PHILL. p. 208.

Prismatic.  $P + \infty = 115^{\circ}$ .  $\check{P}r = 70^{\circ}$  (nearly).

HAÜY. According to PHILLIPS, they are square prisms, having the lateral edges replaced.

Colour yellow, inclining to red or green. Opaque.

Gives sparks with steel.

Before the blowpipe it melts without ebullition into a greenish glass. Reduced to powder, it gelatinises with nitric acid. According to CARPI, it consists of

Silica	38.00.
Lime	19.60.

Magnesia	19·40.
Alumina	2·90.
Oxide of Iron	12·10.
Oxide of Titanium	4·00.
Oxide of Manganese	2·00.

It is found at Capo di Bove and Tivoli near Rome, accompanied by rhombohedral Feld-spar, in the fissures of a volcanic rock.

## MESOLE.

## KOUPHONE-SPAR.

Mesole. BERZELIUS. Edinb. Phil. Journ. Vol. VII. p. 7.

Implanted globules, reniform shapes: composition broad columnar, radiating from the centre.

Colour white, sometimes inclining a little to yellow.

Faintly translucent.

Hardness = 3·5. Sp. Gr. = 2·370.

According to BERZELIUS, it consists of

Silica	42·60.
Alumina	28·00.
Lime	11·43.
Soda	5·63.
Water	12·70.

It contains generally a little carbonate of lime. BERZELIUS gives the formula  $NS^2 + 2 CS^2 + 9 AS + 8 Aq$ .

It is found in Faroe lining the cavities of an amygdaloidal rock, the first stratum being generally Mesoline, the second Mesole, and having crystals of pyramidal and prismatic Kouphone-spar disposed upon it.

## MESOLINE.

## KOUPHONE-SPAR.

Mesoline. BERZELIUS. Edinb. Phil. Journ. Vol. VII. p. 7.

Crystalline coats of a whitish colour on the surface



of the amygdaloid from Faroe, containing the Mesole and the pyramidal and prismatic Kouphone-spars.

This is probably a variety of Chabasie, which is found along with the other species in the above mentioned specimens. The following table contains the analyses of 1. Mesole by BERZELIUS, 2. Chabasie from Fassa by ARFVEDSON, 3. Chabasie from the Giants Causeway by ARFVEDSON, and 4. Chabasie from Gustafsberg by BERZELIUS.

	1.	2.	3.	4.
Silica	47.50	43.38	49.07	50.65.
Alumina	21.40	19.28	18.19	17.90.
Soda	4.80	0.00	12.19	0.00.
Potash	0.00	2.50	a trace.	1.70.
Lime	7.90	8.70	0.00	9.73.
Water	18.19	21.14	19.73	19.90.

BERZELIUS observes that the Mesole was not quite pure, but had a little of the rock attached to it. These analyses, together with those of the other varieties of rhombohedral Kouphone-spar and of Gmelinite, differ only in the kind and proportions to each other of the alkaline base which they contain. The substances themselves are not, all of them, sufficiently known, to say whether, as it is probable, this difference is founded in really different natural-historical species, as in the case of prismatic Feld-spar, Albite, and Labradorite, or whether they should be comprised in one species.

## MOLYBDENA-SILVER.

Molybdena-Silver. JAM. Man. p. 326. Molybdic Silver. PHILL. p. 287.

Rhombohedral. Cleavage, R, perfect.

Lustre metallic. Colour pale steel-grey.

Elastic. Not particularly sectile. Soft. Sp. Gr.

= 8.0., BREITHAUPT.

Before the blowpipe it melts very easily into a globule, that can be entirely volatilised, during which the supporting charcoal is covered with a yellow oxide. If dissolved in the state of powder in nitric acid, a precipitate of sulphur is formed. It consists, according to KLAPROTH, of

Bismuth 95·00.

Sulphur 5·00.

It has been found at Deutsch Pilsen in Hungary, accompanied by several species of the genera Lime-haloide, Iron-pyrites, &c.

It seems that in Hungary several species, different from each other, have been designated by the collective undetermined name of *Molybdena-Silver*. Thus a species very distinct from that described above, presents the following characters:

Form probably rhombohedral. It occurs in imbedded masses, having a general resemblance to three and six-sided prisms.

Cleavage perfect, axotomous. Fracture imperfect conchoidal, uneven, scarcely perceptible.

Lustre metallic. Colour intermediate between tin-white and steel-grey. Streak unchanged, or rather darker, its place becomes shining in the mineral. Opaque.

Very sectile. Thin laminae perfectly flexible. Hardness = 1·5. Sp. Gr. = 7·408.

This species likewise is found in Hungary. Several specimens of it are in the collection of the Johanneum at Gratz. It is accompanied by hexahedral Gold and pyramidal Copper-pyrites, imbedded in rhombohedral Quartz. Its chemical compounds are as yet unknown. Before the blowpipe it gives the reactions of sulphur, tellurium, and bismuth.

Another variety of *Molybdena-Silver* examined by BERZELIUS, which had been communicated to him by Professor WEISS of Berlin, was found to contain only tellurium and bismuth.

## NATIVE LEAD.

## METAL.

Gediegen-Blei. LEONH. S. 223. Plomb natif. BOURNON.  
Cat. p. 333.

Massive. Fracture hackly.

Lustre metallic. Colour pure lead-grey. Streak shining.

Malleable. Hardness = 1.5. Sp. Gr. = 11.3523,  
HAÜY. Disagreeable odour by friction.

It melts easily before the blowpipe, and covers the charcoal with a yellow oxide. Octahedral crystals may be obtained by fusion. Metallic lead, as it occurs in nature, is almost in every instance accompanied by such substances as betray its having once been in a state of fusion. It was first noticed by RATHKE from the island of Madeira, where it is imbedded in vesicular masses, considered as slags by some, and as volcanic rocks by others. Many other localities are of a similar kind. It has been found in a rolled mass of a stone weight in Anglaise river, North America, traversing hexahedral Lead-glance in narrow veins. It has been quoted also from some abandoned mines in the vicinity of Carthagen in Spain, as occurring in capillary and other imitative shapes, engaged in a blackish clay. Lately metallic lead has also been found near Alston in Cumberland. It is associated with hexahedral Lead-glance, rhombohedral Quartz, &c., but also with litharge, and a fused mass resembling a slag. It fills a vein near the surface of the earth, in compact limestone.

## NATIVE NICKEL.

Native Nickel. JAM. Syst. Vol. III. p. 559. Man. p. 326.

Native Nickel. PHILL. p. 282.

Delicate, capillary crystals.



Lustre metallic. Colour brass-yellow, inclining to bronze-yellow and steel-grey.

According to ARFVEDSON, it consists of

Nickel 64·35.

Sulphur 34·26.

Before the blowpipe it melts into a brittle metallic globule; it colours glass of borax violet-blue; in nitric acid it is dissolved without leaving a residue, and forms a pale green solution. It occurs at Johannegeorgenstadt in Saxony, Joachimsthal in Bohemia, and in the Westerwald, accompanied by several species of Iron-pyrites, Lime-haloids, &c. It has been sometimes called *Capillary Pyrites*.

#### NEEDLE-ORE.

##### GLANCE.

Needle-Ore. JAM. Man. p. 326. Acicular Bismuth-Glance. Syst. Vol. III. p. 381. Plumbo-cupriferous Sulphuret of Bismuth. PHILL. p. 274.

Prismatic. Cleavage unknown, imperfect. Fracture uneven.

Lustre metallic. Colour blackish lead-grey.

Hardness = 2·0 ... 2·5. Sp. Gr. = 6·125, JOHN.

Before the blowpipe its sulphur is driven off, and it melts and emits numerous sparkling metallic globules. A button of lead containing copper remains, which communicates a greenish-blue colour to glass of borax. It is soluble in nitric acid, and consists, according to JOHN, of

Bismuth 43·20.

Lead 24·32.

Copper 12·10.

Nickel 1·58.

Tellurium 1·32.

Sulphur 11·58.

Gold 0·79.

It occurs near Catharinenburg in Siberia, imbedded in

rhombohedral Quartz, and accompanied by hexahedral Gold, and several species of the orders Malachite, Glance, and Pyrites.

NEPHRITE.

Nephrite. JAM. Syst. Vol. III. p. 287. Man. p. 327.  
Nephrite. PHILL. p. 134.

Massive: composition impalpable. Fracture coarse splintery, in some varieties slaty in the great.

Colour green, particularly leek-green passing into grey and white. Translucent, often only on the edges.

Not particularly brittle; some varieties are remarkably tough. Hardness = 7·0. Sp. Gr. = 2·932 ... 3·024, BREITHAUPT.

Alone it is infusible before the blowpipe, but becomes white. It consists, according to KASTNER, of

Silica	50·50.
Magnesia	31·00.
Alumina	10·00.
Oxide of Iron	5·50.
Oxide of Chrome	0·05.
Water	2·75.

It is brought from China and Egypt. A large block has lately been found in the alluvial soil of the alum-earth mines at Schwemmsal in Saxony.

NICKELIFEROUS GREY ANTIMONY.

PYRITES.

Nickeliferous Grey Antimony. JAM. Syst. Vol. III. p. 403. Man. p. 327.

Tessular. Cleavage, hexahedron, perfect. Massive: composition granular.

Lustre metallic. Colour steel-grey, inclining to silver-white.

Brittle. Hardness = 5.0 ... 5.5. Sp. Gr. = 6.451, a cleavable variety.

It is partly volatilised before the blowpipe, during which the supporting charcoal is covered with a white coating; at last it melts into a metallic globule, which communicates a blue colour to glass of borax. It consists, according to STROMEYER and KLAPROTH, of

Nickel	36.60	25.25.
Antimony	43.80	47.75.
Arsenic	0.00	11.75.
Sulphur	17.71	15.25.
Iron and Manganese	1.89	0.00.

It is met with in several mines in the principality of Nassau, along with brachytypous Parachrose-baryte, pyramidal Copper-pyrites, hexahedral Lead-glance, &c.

#### NITRATE OF SODA.

##### SALT.

Soude nitratée. HAÜY. Traité, 2de Ed. T. II. p. 214.  
Nitrate of Soda. PHILL. p. 191.

Fundamental form. Rhombohedron.  $R = 106^{\circ} 33'$ . Vol. I. Fig. 7. AP.

$$a = \sqrt{2.05}.$$

Simple form.  $R^*$ .

Char. of Comb. and the combinations not observed. Cleavage, R, perfect. Fracture conchoidal, almost imperceptible. Surface smooth.

Lustre vitreous. Colour white. Streak white. Transparent.

Rather sectile. Hardness = 1.5 ... 2.0. Sp. Gr. = 2.0964, KLAPROTH. Taste cooling.



It is soluble in three times its weight of water at a temperature of 12° R. It melts and deflagrates upon glowing charcoal, but not so violently as the prismatic Nitre-salt. If rubbed in an isolated state, it acquires a very strong negative electricity. It consists of

Nitric Acid 54.97.

Soda 45.03.

according to BERZELIUS' formula,  $\text{Na} \ddot{\text{N}}^{\text{O}}_3$ .

It is found in Peru, in the district of Atacama, near the seaport of Yquique, and according to MARIANO DE RIVERO, occurs with clay in beds of different thickness, extending more than fifty miles, and is worked to great advantage.

## NUTTALLITE.

Nuttallite. BROOKE. Ann. of Phil. XLI. p. 366.

Crystals, right square prisms, imbedded in calcareous spar. Resembling Scapolite, but softer and more glassy in the fracture. Play of light similar to that of Elaolite upon the faces of the prism. Colour grey.

## ORTHITE.

Orthit. BERZELIUS. Afh. i Fysik, &c. Vol. V. Orthite. PHILL. p. 265.

Form, long and straight acicular masses. Massive: composition impalpable. Fracture conchoidal. Lustre vitreous. Colour ash-grey, passing into brown, if the mineral be decomposed. Streak brownish-grey. Opaque. Scratches glass, though with difficulty. Sp. Gr. = 3.288, BERZELIUS.

Before the blowpipe it froths, becomes yellowish-brown, and melts with effervescence into a black vesicular globule; with borax into a transparent one. It gelatinises in heated acids, and according to **BERZELIUS**, it consists of

Silica	32·00.
Lime	7·84.
Alumina	14·80.
Oxide of Cerium	19·44.
Protoxide of Iron	12·44.
Oxide of Manganese	3·40.
Yttria	3·44.
Water	5·36.

It occurs at Finbo near Fahlun in Sweden, along with rhombohedral Quartz, prismatic Feld-spar, Albite, &c. in veins traversing gneiss.

#### PALLADIUM.

##### METAL.

Palladium. **JAM. Syst.** Vol. III. p. 53. Native Palladium. **PHILL.** p. 325.

**Grains.** Octahedrons and prisms with a square base are quoted by **SOWERBY**.

**Lustre** metallic. Colour steel-grey, inclining to silver-white.

**Hardness** superior to wrought iron. **Sp. Gr.** = 11·8, **WOLLASTON**; = 12·14, **LOWRY**.

It is reducible by heat. By itself it is infusible before the blowpipe, but melts with sulphur. With nitric acid it yields a red solution. It consists essentially of palladium, but contains also a small portion of platina and iridium. It occurs along with native Platina in Brazil, and was discovered by **Dr WOLLASTON**. The pure metal is ductile and very malleable; it is flexible in thin slips, but not very elastic.

## PHARMACOLITE.

Pharmacolite. JAM. Syst. Vol. III. p. 543. Pharmaco-  
lite. Arseniate of Lime. PHILL. p. 178.

Capillary crystals, in globular aggregation. Glo-  
bular, reniform, botryoidal. Composition thin  
columnar ... impalpable. Farinaceous.

Lustre vitreous; also pearly in the thin columnar  
particles of composition. Colour white. Trans-  
lucent ... opake.

Sectile, very soft. Sp. Gr. = 2.640, KLAPROTH.

Before the blowpipe it emits an arsenical odour, and  
melts with difficulty into a white enamel. In nitric acid  
it is dissolved without effervescence. According to KLAP-  
ROTH and JOHN, it consists of

*From Wittichen. From Andreasberg.*

Lime	25.00	27.28.
Arsenic Acid	50.54	45.68.
Water	24.46	23.86.

It is found in the principality of Fürstenberg, at An-  
dreasberg in the Hartz, at Riechelsdorf in Hussia, and  
other places, in veins that also contain native Arsenic,  
several species of Cobalt-pyrites, &c.

The description of the *Picropharmacolite* of STROMEYER  
(*Untersuchungen*. Vol. I. p. 135.), does not differ from that  
given of the Pharmacolite. The only difference discovered  
between the two substances consists in a small quantity of  
magnesia which the former contains. It is composed of

Lime	24.646.
Magnesia	3.218.
Oxide of Cobalt	0.998.
Arsenic Acid	46.971.
Water	23.977.

It occurs in the cobalt mines of Riechelsdorf in Hussia,  
along with prismatic Hal-baryte.



## PHOSPHATE OF MANGANESE.

## ORE.

Phosphat of Manganese. JAM. Syst. Vol. III. p. 408.  
 Pitchy Iron-Ore. Id. ibid. Vol. III. p. 248. Phosphat  
 of Manganese. Id. Man. p. 328. Phosphate of Man-  
 ganese. PHILL. p. 248.

Pyramidal or prismatic. Massive: cleavage in  
 three directions perpendicular to each other, one  
 of them more distinct. Fracture small con-  
 choidal.

Lustre resinous, inclining to adamantine. Colour  
 blackish-brown. Streak yellowish-grey. Trans-  
 lucent on the edges. Opake.

Brittle. Hardness = 5.0 ... 5.5. Sp. Gr. = 3.439,  
 VAUQUELIN; = 3.775, ULLMANN.

Before the blowpipe it melts easily into a black scoria,  
 is readily dissolved in nitric acid without effervescence,  
 and consists, according to VAUQUELIN, of

Oxide of Iron 31.00.

Oxide of Manganese 42.00.

Phosphoric Acid 27.00.

It has been found near Limoges in France, in a vein of  
 quartz traversing granite, accompanied by rhombohedral  
 Emerald.

## PICROLITE.

Picrolith (of Hausmann). LEONH. S. 545. Picrolite.  
 PHILL. p. 209.

Massive: composition thin columnar. Fracture  
 splintery.

Lustre faint, inclining to pearly. Colour leek-

green passing into yellow. Streak a little shining. Translucent on the edges.

Hardness between 3.0 and 6.0.

According to ALMROTH, it consists of

Silica	40.04.
Magnesia	38.80.
Water	9.08.
Protoxide of Iron	8.28.
Carbonic Acid	4.70.

It colours glass of borax green, but the colour disappears on cooling. It occurs in irregular veins in the beds of octahedral Iron-ore in the Taberg, and at Nordmarken in Sweden, and has been mentioned also from Reichenstein in Silesia.

#### PICROSMINE.\*

Picrosmine. HAIDINGER.

Fundamental form. Scalene four-sided pyramid.

$P = 151^{\circ} 3'$ ,  $120^{\circ} 0'$ ,  $67^{\circ} 59'$ . Vol. I. Fig. 9. AP.

$$a : b : c = 1 : \sqrt{11.00} : \sqrt{2.75}.$$

Simple forms and combinations not known; the character of the latter prismatic, as it appears from cleavage.

Cleavage.  $\text{Pr} + \infty (M)$  perfect;  $\text{Pr} + \infty (T)$  less,  $\text{Pr} (i) = 117^{\circ} 49'$  still less distinct. Least of all  $P + \infty (s) = 126^{\circ} 52'$ . The product of all the faces of cleavage is represented by Fig. 25. excepting the faces  $o$ .

Fracture uneven, scarcely perceptible.

---

\* Name derived from  $\piικρ\acute{o}\varsigma$ , bitter, and  $\delta\sigma\mu\acute{o}\nu$ , odour, from the bitter and argillaceous odour the mineral exhales when humected.



Lustre pearly, distinct upon  $\text{Pr} + \infty$ , inclining to vitreous upon the other faces. Colour greenish-white, passing into greenish-grey, and mountain-green, sometimes also oil-, leek-, and blackish-green. Streak white, dull. Translucent on the edges ... opake.

Very sectile. Hardness = 2.5 ... 3.0. Sp. Gr. = 2.660 of a cleavable compound variety, 2.596 of a columnar variety.

*Compound Varieties.* Massive: composition granular, strongly coherent. If the composition becomes impalpable, the fracture is earthy. The particles of columnar compositions are very thin; fracture splintery.

Its chemical composition is unknown. Before the blow-pipe it is infusible, but gives out water, becomes first black, then white and opake, and acquires a degree of hardness nearly = 5.0. It is soluble in salt of phosphorus, with the exception of a silica skeleton. When heated with solution of cobalt, it assumes a pale red colour. It appears therefore to contain water, silica, and magnesia.

The cleavable varieties have been found, accompanied by octahedral Iron-ore and macrotypous Lime-haloide, in a bed in primitive rocks. The only locality hitherto known is the iron mine called Engelsburg near Presnitz in Bohemia.

It is likely that many varieties of the common Asbestos of WERNER, (JAM. Syst. Vol. II. p. 156.), particularly that from Zöblitz in Saxony, should be referred to this species. According to WIEGLEB, it consists of

Silica	46.66.
Magnesia	48.45.
Oxide of Iron	4.79.



Various localities are quoted for the common Asbestos ; but since Asbestos contains also varieties of hemi-prismatic and of paratomous Augite-spar, they cannot all be supposed exact, and it would therefore be very interesting to institute a closer natural-historical examination of all these minerals. Among the localities chiefly quoted, are Zöblitz in Saxony, Silesia, the Tyrol, and many other countries along the line of the Alps, the Shetland isles, Portsoy, &c. where it occurs in veins traversing serpentine ; in the Taberg and other places in Sweden, where it occurs in beds, along with octahedral Iron-ore, with several species of Pyrites, rhombohedral and macrotypous Lime-haloide, &c.

## PINITE.

Pinite. JAM. Syst. Vol. II. p. 227. Man. p. 328. Pinite. PHILL. p. 80.

Rhombohedral.  $R - \infty$ .  $R + \infty$ ;  $R - \infty$ .  $R + \infty$ .  
 $P + \infty$ . Cleavage very indistinct. Composition,  $R - \infty$ . Fracture uneven.

Lustre resinous, faint. Colour blackish-green ... greenish-grey. Streak uncoloured. Feebly translucent on the edges.

Sectile. Hardness = 2.0 ... 2.5. Sp. Gr. = 2.782, the crystallised variety from France.

In thin splinters the variety from Auvergne melts imperfectly before the blowpipe, and consists, according to C. G. GMELIN, of

Silica	55.964.
Alumina	25.480.
Potash	7.890.
Soda	0.386.
Oxide of Iron	5.512.
Magnesia	3.760.
Water	1.410.,

with traces of lime, manganese, and animal matter. According to KLAPROTH, the variety from Saxony is infusible before the blowpipe, and consists of alumina 63·75, silica 29·50, and protoxide of iron 6·75.

It occurs in several countries in granite; at Schneeberg in Saxony, in Salzburg, in Auvergne, in Cornwall, in North-America, &c.

#### PLOMBGOMME.

Plomb hydro-aluminé (Plomb gomme). HAÛY. *Traité*, 2de Ed. T. III. p. 410.

Reniform. Surface smooth. Composition thin columnar ... impalpable.

Colour yellowish- and reddish-brown, striped. Translucent.

Scratches octahedral Fluor-haloide, but does not affect glass.

If rubbed in an isolated state, it acquires a strong negative electricity. If quickly heated before the blowpipe, it decrepitates and loses its water; but is infusible by itself. With borax it yields a transparent colourless glass, without reduction of the lead. According to BERZELIUS, it consists of

Oxide of Lead	40·14.
Alumina	37·00.
Water	18·80.
Sulphurous Acid	0·20.
Lime and the Oxides of	} 1·80.
Iron and Manganese	
Silica	0·60.

It occurs at Huelgoet near Poullaouen in Brittany, in clay-slate, along with hexahedral Lead-glance, dodecahedral Garnet-blende, hexahedral Iron-pyrites, and di-prismatic Lead-baryte.

## POLYHALITE.

## SALT.

Polyhalit. STROMEYER. Untersuchungen. Vol. I. p. 144.

Polyhalite. PHILL. p. 199.

Massive: composition columnar. Fracture splintery, uneven.

Lustre resinous. Colour smoke-grey and pearl-grey, flesh-red and brick-red.

Hardness greater than 3.0. Sp. Gr. = 2.7689,

STROMEYER.

Taste saline and bitter.

In the flame of a candle it melts into an opaque globule, is readily dissolved in water, and, according to STROMEYER, consists of

Sulphate of Potash	27.7037.
Anhydrous Sulphate of Lime	44.7429.
Anhydrous Sulphate of Magnesia	20.0347.
Muriate of Soda	0.1910.
Water	5.9535.
Peroxide of Iron	0.3376.

It occurs at Berchtesgaden and Ischel, along with hexahedral Rock-salt, and the two species of Gypsum-haloide. It has lately been discovered also in the salt mines of Vic in Lorraine.

## PYRALLOLITE.

Pyralloolith. NORDENSKIÖLD. Schweiggers Journal für Chemie and Physik. XXXI. 387. Pyralloлите. PHILL. p. 68.

Tetarto-prismatic. Comb. *l. M. T.* Sim. Fig. 81.

Inclination of *M* on *T* =  $94^{\circ} 36'$ ; of *l* on *M* =  $140^{\circ} 49'$ .



Cleavage, distinct parallel to *M* and to *T*, also in the direction of a plane which takes away the more obtuse edge between *M* and *T*; this plane intersects *M* at an angle of  $144^{\circ} 3'$ , and *T* at an angle of  $130^{\circ} 33'$ .

Massive: composition granular. Fracture earthy. Lustre resinous. Colour white, sometimes greenish.

Translucent on the edges ... opaque.

Hardness = 3.5 ... 4.0. It seems to become harder by exposure to the air. Sp. Gr. = 2.55 ... 2.60.

When reduced to powder it phosphoresces with a blueish light. Before the blowpipe it first becomes black, then white, afterwards intumesces and melts on its edges. With borax it yields a transparent glass. According to NORDENSKIÖLD, from whom the whole of the preceding description is taken, it consists of

Silica	56.62.
Magnesia	23.38.
Alumina	3.38.
Lime	5.58.
Oxide of Iron	0.99.
Protoxide of Manganese	0.99.
Water	3.58.

leaving 6.38 of an unknown bituminous substance and loss. It occurs at Storgard in the parish of Pargas in Finland, with several species of the genera Feld-spar and Augite-spar; also with prismatic Titanium-ore and rhombohedral Lime-haloide.

#### PYRORTHITE.

Pyrorthit. BERZELIUS. Afhandl. i Fysik, &c. Vol. V.  
Pyrorthite. PHILL. p. 265.

Probably prismatic. Massive: composition columnar. Fracture conehoidal, splintery, earthy.

Lustre resinous. Colour brownish-black; if decayed, yellowish-brown. Streak brownish-black. Opaque. Is scratched by rhombohedral Lime-haloide. Sp. Gr. = 2.19, BERZELIUS.

If gently heated on one side, it takes fire, and burns without either flame or smoke; after which it becomes white, and melts into a black enamel. It gives a transparent glass with borax, is soluble in heated acids with the exception of a black powder, and consists, according to BERZELIUS, of

Silica	10.43.
Alumina	3.59.
Protoxide of Cerium	13.92.
Protoxide of Iron	6.08.
Yttria	4.87.
Lime	1.81.
Protoxide of Manganese	1.39.
Water	26.50.
Carbon	31.41.

It has been found at Kärarf near Fahlun in Sweden, in a kind of granite, accompanied by prismatic Gadolinite.

## PYROSMALITE.

## MICA.

Pyrosmalite. JAM. Syst. Vol. III. p. 561. Man. p. 329.  
Pyrosmalite. PHILL. p. 235.

Rhombohedral. Combination,  $R - \infty$ .  $R + \infty$ .  
Cleavage,  $R - \infty$  perfect;  $R + \infty$  less distinct.  
Fracture uneven.

Lustre pearly upon  $R - \infty$ ; lower degrees of vitreous lustre in other directions. Colour pale liver-brown, passing into grey and green. Streak paler than the colour. Translucent ... opaque.

Rather brittle. Hardness = 4.0...4.5. Sp. Gr. = 3.077, HAUSMANN.

Before the blowpipe it becomes reddish-brown, and develops fumes of muriatic acid. In a strong fire it melts first into a black scoria, and then into a globule, which is attractable to the magnet. It is easily soluble in glass of borax, and consists, according to HISINGER, of

Silica	35.850.
Protoxide of Iron	21.810.
Protoxide of Manganese	21.140.
Muriate of Iron, with excess of base	} 14.095.
Lime	1.210.
Water	5.895.

It was discovered by Messrs GAHN and CLASON, in the iron-mines of Nordmark in Wermeland in Sweden, and is associated with rhombohedral Lime-haloide and paratomous Augite-spar.

The forms of Pyrosmalite are considered by HAÜY as belonging to the prismatic system. It will probably be found to belong to the genus Pearl-mica.

#### RADIATED ACICULAR OLIVENITE.

Radiated Acicular Olivenite. JAM. Syst. Vol. II. p. 335.  
Oblique Prismatic Arseniate of Copper. PHILL. p. 318.

Hemi-prismatic. Form frequently similar to Fig. 44. having the most acute solid angles replaced by a face *c'*. Inclination of *M* on *M* = 56° 0', of *P* on *M* = 95° 0', of *P* on *c'* (contiguous to the same summit) 99° 30', according to PHILLIPS.  
Lustre pearly upon the face of perfect cleavage. Colour dark verdigris-green, inclining to sky-blue, still darker on the surface. Streak verdigris-green. Translucent on the edges.



Not very brittle. Hardness = 2.5...3.0. Sp. Gr.  
= 4.192.

Before the blowpipe it deflagrates, and emits arsenical vapours. According to CHENEVIX, it consists of

Oxide of Copper 54.00.

Arsenic Acid 30.00.

Water 16.00.

It has hitherto been found only in Cornwall, with several other species of the order Malachite, also with pyramidal Copper-pyrites, rhombohedral Quartz, &c.

#### RED VITRIOL OR SULPHATE OF COBALT.

##### SALT.

Red Vitriol or Sulphate of Cobalt. JAM. Syst. Vol. III.  
p. 23. Man. p. 15. Red Vitriol. Sulphat of Cobalt.  
PHILL. p. 282.

Hemi-prismatic. Similar to the forms of the hemi-prismatic Vitriol-salt, MITSCHERLICH. Stalactitic and coralloidal shapes: composition columnar, in most cases impalpable. Friable.

Lustre vitreous; in very thin columnar compositions it becomes pearly. Colour flesh-red and rose-red ... reddish-white. Semi-transparent ... translucent.

Taste astringent.

It is soluble in water. To glass of borax it communicates a blue colour. According to KOPF, it consists of

Oxide of Cobalt 33.71.

Sulphuric Acid 19.74.

Water 41.55.

It occurs in the rubbish of old mines, at Bieber in the neighbourhood of Hanau.

## RETINITE.

## RESIN.

Retinite. JAM. Syst. Vol. III. p. 478. Retinasphalt.  
PHILL. p. 375.

Roundish, and blunt-edged masses. Fracture conchoidal.

Lustre resinous. Colour green, yellow, red, brown, sometimes in striped delineation. Semi-transparent ... opake.

Hardness = 1.5 ... 2.0, of the variety from Halle.  
Sp. Gr. = 1.135, HATCHETT.

The Retinite from Halle very much resembles a vegetable resin. The purer specimens frequently consist of alternating layers more or less transparent, corresponding to the external shape, and commonly including a cavity.

It emits a strong peculiar odour, even in its natural state, but still more powerfully if rubbed between the fingers; which odour they retain for a considerable time. Its specific gravity is = 1.079.

Retinite, if rubbed in an isolated state, acquires negative electricity. It takes fire at the flame of a candle, melts, and burns with a particular odour. It is partly soluble in alcohol, leaving behind an unctuous residue. According to HATCHETT and BUCHOLZ, it consists of

Vegetable Resin	55.00	91.00.
Asphalt or Bitume	42.00	9.00.
Earthy Matter	3.00	0.00.

It has been found in the beds of earthy brown coal near Halle on the Saale, at Bovey in Devonshire, also in Upper Austria, Moravia, &c.

The different substances called Retinite, Retin-Asphalt, &c. deserve an accurate comparative examination.

## ROSELITE.

## HALOIDE.

Roselite. LÉVY. Ann. of Phil. XLVIII. p. 439. Edinb. Journ. of Science. Vol. II. p. 177.

Prismatic.  $P = 114^\circ 24'$ ,  $79^\circ 15'$ ,  $140^\circ 40'$ . Vol. I. Fig. 9. LÉVY.

$$a : b : c = 1 : \sqrt{0.1909} : \sqrt{0.3761}.$$

Simple forms.  $P - \infty (P)$ ;  $\frac{5}{2} \text{Pr} (e^{\frac{4}{3}}) = 45^\circ 0'$ ;  $\text{Pr} (a^2) = 47^\circ 12'$ ;  $\text{Pr} + \infty (g)$ .

Combination of all these forms represented Fig. 195. Inclination of edge  $z$  on edge  $z = 119^\circ 46'$ . Cleavage perfect parallel to  $P$ . Surface,  $\text{Pr}$  rough, and hollowed out in the middle.

Lustre vitreous. Colour deep rose-red. Streak white. Translucent.

Hardness = 3.0.

According to Mr CHILDREN, it contains water, oxide of cobalt, lime, arsenic acid, and magnesia. Before the blowpipe it gives off water and becomes black. It imparts a blue colour to borax and salt of phosphorus, and is entirely soluble in muriatic acid. It occurs at Schneeberg in Saxony, disposed on rhombohedral Quartz, and was formerly considered as a variety of the prismatic Cobalt-mica, but seems rather to belong to the order Haloide.

## SARCOLITE.

## SPAR.

Sarcolithes de Thomson. HAÜY. Traité, 2de Ed. T. III. p. 177.

Tessular. Combinations of the hexahedron and the octahedron, Vol. I. Fig. 3.



Fracture presenting a vitreous tissue. Colour flesh-red. Hardness sufficient to scratch glass.

It is supposed by HAÜY to be a variety of the hexahedral Kouphone-spar; but the form of the octahedron having never yet been observed in that species, an accurate examination of Sarcolite is still a desideratum.

#### SAUSSURITE.

Saussurite. JAM. Syst. Vol. I. p. 71. Man. p. 182.  
Saussurite. PHILL. p. 135.

Prismatic. Cleavage two faces meeting at angles of  $124^{\circ}$  nearly, pretty distinct. Traces parallel to the short diagonal of that prism. Fracture uneven splintery. Massive: composition granular ... impalpable, strongly coherent.

Lustre pearly, inclining to vitreous upon the faces of cleavage; resinous in compound varieties, particularly when cut and polished. Colour white, passing into mountain-green, greenish- and ash-grey. Streak white.

Brittle. Very difficultly frangible. Hardness = 5.5.  
Sp. Gr. = 3.256 of a granular variety from Piedmont, 3.342 of a compact variety from the Pays de Vaud.

Before the blowpipe it melts with difficulty into a white glass. According to SAUSSURE and KLAPROTH, it consists of

Silica	49.00	44.00.
Alumina	24.00	30.00.
Lime	10.00	4.00.
Magnesia	3.75.	Potash 0.25.
Oxide of Iron	6.50	12.50.

Oxide of Manganese	0.00	0.05.
Soda	5.50	6.00.
Loss	0.75	3.20.

Saussurite, or *Jade*, occurs in primitive mountains, and constitutes with several varieties of the species of paratombous and hemiprismatic Augite-spar, the rocks called gabbro and euphotide. It is found in large masses in the Monte Rosa, and in its neighbourhood; in Corsica; in the Bacher mountain in Lower Stiria, in Bayreuth, &c.

## SCORODITE.

Skorodite. JAM. Syst. Vol. III. p. 547. Man. p. 329.  
 Martial Arseniate of Copper. Skorodite. PHILL. p.  
 320. 321. Skorodit. BREITHAAPT.

Prismatic.  $P = 115^{\circ} 6'$ ,  $102^{\circ} 1'$ ,  $111^{\circ} 34'$ . Vol. I.

Fig. 9. AP.

$$a : b : c = 1 : \sqrt{1.098} : \sqrt{0.792}.$$

Simple forms.  $P - \infty$  ( $k$ );  $P - 1 = 134^{\circ} 37'$ ,  
 $126^{\circ} 25'$ ,  $72^{\circ} 40'$ ;  $P$  ( $P$ );  $(\check{P}r + \infty)^5$  ( $d$ ) =  
 $60^{\circ} 58'$ ;  $\check{P}r + 1$  ( $m$ ) =  $47^{\circ} 59'$ ;  $\check{P}r + \infty$ ;  
 $\check{P}r + \infty$  ( $r$ ).

Char. of Comb. Prismatic.

Comb. 1.  $P - \infty$ . P. Löling, Carinthia.

2.  $P - \infty$ . P.  $\check{P}r + 1$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .

Fig. 19. Löling.

3.  $P - 1$ . P.  $\check{P}r + 1$ .  $(\check{P}r + \infty)^5$ .  $\check{P}r + \infty$ .

$\check{P}r + \infty$ . Saxony.

Cleavage.  $(\check{P}r + \infty)^5$  imperfect, traces of  $\check{P}r + \infty$   
 and of  $\check{P}r + \infty$ . Fracture uneven. Surface;  
 P uneven and irregularly streaked parallel to its  
 own edges;  $\check{P}r + \infty$ , partly also  $(\check{P}r + \infty)^5$  in  
 a vertical direction. The rest of the faces com-  
 monly very smooth and even.

Lustre vitreous, inclining to adamantine on the surface, and to resinous in the interior. Colour principally leek-green, which passes almost into white, or also into olive-green and liver-brown. Streak white. Semi-transparent ... translucent on the edges.

Rather brittle. Hardness = 3.5 ... 4.0. Sp. Gr. = 3.162.

Before the blowpipe it emits an arsenical odour, and melts into a reddish-brown scoria, which acts upon the magnet, if it has been heated long enough to drive off all the arsenic. According to FICINUS, it consists of

Arsenious Acid	31.40.
Sulphuric Acid	1.54.
Water	18.00.
Protoxide of Iron, with Magnesia, Lime, and Manganese	} 47.80.

It occurs in primitive mountains at Schwarzenberg in Saxony with prismatic Arsenical-pyrites, at Löling near Hüttenberg in Carinthia with axotomous Arsenical-pyrites; it is accompanied in the latter place also by octahedral Bismuth and brachytypous Parachrose-baryte. Beautiful specimens have lately been brought from Brazil. It occurs in several of the Cornish mines. The Martial Arseniate of Copper from Cornwall seems to be merely a variety of the Scorodite. It consists, according to CHENEVIX, of oxide of copper 22.5, arsenic acid 33.5, oxide of iron 27.5, water 12.0, and silica 3.0.

#### SELENIURET OF COPPER.

Cuivre sélénié. HAÜY. *Traité*, 2de Ed. T. III. p. 469.  
Seleniuret of Copper. PHILL. p. 304.

Massive; also superficial upon fissures in rhomboidal Lime-haloide.



Lustre metallic. Colour silver-white. Streak shining.

Soft. Malleable.

It acquires negative electricity by friction. It melts easily upon charcoal into a grey malleable globule, giving out a strong smell of selenium, and consists of selenium and copper. It has been hitherto exclusively found in the Skrickerum copper mine, in Smaland in Sweden.

## SERPENTINE.

Serpentine. JAM. Syst. Vol. II. p. 292. Man. p. 36.

Serpentine. PHILL. p. 97.

Prismatic.  $P = 139^{\circ} 34', 105^{\circ} 26', 88^{\circ} 26'$ . Vol. I.

Fig. 9. AP.

$$a : b : c = 1 : \sqrt{4.3} : \sqrt{1.4}.$$

Simple forms.  $P (P)$ ;  $(\check{P}r)^5 (n)$ ;  $(\check{P}r + \infty)^5 (d) = 82^{\circ} 27'$ ;  $\check{P}r (o) = 128^{\circ} 31'$ ;  $\check{P}r + 1 (r) = 92^{\circ} 4'$ ;  $\check{P}r + \infty (b)$ ;  $\bar{P}r + \infty (s)$ .

Char. of Comb. Prismatic.

Comb. 1.  $\check{P}r. P. (\check{P}r + \infty)^5. \check{P}r + \infty. \bar{P}r + \infty.$

Sim. Fig. 25.

2.  $\check{P}r. P. \check{P}r + 1. (\check{P}r)^5. (\check{P}r + \infty)^5. \check{P}r + \infty.$

$\bar{P}r + \infty.$  Fig. 33.

Cleavage. Traces of  $\check{P}r + \infty$  and of  $(\check{P}r + \infty)^5$ , apparent only in a strong light. Fracture flat conchoidal, splintery, uneven. Surface, almost dull, very little glistening, but rather even.

Lustre resinous, indistinct, low degrees of intensity.

Colour dark blackish- and leek-green, seldom lighter shades of oil-green and siskin-green colours, none of them being bright; they pass into yel-

lowish-grey. Streak white, acquires some lustre.

Translucent ... opake.

Sectile. Hardness = 3.0. Sp. Gr. = 2.507 of a greenish-black crystallised variety; = 2.560 of an oil-green, translucent one.

*Compound Varieties.* Massive: composition granular, impalpable. Varieties of this kind present also red, brown, black, yellow, and grey colours, in different veined, spotted, and other delineations. The purer varieties sometimes possess an indistinct slaty structure.

The regular forms have been observed in a blackish-green variety, the locality of which is unknown. Serpentine is said to occur crystallised in the Tyrol. Imbedded crystals, the prismatic form of which, however, is nearly obliterated, occur in the weisstein of Penig in Saxony. Serpentine often contains crystals and grains of octahedral Iron ore, which must be well attended to, if we determine its hardness and specific gravity.

Serpentine is generally divided into two subspecies, the *common* and *precious* Serpentine, the latter of which again comprises a *conchoidal* and a *splintery* kind, distinguished in colour, fracture, and transparency. It hardens on being exposed to fire, and melts only with great difficulty on the edges. According to JOHN, it consists of

Silica	42.50.
Magnesia	38.63.
Alumina	1.00.
Lime	0.25.
Oxide of Iron	1.50.
Oxide of Manganese	0.62.
Oxide of Chrome	0.25.
Water	15.20.

Serpentine forms mountain masses and beds in primitive

rocks, and frequently contains crystals, grains, or compound nodules of various other species. Precious Serpentine, in particular, is often mixed with granular limestone. The different varieties of Serpentine are met with in Saxony, Silesia, Austria, Hungary, Stiria, Italy, Corsica, Sweden, in England and Scotland, and other countries. It is turned on the lathe into vases, and also worked into different ornaments.

## SILLIMANITE.

SPAR.

Sillimanite. BOWEN. Journ. of the Acad. of Sc. of Philadelphia. Vol. III. p. 375.

Hemi-prismatic. It occurs crystallised in four-sided prisms of about  $106^{\circ} 30'$ , the inclination of the base on the axis being  $113^{\circ}$ .

Cleavage parallel to the long diagonal of the prism.

Fracture, uneven, splintery. Surface often rounded, the crystals themselves bent.

Lustre, considerable upon the single face of cleavage. Colour dark grey, passing into clove-brown.

Translucent on the edges.

Hardness, superior to quartz or even to topaz.

Brittle and easily reduced to powder. Sp. Gr.

= 3.410. Electricity or magnetism none.

It was found by BOWEN to contain

Alumina 54.111.

Silica 42.666.

Oxide of Iron 1.999.

Water 0.510.

It is infusible before the blowpipe, whether alone or with borax, and is not acted upon by acids. It occurs in the



town of Saybrook, Connecticut, and was formerly considered as a variety of Anthophyllite. The analysis agrees exactly with that of prismatic Disthene-spar by KLAPROTH, (Vol. II. p. 215.). No exact crystallographic description is given, but the angle of  $106^{\circ} 30'$  is very near the incidence of  $P$  on  $M$ ,  $106^{\circ} 15'$ , in that species, also the specific gravity is not much different, and the great hardness may perhaps be accounted for by the want of a more general diffusion of correct methods for ascertaining this property. Sillimanite is therefore probably a variety of the prismatic Disthene-spar.

## SOMERVILLITE.

Somervillite. BROOKE. Brande's Quarterly Journal. Vol. XVI. p. 274.

Pyramidal.  $P = 134^{\circ} 48', 65^{\circ} 50'$ . Vol. I. Fig. 8.  
BROOKE.

Simple forms.  $a = \sqrt{0.419}$ .  
 $P - \infty (P)$ ;  $P (a)$ ;  $P + \infty (d)$ ;  
 $[P + \infty] (M)$ ;  $(P + \infty)^3 (e) = 126^{\circ} 52' 12''$ ,  
 $143^{\circ} 7' 48''$ .

Combination of all these forms, resembling Fig. 101., having the apex, and the edges between  $g$  and  $l$  replaced.

Cleavage,  $P - \infty$  perfect, none observable parallel to the axis.

Lustre more glassy in the cross fracture than that of pyramidal Garnet. Colour pale dull yellow.

Hardness inferior to that of pyramidal Garnet.

It decrepitates before the blowpipe, and melts alone into a grey coloured globule, with borax into a colourless one. It occurs at Mount Vesuvius, associated with black mica and other minerals.

## SORDAWALITE.

Sordawalite. NORDENSKIÖLD. Edinb. Phil. Journ. Vol. IX.  
p. 162. Sordawalite. PHILL. p. 210.

Massive: composition impalpable; no trace of cleavage. Fracture conchoidal.

Lustre vitreous, inclining to semi-metallic. Colour greenish- or greyish-black. Opaque.

Brittle. Hardness equal to that of glass. Sp. Gr. = 2.530, NORDENSKIÖLD.

It becomes reddish by exposure to the atmosphere. Before the blowpipe it forms with difficulty a blackish globule. With a small quantity of soda it yields a blackish-green globule; with a larger quantity a rough slaggy mass is produced. Borax dissolves it into a green glass. It is partly soluble in muriatic acid. Analysis by NORDENSKIÖLD:

Silica	49.40.
Alumina	13.80.
Peroxide of Iron	18.17.
Magnesia	10.67.
Phosphoric Acid	2.68.
Water	4.38.

It occurs near the town of Sordawala in Finland, in layers from half an inch to an inch in thickness in a primitive rock.

## SPHÆRULITE.

Sphærolite. JAM. Syst. Vol. III. p. 545. Man. p. 330.  
Sphærolite. PHILL. p. 209.

Imbedded spheroidal masses. Surface of some of them smooth, of others rough. Composition columnar ... impalpable. In the latter case the fracture even, splintery.

Colour various shades of brown and grey. Translucent on the edges ... opaque.

Brittle. Hard (it scratches quartz slightly, BREITHAUPT). Sp. Gr. = 2.52 from Spechtshausen; = 2.40 from Hungary, BREITHAUPT.

Before the blowpipe it is almost infusible, only the edges become covered with a sort of enamel. It is said to be very nearly related to obsidian in respect to its composition. It occurs at Glashütte near Schemnitz in Hungary, imbedded in pearlstone, and at Spechtshausen near Tharand in Saxony, imbedded in pitchstone, both varieties of empyrodox Quartz. It was first distinguished by Mr BREITHAUPT.

#### SPINELLANE.

Spinellane. JAM. Syst. Vol. III. p. 549. Man. p. 331.  
Spinellane. PHILL. p. 127.

Tessular form, the dodecahedron, sometimes combined with the hexahedron. PHILL. Grains. Cleavage, the dodecahedron, imperfect. Fracture conchoidal, uneven.

Lustre vitreous, inclining to resinous. Colour greyish-black, passing into ash-grey and brown. Sometimes a whitish play of light parallel to the faces of the hexahedron. Translucent ... opaque. Hardness = 5.5 ... 6.0. Sp. Gr. = 2.282.

Before the blowpipe it is infusible, whether alone or with additions. According to KLAPROTH, it consists of

Silica	43.00.
Alumina	29.50.
Lime	1.50.
Soda	19.00.
Oxide of Iron	2.00.
Sulphur	1.00.
Water	2.50.



It occurs on the shores of the lake of Laach, along with prismatic Feld-spar, hemi-prismatic Augite-spar, octahedral Iron-ore, &c. It resembles pitchstone when broken, and according to the observations of Dr BREWSTER, also in its structure, when examined in thin splinters by a powerful microscope. The name of *Nosin* has been given to it, in honour of Mr NOSE, its first discoverer.

STEATITE OR SOAPSTONE.

Steatite or Soapstone. JAM. Syst. Vol. II. p. 255. Man. p. 125. Soap-stone. PHILL. p. 118.

Crystals, chiefly of the rhombohedral system, and among these particularly such as resemble varieties of rhombohedral Quartz, and macrotypous Limehaloide, the nature of which is as yet problematic. The crystals are found imbedded in the massive varieties of the same mineral. Massive; composition impalpable, fracture uneven, splintery.

Colour generally white, passing into grey, green, yellow, red. Streak having a faint resinous lustre. Translucent on the edges.

Perfectly sectile. Feels greasy. Does not adhere to the tongue. Soft ... very soft. Sp. Gr. = 2.604 ... 2.632, BREITHAUPT.

Before the blowpipe it is very difficultly fusible, and only partly vitrified. According to KLAPROTH, it consists of

	<i>From Baireuth.</i>	<i>From Cornwall.</i>
Silica	59.50	45.00.
Magnesia	30.50	24.75.
Alumina	0.00	9.25.
Oxide of Iron	2.50	1.00.
Water	5.50	18.00.

It is met with at Wunsiedel and Göpfersgrün in Bai-reuth, in the Lizard district in Cornwall, in Saxony, in Piedmont, in Sweden, in China, &c., most commonly in veins, but also sometimes in imbedded irregular masses in serpentine.

#### STILPNOSIDERITE.

##### ORE.

Stilpnosiderite. *JAM. Syst.* Vol. III. p. 549. *Man.* p. 331.

Stilpnosiderite. *PHILL.* p. 227.

Small reniform and irregular dendritic shapes, massive. Composition impalpable. Fracture rather perfectly conchoidal.

Lustre resinous. Colour brownish-black, blackish-brown. Streak yellowish-brown. Feebly translucent on the edges ... opaque.

Brittle. Hardness = 4.5. Sp. Gr. = 3.611, a reniform variety.

Before the blowpipe it becomes black, but is infusible. With borax it yields a dark olive-green glass, but is not melted itself. According to VAUQUELIN and ULLMANN, it consists of

Oxide of Iron	80.25	80.50.
Silica	3.75	2.25.
Water	15.00	16.00.
Oxide of Manganese	0.00	a trace.

From the observations of Mr FREIESLEBEN, relative to the process of smelting this ore, it appears that it also contains phosphoric acid.

It occurs at Scheibenberg and Raschau in Saxony, in the county of Henneberg, in Thuringia, in Nassau, in the Hartz, &c.

Stilpnosiderite is generally considered as a variety of prismatic Iron-ore; it possesses a stronger lustre, from which property the name has been derived.

## STROMNITE.

Bary-Strontianite or Stromnite. TRAILL. Trans. Roy. Soc. Edinb. Vol. IX. P. 1. p. 81. PHILL. p. 187.

Massive: composition thin columnar, and shewing traces of crystallisation.

Colour yellowish-white internally; on the outside, where it appears to be disintegrated, it is greyish-white. Lustre inclining to pearly, faint. Translucent.

Brittle. Hardness = 3.5. Scratches calc-spar, but not fluor-spar. Sp. Gr. = 3.703, TRAILL.

According to Dr TRAILL, it contains

Carbonate of Strontia	68.6.
Sulphate of Baryta	27.5.
Carbonate of Lime	2.6.
Oxide of Iron	0.1.

It effervesces with acids, but is infusible before the blow-pipe. It occurs in veins along with hexahedral Lead-glance, in a kind of clay-slate at Stromness in Orkney.

## SULPHATE OF POTASH.

## SALT.

Potasse sulfatée. HAÜY. Traité, 2de Ed. T. II. p. 187.

Prismatic.  $P = 131^{\circ} 15'$ ,  $112^{\circ} 32'$ ,  $87^{\circ} 34'$ . Vol. I.

Fig. 9. AP.

$$a : b : c = 1 : \sqrt{3.06} : \sqrt{1.69}.$$

Simple forms.  $P - \infty$ ;  $P (P)$ ;  $P + \infty = 106^{\circ} 46'$ ;  $(\check{P}r)^5 (a)$ ;  $(\check{P}r + \infty)^5 (d) = 67^{\circ} 52'$ ;  $\check{P}r (o) = 120^{\circ} 29'$ ;  $\frac{5}{4} \check{P}r + 2 = 60^{\circ} 30'$ ;  $\check{P}r + \infty (p)$ ;  $(\check{P}r + \infty) (s)$ .



Char. of Comb. Prismatic.

Combinations. 1.  $\check{P}r$ .  $\check{P}r + \infty$ .  $\check{P}r + \infty$ . (*Pot. sulf. prismatique*. HAÜY.)

2.  $P$ . ( $\check{P}r + \infty$ )<sup>5</sup>. (*Pot. sulf. dodécaèdre*. HAÜY.)  
Sim. Fig. 7. without *s*.

3.  $\check{P}r$ .  $P$ . ( $\check{P}r$ )<sup>5</sup>.  $P + \infty$ . ( $\check{P}r + \infty$ )<sup>5</sup>.  $\check{P}r + \infty$ .  
 $\check{P}r + \infty$ . Sim. Fig. 30., the edges between *d* and *s* being replaced by the faces of  $P + \infty$ .  
There is almost always regular composition parallel to one or both faces of  $\check{P}r$ .

Cleavage, very indistinct, parallel to  $\check{P}r$  and  $\check{P}r + \infty$ , the latter a little more apparent; Traces of  $\check{P}r + \infty$ . Fracture imperfect conchoidal ... uneven. Surface; ( $\check{P}r + \infty$ )<sup>5</sup>, and partly also  $P + \infty$  irregularly streaked parallel to their common edges of combination; the rest of the faces smooth.

Lustre vitreous, inclining to resinous. Colour white, yellowish or greyish, sometimes superficially greenish or blueish. Streak white, a little shining. Transparent ..., translucent.

Rather brittle. Hardness = 2.5 ... 3.0. Sp. Gr. = 1.731. Taste saline and bitter, disagreeable.

Its chemical formula is  $\check{K} \check{S}^2$ , according to BERZELIUS, corresponding to

Sulphuric Acid 45.93.

Potash 54.07.

(c) It occurs at Mount Vesuvius. The regular forms of this salt have been likewise ascertained to belong to the prismatic system, by Dr BREWSTER, and by Messrs BROOKE and LÉVY.

## TENNANTITE.

## GLANCE.

Tennantite. JAM. Syst. Vol. III. p. 563. Man. p. 332.  
Tennantite. PHILL. p. 304.

Semi-tessular, with inclined faces. Combinations similar to Fig. 158 ... 161; often in regular compositions, according to the law of Fig. 164. Cleavage dodecahedron, imperfect. Sometimes massive, composition granular ... impalpable. Fracture uneven.

Lustre metallic. Colour blackish lead-grey. Streak reddish-grey. Opaque.

Brittle. Scratches prismatic and tetrahedral copper-glance, W. PHILL. Sp. Gr. = 4.375, R. PHILL.

The existence of the regular composition is most easily ascertained by the striæ upon the faces of the hexahedron, which are parallel to the edges of combination with one of the tetrahedrons.

Before the blowpipe Tennantite decrepitates a little, and burns with a blue flame, emitting copious arsenical vapours, and melting at last into a black scoria, which affects the magnetic needle. According to Mr R. PHILLIPS, it consists of

Copper	45.32.
Arsenic	11.84.
Iron	9.26.
Sulphur	28.74.
Silica	5.00.

It occurs in several of the Cornish copper mines, in veins traversing granite and clay-slate, and is accompanied by several ores of copper.

## THOMSONITE.

## KOUPHONE-SPAR.

Thomsonite. BROOKE. Ann. of Phil. Vol. XVI. p. 193.  
 THOMSON. Ibid. p. 408. PHILL. p. 39.

Prismatic.  $P + \infty = 90^\circ 40'$ , BROOKE. Crystals elongated in the direction of the axis, having the apices engaged. Massive: composition columnar, radiating from common centres.

Cleavage, parallel to  $\check{P}r + \infty$ , and  $Pr + \infty$ , forming a rectangular four-sided prism, very easily obtained. Fracture uneven. Surface smooth.

Lustre vitreous, much inclining to pearly. Colour white. Transparent ... translucent.

Brittle. Hardness = 5.0. Sp. Gr. = 2.37, BROOKE.

According to THOMSON and BERZELIUS, it consists of

Silica	36.80	38.30.
Alumina	31.36	30.20.
Lime	15.40	13.54.
Soda	0.00	4.53.
Magnesia	0.20	0.40.
Peroxide of Iron	0.60	0.00.
Water	13.00	13.10.

It intumesces before the blowpipe, and becomes snow-white and opaque, but does not melt. It occurs with axotomous Triphane-spar, in the trap-rocks of Kilpatrick, near Dumbarton in Scotland.

## THULITE.

## SPAR.

Thulite. BROOKE. Crystallography, p. 494. PHILL. p. 211

Cleavage, parallel to the sides of a rhombic prism of  $92^\circ 30'$  and  $87^\circ 30'$ .



Colour rose-red. Streak greyish-white.  
 Scratched by quartz, and yielding to the knife  
 with difficulty.

This mineral is very imperfectly described, as all the properties given do not suffice, if it be a particular species, to distinguish it from the Manganese-spar, at least by characters derived from the descriptions of the two substances. It occurs at Tellemarken in Norway with rhombohedral Quartz, octahedral Fluor-haloïde, and Cyprine, which is said to be a cupriferos variety of pyramidal Garnet.

## TIN-PYRITES.

## GLANCE.

Tin-Pyrites. JAM. Syst. Vol. III. p. 325. Man. p. 332.

Tin Pyrites. Sulphuret of Tin. PHILL. p. 254.

Form probably tessular. Massive: composition granular, strongly coherent. Fracture uneven, imperfect conchoidal.

Lustre metallic. Colour steel-grey, inclining to yellow. Streak black. Opaque.

Brittle. Hardness = 4.0. Sp. Gr. = 4.350,  
 KLAPROTH.

In the collections of Mr RASHLEIGH of Menabilly, and Mr WILLIAMS of Scorrier, crystals of Tin-pyrites are preserved, having apparently the form of regular hexahedrons, but their surface is dull. The traces of cleavage, sometimes observed in massive varieties, seem likewise to be parallel to this form, and at the same time parallel to the dodecahedron.

Before the blowpipe sulphur is driven off, and the mineral melts into a blackish scoria, without yielding a metallic button. It is soluble in nitro-muriatic acid, during which

the sulphur is precipitated. According to KLAPROTH, it consists of

Tin	34.00.
Copper	36.00.
Iron	2.00.
Sulphur	25.00.

It is found near St Agnes in Cornwall, with pyramidal Copper-pyrites, dodecahedral Garnet-blende, &c.

#### TORRELITE.

Torrelite. RENWICK. Ann. of Phil.

No description.

The analysis by Professor RENWICK gives

Silica	32.60.
Peroxide of Cerium	12.32.
Protoxide of Iron	21.00.
Alumina	3.68.
Lime	24.08.
Water	3.50.

It occurs in Sussex county, New Jersey.

#### TRONA.

##### SALT.

For Synonymes, *vide* Vol. II. p. 27. Trona. HAIDINGER, Edinb. Journ. of Science. Vol. II. p. 325.

Hemi-prismatic. Combinations observed resembling Fig. 75., without *r*. Inclination of *M* on *T* =  $103^{\circ} 15'$ , of *n* on *n*, adj. =  $132^{\circ} 30'$ , nearly. Cleavage highly perfect, parallel to *M*, traces parallel to *T* and *n*. Fracture uneven. Surface, *T* often striated parallel to its edges of combination with *M*.

Lustre vitreous. Colour white, sometimes yellow-

ish. Streak white. Transparent ... translucent.

Index of refraction, ord. = 1.43., extr. 1.52.

Hardness = 2.5 ... 3.0. Sp. Gr. = 2.112.

*Compound Varieties.* Thin columnar compositions of crystals lengthened between *M* and *T*; fracture radiated, owing to the longitudinal distinct face of cleavage.

The analysis of this mineral by KLAPROTH has been given above, Vol. II. p. 29., agreeing with BERZELIUS formula  $\text{Na } \ddot{\text{C}}^3 + 4 \text{ Aq}$ , or 37.99 of soda, 40.15 carbonic acid, and 21.86 of water. It does not melt in its water of crystallisation, and is not altered by the influence of the atmosphere. It is formed on the banks of the natron lakes in Sukena, a province of the kingdom of Fezzan in Africa, in the shape of crystalline coats, and occurs also on the surface of the earth. It is exported from thence in considerable quantities under the name of *Trona*. The natural carbonate of soda from the lake of Merida in Columbia, probably also belongs to this species.

## TUNGSTATE OF LEAD.

## BARYTE.

Tungstate of Lead. PHILL. p. 350.

Probably pyramidal. Crystals acute four-sided pyramids and prisms in parallel position, contracted at the ends, and aggregated in bunches.

Lustre resinous. Colour yellowish-grey. Faintly translucent.

Before the blowpipe it melts and gives off vapours of lead, leaving a crystalline globule of a dark colour and metallic aspect, which yields a pale grey powder. When the lead has been driven off, it yields with borax a yellow



globule, transparent and dark red on cooling, and with salt of phosphorus, at a certain degree of saturation, a blue one in the reducing flame. It occurs at Zinnwald in Saxony, associated with rhombohedral Quartz and Mica, and was first noticed as a particular species, and subjected to a chemical examination by Messrs BREITHAUP and LAMPADIUS.

#### TURNERITE.

Turnerite. LÉVY. Ann. of Phil. XVIII. p. 241. PHILL. p. 382.

**Hemi-prismatic.** Combinations having the general appearance of the crystal of prismatic Azure-malachite, represented Fig. 66.

Measurements of the angles, according to LÉVY and PHILLIPS:

$M$ on $M$ (over $i$ ) =	$96^{\circ} 10'$ .	$h$ on $c$ =	$142^{\circ} 29'$ .
$g$ on $g$ (over $i$ ) =	$131^{\circ} 50'$ .	$c$ on $a$ =	$92^{\circ} 55'$ .
$M$ on $x$	= $140^{\circ} 50'$ .	$h$ on $a$ =	$124^{\circ} 36'$ .
$h$ on $M$ (over $x$ ) =	$80^{\circ} 20'$ .	$a'$ on $x$ =	$143^{\circ} 30'$ .
$h$ on $M$ (over $k$ ) =	$99^{\circ} 40'$ .	$h$ on $k$ =	$133^{\circ} 50'$ .

There are moreover five prisms indicated in the situation of  $l, f, P$ , whose edges, contiguous to the face  $h$ , are  $130^{\circ} 34'$ ,  $98^{\circ} 50'$ ,  $94^{\circ} 44'$ ,  $90^{\circ} 0'$ , and  $55^{\circ} 36'$ ; the first and third have been observed by Mr LÉVY, the other three by Mr PHILLIPS.

Cleavage parallel to both diagonals of the prism resulting from the enlargement of the faces  $M$ , one of them more perfect.

Lustre nearly adamantine. Colour several shades of yellow, often inclining to brown. Streak white, sometimes greyish. Transparent ... translucent.

Scratches fluor pretty readily, but yields to the knife.

According to the experiments of Mr CHILDREN, it consists chiefly of alumina, lime, magnesia, and a little iron, but very little silica, and no titanium. It was formerly confounded with prismatic Titanium-ore, but is said to have afterwards been distinguished from it under the name of *Pictite*. Its locality is Mount Sorel in Dauphiny, where it is accompanied by rhombohedral Quartz, prismatic Feldspar, Albite, Crichtonite, and pyramidal Titanium-ore.

## VAUQUELINITE.

## MALACHITE ?

Vauquelinit. LEONH. S. 248. Vauquelinite. Chromate of Lead and Copper. PHILL. p. 350.

Hemi-prismatic. Minute crystals, nearly resembling Fig. 59., with the obtuse edges *oa* replaced, compressed between *P* and *P*, and joined in regular compositions, parallel to a plane, which passes through the crystals in the direction of *ee*, and intersects the acute lateral edges. Inclination of *P* on *P'*, from the other individual, nearly =  $134^{\circ} 30'$ ; of the edge *oa*, or its replacement, on *P*, about  $149^{\circ}$ .

Fracture uneven. Surface, *P* smooth and even, the rest of the faces a little curved.

Lustre adamantine, often faint. Colour blackish-green, olive-green. Streak siskin-green, often inclining to brown. Faintly translucent, with a fine olive-green tint, opaque.

Rather brittle. Hardness = 2.5 ... 3.0. Sp. Gr. = 5.5 ... 5.78, LEONHARD.

*Compound Varieties.* Botryoidal, reniform, massive: composition generally impalpable, surface drusy or rough, fracture imperfect and flat conchoidal, lustre faint resinous.

Alone before the blowpipe it intumesces a little, and then froths and melts into a greyish globule, giving at the same time some globules of lead. In the oxidating flame a small quantity effervesces with, and imparts a green colour to borax and salt of phosphorus, which remains transparent on cooling; but in the reducing flame the globule turns red and transparent, or red and opaque, or finally black, according to the quantity of the mineral employed. According to BERZELIUS, it consists of

Oxide of Lead 60.87.

Oxide of Copper 10.80.

Chromic Acid 28.33.

It occurs at Beresof in Siberia, along with hemi-prismatic and rhombohedral Lead-baryte, and has been quoted also from Brazil, where it likewise accompanies the hemi-prismatic Lead-baryte.

#### VELVET-BLUE COPPER.

##### MALACHITE ?

Velvet-Blue Copper. JAM. Syst. Vol. II. p. 320. Man. p. 332.

Short capillary crystals, in velvety druses and coatings.

Lustre pearly. Colour bright smalt-blue. Translucent.

It has been found lining drusy cavities in prismatic Iron-ore, only at Moldawa in the Bannat of Temeswar, accompanied by several ores of copper. This rare substance is very imperfectly known, and also its chemical composition has not been ascertained.



## WAGNERITE.

Wagnerit. FUCHS. Schweiggers Journal. Vol. III. p. 269.

Hemi-prismatic. Horizontal projection of a crystal represented Fig. 197\* ;  $a$  is not a right angle,  $b$ ,  $k$ , and  $g$ , if enlarged, would produce parallel edges of combination.

Lustre vitreous. Colour several shades of yellow, sometimes nearly orange-yellow, often inclining to grey. Streak white. Translucent.

Hardness = 5.0 ... 5.5. Sp. Gr. = 3.11, FUCHS.

It has been analysed by FUCHS, who found it to consist of

Phosphoric Acid	41.73.
Fluoric Acid	6.50.
Magnesia	46.66.
Oxide of Iron	5.00.
Oxide of Manganese	0.50.

The only locality of Wagnerite known at present, is the valley called Hüllgraben near Werfen in Salzburg, where it occurs in short and irregular veins of rhombohedral Quartz in clay-slate.

## WAVELLITE.

## HALOIDE.

Wavellite. JAM. Syst. Vol. I. p. 389. Man. p. 333. Wavellite. Subphosphate of Alumine. PHILL. p. 146.

Prismatic.  $\text{Pr} = 107^\circ 26'$ .  $\text{P} + \infty = 122^\circ 15'$ ,  
PHILL. Cleavage,  $\text{P} + \infty$  and  $\text{Pr} + \infty$ , perfect.

---

\* I have been indebted for this drawing to Dr GUSTAVUS ROSE, who first ascertained the crystal to which it refers, in the possession of Mr HEULAND, to be Wagnerite. H.

Implanted globules : composition thin columnar.  
Surface drusy.

Lustre of the faces of cleavage intermediate between pearly and vitreous. Colour white, passing into several shades of green, grey, brown, and black. Translucent.

Hardness = 3.5 ... 4.0. Sp. Gr. = 2.337, of the variety from Barnstaple.

Before the blowpipe it loses its lustre and transparency, but does not melt. With boracic acid and iron wire, it yields a globule of phosphuret of iron. It consists, according to FUCHS and BERZELIUS, of

Alumina	37.20	35.35.
Phosphoric Acid	35.12	33.40.
Fluoric Acid	0.00	2.06.
Lime	0.00	0.50.
Oxide of Iron and Manganese	0.00	1.25.
Water	28.00	26.80.

It occurs at Barnstaple in Devonshire, in small veins in clay-slate; at St Austle in Cornwall, in veins traversing granite, accompanied by octahedral Fluor-haloide, pyramidal Tin-ore, pyramidal Copper-pyrites, &c.; in the Shiant isles in Scotland; at Zbirow near Beraun in Bohemia, in a kind of sandstone; at Amberg in the Upper Palatinate, with prismatic Iron-ore, &c.; in fine varieties near Cork in Ireland, and in Brazil.

#### WITHAMITE.

#### AUGITE-SPAR.

Withamite. BREWSTER. Edin. Journ. of Science. Vol. II. p. 218.

Hemi-prismatic. Minute crystals observed similar to Fig. 75, lengthened between *M* and *T*, aggre-

gated in globular masses, radiating from their centres. Inclination of  $r$  on  $T' = 128^\circ 20'$ , of  $M$  on  $T' = 116^\circ 40'$ , nearly, BREWSTER.

Lustre vitreous. Colour carmine-red and pale straw-yellow, in two different directions, perpendicular to each other, and to the lengthened prisms. Streak white. Translucent.

Brittle. Hardness = 6.0 ... 6.5. Sp. Gr. = 3.137, TURNER.

Before the blowpipe it intumesces, but fuses only with difficulty into a dark greenish-grey scoria. Salt of phosphorus dissolves it with effervescence into a globule, which contains a skeleton of silica, and becomes opaque on cooling. It shews nearly the same reactions as the Epidote from Arendal, with which it likewise agrees in most of its other properties. This mineral is named in compliment to Mr WITHAM, who discovered it in Glencoe in Scotland, in a reddish trap-rock.

## YELLOW TELLURIUM.

Yellow Gold-Glance, or Yellow Tellurium. JAM. Syst. Vol. III. p. 379. Yellow Tellurium. PHILL. p. 328.

Prismatic. Combination similar to Fig. 14., having the edges between  $p$  and  $p$ , between  $P$  and  $P$ , and between  $M$  and  $M$  replaced. Inclination of the edge  $y$  on the edge  $y = 74^\circ 30'$ ; of  $p$  on  $p$  (adj.) =  $73^\circ 40'$ , of  $M$  on  $M = 143^\circ$ , of  $p$  on  $M = 123^\circ 30'$ , BROOKE.

Imbedded crystalline laminæ. Traces of cleavage. Fracture uneven.

Lustre metallic. Colour silver-white, much inclining to brass-yellow. Opaque.



Rather brittle. Soft, BREITHAAPT. Sp. Gr. = 10·678, MÜLLER VON REICHENSTEIN.

Before the blowpipe it melts into a metallic globule, and emits a pungent odour. It is soluble in nitric acid, and consists, according to KLAPROTH, of

Tellurium	44·75.
Gold	26·75.
Lead	19·50.
Silver	8·50.
Sulphur	0·50.

As yet it is only known from Nagyag in Transylvania, where it occurs with prismatic Tellurium-glance, hexahedral Glance-blende, macrotypous Parachrose-baryte, &c. in veins traversing porphyry.

#### YTTRO-CERITE.

Yttro-cerite. JAM. Syst. Vol. III. p. 566. Man. p. 334.  
Yttrocerite. PHILL. p. 265.

Massive. Composition granular, strongly coherent, impalpable. Fracture uneven.

Colour violet-blue, inclining to grey and white; sometimes white on the surface. Opaque.

Scratches octahedral Fluor-haloide, and is scratched by rhombohedral Quartz, BERZELIUS. Sp. Gr. = 3·447, BERZELIUS.

Before the blowpipe it loses its colour, and becomes white before it glows, but is infusible by itself. With sulphate of lime it melts into a globule, which becomes white on cooling. According to BERZELIUS, it consists of

Lime	47·63	50·00.
Fluoric Acid	25·05	25·45.
Yttria	9·11	8·10.
Oxide of Cerium	18·22	16·45.

It occurs at Finbo and Broddbo, near Fahlun in Sweden, along with Albite and rhombohedral Emerald, and is imbedded in rhombohedral Quartz.

## YTTRO-TANTALITE.

## ORE.

Ytthro-Tantalite. JAM. Syst. Vol. III. p. 177. Ytthro-columbite. PHILL. p. 271.

i. *Black Ytthro-tantalite.*

Indistinct traces of crystallisation. Fracture lamellar in one direction, coarse granular in another. Disseminated, seldom of the size of a hazelnut. Imperfect metallic lustre. Opaque. Colour black. Streak grey. Brittle. Scratches glass. Sp. Gr. = 5.395, BERZELIUS.

ii. *Yellow Ytthro-tantalite.*

No trace of crystallisation. It is found between felspar in the state of lamellæ, seldom in grains not exceeding the size of a pepper corn. The longitudinal fracture of the lamellæ is foliated, the cross fracture fine grained. Lustre resinous on the surface, vitreous in the fracture. Colour yellowish-brown, accidentally with green spots or stripes. Streak white ... opaque. Scratches glass with difficulty, but is very distinctly scratched by it. Sp. Gr. = 5.882, ECKEBERG.

iii. *Dark Ytthro-tantalite.*

No trace of crystallisation. Occurs with the preceding, commonly in thin laminae, seldom in

grains. Fracture conchoidal in one direction, fine grained in another.

Lustre intermediate between vitreous and resinous. Colour black, inclining but little to brown. Streak white. Very small fragments are translucent, almost colourless, sometimes a little yellowish.

Hardness equal to that of the yellow variety.

From the analysis of these different kinds, BERZELIUS obtained the following results :

	<i>Black.</i>	<i>Yellow.</i>	<i>Dark.</i>
Oxide of Tantalum	57.00	59.50—60.124	51.815.
Yttria	20.25	24.90—29.780	38.515.
Lime	6.25	3.29—	0.500 3.260.
Oxide of Uranium	0.50	8.23—	6.622 1.111.
Tungstic Acid with Tin	8.25 pure	1.25—	1.044 2.592.
Oxide of Iron	3.50	2.72—	1.155 0.555.

These three kinds have been discovered and described by BERZELIUS in the *Afhandlingar i Fysik*, &c., Vol. IV. p. 268. By themselves they are all infusible before the blowpipe ; but they decrepitate and acquire a lighter colour. The black Ytthro-tantalite froths and melts with soda, but not the others. Borax dissolves them and forms a yellowish glass, which easily loses its transparency. They are not acted upon by acids.

The different kinds of Ytthro-tantalite occur at Ytterby, and in the neighbourhood of Fahlun in Sweden.

#### ZEAGONITE.

##### GEM.

Abrazite. Zeagonite. Gismondine. PHILL. p. 11. Gismondin. LEONH. S. 645.

Pyramidal.  $P = 122^{\circ} 54', 85^{\circ} 2'$ . Vol. I. Fig. 8.  
BROOKE. Combination observed,  $P. P + \infty$ .



Cleavage imperfect parallel to  $P + \infty$ . Surface,  $P$  frequently rounded,  $P + \infty$  smooth, and though generally very small, yet possessing high degrees of lustre. Fracture conchoidal.

Lustre adamantine. Colour pale smalt-blue, milk-white, pearl-grey, and rose-red. Translucent, in small crystals nearly transparent.

Hardness = 7.0 ... 7.5.

According to CARPI, it consists of

Silica	41.4.
Lime	48.6.
Alumina	2.5.
Magnesia	1.5.
Oxide of Iron	2.5.

It phosphoresces before the blowpipe, and becomes friable, but is infusible. It gelatinises with acids, without effervescence. It occurs along with white octahedrons of octahedral Fluor-haloide, with prismatic Feld-spar and other species in the drusy cavities of a volcanic rock at Capo di Bove near Rome. In all its characters, Zeagonite is most nearly allied to pyramidal Zircon, as a variety of which it has often been considered, the difference of the angles given by Mr BROOKE being only  $0^{\circ} 25'$  on the terminal edges, and  $0^{\circ} 42'$  on the lateral edges of the fundamental pyramid. Also the refraction is very considerable, and approaches near that of the same species. Pyramidal Zircon will therefore make an interesting point of comparison with the Zeagonite, in future examinations of this mineral. It is evident that the mineral, of which Mr PHILLIPS has given the angle at the base of the four-sided pyramid =  $96^{\circ} 30'$ , and which is said to yield to the nail, must be another species than that described above, the angles of which have been ascertained by Mr BROOKE. The name of *Abrazite* is sometimes applied to a mineral, which seems to be a variety of paratomous Kouphone-spar (Vol. ii. p. 229).

## ZURLITE.

Zurlite. PHILL. p. 212. Zurlit. LEONH. p. 663.

Form, rectangular four-sided prisms, lengthened in the direction of the axis, and having sometimes their lateral edges replaced.

Cleavage indistinct. Fracture conchoidal. Surface rough, generally covered with a white coating, sometimes convex.

Lustre resinous. Colour asparagus-green. Streak said to be pearl-grey.

Hardness about 6·0. Sp. Gr. = 3·274.

It is infusible before the blowpipe, but yields with borax a black glass. Nitric acid dissolves it, partly with effervescence, and assumes a yellow colour.

Zurlite has been discovered and described as above, by REMONDINI, in the Memoirs of the Academy of Naples.

## APPENDIX II.

MINERALS, WHICH WILL PROBABLY NEVER FORM DISTINCT SPECIES IN THE MINERAL SYSTEM.

### ADHESIVE SLATE.

Adhesive Slate. JAM. Syst. Vol. II. p. 68. Man. p. 476.  
Adhesive Slate. PHILL. p. 50.

**Massive**: composition impalpable. Principal fracture slaty, more and less perfect. Cross fracture even, flat conchoidal.

Colour yellowish-grey, passing into white and smoke-grey. A little shining in the streak. Feebly translucent on the edges.

**Sectile**. Adheres strongly to the tongue, feels a little greasy, and is very soft. Sp. Gr. = 2.086, KLAPROTH.

It absorbs water with great avidity, but does not fall to pieces. On being exposed to a red heat, it becomes brownish-red, and loses in weight. It consists, according to KLAPROTH and LAMPADIUS, of

Silica	66.50	30.80.
Alumina	7.00	0.00.
Magnesia	1.50	28.00.
Lime	1.25	0.80.
Oxide of Iron	2.50	11.20.



Carbonic Acid	0·00	27·00.
Water	19·00	0·30.

It occurs at Menil Montant, and Montmartre near Paris.

#### ALUM-SLATE.

Alum-Slate. JAM. Syst. Vol. II. p. 276. Man. p. 443.  
Alum-Slate. PHILL. p. 48.

Massive. Spheroidal shapes. Composition impalpable. Principal fracture imperfectly slaty; cross fracture earthy.

Nearly dull. Colour intermediate between greyish- and blueish-black. Streak black, acquires some lustre. Opaque.

Not very brittle. Intermediate between semi-hard and soft. Sp. Gr. = 2·339 ... 2·588, KIRWAN.

Alum-slate has been divided into two kinds, *common* and *glossy* alum-slate. The latter differs from the former only by fissures having a higher degree of a somewhat metallic lustre, which traverse it in a direction nearly parallel to that of the slaty structure. Alum-slate seems to be closely connected with clay-slate.

Exposed to the fire, it burns and becomes blueish-grey. It occurs in particular beds between clay-slate and greywacke-slate, near Reichenbach in Saxony, also at Reussisch-Ebersdorf, in the valley of the Saale, in several places in the forest of Thuringia, in the Palatinate, in Bohemia, &c.; and is used in manufacturing alum and sulphate of iron. The mineral called *Alum-earth* is in a closer relation to Slate-clay (Vol. III. p. 181.) and to Earthy Coal (Vol. III. p. 62.).

#### BITUMINOUS SHALE.

Bituminous Shale. JAM. Syst. Vol. II. p. 63. Bituminous Marle. PHILL. p. 159.

Massive : composition impalpable. Fracture rather thin and straight, slaty.

Faintly glimmering. Colour brownish-black and blackish-brown. Streak shining, with a resinous lustre. Opaque.

Rather sectile, feels very little greasy. Intermediate between soft and very soft. Sp. Gr. = 1.995, KIRWAN.

According to WERNER, it is slate-clay with a small portion of bitumen. It occurs at Wehrau in Lusatia, also in the neighbourhood of Elbogen in Bohemia, in the Tyrol, in great quantities in Thuringia, and in many other countries, with different varieties of clay, and with coal.

## BOLE.

Bole. JAM. Syst. Vol. II. p. 86. Man. p. 314. Bole. PHILL. p. 53.

Massive : composition impalpable. Fracture perfectly conchoidal, sometimes rather flat.

Faintly glimmering ... dull. Colour brown, yellow, and red. Streak shining, resinous. Feebly translucent on the edges ... opaque.

Rather sectile. Adheres to the tongue, feels greasy, and is very soft, sometimes approaching to soft. Sp. Gr. = 1.600, KLAPROTH ; = 1.977, BREITHAUPT.

If thrown into water, it emits a crackling noise and falls into powder. It occurs in irregular beds or disseminated masses in wacke, trapp-tuff, &c., and is found at Striegau in Silesia, at Scheibenberg in Saxony, the Habichtswald in Hessa, in Thuringia, Tuscany, &c.

## CLAYSTONE.

Claystone. JAM. Syst. Vol. II. p. 66.

Massive. Composition impalpable. Fracture uneven, flat conchoidal, sometimes inclining to slaty.

Colour, different shades of grey and red, none of them bright. Opake.

Not particularly brittle. Does not adhere to the tongue; feels meagre. Sometimes semi-hard, sometimes soft, or even very soft. Sp. Gr. = 2.210, KARSTEN.

Claystone appears to be the residue of the crystalline formation of several kinds of rock, particularly of porphyry; hence its characters are so very different in different specimens, and it seems to exhibit so many passages to other minerals, of which in reality not one is existing. It forms the base of several varieties of porphyry, such as are called clay- or claystone-porphyry, and occurs in various parts of Saxony, as at Chemnitz, Grumbach, also in veins at Frauenstein, Marienberg, Klingenberg, &c.

## COMMON CLAY.

Common Clay. JAM. Syst. Vol. II. p. 57. Pipe-clay.  
Potter's Clay. Loam. PHILL. p. 55. 56.

Massive. Composition impalpable. Fracture uneven, fine earthy in the small; more or less perfectly slaty.

Dull. Colour white, grey, brown, red, yellow, &c., sometimes in striped, veined, or spotted delineations. Streak more or less shining.

Sectile. Adheres more or less strongly to the



tongue. Feels more or less greasy. Soft, sometimes approaching to friable. Not particularly heavy, passing into light. Sp. Gr. of earthy Potter's Clay = 1.800 ... 2.000, KIRWAN; = 2.085, KARSTEN; Slate-clay = 2.600 ... 2.680, KIRWAN; = 2.636, KARSTEN.

Common Clay has been divided into *Loam*, *Potter's Clay*, *Variogated Clay*, and *Slate-Clay*; and Potter's clay again into *earthy* and *slaty*; which division rests either upon particular, though accidental properties, or upon the employment made of the varieties.

Clay is a mixture of decomposed minerals, and hence it is little constant in its composition. Several varieties soften in water, and allow themselves to be kneaded and formed into moulds, a property to which they owe their well known employment. Some are easily fusible, others refractory; some acquire particular tints of colour, others lose theirs, and become white when exposed to a strong heat; upon all of which properties their applicability depends. They occur in beds near the surface of the earth, or covered by the soil in the formations of brown and black coal. In the latter they very often contain remains of vegetables, and are called slate-clay, which is intimately related to bituminous shale and alum-earth.

The appropriate varieties of clay are of various important applications in pottery, in manufacturing stone-ware and porcelain, in constructing furnaces for metallurgic operations, &c.

## DRAWING SLATE OR BLACK CHALK.

Drawing-Slate or Black Chalk. JAM. Syst. Vol. II. p. 273. Man. p. 443. Black Chalk. PHILL. p. 55.

Massive. Composition impalpable. Principal frac-

ture rather imperfectly slaty, cross fracture fine earthy.

Faint glimmering in the principal fracture, dull in the cross fracture. Colour intermediate between greyish- and blueish-black. Retains the colour in the streak, and acquires a higher degree of lustre. Opaque.

Sectile. Soils more or less, and writes. Adheres a little to the tongue, feels fine and rather meagre, and is very soft. Sp. Gr. = 2.114, KIRWAN; = 2.186, BRISSON.

Exposed to fire it loses its black colour, and becomes reddish or reddish-grey. Before the blowpipe it yields a white glass, according to LINK. The variety from Bayreuth has been found by WIEGLEB to consist of

Silica	64.50.
Alumina	11.25.
Oxide of Iron	2.75.
Carbon	11.00.
Water	7.50.

It occurs in rocks of clay-slate, and seems to be very nearly allied to clay-slate and alum-slate. The finest and most applicable varieties come from Italy, Spain, and France. It is also found in Bayreuth, in Thuringia, &c. It is used as a drawing material.

#### FULLER'S EARTH.

Fuller's Earth. JAM. Syst. Vol. II. p. 300. Man. p. 442.

Fuller's Earth. PHILL. p. 52.

Massive. Composition impalpable. Fracture uneven, splintery, earthy: in the great sometimes imperfectly and flat conchoidal, or even slaty.

Dull. Colour green, grey, white. Streak shining, resinous. Feebly translucent on the edges ... opake.

Perfectly sectile. Feels very greasy. Adheres but feebly or not at all to the tongue, and is very soft. Sp. Gr. = 1·819, HOFFMANN; = 2·198, BREITHAAPT.

If thrown into water, it falls to pieces, and forms a paste which is not plastic. It absorbs oil and fat. It is formed by the decomposition of certain rocks, as for instance at Rosswein in Saxony, at Feistritz on the Bacher in Stiria; and probably also at Reifenstein and Rein in the same country, although in these two places the mode of its formation is not so easily observed. It occurs also in Moravia, in great quantities and very pure at Nutfield in Surry, and other places in England, &c., and is used for cleansing woollen cloth.

## LITHOMARGE.

Lithomarge. JAM. Syst. Vol. II. p. 74. Man. p. 311.  
Lithomarge. PHILL. p. 52.

Massive. Spheroidal. Composition impalpable. Fracture uneven, large and flat conchoidal in the large, fine earthy in the small. Sometimes the particles do not cohere, and are found in the shape of a fine scaly powder.

Colour white, pearl-grey, lavender-blue, flesh-red, ochre-yellow. Somewhat shining in the streak. Opake.

Sectile. Adheres strongly to the tongue, feels fine and greasy, and is soft, sometimes friable. Sp. Gr. = 2·435 ... 2·492, BREITHAAPT.



It has been divided into two kinds, the *friable*, and the *solid or indurated Lithomarge*.

It does not fall to pieces when thrown into water; and hardens if exposed to a strong heat. It occurs in various parts of Saxony, as in tin-veins at Boberschau and Altenberg; in porphyry at Rochlitz; in the coal measures at Planitz near Zwickau, where the variety called *Terra miraculosa Saxonix* is found; in the drusy cavities of the Topaz-rock at Auerbach; in serpentine at Zöblitz; in trap in the county of Antrim in Ireland, &c.

#### MOUNTAIN SOAP.

Mountain Soap. JAM. Syst. Vol. II. p. 74. Man. p. 312.  
Bole. PHILL. p. 53.

Massive. Composition impalpable. Fracture fine earthy.

Dull. Colour light brownish-black. Streak shining, resinous. Opaque.

Perfectly sectile. Does not soil, but writes, adheres strongly to the tongue, feels very greasy, is very soft, and light, approaching to not particularly heavy.

It has been found at Olkucz in Poland, and is a very rare mineral.

#### POLISHING SLATE.

Polier or Polishing Slate. JAM. Vol. II. p. 70. Man. p. 425.  
Polishing-slate. PHILL. p. 51.

Massive. Composition impalpable. Principal fracture slaty, thin and straight, cross fracture fine earthy.

Colour yellowish-grey, inclining to white or brown. Feels fine, but meagre, adheres but little or not at

all to the tongue, is very soft, passing into friable.  
Sp. Gr. = 0.590 ... 0.606, HABERLE.

It imbibes water, but does not fall to pieces. It becomes red when burnt, but is infusible. It consists, according to BUCHOLZ, of

Silica	79.00.
Alumina	1.00.
Lime	1.00.
Oxide of Iron	4.00.
Water	14.00.

It is believed to have been formed from the ashes of burnt coal. It occurs at Planitz near Zwickau, and at Kutschlin near Bilin in Bohemia.

## TRIPOLI.

Tripoli. JAM. Syst. Vol. II. p. 71. Man. p. 470. Tripoli. PHILL. p. 53.

Massive. Composition impalpable. Fracture earthy in the small, sometimes slaty in the great.

Colour grey, more particularly yellowish- and ash-grey, passing into white and yellow. Opaque.

Not particularly brittle. Does not adhere to the tongue, feels meagre and a little rough, is said to be soft passing into very soft (it is nevertheless applied as a powerful material for polishing).  
Sp. Gr. = 1.857, DELAMÉTHÉRIE; = 2.202, BUCHOLZ.

It imbibes water, which softens it. When burnt it becomes white, and is hardened; but it is very difficultly fusible. It consists, according to BUCHOLZ and HAASE, of

Silica	81.00	90.00.
Alumina	1.50	7.00.

Oxide of Iron	8.00	3.00.
Sulphuric Acid	3.50	0.00.
Water	5.00	0.00.,

with a trace of Lime. It seems to be nothing but a very fine arenaceous variety of quartz, accidentally mixed with a little clay.

#### UMBER.

Umb. JAM. Syst. Vol. III. p. 241. Umb. PHILL. p. 232.

Massive. Composition impalpable. Fracture large and flat conchoidal in the great, very fine earthy in the small.

Dull. Colour liver-, chestnut-, dark yellowish-brown. Acquires some lustre in the streak. Opake.

Imperfectly sectile. Does not soil, but writes, adheres strongly to the tongue, feels a little rough and meagre, and is very soft. Sp. Gr. = 2.206, BREITHAUPT.

It imbibes water with great avidity, and emits air bubbles, but does not become soft. It occurs in beds with brown jasper in the isle of Cyprus, and is used by painters as a brown colour. Its chemical composition is said to be oxide of iron 48, oxide of manganese 20, silice 13, alumina 5, water 14.

#### WHET-SLATE.

Whet-Slate. JAM. Syst. Vol. II. p. 271. Whet-Slate or Hone. Man. p. 343. Whetslate. Turkey Hone. PHILL. p. 48.

Massive. Composition impalpable, Fracture



straight slaty in the great, fine splintery in the small.

Faintly glimmering, almost dull. Colour greenish-grey, mountain-, asparagus-, oil-green. Streak greyish-white. Translucent on the edges.

Not particularly brittle. Said to be soft in a low degree. (It is sometimes as hard as rhombohedral quartz). Sp. Gr. = 2.722, KIRWAN.

Whet-slate is a slaty rock, containing a great proportion of quartz, in which the component particles (the same as in clay-slate, mica-slate, and gneiss, but in different relative quantities) are so very small, as to withdraw themselves from observation. This may serve for explaining on one hand the passage of whet-slate into clay-slate, on the other hand the employment it allows for grinding, which is impossible in any mineral that in reality is *soft*. Whet-slate occurs in beds between clay-slate, particularly in the older rocks; and the varieties best adapted for use are found at Sonnenberg in Meinungen, and at Probstzelle and Lichtentanne in Saalfeld. They are likewise brought from the Levant. Less useful or fine grained varieties are found in many countries. The varieties from the neighbourhood of Liege, *Argile schisteuse novaculaire* of HAÛY, are not comprehended among the whet-slate of WERNER. They consist of two layers of stone of different colour and composition, one of them being yellowish-grey and very fine grained, the other reddish-brown and coarser. The use of whet-slate as a grinding material is sufficiently known.

## YELLOW EARTH.

Yellow Earth. JAM. Syst. Vol. II. p. 81. Man. p. 312.

Massive. Composition impalpable. Principal frac-

ture more and less imperfectly and thick slaty, sometimes fine earthy. Cross fracture fine earthy. Faintly glimmering, dull. Colour ochre-yellow. Acquires some lustre in the streak. Opake. Sectile. Adheres rather strongly to the tongue. Soils a little and writes. Is very soft, partly also friable. Sp. Gr. = 2.240, BREITHAUPT.

If thrown into water it falls into powder and emits a noise. If burnt it becomes red. It is a mixture of fine sand, oxide of iron, clay, &c., and occurs at Wehrau in Upper Lusatia, in France, &c. It is employed both in its natural state and burnt, in painting houses, &c., as a coarse colouring material.



VOE. I. PLATE I.

Fig. 1. II. The hexahedron, with a pyramidal section, and a pyramidal axis.

**PLATES**

Fig. 2. H. G. Combination of the hexahedron and the octahedron.

**AND**

Fig. 3. The same, the faces of the octahedron.

**EXPLANATIONS.**

Fig. 4. The hexahedron, with a pyramidal section, and a pyramidal axis.

Fig. 5. The hexahedron, with two pyramidal sections, and a pyramidal axis.



VOL. I. PLATE I.

- FIG. 1. H. The hexahedron, with a pyramidal section, and a pyramidal axis.
- FIG. 2. O. The octahedron.
- FIG. 3. H. O. Combination of the hexahedron and the octahedron.
- FIG. 4. The same, the faces of the octahedron larger.
- FIG. 5. The hexahedron, with two rhombohedral sections, and a rhombohedral axis.
- FIG. 6. The hexahedron, with two prismatic sections, and a prismatic axis.

Fig. 1.




Fig. 2.




Fig. 3.




Fig. 4.




Fig. 5.






Fig. 6.









VOL. I. PLATE II.

- FIG. 7. R. A rhombohedron.  
FIG. 8. P. An isosceles four-sided pyramid.  
FIG. 9. P. A scalene four-sided pyramid.  
FIG. 10. P. An isosceles six-sided pyramid.  
FIG. 11. (P)<sup>n</sup>. A scalene six-sided pyramid.  
FIG. 12. (P)<sup>n</sup>. A scalene eight-sided pyramid.

Fig. 7.




Fig. 8.




Fig. 9.




Fig. 10.




Fig. 11.





Fig. 12.








Fig. 13.	$\frac{O}{e}$	The trapezoid.
Fig. 14.	$\frac{O}{e}$	The same in inverse position.
Fig. 15.	$\frac{O}{e}$	A rhombus.
Fig. 16.	$\frac{O}{e}$	The same in inverse position.
Fig. 17.	$\frac{O}{e}$	A rhombus tetragonal-hedra- inverted.
Fig. 18.	$\frac{O}{e}$	The same in inverse position.

VOL. I. PLATE III.

- FIG. 13.  $\frac{O}{2}$  The tetrahedron.  
o
- FIG. 14. —  $\frac{O}{2}$  The same, in inverse position.  
o'
- FIG. 15.  $\frac{C_n}{2}$  A trigonal-dodecahedron.  
c
- FIG. 16. —  $\frac{C_n}{2}$  The same, in inverse position.  
c'
- FIG. 17.  $\frac{B_n}{2}$  A digrammic tetragonal-dodecahedron.  
b
- FIG. 18. —  $\frac{B_n}{2}$  The same, in inverse position.  
b'



Fig. 13.




Fig. 14.




Fig. 15.




Fig. 16.




Fig. 17.





Fig. 18.








PLATE IV

- Fig. 18. A hexahedral pentagonal dodecahedron.
- Fig. 19. The same, in inverse position.
- Fig. 20. A right tetrahedral pentagonal dodecahedron.
- Fig. 21. The same, in inverse position.
- Fig. 22. A left tetrahedral pentagonal dodecahedron.
- Fig. 23. The same, in inverse position.



VOL. I. PLATE IV.

FIG. 19.  $\frac{A_n}{2}$  A hexahedral pentagonal-do-  
 $a$  decahedron.

FIG. 20.  $-\frac{A_n}{2}$  The same, in inverse position.  
 $a'$

FIG. 21.  $r\frac{T_n}{4}$  A right tetrahedral pentagonal-  
 $t$  dodecahedron.

FIG. 22.  $-r\frac{T_n}{4}$  The same, in inverse position.  
 $t'$

FIG. 23.  $l\frac{T_n}{4}$  A left tetrahedral pentagonal-  
 $t''$  dodecahedron.

FIG. 24.  $-l\frac{T_n}{4}$  The same, in inverse position.  
 $t'''$

Fig. 19.




Fig. 20.




Fig. 21.




Fig. 23.




Fig. 22.






Fig. 24.









VOL. I. PART I.

1. The nature of the subject	1	1
2. The nature of the subject	1	1
3. The nature of the subject	1	1
4. The nature of the subject	1	1
5. The nature of the subject	1	1
6. The nature of the subject	1	1
7. The nature of the subject	1	1
8. The nature of the subject	1	1
9. The nature of the subject	1	1
10. The nature of the subject	1	1

VOL. I. PLATE V.

FIG. 25.  $\frac{T_n}{2^i}$ . A tetrahedral trigonal-icosite-  
 $t, t''$  tetrahedron.

FIG. 26. —  $\frac{T_n}{2^i}$ . The same, in inverse position.  
 $t', t'''$

FIG. 27.  $\frac{T_n}{2^{ii}}$ . A trigrammic tetragonal-icosi-  
 $t', t''$  tetrahedron.

FIG. 28. —  $\frac{T_n}{2^{ii}}$ . The same, in inverse position.  
 $t, t'''$

FIG. 29.  $r \frac{T_n}{2^{iii}}$ . A right pentagonal-icositetra-  
 $t', t'''$  hedron.

FIG. 30.  $l \frac{T_n}{2^{iii}}$ . A left pentagonal-icositetrahe-  
 $t, t'$  dron.



Fig. 25.




Fig. 26.




Fig. 27.




Fig. 28.




Fig. 29.






Fig. 30.







VOL. I. PLATE VI

- Fig. 31. D. The dodecahedron  
4
- Fig. 32. Aa. A hexahedral trigonal-isohedron  
a
- Fig. 33. Bb. An octahedral trigonal-isohedron  
b
- Fig. 34. Cc. A digrammic tetragonal-isohedron  
c
- Fig. 35. Ff. A tetraoctahedron  
f
- Fig. 36. Derivation of the tessular forms from the  
hexahedron

VOL. I. PLATE VI.

- FIG. 31. D. The dodecahedron.  
*d*
- FIG. 32. An. A hexahedral trigonal-icositetra-  
*a* hedron.
- FIG. 33. Bn. An octahedral trigonal-icositetra-  
*b* hedron.
- FIG. 34. Cn. A digrammic tetragonal-icositetra-  
*c* hedron.
- FIG. 35. Tn. A tetraconta-octahedron.  
*t*
- FIG. 36. Derivation of the tessular forms from the  
hexahedron.



Fig. 31.




Fig. 32.




Fig. 33.




Fig. 34.




Fig. 35.






Fig. 36.






VOL. I. PLATE VII.

- Fig. 37. Derivation of the principal series of the  
lens having spherical aberration.
- Fig. 38. Derivation of the subsidiary series of  
lens having spherical aberration.





VOL. I. PLATE VII.

FIG. 37. Derivation of the principal series of scalene four-sided pyramids.

FIG. 38. Derivation of the subordinate series of scalene four-sided pyramids.




Fig. 37.






Fig. 38.














VOL. I. PLATE VIII.

FIG. 39. Derivation of scalene four-sided pyramids, having a dissimilar transverse section, from the auxiliary form.

FIG. 40. Derivation of scalene four-sided pyramids, having a dissimilar transverse section, from the fundamental form.




Fig. 39.






Fig. 40.









VOL. I. PLATE IX.

- FIG. 41. P. Fundamental pyramid of the hemiprismatic system.
- FIG. 42. P. Fundamental pyramid of the tetartoprismatic system.
- FIG. 43. Derivation of two subsequent rhombohedrons from each other.
- FIG. 44. Transverse sections of four consecutive rhombohedrons, having the same horizontal projection.



Fig. 41.




Fig. 41




Fig. 42.






Fig. 43.





VOL. I PLATE X

- Fig. 45. Division of leaflets of *Pinus strobus* L.  
with
- Fig. 46. Division of the rhomboid leaflets  
of *Pinus strobus* L. (a regular rhomboid  
leaflet)
- Fig. 47. Division of leaflets of *Pinus strobus* L.  
with
- Fig. 48. Division of leaflets of *Pinus strobus* L.  
producing 1/2 and 1/3 the area of  
a rhomboid leaflet
- Fig. 49. Division of leaflets of *Pinus strobus* L.  
with



VOL. I. PLATE X.

FIG. 45. Derivation of isosceles four-sided pyramids.

FIG. 46. Derivation of the rhombohedron with an infinite axis (a regular six-sided prism).

FIG. 47. Derivation of scalene six-sided pyramids.

FIG. 48. Derivation of isosceles six-sided pyramids.

FIG. 49. Combination of two rhombohedral forms, producing  $EF$  and  $E'F'$ , the *Lines of Combination*.

FIG. 50. Similar combination of three rhombohedral forms.

Fig. 45.




Fig. 46.




Fig. 47.




Fig. 48.




Fig. 49.






Fig. 50.







VOL. I. PLATE 22

Fig. 1. *A. diplopoda*

Fig. 2. *A. diplopoda* (larva)

Fig. 3. *A. diplopoda* (larva)

Fig. 4. *A. diplopoda* (larva)

Fig. 5. *A. diplopoda* (larva)

Fig. 6. *A. diplopoda* (larva)

Fig. 7. *A. diplopoda* (larva)

Fig. 8. *A. diplopoda* (larva)

Fig. 9. *A. diplopoda* (larva)

Fig. 10. *A. diplopoda* (larva)

Fig. 11. *A. diplopoda* (larva)

VOL. I. PLATE XI.

FIG. 51.  $2 (P)^m$ . A di-pyramid.  
 $a, a', b, b'$

FIG. 52.  $\pm \frac{R}{2} \left\{ \begin{matrix} a' \\ a \end{matrix} \right\}$ . A three sided pyramid,  
 formed by alternating pairs of faces of  
 a di-rhombohedron.

FIG. 53.  $\frac{r}{r} \frac{(P)^m}{2} \left\{ \begin{matrix} a \\ a \end{matrix} \right\}$ . A right three-sided trape-  
 zohedron, containing on both ends  
 faces of the same pyramid.

FIG. 54.  $\frac{l}{l} \frac{(P)^m}{2} \left\{ \begin{matrix} b \\ b \end{matrix} \right\}$ . A left three-sided trape-  
 zohedron of the same kind.

FIG. 55.  $\frac{+r}{-r} \frac{(P)^m}{2} \left\{ \begin{matrix} a \\ a' \end{matrix} \right\}$ . A right three-sided tra-  
 pezohedron, the pyramid from which  
 the lower faces are derived being in  
 inverse position from that to which  
 the upper ones belong.

FIG. 56.  $\frac{+l}{-l} \frac{(P)^m}{2} \left\{ \begin{matrix} b \\ b' \end{matrix} \right\}$ . A left three-sided trape-  
 zohedron of the same kind.

Fig. 51.




Fig. 52




Fig. 53




Fig. 54




Fig. 55






Fig. 56







VOI. I. PLATE XII

Fig. 27.  $\frac{A \cdot 2 (C^2)}{B}$  [?] [?]

Fig. 28.  $\frac{A \cdot 1 (C^2)}{B}$  [?] [?]

Fig. 29. [?] [?] [?] [?] [?] [?]

Fig. 30. [?] [?] [?] [?] [?] [?]

Fig. 31. [?] [?] [?] [?] [?] [?]

Fig. 32. [?] [?] [?] [?] [?] [?]

VOL. I. PLATE XII.

FIG. 57.  $\frac{r}{r} \frac{2 ((P)^m)}{2} \left\{ \begin{matrix} a \\ a' \end{matrix} \right\}$ . A right six-sided trapezohedron.

FIG. 58.  $\frac{l}{l} \frac{2 ((P)^m)}{2} \left\{ \begin{matrix} b \\ b' \end{matrix} \right\}$ . A left six-sided trapezohedron.

FIG. 59. Rhombohedral combination.

$$R - 1. (P - 2)^5. R. \frac{5}{4}R. R + 1. (P)^5. R + \infty.$$

$$a \quad b \quad c \quad d \quad e \quad f \quad g$$

FIG. 60. Di-rhombohedral combination.

$$R - \infty. P. 2 (R). P + 1. P + \infty.$$

$$a \quad b \quad c \quad d \quad e$$

FIG. 61.  $\frac{P}{2}$ . A hemi-pyramidal form, analogous to the tetrahedron.

FIG. 62. —  $\frac{P}{2}$ . The same, in inverse position.



Fig. 57




Fig. 58




Fig. 59




Fig. 60




Fig. 61






Fig. 62











VOL. I. PLATE XIII.

FIG. 63.  $\frac{r}{r} \frac{(P)^m}{2}$ . A right four-sided trapezohedron.

FIG. 64.  $\frac{l}{l} \frac{(P)^m}{2}$ . A left four-sided trapezohedron.

FIG. 65.  $\frac{(P)^m}{2}$ . A hemi-pyramidal form, analogous to the tetrahedron, obtained from a scalene eight-sided pyramid.

FIG. 66. —  $\frac{(P)^m}{2}$ . The same, in inverse position.

FIG. 67. Pyramidal combination.  
 $P.$   $P + 1.$   $(P)^5.$   $P + \infty.$   $[P + \infty].$   
 $a$   $b$   $c$   $d$   $e$

FIG. 68. Pyramidal combination.  
 $P.$   $(P)^5.$   $\frac{3}{2\sqrt{2}}P + 3.$   $P + \infty.$   $[P + \infty].$   
 $a$   $c$   $f$   $d$   $e$

Fig. 63.




Fig. 64.




Fig. 65.




Fig. 66.




Fig. 67.






Fig. 68.







Vol. 1 - Development of agriculture in  
Vol. 2 - Development of agriculture in  
Vol. 3 - Development of agriculture in  
Vol. 4 - Development of agriculture in  
Vol. 5 - Development of agriculture in  
Vol. 6 - Development of agriculture in  
Vol. 7 - Development of agriculture in  
Vol. 8 - Development of agriculture in  
Vol. 9 - Development of agriculture in  
Vol. 10 - Development of agriculture in

VOL. I. PLATE XIV.

FIG. 69. and 70. Developements of pyramidal combinations.

FIG. 71. Development of a prismatic combination.

FIG. 72. Prismatic combination.

$$\begin{array}{cccc}
 \text{Pr} - 1. & \text{P} - 1. & \check{\text{Pr}}. & (\check{\text{Pr}} - 1)^2. \\
 a & b & c & d \\
 \text{P}. & \text{P} + \infty. & (\check{\text{Pr}} + \infty)^2. & \check{\text{Pr}} + \infty. \\
 e & f & g & h
 \end{array}$$

FIG. 73. and 74. Explanation of the horizontal striæ upon the faces of the six-sided prism of rhombohedral Quartz.

Fig. 69.




Fig. 70.




Fig. 71.




Fig. 72.




Fig. 73.





Fig. 74.








PLATE VI

Fig. 1. *...*

with parallel lines

Fig. 2. *...*

with parallel lines

Fig. 3. *...*

with parallel lines

Fig. 4. *...*

with parallel lines

Fig. 5. *...*

with parallel lines

Fig. 6. *...*

with parallel lines

Fig. 7. *...*

with parallel lines

Fig. 8. *...*

VOL. I. PLATE XV.

FIG. 75.  $\frac{A_2}{2}$ .  $\frac{T_1}{2}$ . Semi-tessular combination  
 $e$   $f$   
 with parallel faces.

FIG. 76. —  $\frac{A_2}{2}$ .  $\frac{T_1}{2}$ . Semi-tessular combination  
 $e'$   $f$   
 with parallel faces.

FIG. 77.  $\frac{O}{2}$ .  $\frac{C_1}{2}$ . Semi-tessular combination  
 $P$   $l$   
 with inclined faces.

FIG. 78.  $\frac{O}{2}$ . —  $\frac{C_1}{2}$ . Semi-tessular combination  
 $P$   $r$   
 with inclined faces.

FIG. 79. The saddle-shaped lens.

FIG. 80. A rhombohedron with curved faces,  
 produced by composition.



Fig. 75.




Fig. 76.




Fig. 77.




Fig. 78.




Fig. 79.






Fig. 80.











VOL. II. PLATE I.

FIG. 1. Axotomous Arsenical-pyrites.

$\check{P}r.$   $P + \infty.$   
*o* *d*

FIG. 2. Prismatic Arsenical-pyrites.

$\check{P}r - 1.$   $P + \infty.$   
*r* *M*

FIG. 3. Prismatic Andalusite.

$P - \infty.$   $\check{P}r.$   $P + \infty.$   
*P* *l* *M*

FIG. 4. Di-prismatic Iron-ore.

$\check{P}r.$   $P.$   $P + \infty.$   
*P* *o* *M*

FIG. 5. Di-prismatic Olive-malachite.

$\check{P}r.$   $P.$   $P + \infty.$   
*o* *P* *u*

FIG. 6. Prismatic Epsom-salt.

$P.$   $P + \infty.$   $\check{P}r + \infty.$   
*l* *M* *o*

Fig. 1.




Fig. 2.




Fig. 3.




Fig. 4.




Fig. 5.





Fig. 6.










PLATE II

- Fig. 1. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 2. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 3. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 4. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 5. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 6. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 7. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 8. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 9. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 10. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 11. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 12. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 13. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 14. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$
- Fig. 15. *Formica ruginiventris*  
 $P = 1.5$ ,  $W = 1.5$   
 $L = 1.5$

VOL. II. PLATE II.

FIG. 7. Prismatic Melane-glance.

$$P. (\check{P}r + \infty)^5. \check{P}r + \infty.$$

$$P \quad d \quad s$$

FIG. 8. Prismatic Olive-malachite.

$$\check{P}r. P + \infty. \check{P}r + \infty.$$

$$l \quad r \quad n$$

FIG. 9. Prismatic Nitre-salt.

$$\check{P}r + 1. P + \infty. \check{P}r + \infty$$

$$P \quad M \quad h$$

FIG. 10. Prismatic Kouphone-spar.

$$P - \infty. P. \check{P}r + \infty. \check{P}r + \infty.$$

$$P \quad r \quad T \quad M$$

FIG. 11. Axotomous Kouphone-spar.

$$P - \infty. P. \check{P}r + \infty. \check{P}r + \infty.$$

$$P \quad r \quad M \quad T$$

FIG. 12. Prismatic Garnet.

$$P - \infty. \check{P}r. (\check{P}r + \infty)^5. \check{P}r + \infty.$$

$$P \quad r \quad M \quad o$$

Fig. 7.




Fig. 8.




Fig. 9.




Fig. 10.




Fig. 11.






Fig. 12.







VOL. II. PART II.

- 1. The first part of the book is devoted to a general survey of the subject.
- 2. The second part is devoted to a detailed examination of the various aspects of the subject.
- 3. The third part is devoted to a critical analysis of the various theories and opinions.
- 4. The fourth part is devoted to a comparison of the various theories and opinions.
- 5. The fifth part is devoted to a summary of the results of the investigation.
- 6. The sixth part is devoted to a discussion of the practical applications of the subject.
- 7. The seventh part is devoted to a conclusion of the work.







Fig.13.




Fig.14.




Fig.15.




Fig.16.




Fig.17.






Fig.18.





VOL. II. PLATE IV.

Fig. 18. Secondary  
 E - of E. P. + 1 (P. + 2)  
 2  
 3  
 P. + 3

Fig. 19. Primaries Chrysoidea  
 P. P. - 1, P. P. - 2, P. P. - 3  
 4  
 5  
 P. P. - 6, P. P. - 7, P. P. - 8  
 9  
 10  
 P. P. - 11, P. P. - 12, P. P. - 13  
 14  
 15  
 P. P. - 16, P. P. - 17, P. P. - 18  
 19  
 20  
 P. P. - 21, P. P. - 22, P. P. - 23  
 24  
 25  
 P. P. - 26, P. P. - 27, P. P. - 28  
 29  
 30  
 P. P. - 31, P. P. - 32, P. P. - 33  
 34  
 35  
 P. P. - 36, P. P. - 37, P. P. - 38  
 39  
 40  
 P. P. - 41, P. P. - 42, P. P. - 43  
 44  
 45  
 P. P. - 46, P. P. - 47, P. P. - 48  
 49  
 50



VOL. II. PLATE IV.

FIG. 19. Scorodite.




FIG. 20. Prismatic Chrysolite.




FIG. 21. Prismatic Hal-baryte.




FIG. 22. Paratomous Kouphone-spar.




FIG. 23. Prismatic Nitre-salt.




FIG. 24. Di-prismatic Copper-glance.




Fig. 19.




Fig. 20.




Fig. 21.




Fig. 22.




Fig. 23.






Fig. 24.







VOL. II. PLATE V.

Fig. 23. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 24. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 25. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 26. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 27. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 28. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 29. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10  
Fig. 30. *Trinacria* *Trinacria*  
Pl. 1. (P. 2) 11 + 2 Pl. 2  
10

VOL. II. PLATE V.

FIG. 25. Prismatic Corundum.

$$\begin{array}{ccccccc} \check{P}r. & P. & (\check{P} + \infty)^5. & \check{P}r + \infty. & \check{P}r + \infty. & & \\ i & o & s & T & M & & \end{array}$$

FIG. 26. Prismatic Gypsum-haloide.

$$\begin{array}{ccccccc} P - \infty. & P. & (\check{P}r)^5. & (\check{P})^5. & \check{P}r + \infty. & & \\ P & o & n & f & T & & \\ \check{P}r + \infty. & & & & & & \\ & & & & & & M \end{array}$$

FIG. 27. Prismatoidal Manganese-ore.

$$\begin{array}{ccccccc} P - \infty. & \check{P}r. & P. & (\check{P}r - 1)^5. & P + \infty. & & \\ o & d & P & y & M & & \\ (\check{P}r + \infty)^5. & & & & & & \\ & & & & & & s \end{array}$$

FIG. 28. Peritomous Hal-baryte.

$$\begin{array}{ccccccc} P - \infty. & P - 1. & P. & \check{P}r + 1. & P + \infty. & & \\ o & z & y & P & M & & \\ \check{P}r + \infty. & & & & & & \\ & & & & & & h \end{array}$$

FIG. 29. Hopeite.

$$\begin{array}{ccccccc} P - \infty. & \check{P}r. & P. & (\check{P}r + \infty)^5. & \check{P}r + \infty. & & \\ g & M & P & s & p & & \\ \check{P}r + \infty. & & & & & & \\ & & & & & & l \end{array}$$

FIG. 30. Prismatic Melane-glance.

$$\begin{array}{ccccccc} \check{P}r. & P. & (\check{P}r)^5. & (\check{P}r + \infty)^5. & \check{P}r + \infty. & & \\ o & P & a & d & p & & \\ \check{P}r + \infty. & & & & & & \\ & & & & & & s \end{array}$$



Fig. 25.




Fig. 26.




Fig. 27.




Fig. 28.




Fig. 29.






Fig. 30.







VOL. II PLATE VI

Fig. 51. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$

Fig. 52. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$

Fig. 53. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$

Fig. 54. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$

Fig. 55. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$

Fig. 56. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$

Fig. 57. *Prasinella* *Prasinella*

$P_1 - P_2 = P_1 - P_2$   
 $(P_1 + P_2)$





Fig. 31.




Fig. 32.




Fig. 33.




Fig. 34.




Fig. 35.






Fig. 36.





1874

1875

1876

1877

1878

1879

1880

1881

1882

1883

1884

1885

1886

1887

1888



VOL. II. PLATE VII.

FIG. 37. Prismatic Zinc-baryte.




FIG. 38. Di-prismatic Lead-baryte.




FIG. 39. Prismatic Lime-haloide.




FIG. 40. Paratomous Kouphone-spar.




FIG. 41. Prismatic Copper-glance.




Fig. 37.




Fig. 38.




Fig. 39.





Fig. 40.






Fig. 41.









VOL. II. PLATE VIII.

FIG. 42. Prismatic Iron-pyrites.

$$\text{Pr. } P + \infty. \quad \check{\text{Pr}} + \infty, \quad \left\{ \text{Pr} \right\} \left\{ \text{Pr} \right\}.$$

$$M \quad l \quad P$$

FIG. 43. Prismatic Iron-pyrites.

$$\check{\text{Pr.}} \check{\text{Pr.}} P + \infty. \quad \check{\text{Pr}} + \infty, \quad \left\{ \check{\text{Pr}} \right\} \left\{ \check{\text{Pr}} \right\}.$$

$$g \quad M \quad l \quad P$$

FIG. 44. Diatomous Kouphone-spar.

$$\frac{\check{\text{Pr}}}{2}. \quad P + \infty.$$

$$P \quad M$$

FIG. 45. Hemi-prismatic Natron-salt.

$$\frac{P}{2}. \quad (\check{\text{Pr}} + \infty)^3. \quad \text{Pr} + \infty.$$

$$P \quad M \quad l$$

FIG. 46. Prismatic Cobalt-mica.

$$\frac{\check{\text{Pr}}}{2}. \quad \check{\text{Pr}} + \infty. \quad \text{Pr} + \infty.$$

$$M \quad T \quad P$$

FIG. 47. Prismatic Titanium-ore.

$$\frac{\text{Pr}}{2}. \quad \frac{P}{2}. \quad - \quad \frac{\check{\text{Pr}}}{2}. \quad (\check{\text{Pr}} + \infty)^3.$$

$$P \quad r \quad y \quad n$$

Fig. 42.




Fig. 43.




Fig. 44.




Fig. 45.




Fig. 46.






Fig. 47.







VOL. III. PLATE IX.

Fig. 48. *Formica ruginosa* (F.)  
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$   
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$

Fig. 49. *Formica ruginosa* (F.)  
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$   
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$

Fig. 50. *Formica ruginosa* (F.)  
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$   
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$

Fig. 51. *Formica ruginosa* (F.)  
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$   
 $\frac{1}{2} (p + q) - \frac{1}{2} (p + q)$

VOL. II. PLATE IX.

FIG. 48. Hemi-prismatic Sulphur.

$$-\frac{\check{P}r}{2} \quad -\frac{P}{2} \quad P + \infty. \quad (\check{P}r + \infty)^5.$$

*P*            *n*            *M*            *l*

FIG. 49. Prismatic Scheelium-ore.

$$\frac{\check{P}r - 1}{2} \quad \check{P}r. \quad -\frac{\check{P}r - 1}{2} \quad P + \infty.$$

*t*            *u*            *t'*            *r*

$\check{P}r + \infty.$   
*M*

FIG. 50. Hemi-prismatic Kouphone-spar.

FIG. 51. Prismatic Borax-salt.

$$\frac{P}{2} \quad (\check{P}r)^5 \quad -\frac{\check{P}r}{2} \quad (\check{P}r + \infty)^5. \quad \check{P}r + \infty.$$

*o*            *z*            *P*            *r*            *M*

$\check{P}r + \infty.$   
*T*

FIG. 52. Hemi-prismatic Vitriol-salt.

$$P - \infty. \quad \frac{\frac{4}{3}P - 2}{2} \quad \frac{\check{P}r}{2} \quad \frac{P}{2} \quad \check{P}r. \quad -\frac{\check{P}r}{2}$$

*b*            *g*            *v*            *P*            *o*            *t*

$P + \infty. \quad \check{P}r + \infty.$   
*f*            *u*

FIG. 53. Hemi-prismatic Lead-baryte.

$$\frac{\check{P}r}{2} \quad \frac{P}{2} \quad -\frac{P}{2} \quad P + \infty. \quad (\check{P}r + \infty)^4.$$

*k'*            *t*            *v*            *M*            *r*

$\check{P}r + \infty.$   
*g*



Fig. 48.




Fig. 49




Fig. 50.




Fig. 51.




Fig. 52.




Fig. 53.






Fig. 54. Rhombic Enantiomorph

The rhombic enantiomorph from the crystal  
 250 F. L. P. P. (185) the crystal  
 that from the crystal in the crystal of  
 250 F. L. P. P. (185)

Fig. 55. Rhombic Enantiomorph

$$E = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$a = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$b = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$c = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$d = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

Fig. 56. Rhombic Enantiomorph

$$E = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$a = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$b = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$c = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$d = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

Fig. 57. Rhombic Enantiomorph

$$E = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$a = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$b = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$c = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$d = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

Fig. 58. Rhombic Enantiomorph

$$E = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$a = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$b = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$

$$c = \frac{1}{2} (a + b) + \frac{1}{2} (c + d)$$

$$d = \frac{1}{2} (a + b) - \frac{1}{2} (c + d)$$



VOL. II. PLATE X.

FIG. 54. Prismatic Emerald.

The elevation copied from HAÜY, *Traité*, 2de Ed. Pl. 72. Fig. 153., the projection from the crystal in the cabinet of M. DE DRÉE.

FIG. 55. Prismatic Glauber-salt.

$$\frac{P}{2} - \frac{\check{P}r}{2} - \frac{P}{2} \quad (\check{P}r + \infty)^5. \quad \check{P}r + \infty.$$

$$n \quad T \quad z \quad o \quad M$$

$$\check{P}r + \infty.$$

$$P$$

FIG. 56. Prismatic Glauber-salt.

$$P - \infty. \quad \frac{\check{P}r}{2} \quad \frac{P}{2} \quad \check{P}r - 1. \quad - \frac{\check{P}r}{2} \quad - \frac{P}{2}$$

$$l \quad r \quad n \quad y \quad T \quad z$$

$$- \frac{(\check{P}r)^5}{2} \quad - \frac{\check{P}r + 1}{2} \quad - \frac{(\check{P})^5}{2}$$

$$v \quad w \quad d$$

$$(\check{P}r + \infty)^5. \quad \check{P}r + \infty. \quad \check{P}r + \infty.$$

$$o \quad M \quad P$$

FIG. 57. Prismatoidal Gypsum-haloide.

$$\frac{Pl}{2} \quad P + \infty. \quad \check{P}r + \infty.$$

$$l \quad f \quad P$$

FIG. 58. Prismatoidal Gypsum-haloide.

$$\frac{P}{2} - \frac{\frac{4}{3}\check{P}r - 2}{2} \quad P + \infty. \quad (\check{P}r + \infty)^5.$$

$$l \quad o \quad f \quad h$$

$$\check{P}r + \infty.$$

$$P$$

Fig. 54.





Fig. 55.




Fig. 56.




Fig. 57.






Fig. 58.









VOL. II. PART II.

The first part of the book is devoted to a general introduction to the subject of the history of the world, and to a description of the various nations and peoples which have inhabited it. The second part is devoted to a detailed account of the history of the world, from the beginning of time to the present day. The third part is devoted to a description of the various nations and peoples which have inhabited the world, and to a description of their customs, manners, and institutions. The fourth part is devoted to a description of the various nations and peoples which have inhabited the world, and to a description of their customs, manners, and institutions.

VOL. II. PLATE XI.

FIG. 59. Prismatic Brithyne-salt.

$$P - \infty. \frac{P}{2}.$$

$$P \quad f$$

FIG. 60. Prismatic Brithyne-salt.

$$P - \infty. \frac{P}{2} - \frac{\check{P}r}{2} - \frac{P}{2} - \frac{(\check{P}r)^5}{2}.$$

$$P \quad f \quad t \quad n \quad e$$

$$P + \infty. \check{P}r + \infty.$$

$$M \quad s$$

FIG. 61. Prismatic Feld-spar.

$$\frac{\frac{3}{4}\check{P}r + 2}{2} - \frac{\check{P}r}{2} (\check{P}r + \infty)^5. \check{P}r + \infty.$$

$$y \quad P \quad T \quad l \quad M$$

FIG. 62. Prismatic Feld-spar.

$$\frac{\frac{4}{3}\check{P}r - 2}{2} \cdot \frac{\check{P}r}{2} \cdot \frac{P}{2} \cdot \frac{\frac{5}{4}\check{P}r + 2}{2} - \frac{\check{P}r}{2}$$

$$q \quad x \quad s \quad y \quad P$$

$$(\check{P}r + \infty)^5. (\check{P}r + \infty)^5. \check{P}r + \infty.$$

$$T \quad l \quad z \quad z \quad M$$

FIG. 63. Prismatic Azure-malachite.

$$P - \infty. \frac{(\check{P}r - 1)^7}{2} (\check{P}r + \infty)^5. \check{P}r + \infty.$$

$$s \quad d \quad P \quad h$$

FIG. 64. Prismatic Azure-malachite.

$$P - \infty. \frac{\check{P}r}{2} \cdot \frac{P}{2} \cdot \check{P}r - \frac{(\check{P}r - 1)^5}{2}$$

$$s \quad a \quad x \quad M \quad k$$

$$Pr + \infty.$$

$$h$$

Fig. 59.




Fig. 60.




Fig. 61.




Fig. 62.




Fig. 63.







Fig. 64.







VOL. II. PLATE XII.

FIG. 62. Prismatic Axis vertical.

$$P - \alpha \frac{Pr}{Pr - 1} \frac{(Pr - 1)}{(Pr - 1)}$$

$$P + \alpha \frac{(Pr + \alpha)}{(Pr + \alpha)}$$

FIG. 63. Prismatic Axis vertical.

$$P - \alpha \frac{Pr}{Pr - 1} \frac{(Pr - 1)}{(Pr - 1)}$$

$$P + \alpha \frac{(Pr + \alpha)}{(Pr + \alpha)}$$

FIG. 64. Prismatic Axis vertical.

$$P - \alpha \frac{Pr}{Pr + 1} \frac{(Pr + 1)}{(Pr + 1)}$$

$$P + \alpha \frac{(Pr + \alpha)}{(Pr + \alpha)}$$

FIG. 65. Prismatic Axis vertical.

$$P - \alpha \frac{Pr}{Pr + 1} \frac{(Pr + 1)}{(Pr + 1)}$$

$$P + \alpha \frac{(Pr + \alpha)}{(Pr + \alpha)}$$

FIG. 66. Prismatic Axis vertical.

$$P - \alpha \frac{Pr}{Pr + 1} \frac{(Pr + 1)}{(Pr + 1)}$$

$$P + \alpha \frac{(Pr + \alpha)}{(Pr + \alpha)}$$

VOL. II. PLATE XII.

FIG. 65. Prismatic Azure-malachite.

$$P - \infty. \frac{\text{Pr}}{2}. \text{Pr.} - \frac{\text{Pr}-1}{2}. - \frac{(\text{Pr}-1)^3}{2}.$$

*s*      *a*      *M*      *b*      *k*

$$(\text{Pr} + \infty)^3. (\text{Pr} + \infty)^5. \text{Pr} + \infty.$$

*P*      *l*      *h*

FIG. 66. Prismatic Azure-malachite.

$$P - \infty. \frac{\text{Pr}}{2}. \frac{P}{2}. \frac{(\text{Pr}-1)^7}{2}. \frac{(\text{Pr}-1)^6}{2}.$$

*s*      *a*      *x*      *d*      *e*

$$\text{Pr} - 1. \text{Pr.} - \frac{(\text{Pr}-1)^5}{2}. - \frac{\text{Pr}}{2}.$$

*g*      *M*      *k*      *c*

$$P + \infty. (\text{Pr} + \infty)^3. (\text{Pr} + \infty)^5. \text{Pr} + \infty.$$

*f*      *P*      *l*      *h*

FIG. 67. Prismatic Dystome-spar.

$$P - \infty. \frac{P}{2}. \frac{\text{Pr} + 1}{2}. \text{Pr} + 1. P + \infty.$$

*b*      *P*      *a*      *o*      *f*

$$(\text{Pr} + \infty)^3. \text{Pr} + \infty.$$

*g*      *s*

FIG. 68. Prismatic Dystome-spar.

$$P - \infty. \frac{P}{2}. \frac{\text{Pr} + 1}{2}. \text{Pr.} - \frac{(\text{Pr})^3}{2}.$$

*b*      *P*      *a*      *d*      *e*

$$P + \infty. (\text{Pr} + \infty)^3.$$

*f*      *g*

FIG. 69. Prismatic Dystome-spar.

$$P - \infty. \frac{P}{2}. \frac{\text{Pr} + 1}{2}. \frac{(\text{Pr})^5}{2}. \text{Pr.}$$

*b*      *P*      *a*      *q*      *d*

$$\text{Pr} + 1. - \frac{P}{2}. - \frac{(\text{Pr})^3}{2}. - \frac{(\text{Pr})^5}{2}.$$

*o*      *n*      *e*      *i*

$$P + \infty. (\text{Pr} + \infty)^3. \text{Pr} + \infty.$$

*f*      *g*      *u*



Fig. 65.




Fig. 66.




Fig. 67.




Fig. 68.







Fig. 69.











VOL. II. PLATE XIII.

FIG. 70. Prismatic Dystome-spar.

$$\begin{array}{cccc}
 P - \infty & \frac{P}{2} & \frac{\check{P}r + 1}{2} & \frac{(P\check{r})^5}{2} & P\check{r} \\
 b & P & a & q & d \\
 \frac{3}{4} P\check{r} + 1 & P\check{r} + 1 & - \frac{P}{2} & - \frac{(P\check{r})^5}{2} & \\
 \frac{r}{2} & \frac{o}{2} & \frac{n}{2} & \frac{e}{2} & \\
 - \frac{(P-1)^5}{2} & - \frac{(P\check{r})^5}{2} & - \frac{(P\check{r})^5}{2} & - \frac{(P\check{r})^4}{2} & \\
 - \frac{(P\check{r} + 1)^5}{2} & - \frac{(P\check{r})^5}{2} & P + \infty & & \\
 h & m & f & & \\
 (\check{P}r + \infty)^5 & & & & \\
 g & & & & 
 \end{array}$$

FIG. 71. Prismatic Habroneme-malachite.

$$\begin{array}{cccc}
 P - \infty & \frac{\check{P}r - 1}{2} & \frac{P}{2} & P\check{r} & - \frac{\check{P}r - 1}{2} \\
 a & b & P & o & b \\
 - \frac{(P\check{r} - 1)^5}{2} & (P\check{r} + \infty)^5 & \check{P}r + \infty & & \\
 d & f & e & & 
 \end{array}$$

FIG. 72. Paratomous Augite-spar.

$$\begin{array}{cccc}
 \frac{P}{2} & (P\check{r} + \infty)^5 & \check{P}r + \infty & P\check{r} + \infty \\
 s & M & r & l
 \end{array}$$

FIG. 73. Paratomous Augite-spar.

$$\begin{array}{cccc}
 \frac{\check{P}r}{2} & \frac{P}{2} & \frac{(P\check{r})^5}{2} & - \frac{\check{P}r}{2} & - \frac{(P\check{r})^5}{2} \\
 P & s & o & t & z \\
 (\check{P}r + \infty)^5 & & & & \\
 M & & & & 
 \end{array}$$

Fig. 70.




Fig. 71.




Fig. 72.






Fig. 73.







VOL. II. PLATE XIV.

Fig. 14. Hemiphragmatis A. g. sp. nov.

$$\frac{P}{2} - \frac{P_1}{2} = \frac{(P_1 + \infty)^2}{2} - \frac{P_1 + \infty}{2}$$

Fig. 15. Frimataloides A. g. sp. nov.

$$\frac{P_1}{2} - \frac{P}{2} = \frac{P_1}{2} - \frac{P_1 + \infty}{2}$$

Fig. 16. Hemiphragmatis A. g. sp. nov.

$$\frac{P}{2} - \frac{P_1}{2} = \frac{P_1 + \infty}{2} - \frac{(P_1)^2}{2}$$

$$\frac{P_1 + \infty}{2} - \frac{(P_1)^2}{2} = \frac{P_1 + \infty}{2}$$

Fig. 17. Frimataloides A. g. sp. nov.

$$\frac{P_1}{2} - \frac{P}{2} = \frac{P_1}{2} - \frac{P_1 + \infty}{2}$$

$$\frac{P_1}{2} - \frac{P_1 + \infty}{2} = \frac{P_1}{2} - \frac{P_1 + \infty}{2}$$

$$\frac{P_1 + \infty}{2} - \frac{P_1 + \infty}{2} = 0$$

VOL. II. PLATE XIV.

FIG. 74. Hemi-prismatic Augite-spar.

$$\frac{P}{2} - \frac{\check{P}r}{2} \quad (\check{P}r + \infty)^5 \quad Pr + \infty.$$

*r*            *P*            *M*                    *x*

FIG. 75. Prismatoidal Augite-spar.

$$\frac{\check{P}r}{2} \quad \frac{P}{2} - \frac{\check{P}r}{2} \quad \check{P}r + \infty.$$

*r*    *n*            *T*            *M*

FIG. 76. Hemi-prismatic Augite-spar.

$$\frac{P}{2} \quad \frac{\frac{3}{4}\check{P}r + 2}{2} \quad \frac{(\check{P}r)^5}{2} \quad \frac{(P)^5}{2} - \frac{\check{P}r}{2}$$

*r*            *t*            *a*            *i*            *P*

$$- \frac{(\check{P}r)^5}{2} \quad - \frac{(\check{P})^5}{2} \quad - \frac{\frac{3}{4}P + 2}{2}$$

*z*            *k*                            *b*

$$(\check{P}r + \infty)^5 \quad (\check{P}r + \infty)^5 \quad \check{P}r + \infty.$$

*M*                            *c*                            *s*

*Pr + \infty.*

*x*

FIG. 77. Prismatoidal Augite-spar.

$$P - \infty \quad \frac{\check{P}r}{2} \quad \frac{P}{2} \quad \frac{(\check{P})^5}{2} \quad \check{P}r - 1 \quad Pr.$$

*l*            *r*    *n*            *x*                            *y*                            *q*

$$- \frac{\check{P}r}{2} \quad - \frac{(\check{P}r - 1)^5}{2} \quad - \frac{P}{2} \quad - \frac{(\check{P})^5}{2}$$

*T*                            *u*                            *z*                            *d*

$$(\check{P}r + \infty)^5 \quad \check{P}r + \infty.$$

*o*                            *M*

Fig. 74.




Fig. 75.




Fig. 76.








Fig. 77.







- Fig. 76. Rhombic prismatic trichonema-muscularis.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 77. Rhombic Feldspar.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 78. Rhombic Feldspar.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 79. Rhombic Feldspar.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 80. Rhombic Feldspar.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 81. Rhombic Feldspar.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 82. Rhombic Diabase spar.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$
- Fig. 83. Tetarto-prismatic Vitriol salt.  

$$\frac{1}{2} \frac{Pr + \infty}{2} \left\{ \frac{1}{2} Pr + \infty \right\}$$

VOL. II. PLATE XV.

FIG. 78. Hemi-prismatic Habroneme-malachite.

$$- \frac{\text{Pr}}{2} \cdot P + \infty \cdot \text{Pr} + \infty \cdot \{ \text{Pr} + \infty \}.$$

*p*                      *M*                      *s*

FIG. 79. Prismatic Feld-spar.

$$\frac{\check{\text{Pr}}}{2} \cdot \frac{P}{2} \cdot \frac{\frac{3}{4}\check{\text{Pr}} + 2}{2} - \frac{\check{\text{Pr}}}{2} \cdot (\check{\text{Pr}} + \infty)^3.$$

*x*                      *s*                      *y*                      *P*                      *T l*

$$\text{Pr} + \infty \cdot \left\{ -l \frac{(\text{Pr})^3}{4} \right\}.$$

*M*

FIG. 80. Prismatic Feld-spar.

$$\frac{\frac{3}{4}\check{\text{Pr}} + 2}{2} - \frac{\check{\text{Pr}}}{2} \cdot (\check{\text{Pr}} + \infty)^3 \cdot \text{Pr} + \infty.$$

*y*                      *P*                      *T l*                      *M*

$$\left\{ r \text{Pr} + \infty : \check{\text{Pr}} + \infty \cdot \text{Pr} + \infty \right\}.$$

FIG. 81. Prismatic Feld-spar.

$$\frac{\frac{3}{4}\check{\text{Pr}} + 2}{2} - \frac{\check{\text{Pr}}}{2} \cdot (\check{\text{Pr}} + \infty)^3 \cdot \text{Pr} + \infty.$$

*y*                      *P*                      *T l*                      *M*

$$\left\{ l \text{Pr} + \infty : \check{\text{Pr}} + \infty \cdot \text{Pr} + \infty \right\}.$$

FIG. 82. Prismatic Disthene-spar.

$$\frac{\check{\text{Pr}}}{2} \cdot r \frac{P + \infty}{2} \cdot \text{Pr} + \infty.$$

*P*                      *T*                      *M*

FIG. 83. Tetarto-prismatic Vitriol-salt.



Fig. 78.




Fig. 79.




Fig. 80.




Fig. 81.




Fig. 82.





Fig. 83.








Fig. 84. Albin.

$$\frac{P_1}{P_2} = \frac{P_1}{P_2} \cdot \frac{(P_1 + \infty)}{(P_1 + \infty)}$$

Fig. 85. Albin.

$$\frac{P_1}{P_2} = \frac{P_1}{P_2} \cdot \frac{(P_1 + \infty)}{(P_1 + \infty)}$$

Fig. 86. Albin.

$$\frac{P_1}{P_2} = \frac{P_1}{P_2} \cdot \frac{(P_1 + \infty)}{(P_1 + \infty)}$$

Fig. 87. Albin.

$$\frac{P_1}{P_2} = \frac{P_1}{P_2} \cdot \frac{(P_1 + \infty)}{(P_1 + \infty)}$$

$$P_1 + \infty \{ P_1 + \infty \}$$

M



VOL. II. PLATE XVI.

FIG. 84. Albite.

$$\frac{\check{P}r}{2} \cdot r \frac{P}{4} - \frac{\check{P}r}{2} \cdot r \frac{(\check{P}r + \infty)^3}{2}$$

$$x \quad s \quad P \quad l$$

$$l \frac{(\check{P}r + \infty)^5}{2} \cdot \check{P}r + \infty.$$

$$T \quad M$$

FIG. 85. Albite.

$$\frac{\check{P}r}{2} \cdot r \frac{P}{4} \cdot \frac{\frac{5}{4} \check{P}r + 2}{2} \cdot r \frac{\check{P}r - 1}{2} - \frac{\check{P}r}{2}$$

$$x \quad s \quad y \quad g \quad P$$

$$- r \frac{(\check{P}r)^5}{4} \cdot r \frac{(\check{P}r + \infty)^5}{2} \cdot l \frac{(\check{P}r + \infty)^5}{2}$$

$$n \quad l \quad T$$

$$r \frac{(\check{P}r + \infty)^5}{2} \cdot l \frac{(\check{P}r + \infty)^5}{2} \cdot \check{P}r + \infty.$$

$$z \quad z' \quad M$$

FIG. 86. Albite.

$$\frac{\check{P}r}{2} \cdot r \frac{P}{4} \cdot l \frac{P}{4} \cdot \frac{\frac{5}{4} \check{P}r + 2}{2} - \frac{\check{P}r}{2}$$

$$x \quad s \quad s' \quad y \quad P$$

$$- r \frac{(\check{P}r)^5}{4} \cdot r \frac{(\check{P}r + \infty)^5}{2} \cdot l \frac{(\check{P}r + \infty)^5}{2}$$

$$n \quad l \quad T$$

$$r \frac{(\check{P}r + \infty)^5}{2} \cdot l \frac{(\check{P}r + \infty)^5}{2} \cdot \check{P}r + \infty.$$

$$z \quad z' \quad M$$

FIG. 87. Albite.

$$\frac{\check{P}r}{2} \cdot r \frac{P}{4} - \frac{\check{P}r}{2} \cdot r \frac{(\check{P}r + \infty)^3}{2}$$

$$x \quad s \quad P \quad l$$

$$l \frac{(\check{P}r + \infty)^5}{2} \cdot r \frac{(\check{P}r + \infty)^5}{2} \cdot l \frac{(\check{P}r + \infty)^5}{2}$$

$$T \quad z \quad z'$$

$$\check{P}r + \infty. \{ \check{P}r + \infty \}.$$

$$M$$

Fig. 84.





Fig. 85.





Fig. 86.








Fig. 87.







- Fig. 87. *Alnus*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$
- Fig. 88. *Prunella Aemula*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$
- Fig. 89. *Prunella Aemula*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$
- Fig. 90. *Prunella Aemula*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$
- Fig. 91. *Prunella Aemula*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$
- Fig. 92. *Prunella Aemula*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$
- Fig. 93. *Prunella Aemula*  

$$\frac{P_1}{P_2} = \frac{(P_1 + \alpha)}{(P_2 + \alpha)}$$

FIG. 88. Albite.

$$\frac{\check{P}r}{2} - \frac{\check{P}r}{2} \cdot r \frac{(\check{P}r + \infty)^5}{2} \cdot l \frac{(\check{P}r + \infty)^3}{2}$$

$$x \quad P \quad l \quad T$$

$$Pr + \infty \cdot \left\{ -\frac{\check{P}r}{2} : +\frac{\check{P}r}{2} - \frac{\check{P}r}{2} \right\}$$

*M*

FIG. 89. Prismatic Axinite.

$$-l \frac{(\check{P}r)^5}{4} - l \frac{(\check{P})^5}{4} - l \frac{\frac{3}{4}P + 2}{4}$$

$$x \quad u \quad s$$

$$-l \frac{(\check{P}r)^7}{4} \cdot r \frac{(\check{P}r + \infty)^5}{2} \cdot Pr + \infty$$

$$l \quad P \quad r$$

FIG. 90. Prismatic Axinite.

$$-l \frac{(\check{P})^5}{4} \cdot r \frac{(\check{P}r + \infty)^5}{2} \cdot Pr + \infty$$

$$u \quad P \quad r$$

FIG. 91. Prismatic Axinite.

$$\frac{\check{P}r}{2} \cdot r \frac{P}{4} \cdot l \frac{P}{4} \cdot \frac{\frac{3}{4}\check{P}r + 2}{2} - \frac{\check{P}r}{2}$$

$$v \quad t \quad t' \quad y \quad T$$

$$-r \frac{(\check{P}r)^5}{4} - l \frac{(\check{P}r)^5}{4} - l \frac{(\check{P})^5}{4}$$

$$n \quad x \quad u$$

$$-l \frac{\frac{3}{4}P + 2}{4} - l \frac{(\check{P}r)^7}{4} \cdot r \frac{(\check{P}r + \infty)^5}{2}$$

$$s \quad l \quad P$$

$$l \frac{(\check{P}r + \infty)^3}{2} \cdot l \frac{(Pr + \infty)^5}{2} \cdot Pr + \infty$$

$$M \quad z \quad r$$

FIG. 92. Pyramidal Lead-baryte.

$$P - \infty \cdot \frac{2\sqrt{2}}{3} P - 3$$

$$a \quad b$$

FIG. 93. Pyramidal Lead-baryte.

$$P - \infty \cdot \frac{2\sqrt{2}}{3} P - 3 \cdot P$$

$$a \quad b \quad P$$

Fig. 88.




Fig. 89.



Fig. 90.





Fig. 91.




Fig. 92.







Fig. 93.







- Fig. 84. Pyramidal Leaf-bud.  
 $T - \infty$   $\frac{1}{2} T - \frac{1}{2} P - \frac{1}{2} S$   
 $A$
- Fig. 85. Pyramidal Leaf-bud.  
 $\frac{1}{2} T - \frac{1}{2} P - \frac{1}{2} S$   $P - 1$   $T$   
 $A$
- Fig. 86. Pyramidal Germ.  
 $T - \infty$   $P - 1$   $P$   $(P - \frac{1}{2})$   
 $A$   
 $(T - 1)^2$   $P + \frac{1}{2}$   $(P)^2$   $(T)^2$   
 $A$   
 $(P + 1)^2$   $P + \frac{1}{2}$   $(P + \frac{1}{2})$   
 $A$   
 $[P + \infty]^2$   $T + \infty$   $[P + \infty]$   
 $A$
- Fig. 87. Pyramidal Koushous-epur.  
 $P$   $[P + \infty]$   
 $A$
- Fig. 88. Pyramidal Koushous-epur.  
 $T - \infty$   $\frac{1}{2} P - \frac{1}{2} S$   $\frac{1}{2} P - \frac{1}{2} S$   
 $A$   
 $T - \frac{1}{2} P$   $[P + \infty]$   $[P + \infty]$   
 $A$
- Fig. 89. Pyramidal Nivou.  
 $P - 1$   $P$   $(P)^2$   $(P)^2$   
 $A$   
 $P + \infty$   $[P + \infty]$   
 $A$

VOL. II. PLATE XVIII.

FIG. 94. Pyramidal Lead-baryte.

$$P - \infty. \quad \frac{2\sqrt{2}}{3} P - 3. \quad P - 3.$$

*a*                      *b*                      *c*

FIG. 95. Pyramidal Lead-baryte.

$$\frac{2\sqrt{2}}{3} P - 3. \quad \frac{2\sqrt{2}}{3} P - 2. \quad P - 1. \quad P.$$

*b*                      *d*                      *e*                      *P*

FIG. 96. Pyramidal Garnet.

$$P - \infty. \quad P - 1. \quad P. \quad (P - 2)^5.$$

*P*                      *o*                      *c*                      *a*

$$(P - 1)^5. \quad P + 2. \quad (P)^5. \quad (P)^4.$$

*z*                      *b*                      *s*                      *x*

$$(P + 1)^5. \quad P + 4. \quad (P + \infty)^5.$$

*e*                      *r*                      *h*

$$[(P + \infty)^5]. \quad P + \infty. \quad [P + \infty].$$

*f*                      *d*                      *M*

FIG. 97. Pyramidal Kouphone-spar.

$$P. \quad [P + \infty].$$

*P*                      *m*

FIG. 98. Pyramidal Kouphone-spar.

$$P - \infty. \quad \frac{4}{5} P - 4. \quad \frac{4}{5} P - 3. \quad \frac{2\sqrt{2}}{3} P - 3.$$

*o*                      *b*                      *d*                      *e*

$$P - 3. \quad P. \quad [(P + \infty)^5]. \quad [P + \infty].$$

*c*                      *P*                      *r*                      *m*

FIG. 99. Pyramidal Zircon.

$$P - 1. \quad P. \quad (P)^5. \quad (P)^4. \quad (P)^5.$$


*t*                      *P*                      *x*                      *y*                      *z*

$$P + \infty. \quad [P + \infty].$$

*l*                      *s*









VOL. III. PLATE XIII.

- Fig. 100. Pyramidal Truncation.  
 $P - \infty = P - \infty$  (Fig. 100)  
 $P$   
 $P + 1$
- Fig. 101. Pyramidal Truncation.  
 $P + 1 = P + \infty$  (Fig. 101)  
 $P$   
 $P + 1$
- Fig. 102. Pyramidal Truncation.  
 $P + 1 = P + \infty$  (Fig. 102)  
 $P$   
 $P + 1$
- Fig. 103. Pyramidal Truncation.  
 $P + 1 = P + \infty$  (Fig. 103)  
 $P$   
 $P + 1$
- Fig. 104. Pyramidal Truncation.  
 $P - \infty = P - 1$  (Fig. 104)  
 $P$   
 $P + 1$
- Fig. 105. Pyramidal Truncation.  
 $P - \infty = P - 1$  (Fig. 105)  
 $P$   
 $P + 1$



VOL. II. PLATE XIX.

FIG. 100. Pyramidal Titanium-ore.

$$P - \infty. \quad \frac{4}{3} P - 4. \quad (\frac{4}{5} P - 7)^4 ?$$

*o*                      *r*                      *s*

$$P. \quad P + 1.$$

*P*                      *q*

FIG. 101. Pyramidal Tin-ore.

$$P + 1. \quad P + \infty. \quad [P + \infty].$$

*s*                      *t*                      *g*

FIG. 102. Pyramidal Tin-ore.

$$P. \quad P + 1. \quad P + \infty. \quad [P + \infty].$$

*P*                      *s*                      *l*                      *g*

FIG. 103. Pyramidal Tin-ore.

$$P. \quad P + 1. \quad (P)^5. \quad (P + \infty)^5. \quad [P + \infty].$$

*P*                      *s*                      *z*                      *r*                      *g*

FIG. 104. Pyramidal Melichrone-resin.

$$P - \infty. \quad P - 1. \quad P. \quad [P + \infty].$$

*o*                      *t*                      *P*                      *g*

FIG. 105. Pyramidal Manganese-ore.

$$\frac{4}{3} P - 4. \quad P.$$

*a*                      *P*

Fig. 100.




Fig. 101.




Fig. 102.




Fig. 103.




Fig. 104.





Fig. 105.









VOL. II. PLATE XX.

FIG. 106. Pyramidal Manganese-ore.

$$P, \left\{ \frac{P-1}{4} \right\}.$$

$P$

FIG. 107. Pyramidal Manganese-ore.

$$P, \{ P \}.$$

$P$

FIG. 108. Pyramidal Scheelium-baryte.

$$P. \frac{r \left( \frac{2\sqrt{2}}{3} P - 2 \right)^5}{1 \frac{2}{g}}. P + 1. \frac{1 (P+1)^5}{r \frac{2}{b}}.$$

$a$   $P$   $b$

FIG. 109. Pyramidal Copper-pyrites.

$$P - \infty. P - 1. \frac{P}{2}. - \frac{P}{2}. P + 1.$$

$a$   $b$   $P$   $P'$   $c$

FIG. 110. Fergusonite.

$$P - \infty. P. \frac{[(P + \infty)^5]}{2}.$$

$i$   $s$   $r$

FIG. 111. Rhombohedral Alum-haloide.

$$R - \infty. R.$$

$o$   $R$



Fig. 106.




Fig. 107.




Fig. 108.




Fig. 109.




Fig. 110.






Fig. III.







VOI. II. PLATE XXI.

Fig. 112. Rhomboidal Prism-haloid.  
 $R = \infty$   $P = 1$   $P + \infty$   
 $H$

Fig. 113. Rhomboidal Prism-haloid.  
 $H + \infty$   $H + \infty$   
 $\infty$

Fig. 114. Rhomboidal Prism-haloid.  
 $H$   $H + \infty$   
 $P$

Fig. 115. Rhomboidal Prism-haloid.  
 $H = \infty$   $H + \infty$   
 $P$

Fig. 116. Rhomboidal Prism-haloid.  
 $H$   $(P)$   $(P)$   $R + \infty$   $H + \infty$   
 $P$   $\infty$

Fig. 117. Rhomboidal Prism-haloid.  
 $P$   $P + \infty$   
 $P$   $\infty$   $\infty$

VOL. II. PLATE XXI.

FIG. 112. Rhombohedral Fluor-haloide.  
 $R - \infty.$   $P - 1.$   $P + \infty.$   
*P* *r* *M*

FIG. 113. Rhombohedral Lime-haloide.  
 $R - \infty.$   $R + 2.$   
*o* *m*

FIG. 114. Rhombohedral Lime-haloide.  
 $R.$   $R + \infty.$   
*P* *c*

FIG. 115. Rhombohedral Lime-haloide.  
 $R - \infty.$   $R.$   $R + 2.$   
*o* *P* *m*

FIG. 116. Rhombohedral Lime-haloide.  
 $R.$   $(P)^5.$   $(P)^5.$   $R + 2.$   $R + \infty.$   
*P* *r* *y* *m* *c*

FIG. 117. Rhombohedral Lead-baryte.  
 $P.$   $P + \infty.$   
*P, s* *n, n'*



Fig. 112.




Fig. 113.




Fig. 114.




Fig. 115.




Fig. 116.






Fig. 117.





VOE II PLATE XXII

Fig. 118 Rhomboidal Kiesel-mischling

H + L P + G

o

Fig. 119 Rhomboidal Kiesel-mischling

H - G H

o

Fig. 120 Rhomboidal Kiesel-mischling

H - L H + L

o

Fig. 121 Rhomboidal Kiesel-mischling

H - G H + L P + G

o

Fig. 122 Rhomboidal Kiesel-mischling

H + L H + L P + G P + G

o

Fig. 123 Rhomboidal Kiesel-mischling

H - G H + L P + G P + G

o

P + G

o



VOL. II. PLATE XXII.

FIG. 118. Rhombohedral Emerald-malachite.

$$R + 1. \quad P + \infty.$$

$$r \qquad s$$

FIG. 119. Rhombohedral Euchlore-mica.

$$R - \infty. \quad R.$$

$$o \quad R$$

FIG. 120. Rhombohedral Kouphone-spar.

$$R - 1. \quad R. \quad R + 1.$$

$$n \quad P \quad r$$

FIG. 121. Rhombohedral Corundum.

$$R - \infty. \quad R. \quad P + 1. \quad P + \infty.$$

$$o \quad P \quad r \quad s$$

FIG. 122. Rhombohedral Corundum.

$$P + 1. \quad R + 1. \quad P + 2. \quad P + \infty.$$

$$r \quad a \quad b \quad s$$

FIG. 123. Rhombohedral Corundum.

$$R - \infty. \quad \frac{7}{6}P + 1. \quad \frac{5}{4}P + 3. \quad P + 3.$$

$$o \quad c \quad l \quad e$$

$$P + \infty.$$

$$s$$

Fig. 118.




Fig. 119.




Fig. 120.




Fig. 121.




Fig. 122.








Fig. 123.







VOI. II. PLATE XXIII.

Fig. 124. Rhomboidal form.

H—E. H. P + A.

" " P

Fig. 125. Peritonsillar body-blends.

H—o. H—E. H—E. H—E. H—E.

" " " " " "

H—E. H. H. P + o.

" " P

Fig. 126. Rhomboidal body-blends.

H—E. H. (P—E). H. (P—E).

" " P " " "

(P—E). (P—E). P + o.

" " V " "

Fig. 127. Rhomboidal.

H—o. H—E. H. P + m.

" " P " "

Fig. 128. Rhomboidal. Karyone sp.

H. (P—E).

"

VOL. II. PLATE XXIII.

FIG. 124. Rhombohedral Iron-ore.

$$R - 2. \quad R. \quad P + 1.$$

*s*            *P*            *n*

FIG. 125. Peritomous Ruby-blende.

$$R - \infty. \quad R - 2. \quad \frac{4}{3}R - 2. \quad \frac{4}{3}R - 1.$$

*o*            *u*            *z*            *k*

$$R - 1. \quad R. \quad R + \infty.$$

*a*            *P*            *l*

FIG. 126. Rhombohedral Ruby-blende.

$$R - 1. \quad (P - 2)^5. \quad R. \quad (P - 1)^5.$$

*z*            *t*            *P*            *a*

$$\left(\frac{5}{4}P - 1\right)^5. \quad (P)^5. \quad P + \infty.$$

*b*            *h*            *n*

FIG. 127. Eudialyte.

$$R - \infty. \quad R - 2. \quad R. \quad P + \infty.$$

*o*            *z*            *P*            *u*

FIG. 128. Rhombohedral Kouphone-spar.

$$R. \quad 2\{R - \infty\}.$$

*P*

Fig. 121.




Fig. 125.




Fig. 126.





Fig. 127.






Fig. 128.







VOL. II. PLATE XXIV.

Fig. 180. Rhomboidal Limb-faloids.

$$T - R^2 \cdot (T^2 - R - \infty)$$

Fig. 180 and 181. Rhomboidal Limb-faloids.

$$R \cdot \left\{ \frac{R-1}{3} \right\}$$

Fig. 182. Rhomboidal Limb-faloids.

$$R - \infty \cdot H + \infty \cdot \left\{ \frac{H}{3} \right\}$$

Fig. 183. Rhomboidal Limb-faloids.

$$R^2 + \infty \cdot H + \infty \cdot \left\{ \frac{H-1}{3} \right\}$$

Fig. 184. Rhomboidal Limb-faloids.

$$R \cdot \left\{ \frac{H + \infty}{3} \right\}$$

VOL. II. PLATE XXIV.

FIG. 129. Rhombohedral Lime-haloide.

$$(P - 2)^s. (P)^s. \left\{ R - \infty \right\}.$$

*t*                      *r*

FIG. 130 and 131. Rhombohedral Lime-haloide.

$$R. \left\{ \frac{R - 1}{3} \right\}.$$

*P*

FIG. 132. Rhombohedral Lime-haloide.

$$R - \infty. R + \infty. \left\{ \frac{R}{3} \right\}.$$

*o*                      *c*

FIG. 133. Rhombohedral Lime-haloide.

$$R - \infty. R + \infty. \left\{ \frac{R - 1}{3} \right\}.$$

*o*                      *c*

FIG. 134. Rhombohedral Lime-haloide.

$$R. \left\{ \frac{R + \infty}{3} \right\}.$$

*P*



Fig. 129.




Fig. 130.




Fig. 131.




Fig. 132.




Fig. 133.






Fig. 134.









VOL. II. PLATE XXV.

FIG. 135. Rhombohedral Lime-haloide.  
 $R - 1. R + \infty. 2 \{ R - \infty \}.$

FIG. 136. Rhombohedral Ruby-blende.  
 $R - 1. \frac{R + \infty}{2}. P + \infty.$

FIG. 137. Rhombohedral Tourmaline.  
 $R. R + 1. P + \infty. R - \infty.$

FIG. 138. Rhombohedral Tourmaline.  
 $R - \infty. R - 1. R. \frac{[R + \infty]}{2}. P + \infty.$   
 $R - 1. R - \infty.$

FIG. 139. Rhombohedral Ruby-blende.  
 $R - 1. P + \infty. \left\{ \frac{R - 1. R - 1}{3} \right\}.$

FIG. 140. Rhombohedral Ruby-blende.  
 $R - 1. P + \infty. \{ R - 1. R - 1 \}.$

Fig. 135.




Fig. 136.




Fig. 137.




Fig. 138.




Fig. 139.






Fig. 140.







VOI II PLATE XXVI

Fig. 141. Axonometric projection.

$$H - \frac{1}{2} \cdot \frac{P + 1}{2}$$

K

Fig. 142. Axonometric projection.

$$H - \frac{1}{2} \cdot \frac{P + 1}{2}$$

K

Fig. 143. Axonometric projection.

$$H - \frac{1}{2} \cdot \frac{P + 1}{2}$$

K

VOL. II. PLATE. XXVI.

FIG. 141. Axotomous Iron-ore.

$$R - \infty. \quad R. \quad \frac{r}{1} \frac{P + 1}{2}.$$

*a*      *R*      *b*

FIG. 142. Axotomous Iron-ore.

$$R - \infty. \quad R. \quad \frac{1}{r} \frac{P + 1}{2}.$$

*a'*      *R'*      *b'*

FIG. 143. Axotomous Iron-ore.

$$R - \infty. \quad R. \quad \frac{r}{1} \frac{P + 1}{2}, 2\{R - \infty\}.$$

*a*      *R*      *b*



Fig. 141.




Fig. 142.





Fig. 143.








Fig. 145.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 146.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 147.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 148.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 149.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 150.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 151.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 152.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 153.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 154.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$

Fig. 155.  $\frac{R - \alpha}{R} = \frac{1}{R} \frac{1}{1 + \frac{1}{R}}$





Fig. 144.




Fig. 145.




Fig. 146.




Fig. 147.




Fig. 148.






Fig. 149.







VOLE II. PLATE XXVIII.

- Fig. 150. Rhombohedral Emerald.  
 B =  $\infty$ . F. 2 (X) P + L. 2 ((P))  
 P  
 P +  $\infty$   
 W
- Fig. 151. Octahedral Fluor-halide.  
 H. IX  
 P
- Fig. 152. Octahedral Fluor-halide.  
 H. A.  
 P
- Fig. 153. Hexahedral Krypton-spar.  
 H. C.  
 P
- Fig. 154. Dodecahedral Garnet.  
 D. C.  
 P  
 W
- Fig. 155. Hexahedral Lead-glass.  
 H. O. D. B.  
 P  
 C  
 V



VOL. II. PLATE XXVIII.

FIG. 150. Rhombohedral Emerald.

$$R - \infty. P. 2(R). P + 1. 2((P)^{\frac{5}{3}}).$$

$$P \quad t \quad s \quad u \quad a$$

$$P + \infty.$$

$$M$$

FIG. 151. Octahedral Fluor-haloide.

$$H. D.$$

$$i \quad s$$

FIG. 152. Octahedral Fluor-haloide.

$$H. A\sigma.$$

$$i \quad a$$

FIG. 153. Hexahedral Kouphone-spar.

$$H. C_1.$$

$$P \quad o$$

FIG. 154. Dodecahedral Garnet.

$$D. C_1.$$

$$P \quad n$$

FIG. 155. Hexahedral Lead-glance.

$$H. O. D. B.$$

$$P \quad c \quad o \quad l$$

Fig 150.




Fig 151.




Fig 152.




Fig 153.




Fig 154.






Fig 155.











VOIR II. PLATIN XXIX

Fig. 156. Dodecaèdral Cornélium.



P.

Fig. 157. Hexaèdral Gold.



O.

Fig. 158. Tetraèdral Copper-glanze.



P.

Fig. 159 and 160. Tetraèdral Borax.



P.

Fig. 161. Tetraèdral Copper-glanze.



P.

VOL. II. PLATE XXIX.

FIG. 156. Dodecahedral Corundum.




FIG. 157. Hexahedral Gold.




FIG. 158. Tetrahedral Copper-glance.




FIG. 159 and 160. Tetrahedral Boracite.




FIG. 161. Tetrahedral Copper-glance.




Fig. 156.




Fig. 157.




Fig. 158.




Fig. 159.




Fig. 160.






Fig. 161.







VOL. II. PLATE XXX.

Fig. 182. Dodecahedral Garnet-blende.

$$D = \frac{C}{2}$$

$a = b$

Fig. 183. Dodecahedral Garnet-blende.

$$D = \left\{ \begin{array}{l} O \\ H \end{array} \right.$$

$a = b$

Fig. 184. Octahedral Diamond.

$$O = \frac{T}{2}$$

$a = b$

Fig. 185. Hexahedral Iron-pyrite.

$$H = \frac{A}{2}$$

$a = b$

Fig. 186. Hexahedral Iron-pyrite.

$$O = \frac{A}{2}$$

$a = b$

Fig. 187. Hexahedral Iron-pyrite.

$$H = \frac{O}{2}$$

$a = b$

VOL. II. PLATE XXX.

FIG. 162. Dodecahedral Garnet-blende.

$$D. \frac{C_2}{2}$$

$$P \quad y$$

FIG. 163. Dodecahedral Garnet-blende.

$$D. \left\{ \frac{O}{4} \right\}.$$

$$P$$

FIG. 164. Octahedral Diamond.

$$\frac{O}{2} - \frac{T}{2} \quad 2 \{ H \}.$$

$$P \quad n$$

FIG. 165. Hexahedral Iron-pyrites.

$$H. \frac{A_2}{2}$$

$$P \quad e$$

FIG. 166. Hexahedral Iron-pyrites.

$$O. \frac{A_2}{2}$$

$$d \quad e$$

FIG. 167. Hexahedral Iron-pyrites.

$$H. \quad O. \quad \frac{A_2}{2}. \quad C_1. \quad \frac{T_5}{2}.$$

$$P \quad d \quad e \quad u \quad s$$



Fig.162.




Fig.163.




Fig.164.




Fig.165.




Fig.166.





Fig.167.








Fig. 107. Primäres Kuppelprofil

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (107)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (108)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (109)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (110)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (111)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (112)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (113)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (114)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (115)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (116)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (117)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (118)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (119)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (120)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (121)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (122)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (123)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (124)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (125)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (126)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (127)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (128)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (129)$$

$$P = \frac{r}{2} (1 + \cos \alpha) \quad (130)$$



VOL. II. PLATE XXXI.

FIG. 168. Prismatic Epsom-salt.

$$\begin{array}{cccccc} \check{P}r. & \check{P}r. & P. & \check{P}r + 1. & \check{P}r + 1. & \frac{r (\check{P}r)^3}{r \frac{2}{t}} \cdot \frac{l (\check{P}r)^3}{l \frac{2}{s}} \\ n & m & l & r & q & \\ P + \infty. & \check{P}r + \infty. & \check{P}r + \infty. & & & \\ M & o & p & & & \end{array}$$

FIG. 169. Di-prismatic Lead-baryte.

$$\begin{array}{cccccc} P - \infty. & P - 1. & \check{P}r. & P. & (\check{P}r)^3. & \frac{3}{4} \check{P}r + 2. & \check{P}r + 1. & (P)^3. \\ g & w & M & t & v & e & y & o \\ P + \infty. & (\check{P}r + \infty)^3. & (\check{P}r + \infty)^3. & \check{P}r + \infty. & \check{P}r + \infty. & & & \\ P & u & s & l & h & & & \end{array}$$

FIG. 170. Hemi-prismatic Lead-baryte.

$$\begin{array}{cccccc} \frac{P}{2}. & \check{P}r. & \check{P}r + 1. & -\frac{\check{P}r}{2}. & -\frac{P}{2}. & -\frac{(P)^3}{2}. & P + \infty. \\ t & z & y & k & v & b & M \\ (\check{P}r + \infty)^3. & \check{P}r + \infty. & \check{P}r + \infty. & & & & \\ a & g & f & & & & \end{array}$$

FIG. 171. Axotomous Lead-baryte.

$$\begin{array}{cccccc} P - \infty. & \frac{\check{P}r - 1}{2}. & \frac{\check{P}r}{2}. & \frac{\check{P}r + 1}{2}. & \frac{P - 1}{2}. & \frac{(\check{P} - 2)^4}{2}. \\ a & i & f & e & g & h \\ \frac{(\check{P}r - 1)^3}{2}. & \frac{P}{2}. & \frac{(\check{P} - 2)^3}{2}. & \check{P}r - 2. & \check{P}r - 1. & \\ k & P & o & l & m \\ \frac{3}{4} \check{P}r. & -\frac{\check{P}r + 1}{2}. & -\frac{P - 1}{2}. & -\frac{(\check{P} - 2)^4}{2}. & -\frac{(\check{P}r - 1)^3}{2}. \\ n & e' & g' & h' & k' \\ -\frac{P}{2}. & -\frac{(\check{P} - 2)^3}{2}. & P + \infty. & (\check{P} + \infty)^4. & \check{P}r + \infty. \\ P' & o' & c & d & b \end{array}$$

FIG. 172. Prismatic Cobalt-mica.

$$\begin{array}{cccccc} \frac{\check{P}r}{2}. & \frac{P}{2}. & (\check{P}r + \infty)^3. & (\check{P}r + \infty)^3. & \check{P}r + \infty. & \check{P}r + \infty. \\ M & l & k & s & T & P \end{array}$$

FIG. 173. Rhombohedral Kouphone-spar.

$$\begin{array}{cccccc} R - 1. & R. & R + 1. & P + \infty, & 2 \{ R - \infty \}. \\ n & P & r & u & \end{array}$$

Fig. 168.




Fig. 169.




Fig. 170.




Fig. 171.




Fig. 172.





Fig. 173.








Fig. 174. *Platanus Montana* sp. nov. An-  
varius.

Fig. 175. *Platanus* from Ireland.

Fig. 176. *Platanus* *Agilis* sp. nov.

$$\frac{P_1}{P} = \frac{(P_1)^2}{P} = \frac{P_1}{P} = \frac{(P_1)^2}{P}$$

$$(P_1 + x)^2 = P_1 + x \cdot P_1 + x^2$$

Fig. 177. Horizontal projection of the same.

Fig. 178. Pyramidal Copper-pyrites.

$$P - \infty \cdot \frac{P}{2} = \frac{P}{2} \cdot P - \frac{P}{2} \cdot P = \frac{P}{2} \cdot P$$

$$P + 1 = \frac{P - 1}{2} = \frac{P - 1}{2}$$

$$\frac{(P_1)^2}{P} = \frac{P_1}{P} = \frac{P_1}{P}$$

Fig. 179. Pyramidal Copper-pyrites.

$$\frac{P}{2} \cdot P + 1 \cdot P = \frac{P}{2} \cdot P + 1 \cdot P$$

composition of five individuals each  
of the lateral ones being joined to the  
central individual, in a plane perpen-  
dicular to a terminal edge of P.

VOL. II. PLATE XXXII.

FIG. 174. Prismatic Kouphone-spar, from Auvergne.

FIG. 175. Mesolite from Iceland.

FIG. 176. Paratomous Augite-spar.

$$\frac{\check{P}r}{2} \cdot \frac{P}{2} \cdot \frac{(\check{P}r)^5}{2} \quad - \quad \frac{\check{P}r}{2} \quad - \quad \frac{(\check{P})^5}{2}$$

$$P \quad s \quad o \quad t \quad u$$

$$(\check{P}r + \infty)^5 \cdot \check{P}r + \infty \quad \check{P}r + \infty$$

$$M \quad r \quad l$$

FIG. 177. Horizontal projection of the same.

FIG. 178. Pyramidal Copper-pyrites.

$$P - \infty \cdot \frac{P}{2} \cdot \frac{2\sqrt{2}}{3} P - 2 \cdot P - 1 \cdot \frac{3}{2\sqrt{2}} P$$

$$a \quad P \quad g \quad b \quad h$$

$$P + 1 \cdot - \frac{P - 4}{2} \cdot - \frac{2\sqrt{2}}{3} \frac{P - 3}{2}$$

$$c \quad d \quad e$$

$$\frac{(\frac{2\sqrt{2}}{3} P - 5)^5}{2} \cdot - \frac{P}{2}$$

$$f \quad P'$$

FIG. 179. Pyramidal Copper-pyrites.

$$\frac{P}{2} \cdot P + 1 \cdot \{ P - 1 \cdot P \} \cdot \text{Regular}$$

composition of five individuals, each of the lateral ones being joined to the central individual, in a plane perpendicular to a terminal edge of P.

Fig. 174.




Fig. 175.




Fig. 176.




Fig. 177.




Fig. 178.





Fig. 179.








Fig. 180. Hexahedral Gold.

$$C = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

Fig. 181. Hexagonal Copper-Glass.

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

Fig. 182. Rhombohedral Ruby-Glass.

$$R = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

Fig. 183. Hexagonal Ruby-Glass.

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

Fig. 184. Hexagonal Sulphur.

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

(1 + a) (1 + a) (1 + a)

$$P = \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right) - \frac{1}{2} \left( \frac{1}{a} + \frac{1}{b} + \frac{1}{c} \right)$$

Fig. 185. Alumina.

VOL. II. PLATE XXXIII.

FIG. 180. Hexahedral Gold.

$$C_2. \left\{ \frac{O}{4} \right\}.$$

*o*

FIG. 181. Di-prismatic Copper-glance.

$$P - \infty. \quad \check{P}r - 1. \quad \check{P}r. \quad \check{P}r + 1. \quad Pr - 1.$$

*k*                      *e*                      *d*                      *f*                      *o*

$$(\check{P}r - 1)^5. \quad P. \quad Pr. \quad (\check{P}r + \infty)^5.$$

*y*                      *P*                      *p*                      *n*

$$\check{P}r + \infty. \quad Pr + \infty.$$

*s*                      *r*

FIG. 182. Rhombohedral Ruby-blende.

$$R - 1. \quad P + \infty. \quad R + 1. \quad R - 1.$$

*z*                      *n*                      *g*                      *z*

FIG. 183. Hemi-prismatic Ruby-blende.

$$P - \infty. \quad - \frac{\check{P}r + 1}{2}. \quad P + \infty.$$

*b*                      *t*                      *f*

FIG. 184. Hemi-prismatic Sulphur.

$$\frac{\check{P}r}{2}. \quad \frac{P}{2}. \quad \frac{(\check{P}r)^5}{2}. \quad - \frac{\check{P}r}{2}. \quad - \frac{P}{2}.$$

*t*                      *n*                      *q*                      *P*                      *n'*

$$- \frac{(\check{P}r)^5}{2}. \quad - \frac{(\check{P})^5}{2}. \quad P + \infty.$$

*q'*                      *l*                      *f*

$$(\check{P}r + \infty)^7. \quad (\check{P}r + \infty)^5. \quad (\check{P}r + \infty)^5.$$

*w*                      *g*                      *v*

$$\check{P}r + \infty. \quad Pr + \infty.$$

*s*                      *u*

FIG. 185. Allanite.



Fig. 180.




Fig. 181.




Fig. 182.




Fig. 183.




Fig. 184.






Fig. 185.





VOL. II. PLATE XXXIV.

Fig. 186. Acanth.

Fig. 187. Babinonina, copied from Mr. Lavy's figure.

Fig. 188. Babinonina (Latic).

Fig. 189. Babinonina.

Fig. 190. Babinonina, copied from Mr. Lavy's figure.

Fig. 191. Babinonina (Latic).

Fig. 192. Babinonina.

Fig. 193. Babinonina (Latic).

Fig. 194. Babinonina.

Fig. 195. Babinonina.

Fig. 196. Babinonina.

Fig. 197. Babinonina (Latic).

Fig. 198. Babinonina.

Fig. 199. Babinonina.

Fig. 200. Babinonina.

Fig. 201. Babinonina.

Fig. 202. Babinonina.

Fig. 203. Babinonina.

Fig. 204. Babinonina.

Fig. 205. Babinonina.

Fig. 206. Babinonina.

Fig. 207. Babinonina.

Fig. 208. Babinonina.

Fig. 209. Babinonina.

Fig. 210. Babinonina.



VOL. II. PLATE XXXIV.

FIG. 186. Acmite.

FIG. 187. Babingtonite, copied from Mr LEVY's figure.

FIG. 188. Baryto-Calcite.

FIG. 189. Brewsterite.

FIG. 190. Brookite, copied from Mr LEVY's figure.  
 $\check{P}r - 1. \check{P}r. (\frac{4}{3} \check{P} - 2)^5. (\check{P}r - 1)^5.$

$$\begin{array}{cccc}
 a^2 & a^1 & i & b^{\frac{1}{2}} \\
 \frac{4}{3} \check{P}r. & P. & (\check{P}r + \infty)^5. & \check{P}r + \infty. \\
 e^{\frac{3}{8}} & e^5 & m & h^1 \\
 \check{P}r + \infty. & & & \\
 g^1 & & & 
 \end{array}$$

FIG. 191. Childrenite.

$$\begin{array}{cccc}
 \frac{4}{3} P. & P. & \frac{5}{4} \check{P}r + 2. & \check{P}r + \infty. \\
 b & e & a & P
 \end{array}$$

Fig. 186.




Fig. 187.




Fig. 188.




Fig. 189.




Fig. 190.






Fig. 191.









VOL. II. PLATE XXXV.

FIG. 192. Euchroite.

$$\begin{array}{cccc}
 P - \infty. & \check{P}r. & P + \infty. & (\check{P}r + \infty)^5. \\
 P & n & & s \\
 (\check{P}r + \infty)^5. & \check{P}r + \infty. & & \\
 l & k & & 
 \end{array}$$

FIG. 193. Fergusonite.

$$\begin{array}{cccc}
 P - \infty. & P. & \frac{(P - 1)^5}{2} & \frac{[(P + \infty)^5]}{2} \\
 i & s & z & r
 \end{array}$$

FIG. 194. Levyne.

$$\begin{array}{cccc}
 R - \infty. & R - 1. & R. & 2\{R - \infty\}. \\
 o & g & P & 
 \end{array}$$

FIG. 195. Roselite, copied from Mr LÉVY's figure.

FIG. 196. Gmelinite.

$$\begin{array}{ccc}
 R - \infty. & P. & P + \infty. \\
 o & y & u
 \end{array}$$

FIG. 197. Wagnerite, copied from a drawing by  
Dr G. ROSE.

Fig. 192.




Fig. 193.




Fig. 194.




Fig. 195.




Fig. 196.






Fig. 197.







## INDEX.

---

Abrazite	iii. 174	Allanite	iii. 68. 98
Achirite	ii. 172	Allochroit	ii. 359
Achmite	iii. 67	Allochroite	ii. 362
Acicular bismuth- glance	iii. 130	Allophane	iii. 69
Acicular olivenite	iii. 144	Almandin	ii. 359
Acid	ii. 22	Almandine	ii. 363
Acide boracique	ii. 25	Alum	ii. 50
sulfurique	ii. 24	Alum-earth	iii. 178
Acmite	iii. 67	Alum-haloïde	ii. 67
Actinolite	ii. 272. 278	Alum-rock	ii. 68
Actinote	ii. 275	Alum-salt	ii. 50
Adamantine spar	ii. 302	Alum-slate	iii. 178
Adhesive slate	iii. 177	Alumstone	ii. 67
Adipocire, mineral	iii. 107	Alumine fluatée alcaline	ii. 66
Adular	ii. 251	fluatée siliceuse	ii. 308
Adularia	ii. 258	magnésiée	ii. 295
Aëriform carbonic acid	ii. 22	sulfatée	ii. 50
muriatic acid	ii. 23	sulfatée alcaline	ii. 50
Agalmatolite	iii. 100	sous-sulfatée alca- line	ii. 67
Agaric mineral	ii. 89	Alumine, subphosphate of	iii. 169
Agate	ii. 329	Aluminite	iii. 70
Agate-jasper	ii. 328	Amalgam	ii. 431
Alaun	ii. 50	Amalgam, native	ii. 431
Alaunstein	ii. 67	Amazone stone	ii. 263
Albin	ii. 244	Amber	iii. 57
Albite	ii. 255	Amblygonite	iii. 70
Allagite	iii. 123		

Amethyst	ii. 325	Antimony, dodecahedral	ii. 426
Amethyst, oriental	ii. 303	grey	iii. 23. 26
Amiantus	ii. 279	native	ii. 426
Ammonia, muriate of	ii. 39	nickeliferous grey	iii. 131
Ammoniac-salt	ii. 39	octahedral	ii. 427
Ammoniac, sulphat of	iii. 125	oxide of	ii. 152
Ammoniaque muriatée	ii. 39	prismatic	ii. 427
Amphibole	ii. 275	prismatic white	ii. 151
Amphigène	ii. 224	red	iii. 36
Analcime	ii. 227	rhombohedral	ii. 426
Anatase	ii. 379	sulphuret of	iii. 23
Andalusite	ii. 293	sulphuret of silver	
Anhydrite	ii. 62	and	iii. 30
Anhydrous gypsum	ii. 62	white	ii. 152
Ankerite	i. 411	Antimony-baryte	ii. 151
Anorthite	iii. 71	Antimony-blende	iii. 36
Anthophyllite	ii. 211	Antimony-glance	iii. 21
Anthophyllit, blättriger	ii. 207	axifrangible	iii. 5
strahliger	ii. 211	axotomous	iii. 26
Anthracite	iii. 64. 65	prismatic	iii. 4. 21
Anthracolite	ii. 90	prismatoidal	iii. 23. 26
Anthrakolit	ii. 83	Antimony-ochre	ii. 427 iii. 25
Anthrakonit	ii. 84	Apatite	ii. 73
Anthrazit	iii. 65	Aphrit	ii. 349
Antimoine hydro-sulfuré	iii. 36	Aphrite	iii. 72
natif	ii. 426	Aplome	ii. 364
oxidé	ii. 152	Apophyllite	ii. 244. 246
oxidé sulfuré	iii. 36	Aquamarine	ii. 316
sulfuré	iii. 23	oriental	ii. 312
sulfuré plombo-		Arendalite	ii. 286
cuprifère	iii. 5	Arfvedsonite	iii. 73
Antimon, gediegen	ii. 426	Argent antimonial	ii. 427
Antimon-Silber	ii. 427	antimonié sulfuré	iii. 38
Antimonblende	iii. 36	antimonié sulfuré	
Antimonblüthe	ii. 152	noir	iii. 27
Antimonglanz	iii. 23	muriaté	ii. 154
Antimonial silver	ii. 427	natif	ii. 434
Antimony	ii. 426	noir	iii. 27



Argent sulfuré	iii. 11	Arseniksaures Kobalt	ii. 184
sulfuré flexible	iii. 30	Arsenik-Wismuth	iii. 74
Argentiferous copper-		Asbest	ii. 268. 274
glance	iii. 73	Asbestus	ii. 274
Argile schisteuse no-		Asbestus, common	iii. 138
vaculaire	iii. 187	Asche	iii. 73
Arragon	ii. 79	Asphalt	iii. 59
Arragonite	ii. 79	Asteria	ii. 303
Arsenate of cobalt	ii. 184	Atacamite	iii. 74
of copper, martial	iii. 149	Atmosphärische Luft	ii. 20
octahedral	ii. 160	Atmospheric air	ii. 20
oblique prismatic	iii. 144	Atmospheric-gas	ii. 20
prismatic	ii. 164	Atmospheric-water	ii. 21
rhomboidal	ii. 178	Augite	ii. 268
of iron	ii. 162	hemi-prismatic	ii. 274
of lead	ii. 133	oblique-edged	ii. 268
of lime	iii. 135	prismatic	ii. 286
of nickel	ii. 448	prismatoidal	ii. 282
Arsenic	ii. 423	pyramido-prismatic	ii. 268
Arsenic, oxide of	ii. 26	straight-edged	ii. 274
native	ii. 423	Augite-spar	ii. 268
oxydé	ii. 26	hemi-prismatic	ii. 274
sulfuré jaune	iii. 47	paratomous	ii. 268
sulfuré rouge	iii. 50	polystomous	iii. 115
Arsenic-acid	ii. 26	prismatic	ii. 286
Arsenical bismuth	iii. 74	prismatoidal	ii. 282
iron	ii. 449	Auripigment	iii. 47
nickel	ii. 446	Automalite	ii. 298
Arsenical-pyrites	ii. 448	Axinite	ii. 341
axotomous	ii. 448	Axotomous Antimony-	
di-prismatic	ii. 449	glance	iii. 26
prismatic	ii. 448. 449	Arsenical-pyrites	ii. 448
Arsenik, gediegen	ii. 423	Iron-ore	ii. 397
Arsenikblüthe	ii. 26	Kouphone-spar	ii. 246
Arsenikkies	ii. 449	Lead-baryte	ii. 144
Arsenik-Nickel	ii. 446	Triphane-spar	ii. 217
Arsenik-Silber	ii. 427	Azure-malachite	ii. 167
Arseniksaures Eisen	ii. 162	Azure-spar	ii. 288

Azure-spar, dodecahe-		Bismuth, cupreous	iii. 91
dral	ii. 288	cupriferos sul-	
prismatic	ii. 290	phuret of	iii. 91
prismatoidal	ii. 292	native	ii. 430
Azure stone	ii. 288	octahedral	ii. 430
Azurite	ii. 290	plumbo-cupriferos	
		sulphuret of	iii. 130
Babingtonite	iii. 75	sulfuré	iii. 19
Baikalit	ii. 268. 272	sulphuret of	iii. 19
Balas ruby	ii. 298	Bismuth-glance	iii. 19
Bardiglione	ii. 62	acicular	iii. 130
Bary-strontianite	iii. 159	prismatic	iii. 19
Baryt	ii. 121	Bismuthic silver	iii. 78
Baryt, kohlensaurer	ii. 119	Bitterkalk	ii. 94. 98
schwefelsaurer	ii. 121	Bittersalz	ii. 48
Baryte	ii. 101	Bitterspar	ii. 94. 98
axifrangible	ii. 126	Bitume	iii. 59
carbonatée	ii. 119	Bitumen	iii. 59
di-prismatic	ii. 116. 119	Bituminöses Holz	iii. 61
prismatic	ii. 121	Bituminous marle	iii. 178
prismatoidal	ii. 126	marlslate	ii. 90
pyramido-prismatic	ii. 116	Mineral-coal	iii. 61
rhomboidal	ii. 119	shale	iii. 178
sulfatée	ii. 121	wood	iii. 62
sulfatée fétide	ii. 124	Black chalk	iii. 181
Barytes, carbonate of	ii. 119	coal	iii. 61
sulphate of	ii. 121	cobalt-ochre	iii. 78
Baryto-calcite	iii. 76	lead	ii. 191
Bergmannite	iii. 77	Mineral-resin	iii. 59
Bergmilch	ii. 83	silver	ii. 435
Bergpech	iii. 59	tellurium	iii. 16
Bergtheer	iii. 59	wad	ii. 421
Beril, schörlartiger	ii. 308	Blätterkohle	iii. 61
Beryl	ii. 316	Blätterzeolith	ii. 242
Bernstein	iii. 57	Blättrich-strahliger Stil-	
Bimstein	ii. 337	bit	ii. 239
Bismuth	ii. 430	Blättriger Stilbit	ii. 242
arsenical	iii. 74	Pseudomalachit	ii. 166

Blätter-Tellur	iii. 16	Börnstein	iii. 57
Blau-Bleierz	iii. 13	Botryolite	ii. 223
Blaue Eisenerde	ii. 188	Bournonite	iii. 5
Blauspath	ii. 292	Brachytypous Lime-ha-	
Blei, kohlensaures	ii. 130	loide	ii. 98
phosphorsaures	ii. 134	Parachrose-baryte	ii. 101
chromsaures	ii. 137	Braunbleierz	ii. 134
molybdänsaures	ii. 140	Brauneisenstein	ii. 410
Bleierde	ii. 130	Braunkalk	ii. 94
Bleifahlerz	iii. 5	Braunkohle	iii. 61
Bleigelb	ii. 140	Braun-Menakerz	ii. 373
Bleiglanz	iii. 13	Braunspath	ii. 94. 106
Bleischwärze	ii. 130	Braunstein, grauer	ii. 419
Bleischweif	iii. 13	rother	ii. 106
Bleivitriol	ii. 142	piemontischer	ii. 282
Bleiweiss	ii. 130	schwarzer	ii. 416
Blende	iii. 31. 32	Braunsteinkiesel	ii. 359
Blind coal	iii. 64	Brazilian emerald	ii. 353
Bloedite	iii. 79	Breislakite	iii. 80
Blue copper	ii. 167	Breunnerite	i. 411
felspar	ii. 292	Brewsterite	iii. 80
lead	ii. 136. iii. 13	Brithyne-salt	ii. 54
spar	ii. 292	Brittle silver-glance	iii. 27
vitriol	ii. 44	sulphuret of silver	iii. 27
Blutstein	ii. 404	Brochantite	iii. 81
Bole	iii. 179	Brongniartin	ii. 54
Bolognese-spar	ii. 124	Bronzite	ii. 207
Boracic-acid	ii. 25	Brookite	iii. 82
Boracite	ii. 347	Brown coal	iii. 61
Boraté of lime	ii. 220	Brown coal, trapezoidal	iii. 62
of magnesia	ii. 347	Brown lead-spar	ii. 136
of soda	ii. 52	Brownspar	ii. 96. 102
Borax	ii. 52	Brucite	iii. 87. 88
Borax-salt	ii. 52	Bucklandite	iii. 83
Boraxsäure	ii. 25	Bunter Kupferkies	ii. 467
Boraxsaures Natron	ii. 52	Buntkupfererz	ii. 467
Borazit	ii. 348	Byssolith	ii. 275



Cacholong	ii. 332	Cerine	ii. 395
Calamine	ii. 111	Cerinstein	ii. 394
electric	ii. 108	Cerite	ii. 394
prismatic	ii. 108	Cerium, fluatée of	iii. 100
rhomboidal	ii. 111	oxidé siliceux rouge	ii. 394
Calaité	iii. 83	oxydé silicifère	ii. 394
Calamite	ii. 278	Cerium-ore	ii. 394
Calcareous spar	ii. 89	indivisible	ii. 394
tufa	ii. 90	prismatic	iii. 68
Calcedony	ii. 321	uncleavable	ii. 394
Calcsinter	ii. 89	Chabasié	ii. 232
Cannel-coal	iii. 61. 63	Chabasite	ii. 232
Caoutchouk, mineral	iii. 60	Chalk	ii. 89
Capillary pyrites	iii. 130	black	iii. 181
Carbon, mineral	iii. 64	Charcoal, mineral	iii. 64. 66
Carbonate of barytes	ii. 119	Chaux anhydro-sulfatée	ii. 62
of copper, blue	ii. 167	boratée siliceuse	ii. 220
of copper, green	ii. 175	carbonatée	ii. 84
of iron	ii. 102	aluminifère	ii. 94
of lead	ii. 130	ferrifère	ii. 94. 102
of lime	ii. 83	ferrifère perlée	ii. 94
of magnesia	iii. 121	ferro-manganési-	
of magnesia and iron	ii. 98	fère	ii. 94
of manganese	ii. 106	magnésifère	ii. 94. 98
of soda	ii. 27	manganésifère	
of strontian	ii. 116	rose	ii. 94
of zinc	ii. 111	quartzifère	ii. 92
Carbonic-acid	ii. 22	fluatée	ii. 69
Carburetted hydrogen		phosphatée	ii. 73
gas	ii. 18	sulfatée	ii. 57
Carinthine	ii. 278	anhydre	ii. 62
Carnelian	ii. 327	épigène	ii. 65
Carpholite	iii. 116	Chiastolite	iii. 84
Cats eye	ii. 321	Childrenite	iii. 85
Cawk	ii. 125	Chlorite	ii. 193
Celestine	ii. 126	Chloropal	iii. 85
Cellular pyrites	ii. 460. 464	Chlorophæite	iii. 86
Ceririt	ii. 394	Chlorophane	ii. 72

Chondrodite	iii. 87	Cobalt gris	ii. 455
Chromate of iron	ii. 396	prismatic red	ii. 184
of lead	ii. 137	radiated white	ii. 454
of lead and copper	iii. 167	red	ii. 184
Chrom Eisenstein	ii. 396	silver-white	ii. 455
Chrome-ore	ii. 396	sulphate of	iii. 145
Chromsaures Blei	ii. 137	sulphuret of	iii. 88
Chrysoberil	ii. 304	tin-white	ii. 452
Chrysocolla	ii. 158	Cobalt bloom	ii. 184, 186
Chrysolite	ii. 345	Cobalt crust	ii. 186
Chrysoprase	ii. 327	Cobalt-Kies	iii. 88
Cinnabar	iii. 44	Cobalt-mica	ii. 184
hepatic	iii. 45	Cobalt-ochre, black	iii. 78
Cinnamon-stone	ii. 364	yellow and brown	iii. 79
Clay	iii. 180	Cobalt-ore, grey	ii. 454
Clayslate	ii. 203	Cobalt-pyrites	ii. 452
Claystone	iii. 180	hexahedral	ii. 455
Cleavelandite	ii. 251	octahedral	ii. 452
Clinkstone	ii. 259	Cobaltic galena	iii. 88
Coal	iii. 61	Cobaltic lead-glance	iii. 88
black	iii. 61, 62	Coccolite	ii. 272
blind	iii. 64	Cockscomb pyrites	ii. 464
brown	iii. 61, 62	Colophonite	ii. 361
coarse	iii. 63	Columbite	ii. 390
columnar	iii. 65	Columnar coal	iii. 65
common	iii. 61	Common asbestos	iii. 138
earthy	iii. 62	Common clay	iii. 180
foliated	iii. 63	Comptonite	iii. 89
glance	iii. 64	Condrodite	iii. 87
pitch	iii. 63	Copper	ii. 444
slate	iii. 63	blue carbonate of	ii. 167
Coarse coal	iii. 63	of cementation	ii. 446
Cobalt, arseniate of	ii. 184	chromate of lead	
arseniaté	ii. 184	and	iii. 167
arsenical	ii. 452	earthy blue	ii. 170
bright white	ii. 452, 455	green carbonate of	ii. 175
earthy	iii. 78	hydrous phosphate of	ii. 173

- |                      |              |                |              |
|----------------------|--------------|----------------|--------------|
| Copper, lenticular   | ii. 190      | Copper-green   | ii. 159      |
| martial arseniate    |              | common         | ii. 158      |
| of                   | iii. 149     | uncleavable    | ii. 158      |
| muriate of           | iii. 74      | Copper, grey   | iii. 1       |
| native               | ii. 444      | antimonial     | iii. 3       |
| oblique prismatic    |              | arsenical      | iii. 3       |
| arseniate of         | iii. 144     | Copper-mica    | ii. 178      |
| octahedral           | ii. 444      | Copper-Nickel  | ii. 446      |
| octahedral arseniate |              | Copper-ore     | ii. 381      |
| of                   | ii. 160      | octahedral     | ii. 381      |
| oxydulated           | ii. 381      | vitreous       | iii. 8       |
| phosphate of         | ii. 166. 173 | yellow         | ii. 469      |
| prismatic arseniate  |              | Copper-pyrites | ii. 467. 469 |
| of                   | ii. 164      | octahedral     | ii. 467. 469 |
| purple               | ii. 467      | pyramidal      | ii. 469      |
| radiated blue        | ii. 170      | tetrahedral    | iii. 1       |
| red oxide of         | ii. 381      | yellow         | ii. 469      |
| rhomboidal arseniate |              | Cordierite     | ii. 319      |
| of                   | ii. 178      | Corindon       | ii. 299      |
| rhomboidalemerald    | ii. 171      | Cork, rock     | ii. 279      |
| seleniuret of        | iii. 150     | Corneous lead  | ii. 150      |
| seleniuret of silver |              | manganese      | iii. 123     |
| and                  | iii. 94      | mercury        | ii. 156      |
| sulphate of          | ii. 44       | silver         | ii. 154      |
| sulphuret of         | iii. 8       | Corundum       | ii. 295. 299 |
| sulphuret of silver  |              | dodecahedral   | ii. 295      |
| and                  | iii. 73      | octahedral     | ii. 295. 298 |
| variegated           | ii. 467      | prismatic      | ii. 304      |
| velvet-blue          | iii. 168     | rhombohedral   | ii. 299      |
| vitreous             | iii. 8       | rhomboidal     | ii. 299      |
| Copper-black         | ii. 472      | Crichtonite    | ii. 399      |
| Copper-glance        | iii. 1       | Cronstedtite   | iii. 90      |
| argentiferous        | iii. 73      | Cross stone    | ii. 229      |
| di-prismatic         | iii. 5       | Cryolite       | ii. 66       |
| prismatic            | iii. 8       | Cryone-haloide | ii. 66       |
| prismatoidal         | iii. 4       | Crysoberyl     | ii. 304      |
| rhomboidal           | iii. 8       | Crystal, rock  | ii. 325      |
| tetrahedral          | iii. 1       | Cube-ore       | ii. 162      |



Cubizit	ii. 227	Demant	ii. 306
Cuivre arseniaté	ii. 164	Demantspath	ii. 299
hexagonal lamel-		Diallag, talkartiger	ii. 206
liforme	ii. 179	Diallage fibro-laminaire	
lamelliforme	ii. 179	métalloïde	ii. 208
octaèdre aigu	ii. 164	green	ii. 272. 274
octaèdre obtus	ii. 160	métalloïde	ii. 206. 208. 209
primitif	ii. 160	verte	ii. 275
carbonaté	ii. 167. 175	Diamant	ii. 306
bleu	ii. 167	Diamond	ii. 306
terreux	ii. 158	Diaspore	iii. 92
vert	ii. 158. 175	Diatomous Kouphone-	
diopase	ii. 171	spar	ii. 234
gris	iii. 1	Schiller-spar	ii. 206
hydraté siliceux	ii. 158	Dichroite	ii. 319
hydro-siliceux	ii. 158	Diopside	ii. 268. 272
natif	ii. 444	Dioptase	ii. 171
oxidé rouge	ii. 381	Diploite	iii. 118
oxidulé	ii. 381	Di-prismatic Copper-	
phosphaté	ii. 166. 173	glance	iii. 5
pyriteux	ii. 469	Hal-baryte	ii. 119
pyriteux hépatique	ii. 467	Iron-ore	ii. 414
sélénié	iii. 150	Lead-baryte	ii. 130
argental	iii. 94	Olive-malachite	ii. 166
sulfaté	ii. 44	Dipyre	ii. 264
sulfuré	iii. 8	Disthène	ii. 213
Cupreous bismuth	iii. 91	Disthene-spar	ii. 213
manganese	iii. 92	Dodecahedral Azure-	
sulphate of lead	ii. 149	spar	ii. 288
sulphato-carbonate		Corundum	ii. 295
of lead	ii. 149	Garnet	ii. 359
Cupriferous sulphuret		Garnet-blende	iii. 32
of bismuth	iii. 91	Iron-ore	ii. 403
Cyanite	ii. 213	Kouphone-spar	ii. 225
Cymophane	ii. 304	Mercury	ii. 431
Cyprine	ii. 356	Dolomite	ii. 93. 98
Datolite	ii. 220	Doubly refracting spar	ii. 92
		Drawing slate	iii. 181

Duttenstein	ii. 83. 90	Emerald-malachite	ii. 171
Dystome spar	ii. 220	prismatic	iii. 95
		rhombohedral	ii. 171
Earth, fuller's	iii. 182	rhomboidal	ii. 171
Earth, yellow	iii. 187	Emeraude	ii. 316
Earthy coal	iii. 62	Emery	ii. 301
Earthy cobalt	iii. 78	Empyreumatic Hydro-	
Egeran	ii. 354	gen-gas	ii. 18
Eisen, arseniksaures	ii. 162	Empyrodox Quartz	ii. 337
gediegen	ii. 442	Epidote	ii. 282
kohlensaures	ii. 102	manganésifère	ii. 285
phosphorsaures	ii. 188	Epsom-salt	ii. 48
Eisenblau	ii. 188	Erdkobold	ii. 184
Eisenblüthe	ii. 79	Erdpeeh	iii. 59
Eisenchrom	ii. 396	Erdkohle	iii. 61
Eisenerde, grüne	iii. 106	Erdöl	iii. 59
Eisenglanz	ii. 404	Essonite	ii. 364
Eisenkalk	ii. 102	Etain oxydé	ii. 384
Eisenkies	ii. 457	Eucairite	iii. 94
Eisenkiesel	ii. 321	Euchlore-mica	ii. 178
Eisenopal	ii. 332	prismatic	ii. 180
Eisenoxyd	ii. 404	pyramidal	ii. 182
Eisenoxyd-hydrat	ii. 410	rhombohedral	ii. 178
Eisenschüssig Kupfer-		Euchroite	iii. 94
grün	ii. 158	Euclase	ii. 313
Eisentitan	ii. 376	Eudialyte	iii. 96
Eisenvitriol	ii. 41		
Eisspath	ii. 251	Fahlerz	iii. 1
Elaolite	iii. 93	Fahlunite	iii. 97
Elaterit	iii. 59	hard	ii. 320
Electrum	ii. 436	Faserkiesel	ii. 321
Emerald	ii. 313. 316	Faserzeolith	ii. 236
brazilian	ii. 353	Fassait	ii. 268
oriental	ii. 303	Feldspath	ii. 251
prismatic	ii. 313	apyre	ii. 293
rhombohedral	ii. 316	bleu	ii. 292
rhomboidal	ii. 316	gemeiner	ii. 251
Emerald copper	ii. 171	glasiger	ii. 251

Feldspath résinite	ii. 337	Flinty slate	ii. 326
Feldstein	ii. 251	Floatstone	ii. 321
Feld-spar	ii. 250	Flos ferri	ii. 81
blue	ii. 292	Fluate of cerium	iii. 100
prismato-pyrami-		of lime	ii. 69
dal	ii. 264	Fluellite	iii. 101
prismatic	ii. 251	Fluid Mercury	ii. 432
pyramidal	ii. 264	Fluor	ii. 69
rhombohedral	ii. 250	Fluor-haloïde	ii. 69
rhomboidal	ii. 250	octahedral	ii. 69
Felspar	ii. 251	rhomboidal	ii. 73
Fer arseniaté	ii. 162	Fluss	ii. 69
arsenical	ii. 449	Foliated coal	iii. 63
calcaréo-siliceux	ii. 414	Försterite	iii. 102
carburé	ii. 191	Franklinite	ii. 403
chromaté	ii. 396	Fraunensis	ii. 57
natif	ii. 442	Frugardite	ii. 356
oligiste	ii. 404	Fuller's earth	iii. 182
oxidé-carbonaté	ii. 102		
oxydé	ii. 404. 410	Gadolinite	ii. 371
oxydulé	ii. 400	Gahnit	ii. 298
phosphaté	ii. 188	Galena	iii. 13
sulfaté	ii. 41	hexahedral	iii. 13
sulfuré	ii. 457. 462	cobaltic	iii. 88
aculaire radié	ii. 462	Galmei	ii. 108. 111
blanc	ii. 462	Garnet	ii. 354. 359
ferrifère	ii. 465	dodecahedral	ii. 359. 364
magnétique	ii. 465	prismatic	ii. 364. 366
Fergusonite	iii. 98	prismatoidal	ii. 366
Fettstein	iii. 93	pyramidal	ii. 354
Feuerstein	ii. 321	tetrahedral	ii. 357
Fibrolite	iii. 99	Garnet-blende	iii. 32
Figurestone	iii. 100	Gas	ii. 17
Fire-damp	ii. 18	Gaseous Carbonic-acid	ii. 22
Fire-opal	ii. 336	Muriatic-acid	ii. 23
Flexible sulphuret of		Sulphuric-acid	ii. 23
silver	iii. 30	Gediegen Arsenik	ii. 423
Flint	ii. 326	Antimon	ii. 426



Gediegen Eisen	ii. 442	Gold, hexahedral	ii. 436
Gold	ii. 434	native	ii. 436
Kupfer	ii. 444	Gold-glance, graphic	iii. 21
Platin	ii. 441	yellow	iii. 171
Quecksilber	ii. 433	Göthite	ii. 413
Spiessglanz	ii. 426	Grammatit	ii. 275
Silber	ii. 433	Granat	ii. 359
Silvan	ii. 424	Granite, graphic	ii. 264
Tellur	ii. 424	Graphic gold	iii. 21
Wismuth	ii. 430	granite	ii. 264
Gehlenite	iii. 102	tellurium	iii. 21
Gekrösstein	ii. 64	Graphite	ii. 191
Gelbbleierz	ii. 140	Graphite-mica	ii. 191
Gelbes Rauschgelb	iii. 47	Grau-Braunstein	ii. 419
Gelb-Menakerz	ii. 373	Grau-Manganerz	ii. 419
Gem	ii. 293	Graugiltigerz	iii. 1
Gibbsite	iii. 103	Grauspiesglaserz	iii. 23
Gieseckite	iii. 104	Green earth	ii. 193
Gips	ii. 57	iron-earth	iii. 86. 106
Gismondin	iii. 174	lead-spar	ii. 136
Glance	iii. 1	vitriol	ii. 41
Glance-blende	iii. 31	Grenat	ii. 359
Glance-coal	iii. 64	Grenatite	ii. 366
Glanzerz	iii. 11	Grey antimony	iii. 23. 26
Glanz-Kobold	ii. 455	nickeliferous	iii. 131
Glanzkohle	iii. 65	Grey copper	iii. 1
Glaserz	iii. 11	antimonial	iii. 3
Glass, Muscovy	ii. 202	arsenical	iii. 3
Glauberite	ii. 54	Grobkohle	iii. 61
Glauber-salt	ii. 31	Grossular	ii. 359
anhydrous	ii. 33	Grünbleierz	ii. 134
prismatic	ii. 31	Grüne Eisenerde	iii. 106
Glaubersalz	ii. 31	Grünerde	ii. 194
Glimmer	ii. 198	Gurhofian	ii. 99
Gmelinite	iii. 104	Gyps	ii. 57
Gold	ii. 436	Gypsum	ii. 57
gediegen	ii. 436	anhydrous	ii. 62
graphic	iii. 21	axifrangible	ii. 57

Gypsum, prismatic	ii. 62	Hemi-prismatic Ruby-	
prismatoidal	ii. 57	blende	iii. 42
Gypsum-haloïde	ii. 57	Schiller-spar	ii. 207
prismatic	ii. 62	Sulphur	iii. 49
prismatoidal	ii. 57	Vitriol-salt	ii. 41
		Hepatic Cinnabar	iii. 45
Habroneme-malachite	ii. 173	Hepatit	ii. 121
hemi-prismatic	ii. 175	Hepatite	ii. 124
prismatic	ii. 173	Hessonite	ii. 365
Hair-salt	ii. 50	Heulandite	ii. 240. 242
Hal-baryte	ii. 116	Hexahedral Cobalt-py-	
di-prismatic	ii. 119	rites	ii. 455
hemi-prismatic	iii. 77	Glance-blende	iii. 31
peritomous	ii. 116	Gold	ii. 436
prismatic	ii. 121	Iron-pyrites	ii. 457
prismatoidal	ii. 126	Kouphone-spar	ii. 227
Haloïde	ii. 57	Lead-glance	iii. 13
Halotrichum	ii. 50	Lirocone-malachite	ii. 162
Hard Fahlunite	ii. 320	Pearl-Kerate	ii. 154
Harmotome	ii. 229	Rock-salt	ii. 36
Hart-Wasser	ii. 21	Silver	ii. 433
Hatchetine	iii. 106	Silver-glance	iii. 11
Häüyne	iii. 107	Hialith	ii. 332
Heavy-spar	ii. 121	Hiazinth	ii. 368
Heliotrop	ii. 321	Hisingerite	iii. 108
Heliotrope	ii. 327	Holz, bituminöses	iii. 61
Helvine	ii. 357	Hone	iii. 186
Hematite, black	ii. 418	Honestone	iii. 56
brown	ii. 412	Honigstein	iii. 56
red	ii. 408	Hopeite	iii. 109
Hemi-prismatic Augite-		Hornblei	ii. 148
spar	ii. 274	Hornblende	ii. 274
Habroneme-mala-		Hornerz	ii. 154
chite	ii. 175	Hornquecksilber	ii. 156
Hal-baryte	iii. 77	Horn silver	ii. 154
Kouphone-spar	ii. 242	Hornstein	ii. 321
Lead-baryte	ii. 137	Hornstone	ii. 321
Natron-salt	ii. 27	Houille	iii. 61

Humboldtine	iii. 110	Iron, native	ii. 442
Humboldtite	ii. 220	octahedral	ii. 442
Humite	iii. 110	oxydulated	ii. 339
Hyacinth	ii. 365. 369	prismatic blue	ii. 188
Hyalite	ii. 332	phosphate of	ii. 188
Hyalosiderite	iii. 111	spathose	ii. 102
Hydrate of Magnesia	iii. 112	specular	ii. 404
Hydrogen-gas	ii. 17	sulphate of	ii. 41
carburetted	ii. 18	titanitic	ii. 397
empyreumatic	ii. 18	tungstate of	ii. 387
phosphorous	ii. 19	Iron-earth, green	iii. 86. 106
phosphuretted	ii. 19	Iron-flint	ii. 328
pure	ii. 17	Iron-froth, red	ii. 408
sulphureous	ii. 19	brown	ii. 421
sulphuretted	ii. 19	Iron-mica	ii. 188
Hydrolite	iii. 104	Iron-ore	ii. 397
Hydrophane	ii. 332	axotomous	ii. 397
Hyperstene	ii. 209	black	ii. 418
		brown	ii. 410
Ice-spar	ii. 251	columnar clay	ii. 408
Ichthyophthalm	ii. 246	di-prismatic	ii. 414
Idocrase	ii. 354	dodecahedral	ii. 403
Idokras	ii. 354. 364	lenticular clay	ii. 408
Ignis fatuus	ii. 20	magnetic	ii. 401
Ilvait	ii. 414	micaceous	ii. 408
Indianite	iii. 113	octahedral	ii. 399
Indicolite	ii. 353	pitchy	iii. 136
Iolite	ii. 319	prismatic	ii. 410
Iridium	iii. 114	red	ii. 404. 407
Iridium and osmium,		rhombohedral	ii. 404
alloy of	iii. 114	rhomboidal	ii. 404
Iron	ii. 442	specular	ii. 407
arseniate of	ii. 162	Iron-pyrites	ii. 457. 462
arsenical	ii. 449	common	ii. 457
carbonate of	ii. 102	hexahedral	ii. 457
chromate of	ii. 396	magnetic	ii. 465
earthy blue	ii. 190	prismatic	ii. 461
hydrous oxide of	ii. 410	rhombohedral	ii. 465



Iron-pyrites, rhomboidal	ii. 465	Kieselmalachit	ii. 158
white	ii. 462	Kieselschiefer	ii. 321
Iron-sand	ii. 401	Killinite	iii. 117
Ironshot copper-green	ii. 159	Knebelite	iii. 118
Iron-sinter	iii. 115	Kobalt, arseniksaures	ii. 184
Iron-stone, green	ii. 364	Kobaltblüthe	ii. 184
		Kobaltglanz	ii. 455
Jade	iii. 149	Kochsalz	ii. 36
Jamesonite	i. 471	Kohlenblende	iii. 65
Jargon de Ceylon	ii. 371	Kohlensäure	ii. 22
Jasper	ii. 321	Kohlensaurer Baryt	ii. 119
Jayet	iii. 61	Strontian	ii. 116
Jeffersonite	iii. 115	Kohlensaures Eisen	ii. 102
Jet	iii. 61	Blei	ii. 130
		Kupfer	ii. 167. 175
Kalamit	ii. 275	Mangan	ii. 106
Kalk	ii. 84	Natron	ii. 27
flusssäurer	ii. 69	Kohlenwasserstoffgas	ii. 18
kohlensäurer	ii. 84	Kokkolith	ii. 268
phosphorsaurer	ii. 73	Kolophonit	ii. 359
wasserfreier schwe-		Korund	ii. 299
felsaurer	ii. 62	Kouphone-spar	ii. 224
wasserhaltiger		axotomous	ii. 246
schwefelsaurer	ii. 57	diatomous	ii. 234
Kalkstein	ii. 83	dodecahedral	ii. 225
Kalktuff	ii. 83	hemi-prismatic	ii. 242
Kallochrom	ii. 137	hexahedral	ii. 227
Kalzedon	ii. 321	paratomous	ii. 229
Kamkies	ii. 462	prismatic	ii. 236
Kaneelstein	ii. 364	prismatoidal	ii. 239
Kannelkohle	iii. 61	pyramidal	ii. 244
Kaolin	ii. 263	rhombohedral	ii. 232
Karinthin	ii. 275	trapezoidal	ii. 224
Karpholite	iii. 116	Kreide	ii. 83
Karstenit	ii. 62	Kreuzstein	ii. 229
Katzenauge	ii. 321	Krisoberil	ii. 304
Kerate	ii. 154	Krisolith	ii. 345
Kieselpupfer	ii. 158	Krisopras	ii. 321

- |                           |              |                        |          |
|---------------------------|--------------|------------------------|----------|
| Kryolith                  | ii. 66       | Lazulith               | ii. 292  |
| Krystallisirte Blaueisen- |              | körniger               | ii. 290  |
| erde                      | ii. 188      | splittriger            | ii. 292  |
| Kupfer, gediegen          | ii. 444      | Lead, arseniate of     | ii. 133  |
| kohlensaures              | ii. 167. 175 | blue                   | iii. 13  |
| phosphorsaures            | ii. 173      | carbonate of           | ii. 130  |
| Kupferbraun               | ii. 381      | chromate of            | ii. 137  |
| Kupferfahlerz             | iii. 1       | corneous               | ii. 150  |
| Kupferglanz               | iii. 8       | cupreous sulphate of   | ii. 149  |
| Kupferglas                | iii. 8       | cupreous sulphato-     |          |
| Kupferglimmer             | ii. 178      | carbonate of           | ii. 149  |
| Kupfergrün                | ii. 158      | molybdate of           | ii. 140  |
| Kupferindig               | iii. 118     | murio-carbonate of     | ii. 150  |
| Kupferkies                | ii. 469      | native                 | iii. 129 |
| gemeiner                  | ii. 469      | phosphate of           | ii. 133  |
| bunter                    | ii. 467      | sulphate of            | ii. 142  |
| Kupferlasur               | ii. 167      | sulphato-tri-carbo-    |          |
| Kupfernickel              | ii. 446      | nate of                | ii. 144  |
| Kupferroth                | ii. 381      | sulphato-carbonate of  | ii. 148  |
| Kupferschaum              | ii. 180      | sulphuret of           | iii. 13  |
| Kupfersmaragd             | ii. 171      | tungstate of           | iii. 165 |
| Kupfervitriol             | ii. 44       | Lead and copper, chro- |          |
| Kyanite                   | ii. 213      | mate of                | iii. 167 |
| Labrador                  | ii. 251      | Lead-baryte            | ii. 130  |
| Labrador schiller-spar    | ii. 209      | axotomous              | ii. 144  |
| Labradore felspar         | ii. 258      | di-prismatic           | ii. 130  |
| Labradorite               | ii. 257      | hemi-prismatic         | ii. 137  |
| Lapis lazuli              | ii. 288      | peritomous             | ii. 151  |
| Lapis ollaris             | ii. 196      | prismatic              | ii. 142  |
| Lasurstein                | ii. 288      | pyramidal              | ii. 140  |
| Latrobite                 | iii. 118     | rhombohedral           | ii. 133  |
| Laumonite                 | ii. 234      | Lead-glance            | iii. 13  |
| Lave altérée alunifère    | ii. 67       | cobaltic               | iii. 88  |
| vitreuse obsidienne       | ii. 337      | hexahedral             | iii. 13  |
| vitreuse perlée           | ii. 337      | Lead-spar, brown       | ii. 136  |
| vitreuse punicée          | ii. 337      | di-prismatic           | ii. 130  |
| Lazulite                  | ii. 289. 290 | green                  | ii. 136  |
|                           |              | hemi-prismatic         | ii. 137  |

Lead-spar, prismatic	ii. 137. 142	Liquid Sulphuric-acid	ii. 24
pyramidal	ii. 140	Liriconite	ii. 160
red	ii. 137	Lirocone-malachite	ii. 160
rhomboidal	ii. 133	hexahedral	ii. 162
tri-prismatic	ii. 142	prismatic	ii. 160
Lebererz	iii. 44	Lithomarge	iii. 183
Leberkies	ii. 462. 465	Loam	iii. 180
Leelite	iii. 119	Loboite	ii. 356
Lenticular copper	ii. 160	Lomonit	ii. 234
Lepidolite	ii. 202	Luft, atmosphärische	ii. 20
crystallized	ii. 353	Lumachella	ii. 91
Leucite	ii. 224	Lydian stone	ii. 326
Leuzit	ii. 224	Macle	ii. 258
Levyne	iii. 120	Maclureite	iii. 87. 88
Lievrite	ii. 414	Macrotypous Lime-haloide	ii. 93
Ligurite	iii. 121	Parachrose-baryte	ii. 106
Lime, arseniate of	iii. 135	Magnesia, borate of	ii. 347
borate of	ii. 220	carbonate of	iii. 121
carbonate of	ii. 83	hydrate of	iii. 112
fluat of	ii. 69	native	iii. 112
phosphate of	ii. 73	sulphate of	ii. 48
sulphate of	ii. 57	Magnesia and iron, carbonate of	ii. 98
tungstate of	ii. 113	Magnesian marble	iii. 122
Lime-haloide	ii. 79	Magnésie, boratée	ii. 348
brachytypous	ii. 98	sulfatée	ii. 48
macrotypous	ii. 93	Magnesite	iii. 121
paratomous	ii. 100	Magneteisenstein	ii. 399
prismatic	ii. 79	Magnetic iron-ore	ii. 401
rhombohedral	ii. 83	Magnetkies	ii. 465
Limestone	ii. 83	Malachite	ii. 158. 175
brachytypous	ii. 98	di-prismatic green	ii. 175
macrotypous	ii. 93	common	ii. 175
magnesian	ii. 94	prismatic	ii. 167
prismatic	ii. 79	prismatic blue	ii. 167
rhomboidal	ii. 83	prismatic green	ii. 173
Linsenerz	ii. 160		
Linsenkupfer	ii. 160		



Malacolithe	ii. 268	Marble, magnesian	iii. 122
Mangan, kohlenaures	ii. 106	Marekanite	ii. 339
Manganblende	iii. 31	Margarite	ii. 204
Manganese, black	ii. 416	Marl	ii. 90
carbonate of	ii. 106	Marle, bituminous	iii. 178
compact grey oxide		Marlslate, bituminous	ii. 90
of	ii. 418	Marmo bardiglio di Ber-	
corneous	iii. 123	gamo	ii. 65
cupreous	iii. 92	Marmolite	iii. 124
grey oxide of	ii. 419	Martial arseniate of	
phosphate of	iii. 136	copper	iii. 149
rhomboidal red	ii. 106	Mascagnine	iii. 125
siliciferous oxide of	iii. 122	Meionite	ii. 264
sulphuret of	iii. 31	Melane-glance	iii. 27
Manganèse, carbonaté	ii. 106	Melanit	ii. 359
oxidé carbonaté	ii. 106	Melanite	ii. 361
oxidé hydraté	ii. 416	Melichrone-resin	iii. 56
oxidé rose silicifère		Mellilite	iii. 125
amorphe	ii. 106	Mellite	iii. 56
oxydé	ii. 419	Menachine-ore, brown	ii. 375
oxydé hydraté con-		yellow	ii. 375
crétionné	ii. 418	Menilite	ii. 332
oxydé noir-brunatre	ii. 418	Mercure argental	ii. 431
sulfuré	iii. 31	muriaté	ii. 156
Manganese-blende	iii. 31	natif	ii. 433
Manganese-ore	ii. 416	sulfuré	iii. 44
black	ii. 418	Mercury	ii. 431
compact	ii. 418	dodecahedral	ii. 431
fibrous	ii. 418	fluid	ii. 432
foliated black	ii. 416	liquid native	ii. 432
grey	ii. 419	muriate of	ii. 156
prismatic	ii. 418, 419	pyramidal corneous	ii. 156
prismatoidal	ii. 419	sulphuret of	iii. 44
pyramidal	ii. 416	Mergel	ii. 83
uncleavable	ii. 418	Mergelschiefer, bitumi-	
Manganese-spar	iii. 122	nöser	ii. 83
Manganglanz	iii. 31	Mesole	iii. 126
Marble	ii. 93	Mesoline	iii. 126

Mesolite	ii. 237	Mountain soap	iii. 184
Mesotype	ii. 236	tallow	iii. 107
épointée	ii. 244	Mullers glass	ii. 332
Metal	ii. 423	Muriate of ammonia	ii. 39
Meteoreisen	ii. 442	of copper	iii. 74
Mica	ii. 178. 198	of mercury	ii. 156
rhomboïdal	ii. 193. 198	of silver	ii. 154
Miomite	ii. 97	Muriatic-acid	ii. 23
Mine d'argent grise an-		Muriazit	ii. 62
timoniale	iii. 30	Murio-carbonate of lead	ii. 150
Mineral-Alkali	ii. 27	Muscovy glass	ii. 202
Mineral, agaric	ii. 89		
Mineral adipocire	iii. 107	Nacrite	ii. 196
caoutchouk	iii. 60	Nagyager-erz	iii. 16
carbon	iii. 64	Naphtha	iii. 59
charcoal	iii. 64. 66	Native Amalgam	ii. 431
oil	iii. 59	Antimony	ii. 426
pitch	iii. 59	Arsenic	ii. 423
turquois	iii. 83	Bismuth	ii. 430
Mineral-coal	iii. 61	Copper	ii. 444
bituminous	iii. 61	Gold	ii. 436
non-bituminous	iii. 64	Iron	ii. 442
Mineral-resin	iii. 57	Lead	iii. 129
black	iii. 59	Nickel	iii. 129
yellow	iii. 57	Palladium	iii. 134
Mispickel	ii. 449	Platina	ii. 441
Molybdänglanz	iii. 18	Quicksilver	ii. 432
Molybdänsaures Blei	ii. 140	Silver	ii. 433
Molybdate of lead	ii. 140	Tellurium	ii. 424
Molybdena, rhomboidal	iii. 18	Natrolite	ii. 237
sulphuret of	iii. 18	Natron	ii. 27
Molybdena-glance	iii. 18	boraxsaures	ii. 52
Molybdena-silver	iii. 127	kohlensaures	ii. 27
Molybdène sulfuré	iii. 18	prismatic	ii. 27
Molybdic silver	iii. 127	schwefelsaures	ii. 31
Moonstone	ii. 264	Natron-salt	ii. 27
Moor coal	iii. 62	hemi-prismatic	ii. 27
Moorkohle	iii. 61	prismatic	ii. 29

Natürlich Amalgam	ii. 431	Octahedral Copper-ore	ii. 381
Kochsalz	ii. 36	Copper-pyrites	ii. 467
Mineral-Alkali	ii. 27	Corundum	ii. 298
Natürlicher Salmiak	ii. 39	Diamond	ii. 306
Salpeter	ii. 34	Fluor-haloide	ii. 69
Schwefel	iii. 52	Iron-ore	ii. 399
Vitriol	ii. 41. 44. 46	Iron	ii. 442
Needle-ore	iii. 130	Octahedrite	ii. 379
Nepheline	ii. 250	Oil, mineral	iii. 59
Nephrite	iii. 131	Oktaedrit	ii. 379
Nickel, arsenical	ii. 446	Olive-malachite	ii. 164
arseniaté	ii. 448	di-prismatic	ii. 166
arsenate of	ii. 448	prismatic	ii. 164
native	iii. 129	Olivenerz	ii. 164. 166
Nickel-ochre	ii. 448	Olivenit	ii. 164
Nickel-pyrites	ii. 446	Olivenite acicular	ii. 164
Nickeliferous grey an-		di-prismatic	ii. 160. 166
timony	iii. 131	hexahedral	ii. 162
Nigrine	ii. 376	prismatic	ii. 164. 166. 173
Nitrate of soda	iii. 132	radiated acicular	iii. 144
of potash	ii. 34	Olivenkupfer	ii. 164
Nitre	ii. 34	Olivin	ii. 345
Nitre-salt	ii. 34	Omphazit	ii. 268
Non-bituminous Mine-		Oolite	ii. 89
ral-coal	iii. 64	Opal	ii. 332
Nosin	iii. 157	Opal-jasper	ii. 335
Nuttallite	iii. 133	Opal-jaspis	ii. 332
		Or natif	ii. 434
Oblique prismatic ar-		Ore	ii. 373
seniate of copper	iii. 144	Oriental amethyste	ii. 303
Obsidian	ii. 337	aquamarine	ii. 312
Octahedral Alum-salt	ii. 50	emerald	ii. 303
Ammoniac-salt	ii. 39	ruby	ii. 303
Arsenic-acid	ii. 26	sapphire	ii. 303
Bismuth	ii. 430	topaz	ii. 303
Chrome-ore	ii. 396	Orpiment	iii. 47. 48
Cobalt-pyrites	ii. 452	yellow	iii. 47
Copper	ii. 444	red	iii. 49



Orthite	iii. 133	Péridot	ii. 345
Osmium, alloy of iri-		Peritomous Hal-baryte	ii. 116
dium and	iii. 114	Lead-baryte	ii. 151
Oxide of antimony	ii. 152	Ruby-blende	iii. 44
of arsenic	ii. 26	Titanium-ore	ii. 376
of iron, hydrous	ii. 410	Perlglimmer	ii. 304
of manganese, grey		Perlstein	ii. 337
compact	ii. 418	Petaline-spar	ii. 248
grey	ii. 419	Petalite	ii. 248
siliciferous	iii. 122	Petrosilex résinite	ii. 337
of tin	ii. 384	Pharmacolite	iii. 135
of zinc, red	ii. 380	Pharmakosiderit	ii. 162
siliceous	ii. 108	Phisalit	ii. 308
		Phosphate of cop-	
Palladium	iii. 134	per	ii. 166. 173
Papierkohle	iii. 61	hydrous	ii. 173
Parachrose-baryte	ii. 101	of iron	ii. 188
brachytypous	ii. 101	of lead	ii. 133
macrotypous	ii. 106	of lime	ii. 73
Paranthine	ii. 264	of manganese	iii. 136
Paratomous Augite-spar	ii. 268	of uranium	ii. 182
Kouphone-spar	ii. 229	Phosphorit	ii. 73
Lime-haloide	ii. 100	Phosphorkupfererz	ii. 173
Pargasite	ii. 281	Phosphorous Hydrogen-	
Pea-stone	ii. 89	gas	ii. 19
Peach	ii. 198	Phosphorsaurer Kalk	ii. 73
Pearl-kerate	ii. 154	Phosphorsaures Blei	ii. 134
hexahedral	ii. 154	Eisen	ii. 188
pyramidal	ii. 156	Kupfer	ii. 166. 173
Pearl-mica	ii. 204	Phosphorwasserstoffgas	ii. 19
Pearlspar	ii. 94	Photizite	iii. 123
Pearlstone	ii. 337	Physalite	ii. 311
Pecherz	ii. 393	Picnit	ii. 308
Pechkohle	iii. 61	Picrolite	iii. 136
Pechstein	ii. 337	Picropharmacolite	iii. 135
Pechuran	ii. 393	Picrosmine	iii. 137
Peliom	ii. 319	Pictite	iii. 167
Pentaklasit	ii. 268	Pierre de trippes	ii. 64

Pinite	iii. 139	Porcelain-spar	ii. 260
Pipe-clay	iii. 180	Pot-stone	ii. 196
Pirenïit	ii. 359	Potash, nitrate of	ii. 34
Pirop	ii. 359	sulphate of	iii. 159
Pisolite	ii. 89	Potasse nitratée	ii. 34
Pistazit	ii. 282	sulfatée	iii. 159
Pitch, mineral	iii. 59	Potter's-clay	iii. 180
Pitch-blende	ii. 393	Prase	ii. 326
Pitch coal	iii. 63	Prehnite	ii. 217
Pitch-ore	ii. 393	Prismatic Andalusite	ii. 293
Pitchstone	ii. 337	Antimony	ii. 427
Pitchy iron-ore	iii. 136	Antimony-baryte	ii. 151
Plasma	ii. 321	Antimony-glance	iii. 4. 21
Platina	ii. 441	arseniate of cop-	
Pleonaste	ii. 295	per, oblique	iii. 144
Plomb carbonaté	ii. 130	Arsenical-pyrites	ii. 449
carbonaté rhomboi-		Augite-spar	ii. 286
dal	ii. 144	Axinite	ii. 341
chromaté	ii. 137	Azure-malachite	ii. 167
hydro-aluminé	iii. 140	Azure-spar	ii. 290
molybdaté	ii. 140	Bismuth-glance	iii. 19
natif	iii. 129	Boracic-acid	ii. 25
phosphaté	ii. 134	Borax-salt	ii. 52
sulfaté	ii. 142	Brithyne-salt	ii. 54
sulfuré	iii. 13	Chrysolite	ii. 345
sulfuré antimoni-		Cobalt-mica	ii. 184
fère	iii. 5	Copper-glance	iii. 8
sulfure plombo-cu-		Corundum	ii. 304
prifère	iii. 5	Cryone-haloïde	ii. 66
Plombgomme	iii. 140	Disthene-spar	ii. 213
Plumbago	ii. 191	Dystome-spar	ii. 220
Plumbo-cuprifereous sul-		Emerald	ii. 313
phuret of bismuth	iii. 130	Emerald-malachite	iii. 95
Polishing slate	iii. 184	Epsom-salt	ii. 48
Polyhalite	iii. 141	Euchlore-mica	ii. 180
Polyxen	ii. 441	Feld-spar	ii. 251
Porcelain-earth	ii. 259	Gadolinite	ii. 371
Porcelain-jasper	ii. 328	Glauber-salt	ii. 31

Prismatic Gypsum-haloide	ii. 62	Prismatoidal Hal-baryte	ii. 126
Habroneme-malachite	ii. 173	Kouphone-spar	ii. 239
Hal-baryte	ii. 121	Manganese-ore	ii. 419
Iron-mica	ii. 188	Schiller-spar	ii. 209
Iron-ore	ii. 410	Sulphur	iii. 47
Iron-pyrites	ii. 461	Pseudomalachit blättriger	ii. 173
Kouphone-spar	ii. 236	Pumice	ii. 337
Lead-baryte	ii. 142	Pure Atmospheric-gas	ii. 20
Lime-haloide	ii. 79	Atmospheric-water	ii. 21
Lirocone-malachite	ii. 160	Hydrogen-gas	ii. 17
Melane-glance	iii. 27	Purple-blende	iii. 36
Natron-salt	ii. 29	Pycnite	ii. 308. 311
Nickel-pyrites	ii. 446	Pyralloite	iii. 141
Nitre-salt	ii. 34	Pyramidal Copper-pyrites	ii. 469
Olive-malachite	ii. 164	Euchlore-mica	ii. 182
Petalinē-spar	ii. 248	Feld-spar	ii. 264
Purple-blende	iii. 36	Garnet	ii. 354
Quartz	ii. 319	Kouphone-spar	ii. 244
Scheelium-ore	ii. 387	Lead-baryte	ii. 140
Schiller-spar	ii. 211	Manganese-ore	ii. 416
Sulphur	iii. 52	Melichrone-resin	iii. 56
Talc-mica	ii. 193	Pearl-kerate	ii. 156
Tantalum-ore	ii. 390	Scheelium-baryte	ii. 113
Tellurium-glance	iii. 16	Tin-ore	ii. 384
Titanium-ore	ii. 373	Titanium-ore	ii. 379
Topaz	ii. 308	Zircon	ii. 368
Triphane-spar	ii. 216	Pyreneite	ii. 361
Vitriol-salt	ii. 46	Pyrites	ii. 446
Zinc-baryte	ii. 108	auriferous	ii. 461
Prismatoidal Antimony-glance	iii. 23. 26	capillary	iii. 130
Augite-spar	ii. 282	cellular	ii. 460. 464
Azure-spar	ii. 292	cockscomb	ii. 464
Copper-glance	iii. 4	hepatic	ii. 464
Garnet	ii. 366	magnetic	ii. 465
Gypsum-haloide	ii. 57	radiated	ii. 464



Pyrites, spear	ii. 464	Realgar	iii. 48. 50
Pyromorphit	ii. 134	Red antimony	iii. 36
Pyrop	ii. 359	manganese, rhom-	
Pyrope	ii. 361	boidal	ii. 106
Pyrorthite	iii. 142	orpiment	iii. 49
Pyrosmalite	iii. 143	silver	iii. 38
Pyro-smaragdus	ii. 72	vitriol	iii. 145
Pyroxène	ii. 268	Resin	iii. 56
Quartz	ii. 319. 325	Retinasphalt	iii. 146
common	ii. 326	Retinite	iii. 146
empyrodox	ii. 337	Rhætizit	ii. 213
fibrous	ii. 327	Rhodochrosit	ii. 106
fusible	ii. 337	Rhodonite	iii. 123
hyalin-concrétionné	ii. 332	Rhombohedral Alum-	
indivisible	ii. 332. 337	haloide	ii. 67
prismatic	ii. 319	Antimony	ii. 426
prismato-rhomboi-		Corundum	ii. 299
dal	ii. 319	Emerald	ii. 316
résinite	ii. 332	Emerald-malachite	ii. 171
rhombohedral	ii. 321	Euchlore-mica	ii. 178
rhomboïdal	ii. 321	Feld-spar	ii. 250
rose	ii. 326	Fluor-haloide	ii. 73
spongiform	ii. 321	Graphite-mica	ii. 191
uncleavable	ii. 332	Iron-ore	ii. 404
Quecksilber, gediegen	ii. 433	Iron-pyrites	ii. 465
Quecksilber-Hornerz	ii. 156	Kouphone-spar	ii. 232
Quecksilber-Lebererz	iii. 44	Lead-baryte	ii. 133
Quicksilver, native	ii. 432	Lime-haloide	ii. 83
Quicksilver liver-ore	iii. 45	Molybdena-glance	iii. 18
Radiated acicular oli-		Pearl-mica	ii. 204
venite	iii. 144	Quartz	ii. 321
Rauschgelb	iii. 47	Ruby-blende	ii. 38
gelbes	iii. 47	Talc-mica	ii. 198
rothes	iii. 50	Tourmaline	ii. 349
Rauchwacke	iii. 73	Zinc-baryte	ii. 111
Rautenspath	ii. 94. 96	Rhomb-spar	ii. 96. 98
		Rock-cork	ii. 279
		Rock-crystal	ii. 325

Rock-milk	ii. 89	Salt	ii. 27
Rock-salt	ii. 36	common	ii. 36
Rock-wood	ii. 279	Salzsäure	ii. 23
Roestone	ii. 89	Saphir	ii. 299
Rohwand	ii. 100	Sapphire	ii. 301
Röschgewächs	iii. 29	oriental	ii. 303
Rose quartz	ii. 326	d'eau	ii. 321
Roselite	iii. 147	Sarcolite	iii. 104. 147
Rosszahn	ii. 100	Sassoline	ii. 25
Rothbleierz	ii. 137	Satin-spar	ii. 82
Rotheisenstein	ii. 404	Saugkalk	ii. 84
Rothes Rauschgelb	iii. 50	Saussurite	iii. 148
Rothgiltigerz	iii. 38	Scapolite	ii. 264
Rothkupfererz	ii. 381	Schabasit	ii. 232
Rothspiesglaserz	iii. 36	Schalstein	ii. 286
Rubinglimmer	ii. 413	Schéelin, calcaire	ii. 113
Ruby	ii. 301	ferruginé	ii. 387
oriental	ii. 303	Scheelit	ii. 113
spinelle	ii. 295. 298	Scheelium-baryt	ii. 113
balas	ii. 298	Scheelium-ore	ii. 387
Ruby-blende	iii. 38	Schieferspath	ii. 83. 84
hemi-prismatic	iii. 42	Schilfglaserz	iii. 31
peritomous	iii. 44	Schiller-spar	ii. 206. 207
prismato-rhomboidal	iii. 44	axotomous	ii. 274
rhombohedral	iii. 38	common	ii. 206
rhomboidal	iii. 38	diatomous	ii. 206
Ruby silver	iii. 38	hemi-prismatic	ii. 207
Ruby sulphur	iii. 49	labradore	ii. 209
Russkohle	iii. 61	prismatic	ii. 211
Rutile	ii. 376	prismatoidal	ii. 209
		Schillerspath	ii. 206
		Schillerstein	ii. 206. 207
Sahlit	ii. 268	Schmelzstein	ii. 264
Sal ammoniac	ii. 39	Schmirgel	ii. 299
Salamstein	ii. 296. 299	Schörl	ii. 349
Salamstone	ii. 301	Schörlartiger Beril	ii. 308
Salmiak	ii. 39	Schrifterz	iii. 21
Salpeter	ii. 34	Schrift-Tellur	iii. 21

Schwaden	ii. 23	Silber, gediegen	ii. 433
Schwarz Braunstein,		Silberglanz	iii. 11
blättriger	ii. 416	Silber-Hornerz	ii. 154
dichter	ii. 418	Silberspiessglanz	ii. 427
fasriger	ii. 418	Silice fluatée alumi-	
Schwarzbleierz	ii. 130	neuse	ii. 308
Schwarzzeisenstein	ii. 418	Siliceous oxide of zinc	ii. 108
Schwarzerz	iii. 1. 31	sinter	ii. 332
Schwarzgiltigerz	iii. 1. 27	Siliciferous oxide of	
Schwarzkohle	iii. 61	manganese	iii. 122
Schwarzmanganerz	ii. 418	Sillimanite	iii. 153
Schwarzspiesglaserz	iii. 5	Silvan, gediegen	ii. 424
Schwefel	iii. 52	Silver	ii. 433
Schwefelkies	ii. 457	antimonial	ii. 429
Schwefelsäure	ii. 24	arsenical	ii. 429
Schwefelsaurer Baryt	ii. 121	bismuthic	iii. 78
Kalk, wasserfreier	ii. 62	black	ii. 435
Kalk, wasserhalti-		brittle sulphuret of	iii. 27
ger	ii. 57	flexible sulphuret	
Strontian	ii. 126	of	iii. 30
Schwefelsaures Natron	ii. 31	hexahedral	ii. 433
Schwefelwasserstoffgas	ii. 19	hexahedral corne-	
Schweflichte Säure	ii. 23	ous	ii. 154
Schwerspath	ii. 121	molybdic	iii. 127
Schwerstein	ii. 113	muriate of	ii. 154
Schwimmkiesel	ii. 321	native	ii. 433
Schwimstein	ii. 321	red	iii. 38
Scolezite	ii. 233	sulphuret of	iii. 11
Scorodite	iii. 149	vitreous	iii. 11
Scorza	ii. 371	white	iii. 29
Sea-salt	ii. 37	Silver and antimony,	
Selenite	ii. 60	sulphuret of	iii. 30
Seleniuret of copper	iii. 150	Silver and copper, se-	
of silver and cop-		leniuret of	iii. 94
per	iii. 94	sulphuret of	iii. 73
Semi-opal	ii. 335	Silver-glance	iii. 11
Serpentine	iii. 151	brittle	iii. 27
Shale, bituminous	iii. 178	hexahedral	iii. 11



Silver-glance, rhomboidal	iii. 27	Spath en tables	ii. 286
Sinter, siliceous	ii. 332	Spathose iron	ii. 102
Skapolith	ii. 264	Spatheisenstein	ii. 102
Skorodite	iii. 149	Speiskobalt	ii. 452
Slate, adhesive	iii. 177	Speiskobold, weisser	ii. 452
polishing	iii. 184	Sphærolite	iii. 155
Slate coal	iii. 63	Sphærosiderit	ii. 102
Slate-spar	ii. 90	Sphene	ii. 373
Smaragd	ii. 316	Spiessglanzbleierz	iii. 5
Smaragdite	ii. 274	Spiessglanzweiss	ii. 152
Smoky topaz	ii. 330	Spiesglas-Silber	ii. 427
Snuff, Spanish	ii. 425	Spinel	ii. 295
Soap, mountain	iii. 184	Spinellane	iii. 156
Soapstone	iii. 157	Spinelle ruby	ii. 295
Soda	ii. 17	Spinelle zincifère	ii. 298
borate of	ii. 52	Spodumene	ii. 216
carbonate of	ii. 27	Sprödglasserz	iii. 27
nitrate of	iii. 132	Stangenkohle	iii. 65
sulphate of	ii. 31	Staphyline-malachite	ii. 158
Sodalite	ii. 225. 226	Staurolite	ii. 366
Somervillite	iii. 154	Staurotide	ii. 366
Sommite	ii. 250	Steatite	iii. 157
Sordawalite	iii. 155	Steinheillite	ii. 320
Soude boratée	ii. 52	Steinsalz	ii. 36
carbonatée	ii. 27	Stilbite	ii. 239. 242
muriatée	ii. 36	Stilpnosiderite	iii. 158
nitratée	iii. 132	Stinkgyps	ii. 57
sulfatée	ii. 31	Stinkkalk	ii. 84
Soufre	iii. 52	Stinkmergel	ii. 84
Spanish snuff	ii. 425	Stinkstein	ii. 83
Spar	ii. 206	Stinkzinner	iii. 44
calcareous	ii. 89	Strahlkies	ii. 462
doubly refracting	ii. 92	Strahlstein	ii. 268. 274
Bolognese-	ii. 124	Strahlzeolith	ii. 239
Spargelstein	ii. 73	Stromnite	iii. 159
Spärkies	ii. 462	Stronthian	ii. 116
Sparry iron	ii. 101	Strontian, carbonate of	ii. 116
Spath chatoyant	ii. 206	kohlensaurer	ii. 116

- Strontian, schwefelsaurer ii. 126  
     sulphate of ii. 126  
 Strontiane carbonatée ii. 116  
     sulfatée ii. 126  
 Strontianite ii. 116  
 Subphosphate of alu-  
     mine iii. 169  
 Succin iii. 57  
 Sulphate of ammonia iii. 125  
     of barytes ii. 121  
     of cobalt iii. 145  
     of copper ii. 44  
     of iron ii. 41  
     of lime ii. 57  
     of lead ii. 142  
     of magnesia ii. 48  
     of potash iii. 159  
     of soda ii. 31  
     of strontia ii. 126  
     of zinc ii. 46  
 Sulphato-carbonate of  
     of lead ii. 148  
 Sulphato-tri-carbonate  
     of lead ii. 144  
 Sulphur iii. 47. 52  
     hemi-prismatic iii. 49  
     prismatic iii. 52  
     prismatoidal iii. 47  
 Sulphureous Hydrogen-  
     gas ii. 19  
 Sulphuret of antimony iii. 23  
     of bismuth iii. 19  
     of bismuth, cupri-  
         ferous iii. 91  
     of bismuth, plum-  
         bo-cupriferous iii. 130  
     of cobalt iii. 88  
     of copper iii. 8  
 Sulphuret of lead iii. 13  
     of manganese iii. 31  
     of mercury iii. 44  
     of molybdena iii. 18  
     of silver iii. 11  
     of silver, brittle iii. 27  
     of silver, flexible iii. 30  
     of silver and anti-  
         mony iii. 30  
     of tin iii. 163  
     of zinc iii. 32  
     triple iii. 5  
 Sulphuretted hydrogen gas ii. 19  
 Sulphuric-acid ii. 23  
     aëriiform ii. 23  
     gaseous ii. 23  
     liquid ii. 24  
 Sunstone ii. 264  
 Surturbrand iii. 64  
 Swath ii. 23  
 Swine-stone ii. 90  
 Tabular-spar ii. 286  
 Tafelspath ii. 286  
 Talc ii. 193  
     venetian ii. 198  
 Talc-mica ii. 193  
     prismatic ii. 193  
     rhomboidal ii. 198  
     rhomboidal ii. 198  
 Talk ii. 194  
 Tallow, mountain iii. 107  
 Tantale oxidé ii. 390  
 Tantalite ii. 390  
 Tantalum-ore ii. 390  
 Télésie ii. 299  
 Tellure natif aurifère  
     et argentifère iii. 21

Tellure natif aurifère et		Tin-stone	ii. 386
plombifère	iii. 16	Tinder-ore	iii. 37
auro-argenti-		Tinkal	ii. 52
fère	iii. 21	Titane anatase	ii. 379
auro-ferrifère	ii. 424	calcaréo-siliceux	ii. 373
auro-plombifère	iii. 16	oxydé	ii. 376
ferrifère et auri-		silicéo-calcaire	ii. 373
fère	ii. 424	Titanite	ii. 375. 376
Tellurium	ii. 424	Titanitic iron	ii. 397
black	iii. 16	Titanium-ore	ii. 373
graphic	iii. 21	peritomous	ii. 376
hexahedral	ii. 424	prismatic	ii. 373
native	ii. 424	prismato-pyramidal	ii. 376
prismatic black	iii. 16	pyramidal	ii. 379
yellow	iii. 171	Topaz	ii. 308
Tellurium-glance	iii. 16	oriental	ii. 303
Tennantite	iii. 161	prismatic	ii. 303
Terra miraculosa Sax-		smoky	ii. 330
oniæ	iii. 184	Topfstein	ii. 194
Tesselite	ii. 247	Torrelite	iii. 164
Tetarto-prismatic Vi-		Tourmaline	ii. 349
triol-salt	ii. 44	Trapezoidal Kouphone-	
Tetrahedral Boracite	ii. 347	spar	ii. 224
Copper-glance	iii. 1	Traublenblei	ii. 134
Garnet	ii. 357	Tremolite	ii. 278
Tetraklasit	ii. 264	Tremolith	ii. 275
Thomsonite	iii. 162	Triclasite	iii. 97
Thoneisenstein	ii. 404. 410	Triphane	ii. 216
Thulite	iii. 162	Triphane-spar	ii. 216
Thumerstone	ii. 344	axotomous	ii. 217
Thumite	ii. 344	prismatic	ii. 216
Tile-ore	ii. 382	Triple sulphuret	iii. 5
Tin, oxide of	ii. 384	Tripoli	iii. 185
sulphuret of	iii. 163	Trona	ii. 27. iii. 164
Tin-ore	ii. 384	Tufa, calcareous	ii. 90
pyramidal	ii. 384	Tungstate of iron	ii. 387
cornish	ii. 386	of lead	iii. 165
Tin-pyrites	iii. 163	of lime	ii. 113



Tungsten	ii. 113	Vitriol, red	iii. 145
Turkey hone	iii. 186	rhomboidal	ii. 41
Turmalin	ii. 349	white	ii. 46
Turnerite	iii. 166	Vitriol-Bleierz	ii. 142
Turquoise, mineral	iii. 83	Vitriol-salt	ii. 41
Turquoise	iii. 83	hemi-prismatic	ii. 41
		prismatic	ii. 46
Umber	iii. 186	tetarto-prismatic	ii. 44
Uncleavable Cerium-ore	ii. 394	Vivianite	ii. 188
Manganese-ore	ii. 418	Vulpinite	ii. 64
Quartz	ii. 332		
Staphyline-mal-		Wad, black	ii. 421
chite	ii. 158	Wagnerite	iii. 169
Uranium-ore	ii. 393	Wand, rohe	ii. 100
Uran-Glimmer	ii. 182	Wandstein	ii. 100
Uran-mica	ii. 182	Wasser, Hart-	ii. 21
Uran-ochre	ii. 393	Weich-	ii. 21
Uran-Oxyd	ii. 182	Wasserblei	iii. 16
Uran-Pecherz	ii. 393	Wasserkies	ii. 462
Urane oxydé	ii. 182	Wasserstoffgas	ii. 17
Urane oxydulé	ii. 393	Water	ii. 21
Uranite	ii. 182	Wavellite	iii. 169
Uranium-ore	ii. 393	Weich-Wasser	ii. 21
Uranium, indivisible	ii. 393	Weichgewächs	iii. 12
phosphate of	ii. 182	Weissbleierz	ii. 130
		Weisser Speiskobold	ii. 452
Variolite	ii. 259	Weissgiltigerz	iii. 29
Vauquelinite	iii. 167	Weisspiesglaserz	ii. 151
Venetian talc	ii. 198	Wernerite	ii. 264
Vesuvian	ii. 354	Whet-slate	iii. 186
Velvet-blue copper	iii. 168	White antimony	ii. 152
Vitreous copper	iii. 8	cobalt, radiated	ii. 454
silver	iii. 11	silver	iii. 29
Vitriol, blue	ii. 44	vitriol	ii. 46
green	ii. 41	Wismuth, gediegen	ii. 430
natürlicher	ii. 41, 44, 46	Wismuthglanz	iii. 19
prismatic	ii. 44	Withamite	iii. 170
pyramidal	ii. 46	Witherite	ii. 119

Wolfram	ii. 387	Zeolite, trapezoidal	ii. 224
Wollastonite	ii. 286	Zeolith	ii. 236
Wood, bituminous	iii. 62	Ziegelerz	ii. 381
Wood, rock	ii. 279	Zinc, carbonate of	ii. 111
Wood-opal	ii. 335	carbonaté	ii. 111
Wood-stone	ii. 326	oxidé	ii. 108
Wood-tin	ii. 386	oxidé ferrifère lamel-	
Würfelerz	ii. 162	laire brun rouge-	
		atre	ii. 380
Yellow earth	iii. 187	oxidé silicifère	ii. 108
gold-glance	iii. 171	red	ii. 380
Mineral-resin	iii. 57	red oxide of	ii. 380
orpiment	iii. 47	siliceous oxide of	ii. 108
tellurium	iii. 171	sulphate of	ii. 46
Yenite	ii. 414	sulfaté	ii. 46
Ytthro-cerite	iii. 172	sulfuré	iii. 32
Ytthro-columbite	iii. 173	sulphuret of	iii. 32
Ytthro-tantalite	iii. 173	Zink-baryte	ii. 108
		prismatic	ii. 108
Zeagonite	iii. 174	rhombohedral	ii. 111
Zeilanit	ii. 295	Zinc-blende	iii. 32
Zelkies	ii. 457. 462	Zinc-ore	ii. 380
Zeolite, axifrangible	ii. 244. 246	Zinerz, Kornisch	ii. 384
diatomous	ii. 234	Zinkvitriol	ii. 46
di-prismatic	ii. 234	Zinkglas	ii. 108
dodecahedral	ii. 224. 225	Zinkoxyd	ii. 380
efflorescente	ii. 234	Zinkspath	ii. 111
foliated	ii. 242	Zinnerz	ii. 384
hemi-prismatic	ii. 242	Zinnober	iii. 44
hexahedral	ii. 227	Zinnstein	ii. 384
prismatic	ii. 236	Zircon	ii. 368
prismatoidal	ii. 239. 242	Zirkon	ii. 368
pyramidal	ii. 229. 244	Zoisit	ii. 282
pyramido-prismatic	ii. 229	Zölestin	ii. 126
radiated	ii. 239	Zurlite	iii. 176
rhomboidal	ii. 232		

## ERRATA.

### VOL. II.

*Page 76. line 7. for parallel with faces, read with parallel faces.*


90.	20.	$\ddot{C}^2$	$\ddot{C}^2$
131.	8.	$\check{P}r + \infty. \check{P}r + \infty$	$\check{P}r + \infty. \check{P}r + \infty.$
145.	10.	$\frac{+(P-2)^4}{2}$	$\frac{+(\check{P}-2)^4}{2}$
156.	5. from below	$\frac{2\sqrt{2}}{2}$	$\frac{2\sqrt{2}}{3}$
208.	10.	$\check{P} + \infty$	$\check{P}r + \infty.$
244.	21.	$P + \infty (m)$	$[P + \infty] (m).$
315.	12.	154	153.
367.	14.	forms	formed.
377.	5.	$67^\circ 58'$	$73^\circ 31'$
379.	15.	$126^\circ$	$136^\circ.$


### VOL. III.

45.	27. for rhombohedral	<i>read</i>	peritomous.
118.	12. Kupferinding		Kupferindig.
120.	7.	$\sqrt{8\cdot3}$	$\sqrt{8\cdot38}.$













**RETURN CIRCULATION DEPARTMENT**  
**TO → 202 Main Library**

LOAN PERIOD 1	2	3
<b>HOME USE</b>		
4	5	6

**ALL BOOKS MAY BE RECALLED AFTER 7 DAYS**


RENEWALS AND RECHARGES MAY BE MADE 4 DAYS PRIOR TO DUE DATE.  
 LOAN PERIODS ARE 1-MONTH, 3-MONTHS, AND 1-YEAR.  
 RENEWALS: CALL (415) 642-3405

**DUE AS STAMPED BELOW**

1991		
JAN 03 1991		
AUTO DISC OCT 20 '90		
SENT ON ILL		
OCT 29 2001		
U. C. BERKELEY		

YB 29850

U.C. BERKELEY LIBRARIES



C004146661

GE362  
M63

96966



