



Cite this article: Mao Y, Yang S, Xue C, Zhang M, Wang W, Song Z, Zhao X, Sun J. 2018 Rapid degradation of malachite green by CoFe_2O_4 -SiC foam under microwave radiation. *R. Soc. open sci.* **5**: 180085.

<http://dx.doi.org/10.1098/rsos.180085>

Received: 19 January 2018

Accepted: 25 May 2018

Subject Category:

Chemistry

Subject Areas:

environmental chemistry/environmental science/environmental engineering

Keywords:

microwave, CoFe_2O_4 -SiC foam, organics, degradation, continuous treatment

Author for correspondence:

Yanpeng Mao

e-mail: maoyanpeng@sdu.edu.cn

[†]These authors contributed equally to this study.

This article has been edited by the Royal Society of Chemistry, including the commissioning, peer review process and editorial aspects up to the point of acceptance.

Electronic supplementary material is available online at <https://dx.doi.org/10.6084/m9.figshare.c.4130039>.



Rapid degradation of malachite green by CoFe_2O_4 -SiC foam under microwave radiation

Yanpeng Mao[†], Shanxiu Yang[†], Chao Xue, Miaomiao Zhang, Wenlong Wang, Zhanlong Song, Xiqiang Zhao and Jing Sun

National Engineering Laboratory of Coal-fired Pollutants Emission Reduction, School of Energy and Power Engineering, Shandong University, Jinan 250100, People's Republic of China

SY, 0000-0003-1819-060X

This study demonstrated rapid degradation of malachite green (MG) by a microwave (MW)-induced enhanced catalytic process with CoFe_2O_4 -SiC foam. The catalyst was synthesized from CoFe_2O_4 particles and SiC foam by the hydrothermal method. X-ray diffraction and scanning electron microscopy techniques were used to confirm that CoFe_2O_4 particles were settled on the surface of SiC foam. In this experiment, a novel fixed-bed reactor was set up with this catalyst for a continuous flow process in a MW oven. The different parameters that affect the MW-induced degradation rate of MG were explored. The MW irradiation leads to the effective catalytic degradation of MG, achieving 95.01% degradation within 5 min at pH 8.5. At the same time, the good stability and applicability of CoFe_2O_4 -SiC foam for the degradation process were also discussed, as well as the underlying mechanism. In brief, these findings make the CoFe_2O_4 -SiC foam an excellent catalyst that could be used in practical rapid degradation of MG.

1. Introduction

Rapid industrial and economic development could increase the risk of environmental pollution. In particular, industries such as paper mills, pharmaceutical production, textile printing and dyeing industry can produce persistent pollutants in waste water that are difficult to degrade after discharge. These persistent pollutants are very harmful to wildlife and humans. As a representative organic dye, malachite green (MG) is usually used in the tinting of silk, leather and

paper, and its triphenylmethane structure is toxic. Therefore, MG poses a major risk in the soil environment, with the possibility of eventual ecosystem disruption [1]. Studies have shown that MG cannot undergo efficient biodegradation [2]: it can stay in the muscle and organs of catfish for as long as ten days. Moreover, it will contaminate most animals that are in contact with it [3–5].

Because of the potential ecological damage from organic pollutants, many researchers have investigated their removal methods.

In the traditional treatment of organic solutions, the adsorption method is commonly used. The characteristic of the adsorption method is to transfer the organic matter in the water from the water phase to the solid phase, but the structure of the organic matter itself does not change. Sharma *et al.* [6] synthesized starch/poly (alginic acid-*cl*-acrylamide) nanohydrogel (ST/PL(AA-*cl*-AAM)NHG) by the polymerization method. The study found that this nanohydrogel was effective for removal of coomassie brilliant (CB) blue dye from aqueous solution and the adsorption of CB onto ST/PL(AA-*cl*-AAM)NHG was immensely dependent upon various parameters. Javadian *et al.* [7] synthesized polyaniline/*g*-alumina nanocomposite by the chemical oxidation method. Batch adsorption experiments were conducted for removing three types of hazardous dyes, Reactive Red 194, Acid Blue 62 and Direct Blue 199, from aqueous solution and the effects of pH, adsorbent dosage, contact time and initial concentration of dyes were investigated. The results showed that the polyaniline/*g*-Al₂O₃ nanocomposite could be used as a suitable adsorbent for textile waste water purification. In addition, compared to the traditional methods, in recent years, the microwave (MW) irradiation method as a new way to eliminate organics in water has become a hot topic. MW irradiation, an electromagnetic wave with a frequency range from 300 MHz to 300 GHz [8], has been used for heating since 1937. Compared with conventional heating methods [9], MW irradiation has a higher heating rate and exhibits selective and volumetric heating properties [10]. Owing to these features, it has been widely studied for removing organics from wastewater, especially during recent years. The topics studied include the catalyst, the equipment used for degradation and different ways to apply MW irradiation.

There are different methods of applying MW irradiation to treat waste water. They can be categorized into Fenton/Fenton-like process, catalytic wet air oxidation and combinations of MW radiation with other physical fields. Particularly, MW-induced catalytic degradation (MICD) and MW-induced catalytic oxidation (MICO) are the most popular processes. In MICD, MW irradiation is combined with a suitable MW absorbent (catalyst), and in the MICO process MW irradiation is combined with a suitable MW absorbent (catalyst) and oxidants.

As the absorption of MW radiation is selective [11], the appropriate materials should be used to degrade organics. The catalyst as a key factor has also been studied widely. In recent years, MW absorbents such as metallic particles [12], active carbon (AC) [13] and polymers [14] have been examined for waste water treatment. Ghaedi *et al.* [15] used AC loaded with zinc oxide nanoparticles to degrade MG. In addition to the effects of initial dye concentration, pH and absorbent dosage, the authors also studied the kinetics and found that the adsorption of MG follows a pseudo-second-order rate equation. An MG degradation rate of more than 95% was achieved. Gao *et al.* [16] loaded MgFe₂O₄ on SiC to degrade the azo dye Direct Black BN. The high degradation efficiency (96.5% after 5 min) was attributed to the MW-induced ·OH radicals and holes. Chen *et al.* [17] used carbon nanotubes as the catalyst in the degradation of methyl parathion and methyl orange. Complete degradation was achieved within 7 min with an irradiation power of 450 W at pH = 6.0. Although these studies showed very high degradation rates, several problems remained. The catalyst particles used were fine and therefore difficult to separate from waste water. Moreover, most of these processes are not continuous, which lowers the reaction efficiency. Bo *et al.* [18] used carbon-supported copper as a catalyst in a continuous reaction process: waste water flowed through a catalyst-filled reactor, and after 5 h of operation the degradation rate of *p*-nitrophenol (PNP) was 91.8%. Longli Bo *et al.* [19] investigated the degradation of PNP using granular activated carbon as a catalyst; the degradation rate reached 90% after 2 h of MW irradiation. Zhang [20] synthesized coal fly ash/CoFe₂O₄ (CFA/CFO) composites for the removal of MG from aqueous solution. The adsorption of MG onto CFA/CFO fitted quite well to the Freundlich and DKR isotherm models. The removal efficiency was 90% by MW irradiation, indicating that the composite could potentially be used for the efficient removal of MG from water.

It is well known that SiC foam has good adsorbability and porosity, as well as excellent MW absorption. In this experiment, we used SiC foam as a skeleton and loaded it with CoFe₂O₄ particles, which are also good absorbers of MW radiation. Using MG as a representative organic pollutant in waste water, the CoFe₂O₄-SiC foam was placed in a fixed bed as the catalyst to degrade MG under MW irradiation. Gao *et al.* [16] used granular SiC loaded with MgFe₂O₄ on the surface; the SiC foam with CoFe₂O₄ had good porosity and is suited for a continuous reactor. In this article, the degradation




Figure 1. Diagrammatic sketch of experimental set-up equipped with the microwave system (1. Solution container, 2. Gas cylinder, 3. Condenser tube, 4. Valves, 5. Fixed bed quartz reactor, 6. Microwave oven, 7. Peristaltic pump, 8. Solution container, 9. Gas washing bottle, 10. Gas washing bottle, 11. Gas collection bottle, 12. Ultraviolet spectrophotometer and 13. LC-MS).

efficiency and activity of the prepared catalysts were investigated. The stability and applicability of $\text{CoFe}_2\text{O}_4\text{-SiC}$ for use in the degradation process were also discussed, and a possible degradation mechanism was proposed.

2. Material and methods

2.1. Preparation of catalysts

SiC foam was purchased from Jingxian County Hengtong casting material factory; this is used to filter liquid iron in industry. Iron(III) nitrate nonahydrate ($\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$), cobalt nitrate hexahydrate ($\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$), absolute ethanol and hydrofluoric acid were purchased from Sinopharm Chemical Reagent Co., Ltd MG was obtained from Zhiyuan Chem. Co., Ltd (Tianjin, China). Sodium hydroxide (NaOH) was purchased from Yili Fine Chem. Co., Ltd (Beijing, China). Apart from the SiC foam, all the chemicals were of analytical grade and used without further purification. Ultrapure water was used throughout the study.

2.2. Catalyst and characteristics

The $\text{CoFe}_2\text{O}_4\text{-SiC}$ foam catalyst was synthesized by a hydrothermal method. The SiC foam was washed with distilled water several times and dried at 80°C in air for 4 h. $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ (0.005 mol) and $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ (0.0025 mol) were dissolved in 200 ml of distilled water. After 10 min of stirring, 10 ml of NaOH solution (3.5 mol l^{-1}) was added, and the mixed solution was stirred for 30 min afterwards. The suspension and the SiC foam were transferred to a 250 ml Teflon-lined autoclave, and heated at 150°C for 12 h. After cooling to room temperature, the foam was taken out and washed with distilled water and absolute ethanol several times, and then dried at 80°C in air for 4 h. Finally, the foam was placed in a muffle furnace and heated at 550°C for 8 h. For comparison, we also prepared CoFe_2O_4 , using the same method with 6.25×10^{-4} mol $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and 3.125×10^{-4} mol $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$. The amount of CoFe_2O_4 loaded on the foam was determined by the weight change in SiC.

2.3. Experimental methods

MG was selected as the target pollutant rather than real industrial waste water to investigate the performance of the synthesized $\text{CoFe}_2\text{O}_4\text{-SiC}$ catalysts. The experiment was carried out in a simple fixed-bed reactor; the experiment flow chart is as shown in figure 1. Firstly, four pieces of the $\text{CoFe}_2\text{O}_4\text{-SiC}$ catalyst were put into the reactor and the system was washed using distilled water for 5 min. Secondly, the microwave oven (M3-L233C, 2450 MHz, Midea, China) and gas cylinder were opened simultaneously at 900 W for 60 s to dry the system. Afterwards, MG solution was pumped into the reactor by a peristaltic pump which could control the flow speed; meanwhile a microwave oven and cooling system were switched on. In the middle of the reactor containing the $\text{CoFe}_2\text{O}_4\text{-SiC}$ catalyst, the pollutant in the waste water was degraded by a combination of catalyst and MW irradiation. The exhaust gas was first

passed through the gas absorbing bottles and collected using a gas collection bottle. At the other end of the reactor, a condenser tube was connected with the reactor to cool the solution heated by the MW irradiation. The solution after cooling was collected, and the residual MG and the degradation products were measured using the spectrophotometry method and high-performance liquid chromatography, respectively.

The degradation rate (R) by the MW catalytic reaction was calculated by the following equation:

$$R = \frac{(C_0 - C)}{C_0} \times 100\%, \quad (2.1)$$

where C_0 is the original concentration of MG and C is the concentration of MG after the reaction.

The experiment parameters were varied in the range of 2.5–10.5 for pH, 10–25 ml min⁻¹ for flow rate, 90–900 W for MW power and 20–50 mg l⁻¹ for MG initial concentration.

2.4. Instrumentation

The morphology and surface characteristics of SiC and CoFe₂O₄-SiC were observed with a Shimadzu EPMA-1600 Electron Probe Microanalyzer. The powder X-ray diffraction (XRD) spectra of the catalyst were obtained (LabX XRD-6000, Shimadzu, Japan) with Cu KR radiation. The pH values of the MG solutions were adjusted using a PHS-3C pH meter (Shanghai, China) combined with a glass electrode. The concentration of MG was measured by an ultraviolet spectrophotometer (TU-1901, Persee, Beijing, China). The degradation product from the reactor was measured by liquid chromatography–mass spectrometry (LC-MS; Agilent-6100, Germany).

3. Results and discussion

3.1. Characterization of CoFe₂O₄-SiC

XRD patterns, scanning electron microscopy (SEM) images and X-ray photoelectron spectral features were used to study the crystal structure and morphological feature of the CoFe₂O₄-SiC foam. Figure 2*a,b* shows photographic images of the SiC and CoFe₂O₄-SiC foams, respectively. As shown in figure 2*c*, before loading the catalyst, the SEM image indicates that the surface of SiC was porous and smooth, and the porous structure could facilitate the adsorption of CoFe₂O₄. Figure 2*d* shows the SEM image after loading the CoFe₂O₄ particles (shown as spheres attached to the apertures). These results suggest the successful deposition of catalyst microparticles. As shown in figure 2*f*, the prepared CoFe₂O₄-SiC has sharp XRD peaks, showing a CoFe₂O₄ crystal pattern which is in agreement with previous reports [21].

The chemical composition and electronic structure of the synthesized CoFe₂O₄-SiC foam are given. As observed in figure 3, the survey spectrum of CoFe₂O₄-SiC foam displayed peaks of Co, Fe, O, C and Si. The peaks at 539.7 eV (O 1s), 110.2 eV (Si 2p), 292.2 eV (C 1p), 735.7 eV (Fe 2p) and 810.12 eV (Co 2p) are shown in electronic supplementary material, figure SF-1. It confirmed the presence of CoFe₂O₄, loaded on the surface of the SiC foam.

3.2. Activity of CoFe₂O₄ in microwave-assisted catalytic reaction

The activity of CoFe₂O₄ was examined both in the absence and presence of MW irradiation. As shown in figure 4, with MW and without the catalyst, the solution passing through the reactor maintained the initial MG concentration (20 mg l⁻¹). The same was found with the catalyst and without MW (final MG concentration: 19.625 mg l⁻¹); it can be seen that SiC foam had no effect on the adsorption of MG solution. However, when both the MW radiation (900 W) and the catalyst were present, the MG concentration was dramatically reduced to 2.627 mg l⁻¹. Therefore, both MW irradiation and CoFe₂O₄-SiC foam are required to effectively remove MG from the water.

3.3. Catalyst performance under different operation conditions

3.3.1. Influence of initial pH

The effect of initial pH on the degradation rate of MG is shown in figure 5. The pH of the original MG solution was 4.5, and it was then adjusted to various pH values between 2.5 and 10.5 by using HCl and NaOH. In general, MG removal rate was enhanced as the pH increased from 2.5 to 8.5, and then declined slightly between pH 8.5 and 10.5. In the range of 2.5–8.5, the degradation rate of MG increased from




Figure 2. Photographs of (a) SiC and (b) CoFe₂O₄-SiC foams. SEM images of (c) SiC and (d) CoFe₂O₄-SiC foams. XRD patterns of (e) SiC and (f) CoFe₂O₄-SiC foam.

82.1% (pH = 2.5) to 95.01% (pH = 8.5), and the degradation rate of MG declined from 95.01% (pH = 8.5) to 93.07% (pH = 10.5) when the loaded ratio of CoFe₂O₄/SiC was 23.03 mg g⁻¹. Increasing the pH was evidently an unfavourable factor for the removal of MG. This is attributed to the influence of pH on the surface charge of the catalyst in the solution; the prediction of actual charge on CoFe₂O₄ is challenging due to the different pH of the MG solution. On the other hand, around pH 8.5, more of ·OH species was generated according to equations (3.6)–(3.9), which would increase the degradation rate and efficiency of MG. With regard to the SiC foam, because of the SiC foam contained a small amount of metal elements, such as aluminium and iron, there was still the Fenton-like reaction on its surface. Therefore with the increase of pH, the reaction was promoted and the degradation rate of MG reached its highest at pH = 8.5.




Figure 3. X-ray photoelectron survey spectrum of $\text{CoFe}_2\text{O}_4\text{-SiC}$ foams.




Figure 4. Concentration of MG under different conditions: (1) with neither irradiation nor catalyst, (2) without catalyst, (3) without irradiation, and (4) with both irradiation and catalyst. Original MG concentration: 20 mg l^{-1} , current speed: 10 ml min^{-1} , pH: 4.5, and MW irradiation: 900 W.




Figure 5. Effect of initial pH with different CoFe_2O_4 loadings. Initial concentration of MG: 20 mg l^{-1} , MW irradiation power: 900 W and current speed: 10 ml min^{-1} .




Figure 6. Effect of MW power with different CoFe_2O_4 loadings. Initial concentration of MG: 20 mg l^{-1} , initial pH: 4.5 and current speed: 10 ml min^{-1} .

3.3.2. Influence of microwave power

The power of MW irradiation is an important operating parameter in MW-assisted catalytic reactions. In this experiment, five different power settings of the microwave oven were used (90, 270, 500, 720 and 900 W), while other conditions were fixed (pH: 4.5, flow rate: 10 ml min^{-1} and initial MG concentration: 20 mg l^{-1}). As shown in figure 6, the degradation rate of MG by CoFe_2O_4 -SiC increases monotonically with the MW power in the range of 90–900 W. There are also two turning points at 270 and 720 W, between which the MG degradation changes the fastest with MW power (i.e. steepest slope). When only SiC foam was used, on the other hand, the MG degradation ratio changes at the same rate with increasing MW power. There are two potential mechanisms for the enhanced MG degradation. First of all, a higher MW power leads to a higher temperature, which inevitably accelerates the degradation reaction. Secondly, more hotspots are generated as more MW energy is absorbed by CoFe_2O_4 , thereby producing more catalytically active sites on the CoFe_2O_4 particle surface. At the same time, the SiC foam can effectively absorb the MW irradiation, and the increased degradation of MG on the surface of SiC foam alone is mainly attributed to the temperature change. Therefore, in subsequent experiments we used the MW power of 900 W and the CoFe_2O_4 -SiC catalyst, unless noted otherwise.

3.3.3. Influence of initial malachite green concentration

The effect of initial MG concentration in the range of 20 – 50 mg l^{-1} on the degradation rate was investigated. As shown in figure 7, the degradation rate of MG decreased with its initial concentration. In this experiment, the MG solution was moving through the reactor while being irradiated by MW. The MG then made contact with the catalyst on the surface of the CoFe_2O_4 -SiC foam. When the MG concentration was high, the number of hotspots on the surface was insufficient for degrading the MG in time, hence the reduced degradation rate. Therefore, the concentration of MG in the solution is another important parameter of the reaction.

3.3.4. Influence of flow speed

Unlike previous studies, the reactor here was designed to allow the MG solution to flow through at a rate (10 – 25 ml min^{-1}) controlled by a peristaltic pump. As shown in figure 8, the degradation rate of MG decreased with rising current speed. Particularly, when only SiC foam was used, the degradation rate dropped sharply at 15 ml min^{-1} . As the MW radiation heats water in the reactor, a higher flow rate means less temperature rise in the reactor, which could have a huge impact on the reaction. The CoFe_2O_4 particles loaded on the SiC foam could absorb more MW radiation and raise the temperature even further. This could offset the reduced temperature rise and prevent the MG degradation rate from dropping rapidly. The effect of current speed indicates that, in a continuous-mode reaction, a slower speed of solution flow is beneficial for the reaction.




Figure 7. Effect of initial concentration of MG with different CoFe₂O₄ loadings. Initial pH: 4.5, current speed: 10 ml min⁻¹, MW irradiation power: 900 W.




Figure 8. Effect of current speed with different CoFe₂O₄ loadings. Initial concentration of MG: 20 mg l⁻¹, initial pH: 4.5 and MW power: 900 W.

3.3.5. Influence of CoFe₂O₄ loading

The degradation rate was enhanced with more CoFe₂O₄ catalyst, as it provides more active sites on the surface of SiC foam in contact with MG during the MW-assisted catalytic reaction (figures 5–8). However, as the amount of CoFe₂O₄ particles increased beyond a certain threshold, the particles start to overlap, causing no obvious increase of effective contact with MG. Considering that the power of MW irradiation and the current speed both affect the reaction, the amount of CoFe₂O₄ should be adjusted accordingly.

3.4. Catalytic stability of CoFe₂O₄–SiC

The stability and recyclability of a catalyst are very important in practical applications. In this study, the used CoFe₂O₄–SiC foam was taken out, washed several times with ultrapure water, dried at 80°C for 4 h and then reused under MW irradiation. As shown in figure 9, after 10 consecutive runs, the degradation rate remained as high as 81.53%, indicating that the CoFe₂O₄–SiC possesses good stability in the MW-assisted catalytic degradation reaction. Zhang [20] synthesized CFA/CFO composites, but the composite must be regenerated by the thermal method. However, the stability of the CoFe₂O₄–SiC foam was very good and did not need the regenerative process. Compared with the study of Gao *et al.* [16], the stability of CoFe₂O₄–SiC foam was better than that of MgFe₂O₄–SiC.




Figure 9. Stability of CoFe₂O₄-SiC foam.

3.5. Activation and degradation mechanisms

3.5.1. Hot spots

Unlike conventional heating methods, MW radiation permeates and heats materials at the molecular level. Specifically, the dipole molecules under MW radiation can never rotate fast enough to follow the oscillating electric field. This phenomenon leads to the thermal effect, as a large amount of energy is consumed by this type of delay [22,23]. Some particles on the catalyst surface can absorb MW radiation more strongly than other parts, reaching a temperature of 1000°C or higher [24]. These overheated particles are referred to as ‘hot spots’ [25], and they have been proved to promote the degradation of organic pollutants due to the high temperature [26].


In this case, the CoFe₂O₄ particles (figure 2d) loaded on SiC foam can become much hotter than other parts. Additionally, the SiC foam is also effective in absorbing MW radiation. Therefore, when the waste water flowed into the reactor, the high temperature caused the water to vaporize, leaving MG on the catalyst surface to be degraded by CoFe₂O₄ particles under MW irradiation. At the same time, because the whole reaction was exposed to air, the large organic molecules were further oxidized into smaller ones.

3.5.2. Hydroxyl radical as oxidation agent

The Fenton process is a typical advanced oxidation process [27], in which the main reactions can be expressed according to the following equations:



and



The $\cdot\text{OH}$ (figure 10) radicals produced by the Fenton process are strongly oxidizing, and therefore could be used to degrade organics. When Fe^{2+} is replaced with other species (denoted as M^{n+1}), $\cdot\text{OH}$ still can be generated from catalysing H_2O_2 through a slightly different Fenton-like process, as shown in the following equations [28,29]:



and



The Fenton/Fenton-like processes are the main mechanisms for generating $\cdot\text{OH}$. When combined with MW irradiation, the process is accelerated to produce $\cdot\text{OH}$ more rapidly [30]. Gao *et al.* [16] confirmed that in the MW-assisted catalytic reaction with MgFe₂O₄-SiC, $\cdot\text{OH}$ could still be generated






Figure 10. Possible mechanism of MW-induced catalytic degradation of MG.

without adding H_2O_2 . Therefore, in this experiment, the $\cdot\text{OH}$ could be generated by MW irradiation with the $\text{CoFe}_2\text{O}_4\text{-SiC}$ foam catalyst via the following equations:



and



With the generated $\cdot\text{OH}$ and H^+ , the organics in the waste water could be oxidized into small molecules [31]. Hence, there are good reasons to believe that $\cdot\text{OH}$ and H^+ are the main active species in the MW-assisted catalytic degradation of MG [32].

3.6. Degradation products

A variety of degradation products were identified from the collected solution after the reaction by LC-MS analysis. Electronic supplementary material, figure SF-2(a), shows the liquid chromatogram of the solution before the reaction, showing a single peak at 3.5 min. The corresponding MS peak in electronic supplementary material, figure SF-2(a), is located at $m/z = 329$, confirming that MG was the only organic matter in the original solution. In the chromatogram after the reaction (electronic supplementary material, figure SF-2(b)), in addition to the MG peak at 3.5 min, two additional peaks appeared at 6.7 and 6.8 min. The former has a formula weight of 273 according to the MS, and the intensity of the latter was very weak and could be ignored. Liu *et al.* [33] investigated the reaction intermediate in the photocatalytic oxidation of MG. Based on that study, the MG degradation process can be described by the reactions in electronic supplementary material, figure SF-3. First, MG is oxidized to dimethylnitrosamine and quinones. Indeed, a small amount of quinones was identified in electronic supplementary material, figure SF-2(b). Considering that the boiling points of the quinones are low and the temperature in the reactor was very high, some of the quinones could have volatilized into air during the experiment and were not detected by LC-MS. At the same time, most quinones were oxidized to carbon dioxide and water by oxygen.

Compared with traditional adsorption treatment of organic matter in aqueous medium, the process of MW catalytic degradation was a chemical process, and MG in aqueous medium was degraded into small molecules. Furthermore, the efficiency of MW degradation and adsorption were both very high, hence the MW catalytic degradation system could be used in practical application.

4. Conclusion

In this work, CoFe_2O_4 loaded on a SiC foam support was successfully synthesized by a hydrothermal method. The SiC skeleton effectively improved the ability to absorb MW radiation. The prepared CoFe_2O_4 -SiC foam was shown to be a novel and efficient catalyst during the MW-assisted catalytic degradation of MG. The degradation rate reached 95.01% in less than 5 min. In addition, the effects of reaction conditions (MW power, pH, flow speed, amount of catalyst and initial MG concentration) on the degradation rate were examined. Moreover, a possible mechanism for the MW-assisted catalytic process was proposed. The temperature rise from heating by MW irradiation and the generated $\cdot\text{OH}$ radicals are key for the reaction. The overall process was continuous and highly efficient, and the catalyst had good recyclability. Therefore, this new MW catalyst exhibited high degradation efficiency, broad pH range and excellent stability. It is expected to have great potential in applications of waste water treatment.

Data accessibility. This article does not contain any additional data.

Authors' contributions. Y.M. and designed the project. S.Y., C.X. performed the research. S.Y. and Y.M. wrote the manuscript. M.Z., W.W., Z.S., X.Z. and J.S. analysed the data. All the authors gave their final approval for publication. Competing interests. We declare we have no competing interests.

Funding. The authors thank the support of National Natural Science Foundation of China (grant nos. 51506116, 51576118 and 51376112), Shandong Science Fund for Distinguished Young Scholars (JQ201514), Young Scholars Program of Shandong University (2016WLJH37) and the Fundamental Research Funds of Shandong University (2016JC004).

Acknowledgements. The authors thank Y.M. for reviewing the manuscript, W.W., Z.S., X.Z. and J.S. for technical support, and particularly C.X. and M.Z. for providing support.

References

- Jalil AA, Triwahyono S, Adam SH, Rahim ND, Aziz MAA, Hairon NHH, Razali NAM, Abidin MAZ, Mohamadiah MKA. 2010 Adsorption of methyl orange from aqueous solution onto calcined Lapindo volcanic mud. *J. Hazard. Mater.* **181**, 755–762. (doi:10.1016/j.jhazmat.2010.05.078)
- Chen G-y, Miao S. 2010 HPLC determination and MS confirmation of malachite green, gentian violet, and their leuco metabolite residues in channel catfish muscle. *J. Agric. Food Chem.* **58**, 7109–7114. (doi:10.1021/jf9043925)
- Culp SJ *et al.* 2002 Mutagenicity and carcinogenicity in relation to DNA adduct formation in rats fed leucomalachite green. *Mutat. Res. Fundam. Mol. Mech. Mutagen.* **506–507**, 55–63. (doi:10.1016/S0027-5107(02)00152-5)
- Bergwerff AA, Scherpenisse P. 2003 Determination of residues of malachite green in aquatic animals. *J. Chromatogr. B* **788**, 351–359. (doi:10.1016/S1570-0232(03)00042-4)
- Mittelstaedt RA *et al.* 2004 Genotoxicity of malachite green and leucomalachite green in female Big Blue B6C3F₁ mice. *Mutat. Res. Genet. Toxicol. Environ. Mutagen.* **561**, 127–138. (doi:10.1016/j.mrgentox.2004.04.003)
- Sharma G *et al.* 2017 Efficient removal of coomassie brilliant blue R-250 dye using starch/poly(alginate acid-*cl*-acrylamide) nanohydrogel. *Process Saf. Environ. Prot.* **109**, 301–310. (doi:10.1016/j.psep.2017.04.011)
- Javadian H, Angaji MT, Naushad M. 2014 Synthesis and characterization of polyaniline/ γ -alumina nanocomposite: a comparative study for the adsorption of three different anionic dyes. *J. Ind. Eng. Chem.* **20**, 3890–3900. (doi:10.1016/j.jiec.2013.12.095)
- Wang J, Guo B, Zhang X, Zhang Z, Han J, Wu J. 2005 Sonocatalytic degradation of methyl orange in the presence of TiO_2 catalysts and catalytic activity comparison of rutile and anatase. *Ultrason. Sonochem.* **12**, 331–337. (doi:10.1016/j.ultsonch.2004.05.002)
- Mehdizadeh SN, Eskicioglu C, Bobowski J, Johnson T. 2013 Conductive heating and microwave hydrolysis under identical heating profiles for advanced anaerobic digestion of municipal sludge. *Water Res.* **47**, 5040–5051. (doi:10.1016/j.watres.2013.05.055)
- Zhang X, Wang Y, Li G, Qu J. 2006 Oxidative decomposition of azo dye C.I. Acid Orange 7 (A07) under microwave electrodeless lamp irradiation in the presence of H_2O_2 . *J. Hazard. Mater.* **134**, 183–189. (doi:10.1016/j.jhazmat.2005.10.046)
- Galan A-M, Calinescu I, Trifan A, Winkworth-Smith C, Calvo-Carrascal M, Dodds C, Binner E. 2017 New insights into the role of selective and volumetric heating during microwave extraction: investigation of the extraction of polyphenolic compounds from sea buckthorn leaves using microwave-assisted extraction and conventional solvent extraction. *Chem. Eng. Process.* **116**, 29–39. (doi:10.1016/j.cep.2017.03.006)
- Liu B, Li S, Zhao Y, Wu W, Zhang X, Gu X, Li R, Yang S. 2010 Enhanced degradation of 4-nitrophenol by microwave assisted Fe/EDTA process. *J. Hazard. Mater.* **176**, 213–219. (doi:10.1016/j.jhazmat.2009.11.015)
- Zhang Y, Quan X, Chen S, Zhao Y, Yang F. 2006 Microwave assisted catalytic wet air oxidation of H-acid in aqueous solution under the atmospheric pressure using activated carbon as catalyst. *J. Hazard. Mater.* **137**, 534–540. (doi:10.1016/j.jhazmat.2006.02.036)
- Cai M-Q, Zhu Y-Z, Wei Z-S, Hu J-Q, Pan S-D, Xiao R-Y, Dong C-Y, Jin M-C. 2017 Rapid decolorization of dye Orange G by microwave enhanced Fenton-like reaction with delafossite-type CuFeO_2 . *Sci. Total Environ.* **580**, 966–973. (doi:10.1016/j.scitotenv.2016.12.047)
- Ghaedi M, Ghaedi AM, Hossainpour M, Ansari A, Habibi MH, Asghari AR. 2014 Least square-support vector (LS-SVM) method for modeling of methylene blue dye adsorption using copper oxide loaded on activated carbon: kinetic and isotherm study. *J. Ind. Eng. Chem.* **20**, 1641–1649. (doi:10.1016/j.jiec.2013.08.011)
- Gao J, Yang S, Li N, Meng L, Wang F, He H, Sun C. 2016 Rapid degradation of azo dye Direct Black BN by magnetic MgFe_2O_4 -SiC under microwave radiation. *Appl. Surf. Sci.* **379**, 140–149. (doi:10.1016/j.apsusc.2016.04.041)
- Chen J, Xue S, Song Y, Shen M, Zhang Z, Yuan T, Tian F, Dionysiou DD. 2016 Microwave-induced carbon nanotubes catalytic degradation of organic pollutants in aqueous solution. *J. Hazard. Mater.* **310**, 226–234. (doi:10.1016/j.jhazmat.2016.02.049)
- Bo LL, Zhang YB, Quan X, Zhao B. 2008 Microwave assisted catalytic oxidation of *p*-nitrophenol in aqueous solution using carbon-supported copper catalyst. *J. Hazard. Mater.* **153**, 1201–1206. (doi:10.1016/j.jhazmat.2007.09.082)
- Bo L, Quan X, Chen S, Zhao H, Zhao Y. 2006 Degradation of *p*-nitrophenol in aqueous solution by microwave assisted oxidation process through a granular activated carbon fixed bed. *Water Res.* **40**, 3061–3068. (doi:10.1016/j.watres.2006.06.030)
- Zhang M, Mao Y, Wang W, Yang S, Song Z, Zhao X. 2016 Coal fly ash/ CoFe_2O_4 composites: a magnetic adsorbent for the removal of malachite green from aqueous solution. *RSC Adv.* **6**, 93 564–93 574. (doi:10.1039/C6RA08939A)
- Feng J, Wang Y, Hou Y, Li J, Li L. 2016 Synthesis and microwave absorption properties of coiled carbon nanotubes/ CoFe_2O_4 composites. *Ceram. Int.* **42**, 17 814–17 821. (doi:10.1016/j.ceramint.2016.08.110)

22. Hidaka H, Saitou A, Honjou H, Hosoda K, Moriya M, Serpone N. 2007 Microwave-assisted dechlorination of polychlorobenzenes by hypophosphite anions in aqueous alkaline media in the presence of Pd-loaded active carbon. *J. Hazard. Mater.* **148**, 22–28. (doi:10.1016/j.jhazmat.2007.01.143)
23. Menéndez JA, Inguanzo M, Pis JJ. 2002 Microwave-induced pyrolysis of sewage sludge. *Water Res.* **36**, 3261–3264. (doi:10.1016/S0043-1354(02)00017-9)
24. Zhang L, Liu X, Guo X, Su M, Xu T, Song X. 2011 Investigation on the degradation of brilliant green induced oxidation by NiFe₂O₄ under microwave irradiation. *Chem. Eng. J.* **173**, 737–742. (doi:10.1016/j.cej.2011.08.041)
25. Shi L, Yang C, Su X, Wang J, Xiao F, Fan J, Feng C, Sun H. 2014 Microwave-hydrothermal synthesis of CuO nanorods and their catalytic applications in sodium humate synthesis and RhB degradation. *Ceram. Int.* **40**, 5103–5106. (doi:10.1016/j.ceramint.2013.10.104)
26. Tai H-S, Jou C-JG. 1999 Application of granular activated carbon packed-bed reactor in microwave radiation field to treat phenol. *Chemosphere* **38**, 2667–2680. (doi:10.1016/S0045-6535(98)00432-9)
27. Zhao H, Chen Y, Peng Q, Wang Q, Zhao G. 2017 Catalytic activity of MOF(2Fe/Co)/carbon aerogel for improving H₂O₂ and OH generation in solar photo-electro-Fenton process. *Appl. Catal. B* **203**, 127–137. (doi:10.1016/j.apcatb.2016.09.074)
28. Yang Y, Wang P, Shi S, Liu Y. 2009 Microwave enhanced Fenton-like process for the treatment of high concentration pharmaceutical wastewater. *J. Hazard. Mater.* **168**, 238–245. (doi:10.1016/j.jhazmat.2009.02.038)
29. Carta R, Desogus F. 2013 The enhancing effect of low power microwaves on phenol oxidation by the Fenton process. *J. Environ. Chem. Eng.* **1**, 1292–1300. (doi:10.1016/j.jece.2013.09.022)
30. Wu J, Pu W, Yang C, Zhang M, Zhang J. 2013 Removal of benzotriazole by heterogeneous photoelectro-Fenton like process using ZnFe₂O₄ nanoparticles as catalyst. *J. Environ. Sci.* **25**, 801–807. (doi:10.1016/S1001-0742(12)60117-X)
31. Eremia SAV, Chevalier-Lucia D, Radu G-L, Marty J-L. 2008 Optimization of hydroxyl radical formation using TiO₂ as photocatalyst by response surface methodology. *Talanta* **77**, 858–862. (doi:10.1016/j.talanta.2008.07.056)
32. He H, Yang S, Yu K, Ju Y, Sun C, Wang L. 2010 Microwave induced catalytic degradation of crystal violet in nano-nickel dioxide suspensions. *J. Hazard. Mater.* **173**, 393–400. (doi:10.1016/j.jhazmat.2009.08.084)
33. Liu C-G, Zheng T, Liu S, Zhang H-Y. 2016 Photodegradation of malachite green dye catalyzed by Keggin-type polyoxometalates under visible-light irradiation: transition metal substituted effects. *J. Mol. Struct.* **1110**, 44–52. (doi:10.1016/j.molstruc.2016.01.015)